

Thermal Conductivity of Alumina-Toughened Zirconia Composites

Narottam P. Bansal Glenn Research Center, Cleveland, Ohio

Dongming Zhu U.S. Army Research Laboratory, Glenn Research Center, Cleveland, Ohio Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- TECHNICAL PUBLICATION. Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peerreviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- TECHNICAL MEMORANDUM. Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- CONTRACTOR REPORT. Scientific and technical findings by NASA-sponsored contractors and grantees.

- CONFERENCE PUBLICATION. Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- SPECIAL PUBLICATION. Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- TECHNICAL TRANSLATION. Englishlanguage translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized databases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at *http://www.sti.nasa.gov*
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA Access Help Desk at 301-621-0134
- Telephone the NASA Access Help Desk at 301–621–0390
- Write to: NASA Access Help Desk NASA Center for AeroSpace Information 7121 Standard Drive Hanover, MD 21076



Thermal Conductivity of Alumina-Toughened Zirconia Composites

Narottam P. Bansal Glenn Research Center, Cleveland, Ohio

Dongming Zhu U.S. Army Research Laboratory, Glenn Research Center, Cleveland, Ohio

National Aeronautics and Space Administration

Glenn Research Center

December 2003

Acknowledgments

This work was supported by NASA's Zero CO2 Emission Technology (ZCET) Project of the Aerospace Propulsion and Power Program. The authors are grateful to John Setlock for processing of the composite materials, Bob Angus for hot pressing, and Ralph Garlick for x-ray diffraction analysis during the course of this research.

> This work was sponsored by the Low Emissions Alternative Power Project of the Vehicle Systems Program at the NASA Glenn Research Center.

> > Available from

NASA Center for Aerospace Information 7121 Standard Drive Hanover, MD 21076 National Technical Information Service 5285 Port Royal Road Springfield, VA 22100

Available electronically at http://gltrs.grc.nasa.gov

Thermal Conductivity of Alumina-Toughened Zirconia Composites

Narottam P. Bansal National Aeronautics and Space Administration Glenn Research Center Cleveland, Ohio 44135

Dongming Zhu U.S. Army Research Laboratory National Aeronautics and Space Administration Glenn Research Center Cleveland, Ohio 44135

Summary

10-mol% yttria-stabilized zirconia (10YSZ)-alumina composites containing 0 to 30 mol% alumina were fabricated by hot pressing at 1500 °C in vacuum. Thermal conductivity of the composites, determined at various temperatures using a steady-state laser heat flux technique, increased with increase in alumina content. Composites containing 0, 5, and 10-mol% alumina did not show any change in thermal conductivity with temperature. However, those containing 20 and 30-mol% alumina showed a decrease in thermal conductivity with increase in temperature. The measured values of thermal conductivity were in good agreement with those calculated from simple rule of mixtures.

Introduction

A fuel cell is an electrochemical device where the chemical energy of a fuel such as hydrogen is converted into electricity by electrochemical oxidation of the fuel. The only by-products of this process are water and heat. Various types of fuel cells (polymer electrolyte fuel cell, alkaline fuel cell, phosphoric acid fuel cell, methanol fuel cell, molten carbonate fuel cell, and solid oxide fuel cell) are being developed as power sources for a large number of applications. Solid oxide fuel cells¹ (SOFC) offer several advantages over other types of fuel cells such as high efficiency, low emissions, high power density, fuel flexibility, and internal fuel reforming. Yttria-stabilized zirconia (YSZ) is the most commonly used electrolyte for high-temperature SOFC because of its high oxide ion conductivity and stability in oxidizing and reducing atmospheres. However, like other ceramic materials, zirconia has low fracture toughness and poor strength. For aeropropulsion applications, the thin electrolyte membrane (10 to 50 μ m thick) of the planar anode-supported SOFC needs to be strong and tough as it would be subjected to severe vibrations and thermal cycling during take-off and landing. It has been recently demonstrated²⁻⁴ that the additions of alumina to 10YSZ make it stronger, tougher, lighter, and stiffer at room temperature as well as at 1000 °C. However, no information is available about the thermal conductivity of these composites. The objective of the present study was to investigate the effects of alumina additions on the thermal conductivity of 10YSZ in the SOFC operating temperature region.

Materials and Experimental Methods

The starting materials used were 10 mol% yttria fully-stabilized zirconia powder (HSY–10, average particle size 0.41 μ m, specific surface area 5.0 m²/g) from Daiichi Kigenso Kagaku Kogyo Company, Japan and alumina powder (Baikalox CR–30, 99.99 percent purity, average particle size

 $0.05 \ \mu\text{m}$, specific surface area $25 \ \text{m}^2/\text{g}$) from Baikowski International Corporation, Charlotte, North Carolina. Appropriate quantities of 10YSZ powder and alumina powder were slurry mixed in acetone and ball milled for ~24 h using zirconia milling media. Acetone was evaporated and the powder dried in an electric oven. The resulting powder was loaded into a graphite die and hot pressed at 1500 °C in vacuum under 30 MPa pressure into 1 in. diameter discs using a mini-hot press. Grafoil was used as spacers between the specimen and the punches. Load was released before onset of cooling^{2,4} after an isothermal hold at high temperature resulting in dense and crack free ceramic composite samples. Residual grafoil from disc surfaces was burned off in air.

Thermal Conductivity Measurement

One inch (25.4 mm) diameter hot pressed discs of 10YSZ-alumina composites were used for thermal conductivity measurements. Thermal conductivity testing of the ceramic materials was carried out using a 3.0 kW CO₂ laser (wavelength 10.6 μ m) high-heat flux rig. A schematic diagram of the test rig, photos of the actual test facilities and the general test approach have been described elsewhere.⁵ In this steady-state laser heat flux test method, the specimen surface was heated by a laser beam, and backside air-cooling was used to maintain the desired temperature. A uniform laser heat flux was obtained over the 23.9 mm diameter aperture region of the specimen surface by using an integrating ZnSe lens combined with the specimen rotation. Platinum wire flat coils (wire diameter 0.38 mm) were used to form thin air gaps between the top aluminum aperture plate and stainless-steel back plate to minimize the specimen heat losses through the fixture.

Thermal conductivity of ceramic materials, $k_{ceramic}$, can be determined from the pass-through heat flux q_{thru} and measured temperature difference $\Delta T_{ceramic}$ across the ceramic specimen thickness $l_{ceramic}$ under the steady-state laser heating conditions⁵

$$k_{ceramic} = q_{thru} \cdot l_{ceramic} / \Delta T_{ceramic} \tag{1}$$

The actual pass-through heat flux q_{thru} for a given ceramic specimen was obtained by subtracting the laser reflection loss (measured by a 10.6 µm reflectometer) and the calculated radiation heat loss (total emissivity was taken as 0.50 for the oxides) at the ceramic surface from the laser delivered heat flux (i.e., $q_{thru} = q_{delivered} - q_{reflected} - q_{radiated}$). Note that the non-reflected laser energy is absorbed at or near the specimen surfaces because of the quite high emissivity at the 10.6 µm laser wavelength region for the oxides. In some test cases, the pass-through heat flux q_{thru} was verified with an internal heat flux gauge incorporated with the substrates (instrumented specimens) via an embedded miniature thermocouple. For the hot pressed bulk specimens, the temperature difference $\Delta T_{ceramic}$ in the ceramic was directly measured by using two 8µm pyrometers at both specimen front heating and back side air cooling surfaces.

Results and Discussion

Compositions of various 10YSZ-alumina composites used in this study and their densities, ρ , are presented in table I. The specimens are at least 99 percent dense. Density decreased with increase in alumina content, as expected. X-ray diffraction patterns from various 10YSZ-alumina composites are shown in figure 1. Cubic zirconia and α -alumina were the only phases present indicating the absence of any chemical reaction between the constituent materials during hot pressing at elevated temperatures. Typical SEM micrographs taken from the polished cross-sections of various YSZ/alumina composites are shown in figure 2. Alumina particulates are uniformly dispersed throughout the material. The dark areas represent alumina while the light areas indicate the 10YSZ matrix, as confirmed from EDS analysis (fig. 3). TEM micrograph and dot maps for various elements for the composite containing 30 mol%

alumina are shown in figure 4. The average equiaxed grain size is less than 1.0 µm for either YSZ matrix or alumina. The high magnification TEM micrographs showing grain boundaries and triple junctions for the 0 and 30 mol% alumina composites are presented in figures 5 and 6, respectively. The grain boundaries as well as the triple junctions are clean for either composite, indicating the absence of any amorphous phase. No appreciable deformation or microcracks of adjacent grains in the composites, which might occur due to thermoelastic mismatches between the YSZ matrix and the alumina particulates, was observed from the analysis of TEM micrographs.

Table I.—Compositions of 10YSZ-alumina composites						
Sample	Composition (mol%)		Density, p			
No.	10YSZ	Al_2O_3	(g/cm^3)			
A2-0	100	0	6.09 ± 0.05			
A2-5	95	5	5.89 ± 0.01			
A2-10	90	10	5.80 ± 0.01			
A2-20	80	20	5.57 ± 0.01			
A2-30	70	30	5.38 ± 0.04			
Al_2O_3	0	100	3.94 ± 0.03			



Figure 1.—X-ray diffraction patterns for 10YSZ reinforced with different alumina contents as indicated. "Z" and "A" indicate cubic-zirconia and α -alumina, respectively.



Figure 2.—SEM micrographs showing polished cross-sections of 10YSZ-alumina composites containing various alumina mol%.



Figure 3.—SEM micrograph and EDS analysis of 10YSZ-alumina composite containing 10 mol% alumina; dark area (A): alumina, light area (B): zirconia.



Figure 4.—TEM micrograph showing zirconia and alumina grains and dot maps of different elements for 10YSZ-alumina composite containing 30 mol% alumina.



Figure 5.—High magnification TEM micrographs showing grain boundaries in 10YSZ-alumina composites containing 0 or 30 mol% alumina.



0 mol% alumina

30 mol% alumina







Thermal conductivities of hot pressed specimens of 10YSZ-alumina composites of various compositions, as a function of temperature, are shown in figure 7. Results for 10YSZ and alumina are also shown for comparison. Data for alumina shows a large scatter particularly in the low temperature region. As alumina has much higher thermal conductivity at low temperatures, the precision of steady-state laser technique, used in the current study, is not as good due to small thermal gradient across the test specimen at low temperatures. Thicker test specimens of alumina may improve the precision. Thermal conductivity increased with increase in alumina content. This is expected, as the thermal conductivity of alumina is much higher¹² than that of 10YSZ. The increase in thermal conductivity with alumina additions is more significant at lower temperatures than at higher temperatures. Thermal conductivity of composites containing 0, 5, and 10-mol% alumina exhibited slight changes with temperature. However, those containing 20 and 30-mol% alumina showed a sharper decrease in thermal conductivity with increase in temperature.

Microstructures of composites of various compositions (fig. 2) show that alumina phase is uniformly dispersed within the major continuous 10YSZ phase. For materials with such a microstructure, when thermal conductivity of the dispersed phase (alumina) is much higher than that of the continuous phase (10YSZ), the thermal conductivity of the composite (k_c) is given by¹⁰

$$k_c = k_{10YSZ} \left[(1 + 2V_{A12O3}) / (1 - V_{A12O3}) \right]$$
⁽²⁾

where *k* represents the thermal conductivity and *V* the volume fraction. Thermal conductivity of the composites was also calculated using the simple rule of mixtures:

$$k_c = (k_{10YSZ} \cdot V_{10YSZ}) + (k_{Al2O3} \cdot V_{Al2O3})$$
(3)

Thermal conductivity of various 10YSZ-alumina composites at 1000 °C were calculated from Eqs. (2) and (3) using values of 2.15 and 6.88 W/m-K for thermal conductivity of 10YSZ and alumina, respectively, measured in the current study. The calculated and measured values are compared in table II. The measured values of thermal conductivity of 10YSZ-alumina mixtures are in much better agreement with those calculated from the rule of mixtures Eq. (3), rather than from Eq. (2).

Thermal conductivity of alumina from various studies is compared in figure 8. Results of the present study are in good agreement with those reported by other researchers, particularly at high temperatures. However, values reported by Santos and Taylor¹¹ are high compared with other studies. Literature values of thermal conductivity of yttria-stabilized zirconia containing various mol% of the stabilizer are shown in figure 9, along with the results of the current study for 10 mol% (16.9 wt%) yttria containing zirconia. Significant variation is seen in the results for different compositions due to different microstructures resulting from various amounts of yttria stabilizer. Thermal conductivity of zirconia decreases with increase in yttria content up to 5.12 mol% (9 wt%). However, thermal conductivity increased for compositions containing higher yttria content. The 3YSZ consists almost entirely of tetragonal (*t*) phase.¹⁵ Compositions containing >3 mol% (5.3 wt%) yttria contain a significant amount of the monoclinic (*m*) phase and the microstructure consists of a two-phase mixture of *t* and *m* phases. The 10YSZ composition of the present study, containing 10 mol% (16.9 wt%) yttria, is fully stabilized and consists of the cubic phase of zirconia.

Sample	Composition (mol%)		Thermal conductivity (W/m-K) at 1000 °C		
No.	10YSZ	Al ₂ O ₃	Measured	Calculated from	Calculated from
			(This study)	Eq. (2)	Eq. (3)
A2-0	100	0	2.2		
A2-5	95	5	2.5	2.5	2.4
A2-10	90	10	2.7	3.0	2.7
A2-20	80	20	3.0	4.0	3.2
A2-30	70	30	3.3	5.3	3.7
Al_2O_3	0	100	6.9		

Table II.-Measured and calculated thermal conductivities of 10YSZ-alumina composites at 1000 °C



Figure 8.—Thermal conductivity of alumina from various studies.



Figure 9.—Thermal conductivity of zirconia containing different mol% of yttria content.

Summary

Thermal conductivity of 10YSZ-alumina composites containing 0 to 30 mol% alumina has been determined as a function of temperature. Thermal conductivity increased with an increase in alumina content. Thermal conductivity showed slight change with temperature for 0, 5, and 10 mol% alumina compositions whereas it decreased with temperature for composites containing 20 and 30 mol% alumina. The measured thermal conductivity values are in good agreement with those calculated from simple rule of mixtures.

References

- 1. N.Q. Minh, "Ceramic Fuel Cells," J. Am. Ceram. Soc., 76 [3], 563–588 (1993).
- S.R. Choi and N.P. Bansal, "Strength and Fracture Toughness of YSZ/Alumina Composites for Solid Oxide Fuel Cells," *Ceram. Eng. Sci. Proc.*, 23 [3] 741–750 (2002).
- 3. S.R. Choi and N.P. Bansal, "Strength, Fracture Toughness, and Slow crack Growth of Zirconia/ Alumina Composites at Elevated Temperature," NASA/TM—2003-212108 (2003).
- 4. N.P. Bansal and S.R. Choi, "Processing of Alumina-Toughened Zirconia Composites," NASA/TM—2003-212451, May 2003.
- 5. D. Zhu, N.P. Bansal, K.N. Lee, and R.A. Miller, "Thermal Conductivity of Ceramic Thermal Barrier and Environmental Barrier Coating Materials," NASA/TM—2001-211122, Sept. 2001.
- 6. M. Miyamara, H. Yanagida, and A. Asada, "Effects of Al₂O₃ Additions on Resistivity and Microstructure of Yttria-Stabilized Zirconia," *Am. Ceram. Soc. Bull.*, **64** [4], 660–664 (1985).
- F. Ishizaki, T. Yoshida, and S. Sakurada, "Effect of Alumina Additions on the Electrical Properties of Yttria Doped Zirconia," Proc. 1st Int. Symp. On Solid Oxide Fuel Cells (S.C. Singhal, Ed.), The Electrochemical Society, Pennington, NJ; pp. 3–14 (1989).
- 8. E.P. Butler and J. Drennan, "Microstructural Analysis of Sintered High-Conductivity Zirconia with Al₂O₃ Additions," *J. Am. Ceram. Soc.*, **65** [10], 474–478 (1982).
- 9. K. An, K.S. Ravichandran, R.E. Dutton, and S.L. Semiatin, "Microstructure, Texture, and Thermal Conductivity of Single Layer and Multilayer Thermal Barrier Coatings of Y₂O₃.Stabilized ZrO₂ and Al₂O₃ Made by Physical Vapor Deposition," *J. Am. Ceram. Soc.*, **82** [2], 399–406 (1999).
- 10. W.D. Kingery, H.K. Bowen, and D.R. Uhlmann, Introduction to Ceramics, 2nd edition, John Wiley, New York, p. 636 (1976).
- 11. W.N.D. Santos and R. Taylor, Effect of Porosity on the Thermal Conductivity of Alumina, *High Temp. High Pressures*, **25**, 89–98 (1993).
- 12. G.E. Youngblood, R.W. Trice, and R.P. Ingel, Thermal Diffusivity of Partially and Fully Stabilized (Yttria) Zirconia Single Crystals, *J. Am. Ceram. Soc.*, **71**, 3255–260 (1988).
- 13. Y.S. Touloukian, R.W. Powell, C.Y. Ho, and P.G. Clemens, *Thermophysical Properties of Solids*, vol. 2, pp. 93–98, Edited by Y.S. Touloukian and C.Y. Ho, Plenum Press, New York, 1970.
- 14. R.G. Munro, Evaluated Material Properties for a Sintered α-alumina, *J. Am. Ceram. Soc.*, **80** [8], 1919–28 (1997).
- 15. D.P.H. Hasselman, L.F. Johnson, L.D. Bentsen, R. Syed, and H.L. Lee, Thermal Diffusivity and Conductivity of Dense Polycrystalline ZrO₂ Ceramic, *Am. Ceram. Soc. Bull.*, **66** [5], 799–806 (1987).
- 16. R. Stevens, Zirconia and Zirconia Ceramics, 2nd ed., p. 30, Magnesium Elekton, Ltd., U.K., 1986.
- 17. R. Barea, M. Belmonte, M.I. Osendi, and P. Miranzo, Thermal Conductivity of Al₂O₃/SiC Platelet Composites, *J. Eur. Ceram. Soc.*, 23 [11], 1773–1778 (2003).

REPORT DOCUMENTATION PAGE

Form Approved OMB No. 0704-0188

gathering and maintaining the data needed, an	ormation is estimated to average 1 hour per i	esponse, including the time for review	ving instructions, searching existing data sources	
collection of information, including suggestions Davis Highway, Suite 1204, Arlington, VA 222	d completing and reviewing the collection of i for reducing this burden, to Washington Head 02-4302, and to the Office of Management ar	information. Send comments regardin Iquarters Services, Directorate for Info Id Budget, Paperwork Reduction Proj	g this burden estimate or any other aspect of this prmation Operations and Reports, 1215 Jefferson ect (0704-0188), Washington, DC 20503.	
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE	3. REPORT TYPE AND	ID DATES COVERED	
	December 2003	Tech	hnical Memorandum	
4. TITLE AND SUBTITLE		5.	. FUNDING NUMBERS	
Thermal Conductivity of Al	umina-Toughened Zirconia Cor	nposites	NIDE 22 700 02 04	
6. AUTHOR(S)			WBS-22-7/08-02-06	
Narottam P. Bansal and Dor	ngming Zhu			
7. PERFORMING ORGANIZATION N	AME(S) AND ADDRESS(ES)	8.	PERFORMING ORGANIZATION REPORT NUMBER	
National Aeronautics and S	pace Administration			
John H. Glenn Research Ce	nter at Lewis Field		E-14314	
Cieveland, Ohio 44135–3	91			
9. SPONSORING/MONITORING AGE	NCY NAME(S) AND ADDRESS(ES)	10	0. SPONSORING/MONITORING AGENCY REPORT NUMBER	
National Aeronautics and S	pace Administration			
Washington, DC 20546–00	001		NASA TM-2003-212896	
<i>, ,</i>				
II. SUFFLEMENIAKT NUIES				
	, <u>8</u> • • • • • • • • • • • • • • •	,		
12a. DISTRIBUTION/AVAILABILITY S	STATEMENT	11	2b. DISTRIBUTION CODE	
Unclassified - Unlimited				
		I		
Subject Categories: 7, 24, a	nd 27 Distrib	oution: Nonstandard		
Subject Categories: 7, 24, a Available electronically at http://	nd 27 Distrib	ution: Nonstandard		
Subject Categories: 7, 24, a Available electronically at http:// This publication is available from	nd 27 Distrib /gltrs.grc.nasa.gov n the NASA Center for AeroSpace In	vution: Nonstandard		
Subject Categories: 7, 24, a Available electronically at <u>http:/</u> This publication is available from 13. ABSTRACT (<i>Maximum 200 word</i>	nd 27 Distrib /gltrs.grc.nasa.gov n the NASA Center for AeroSpace In s)	nution: Nonstandard formation, 301–621–0390.		
 Subject Categories: 7, 24, a Available electronically at http:// This publication is available from 13. ABSTRACT (Maximum 200 word 10-mol% yttria-stabilized z hot pressing at 1500 °C in v steady-state laser heat flux v 10-mol% alumina did not sl 30-mol% alumina showed a thermal conductivity were i 	nd 27 Distrib /gltrs.grc.nasa.gov n the NASA Center for AeroSpace In s) irconia (10YSZ)-alumina compo acuum. Thermal conductivity of echnique, increased with increas now any change in thermal conductivi a decrease in thermal conductivi n good agreement with those ca	oution: Nonstandard formation, 301–621–0390. Disites containing 0 to 30 n f the composites, determin ise in alumina content. Con fuctivity with temperature. ty with increase in temper lculated from simple rule	nol% alumina were fabricated by led at various temperatures using a mposites containing 0, 5, and . However, those containing 20 and ature. The measured values of of mixtures.	
 Subject Categories: 7, 24, a Available electronically at http:// This publication is available from 13. ABSTRACT (Maximum 200 word 10-mol% yttria-stabilized z hot pressing at 1500 °C in v steady-state laser heat flux to 10-mol% alumina did not sl 30-mol% alumina showed a thermal conductivity were i 14. SUBJECT TERMS Ceramic composites; Zircon 	nd 27 Distrib /gltrs.grc.nasa.gov in the NASA Center for AeroSpace In s) irconia (10YSZ)-alumina compo- acuum. Thermal conductivity of technique, increased with increase now any change in thermal conductivit in good agreement with those ca	nution: Nonstandard formation, 301–621–0390. posites containing 0 to 30 n f the composites, determine use in alumina content. Con luctivity with temperature ty with increase in temper lculated from simple rule ity	101% alumina were fabricated by led at various temperatures using a mposites containing 0, 5, and . However, those containing 20 and ature. The measured values of of mixtures. 15. NUMBER OF PAGES 15. 16. PRICE CODE	
 Subject Categories: 7, 24, a Available electronically at http:// This publication is available from 13. ABSTRACT (Maximum 200 word) 10-mol% yttria-stabilized z hot pressing at 1500 °C in v steady-state laser heat flux to 10-mol% alumina did not sl 30-mol% alumina showed a thermal conductivity were i 14. SUBJECT TERMS Ceramic composites; Zircon 17. SECURITY CLASSIFICATION OF REPORT 	nd 27 Distrib /gltrs.grc.nasa.gov n the NASA Center for AeroSpace In s) irconia (10YSZ)-alumina compo- acuum. Thermal conductivity or technique, increased with increase now any change in thermal conductivity n good agreement with those ca hia-alumina; Thermal conductivity 18. SECURITY CLASSIFICATION OF THIS PAGE	Initial Security CLASSIFICATI	nol% alumina were fabricated by ned at various temperatures using a mposites containing 0, 5, and . However, those containing 20 and ature. The measured values of of mixtures. 15. NUMBER OF PAGES 15 16. PRICE CODE ION 20. LIMITATION OF ABSTRACT	
Subject Categories: 7, 24, a Available electronically at http:// This publication is available from 13. ABSTRACT (Maximum 200 word 10-mol% yttria-stabilized z hot pressing at 1500 °C in v steady-state laser heat flux 1 10-mol% alumina did not sl 30-mol% alumina showed a thermal conductivity were i 14. SUBJECT TERMS Ceramic composites; Zircon 17. SECURITY CLASSIFICATION OF REPORT Unclassified	nd 27 Distrib /gltrs.grc.nasa.gov in the NASA Center for AeroSpace In s) irconia (10YSZ)-alumina compo- acuum. Thermal conductivity of technique, increased with increase now any change in thermal conductivity a decrease in thermal conductivity n good agreement with those can hia-alumina; Thermal conductive 18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	ution: Nonstandard formation, 301–621–0390. osites containing 0 to 30 n f the composites, determinate in alumina content. Conductivity with temperature. ty with increase in temper lculated from simple rule ity 19. SECURITY CLASSIFICATIOF ABSTRACT Unclassified	100% alumina were fabricated by led at various temperatures using a mposites containing 0, 5, and . However, those containing 20 and ature. The measured values of of mixtures. 15. NUMBER OF PAGES 15. 16. PRICE CODE ION 20. LIMITATION OF ABSTRACT	