


Serial Charging Test On High Capacity Li-ion Cells for the Orbiter Advanced Hydraulic Power System

Judith A. Jeevarajan
Brad Irlbeck
NASA- JSC


**2004 NASA Battery Workshop
November 16-18, 2004**

Judith Jeevarajan/Brad Irlbeck/NASA-JSC



Introduction

- **Objective and Test Description**
- **Test Data**
- **General Observations and Conclusions**




Objective: Confirm That Charging a Series String of JSB 190 Ah Cells Is Feasible and Results in Acceptable Cell to Cell Voltage Differences

- Intent was to accelerate cell aging to see if cell to cell differences impact useful capacity



Description: Test conducted from April - August 2004 with a module consisting of six cells in series


Test plan sequence included 30 cycles performed over 6 months:

Start:	12 Charge / Discharge Cycles (Back to Back Cycles)	} 40 °C & 80% SOC Storage Between Cycles (changed to 30 °C after month 2)
1 Month:	1 Charge / Discharge Cycle	
2 Months:	1 Charge / Discharge Cycle	
3 Months:	1 Charge / Discharge Cycle	
4 Months:	1 Charge / Discharge Cycle	
5 Months:	1 Charge / Discharge Cycle	
6 Months:	1 Charge / Discharge Cycle	
6 Months:	12 Charge / Discharge Cycles (Back to Back Cycles)	



Module Configuration





Cell History



Cell Position	Cell S/N	Cell Previous Testing
1	003	3 month, 30 deg C Capacity Loss 8/01
2	013	None
3	022	None
4	096	None
5	111	Discharge vs Temp 2/02 (1 cycle each at 0°C, 5°C, 10°C, 15°C, 25°C, 40°C and 65°C)
6	126	None

Capacity Cell Cycle Tests Performed Prior to Serial Charging Test (Ah at C/10 from 4.1 to 3.0 VDC)		
199.3,	199.2,	199.3
190.4,	190.6,	190.6
195.8,	195.9,	195.8
193.6,	193.9,	193.8
201.7,	201.6,	201.4
196.3,	196.1,	195.8



Charge /Discharge Protocol

Placed in Chamber at 20 °C for Charge or Discharge

Charge:

- C/5 (38 A) to 24.6 V (4.1 V per cell)
- Constant voltage until current decreases to C/100 (1.9 A) or any one cell reaches 4.15 V

Discharge:


- C/2 (95 A) from 24.6 to 18.0 V (4.1 to 3.0 V per cell) or any one cell reaches 2.80 V with 5 second, 2.7 C (513 A) pulses at 15, 20, 50, 70, 85, 90 minutes
- C/10 (19 A) to 18.0 V or any one cell reaches 2.80 V

Partial Charge (only for storage between the 6 monthly cycles):

- C/5 (38 A) to 80% SOC

Placed in Chamber at 40 °C and 80% SOC for 1 Month Storage Between Cycles

- Changed to 30 °C after cycle 14



Cutoff Points for Each Cycle




Cycle	CC Charge Stop	CV Charge Stop	C/2 Discharge Stop	C/10 Discharge Stop
1	24.6 V	1.9 A	18 V	2.8 V (6)
2	24.6 V	1.9 A	18 V	2.8 V (6)
3	24.6 V	1.9 A	18 V	2.8 V (4)
4	24.6 V	1.9 A	18 V	2.8 V (4)
5	24.6 V	1.9 A	18 V	2.8 V (4)
6	24.6 V	1.9 A	18 V & 2.8 V(4)	2.8 V (4)
7	24.6 V	1.9 A	18 V & 2.8 V(4)	2.8 V (4)
8	24.6 V	1.9 A	18 V & 2.8 V(4)	2.8 V (4)
9	24.6 V	1.9 A	18 V & 2.8 V(4)	2.8 V (3)
10	24.6 V	1.9 A	18 V	2.8 V (6)
11	24.6 V	1.9 A	18 V	2.8 V (6)
12	24.6 V	1.9 A	18 V	2.8 V (4)
13	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
14	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
15	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)

Cycle	CC Charge Stop	CV Charge Stop	C/2 Discharge Stop	C/10 Discharge Stop
16	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
17	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
18	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
19	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
20	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
21	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
22	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
23	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
24	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
25	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
26	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
27	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
28	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
29	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)
30	24.6 V	1.9 A	2.8 V (3)	2.8 V (3)

Note: numbers in parenthesis (x) indicate the cell which caused cutoff


Cutoff Points	CC Charge Stop	Module = 24.6 V	or	1 st Cell = 4.15 V
	CV Charge Stop	Current = 1.9 A	or	1 st Cell = 4.15 V
	C/2 Discharge Stop	Module = 18.0 V	or	1 st Cell = 2.8 V
	C/10 Discharge Stop	Module = 18.0 V	or	1 st Cell = 2.8 V




Typical Module Level Performance for One Cycle (cycle 1)



Crane Serial Charging Test - Module Parameters (cycle 1)






Typical Cell Level Performance for One Cycle (cycle 1)



Crane Serial Charging Test - Cell Parameters, (cycle 1)







Cell Voltage Long Term Trends



Crane Serial Charging Test Long Term Trend






Module Level Performance Changes




Crane Serial Charging Test - Cycle Comparison (cycle 1 vs cycle 12)

Timescale Shifted Slightly to Distinguish Between Traces



Little Change in Initial 12 Back to Back Cycles




Module Level Performance Changes



Crane Serial Charging Test - Cycle Comparison (cycle 1 vs cycle 30)

Timescale Shifted Slightly to Distinguish Between Traces



Little Change in Final Group of Back to Back Cycles




Module Level Voltage Trends




Crane Serial Charging Test - Module Voltage at Beginning & End of Discharge

Charge to Module = 24.6 V or 1st Cell = 4.15 V
Discharge to Module = 18.0 V or 1st Cell = 2.8 V




Increase In End of Discharge Voltage as Cells Age Because Discharge Cutoff Point Has Changed from Module Level to Cell Level



Cell Level Voltage Trends

Crane Serial Charging Test - Cell Voltage at Start and End of Discharge

Charge to Module = 24.6 V or 1st Cell = 4.15 V
Discharge to Module = 18.0 V or 1st Cell = 2.8 V



Cell 3 Becomes the Driver for the Discharge Cutoff Point (compared to other cells, this cell has lowest initial resistance and mid range initial capacity)




Cell-to-Cell Comparison During Charge




Crane Serial Charging Test - Cycle Comparison (cycle 1 vs cycle 30)

Voltage Scale Shifted to Distinguish Between Traces



Little Change in Charge Performance or Order of Cell Voltage
(cell with highest voltage to cell with lowest voltage)


Judith Jeevarajan/Brad Irlbeck/NASA-JSC




Cell-to-Cell Comparison During Discharge

Crane Serial Charging Test - Cycle Comparison (cycle 1 vs cycle 30)

X and Y Axis Shifted to Distinguish Between Traces




Little Change in Order of Cell Voltage, But Discharge Duration Has Decreased




Module Capacity Long Term Trends



Crane Serial Charging Test - Charge and Discharge Capacity







Module Resistance Trends

Crane Serial Charging Test - Module Resistance for All Pulses


Resistance Calculated (dV/dI) From Start of Pulse To End of Power Pulse






Module Resistance Trends

Crane Serial Charge Test - Module Resistance During Discharge
Resistance Calculated (dV/dI) From Start of Pulse To End of Power Pulse







Cell Resistance Trends

Crane Serial Charge Test - Resistance at the 90 Minute Pulse

Resistance Calculated (dV/dI) From Start of Pulse To End of Power Pulse





Cell to Cell Ranking



Cycle 1

Internal Resistance	Voltage - Charge	Voltage - Early in Discharge	Voltage - Late in Discharge
1	1	2	2
5	2	5	5
2	5	1	1
6	4	6	3
4	6	4	4
3	3	3	6

Highest
↓
Lowest

Cycle 12

Internal Resistance	Voltage - Charge	Voltage - Early in Discharge	Voltage - Late in Discharge
1	1	2	2
5	2	5	5
2	5	1	1
6	4	6	3
4	3	4	6
3	6	3	4

Cycle 17

Internal Resistance	Voltage - Charge	Voltage - Early in Discharge	Voltage - Late in Discharge
5	1	1	1
1	2	5	2
6	5	2	5
2	4	6	4
3	3	4	6
4	6	3	3


Highest
↓
Lowest

Cycle 30

Internal Resistance	Voltage - Charge	Voltage - Early in Discharge	Voltage - Late in Discharge
5	1	1	1
1	2	5	2
6	5	2	5
2	4	6	4
3	3	4	6
4	6	3	3

○ = Cell Causing Discharge Cutoff

- *The Relative Order is Generally Consistent*
- *Cells With Higher Internal Resistance Have Higher Voltage Throughout Charge/Discharge Cycle*
- *Cells With Lower Internal Resistance Cause the Discharge Cutoff*




Individual Cell Capacity Cycles



Cells Subjected to Capacity Cycles Before and After Serial Charging Test

- Pretest (3 cycles) 4.1 to 3.0 VDC at 19 amps
- Post Test (1 cycle) 4.1 to 3.0 VDC at 95 amps Followed By 19 amps to 3.0 VDC

Parameter	Cell 1 (s/n 003)	Cell 2 (s/n 013)	Cell 3 (s/n 022)	Cell 4 (s/n 096)	Cell 5 (s/n 111)	Cell 6 (s/n 126)
Ah Pretest Cycle 1	199.30	190.43	195.76	193.60	201.72	196.28
Ah Pretest Cycle 2	199.19	190.63	195.91	193.85	201.56	196.07
Ah Pretest Cycle 3	199.35	190.58	195.75	193.80	201.35	195.81
Ah Post Test	187.47	184.84	189.40	188.86	183.98	188.04
Decrease During Serial Charging Test	6.0%	3.0%	3.2%	2.5%	8.6%	4.0%



General Observations



Although it looks like module level voltage drives the cutoff for charge, the actual cutoff is due to unbalanced cell voltages that drive the module voltage up.

Individual cell voltage drives the cutoff for discharge

Low resistance cells are the first to reach the low-voltage cutoff

Cell-to-Cell voltage differences are generally small and show similar trends for each cycle

Increase for a distinct window during charge and at the end of discharge

Increase in max to min cell voltage difference with time / cycles

Decrease in max to min cell voltage difference during high current pulses with time / cycles


Individual cell voltage trends (with respect to other cells) are very repeatable from cycle to cycle, although voltage slowly degrades with time / cycles (resistance growth)

Much more difference observed near end of discharge

Little change in order of cell voltage (cell with highest voltage to cell with lowest voltage)


Temp sensor on the side of cell (between 2 cells) shows much greater rise during discharge than for single cell tests (18 °C vs 5 °C)

Conclusion: Serial Charging of this string of cells is feasible as it has only a minor impact on useful capacity



Acknowledgment


NSWC – Crane, Indiana for performing the tests.




Cell Level Temperatures - Discharge (cycle 1)



Crane Serial Charging Test - Top of Cell Temp (cycle 1)





Cell Level Temperatures - Discharge (cycle 1)



Crane Serial Charging Test - Side of Cell Temp (cycle 1)

