



Determination of Turbine Blade Life From Engine Field Data

*Erwin V. Zaretsky, Jonathan S. Litt, and Robert C. Hendricks
Glenn Research Center, Cleveland, Ohio*

*Sherry M. Soditus
United Airlines Maintenance, San Francisco, California*

NASA STI Program . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) program plays a key part in helping NASA maintain this important role.

The NASA STI Program operates under the auspices of the Agency Chief Information Officer. It collects, organizes, provides for archiving, and disseminates NASA's STI. The NASA STI program provides access to the NASA Aeronautics and Space Database and its public interface, the NASA Technical Reports Server, thus providing one of the largest collections of aeronautical and space science STI in the world. Results are published in both non-NASA channels and by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services also include creating custom thesauri, building customized databases, organizing and publishing research results.

For more information about the NASA STI program, see the following:

- Access the NASA STI program home page at <http://www.sti.nasa.gov>
- E-mail your question to help@sti.nasa.gov
- Fax your question to the NASA STI Information Desk at 443-757-5803
- Phone the NASA STI Information Desk at 443-757-5802
- Write to:
STI Information Desk
NASA Center for AeroSpace Information
7115 Standard Drive
Hanover, MD 21076-1320

NASA/TP—2013-217030



Determination of Turbine Blade Life From Engine Field Data

*Erwin V. Zaretsky, Jonathan S. Litt, and Robert C. Hendricks
Glenn Research Center, Cleveland, Ohio*

*Sherry M. Soditus
United Airlines Maintenance, San Francisco, California*

National Aeronautics and
Space Administration

Glenn Research Center
Cleveland, Ohio 44135

April 2013

This work was sponsored by the Fundamental Aeronautics Program
at the NASA Glenn Research Center.

Level of Review: This material has been technically reviewed by an expert reviewer(s).

Available from

NASA Center for Aerospace Information
7115 Standard Drive
Hanover, MD 21076-1320

National Technical Information Service
5301 Shawnee Road
Alexandria, VA 22312

Available electronically at <http://www.sti.nasa.gov>

Determination of Turbine Blade Life From Engine Field Data

Erwin V. Zaretsky, Jonathan S. Litt, and Robert C. Hendricks
National Aeronautics and Space Administration
Glenn Research Center
Cleveland, Ohio 44135

Sherry M. Soditus
United Airlines Maintenance
San Francisco, California 94128

Summary

It is probable that no two engine companies determine the life of their engines or their components in the same way or apply the same experience and safety factors to their designs. Knowing the failure mode that is most likely to occur minimizes the amount of uncertainty and simplifies failure and life analysis. Available data regarding failure mode for aircraft engine blades, while favoring low-cycle, thermal-mechanical fatigue (TMF) as the controlling mode of failure, are not definitive. Sixteen high-pressure turbine (HPT) T-1 blade sets were removed from commercial aircraft engines that had been commercially flown by a single airline and inspected for damage. Each set contained 82 blades. The damage was cataloged into three categories related to their mode of failure: (1) TMF, (2) Oxidation/erosion (O/E), and (3) Other. From these field data, the turbine blade life was determined as well as the lives related to individual blade failure modes using Johnson-Weibull analysis. A simplified formula for calculating turbine blade life and reliability was formulated. The L_{10} blade life was calculated to be 2427 cycles (11 077 hr). The resulting blade life attributed to O/E equaled that attributed to TMF. The category that contributed most to blade failure was "Other." If there were no blade failures attributed to O/E and TMF, the overall blade L_{10} life would increase approximately 11 to 17 percent.

1.0 Introduction

The service life of an aircraft gas turbine engine is based on deterministic calculations of low-cycle fatigue (LCF) and previous field experience with similar engines. It is probable that no two engine companies determine the life of their engines in the same way or apply the same experience and safety factors to their designs (Ref. 1). Davis and Stearns (Ref. 2) and Halila, Lenahan, and Thomas (Ref. 3) discuss the mechanical and analytical methods and procedures for turbine engine and high-pressure turbine (HPT) design. The designs of the engine components are based on life predictions by using material test curves that relate life in cycles or time (hr) as a function of stress. Six criteria for failure were presented: (1) Stress rupture; (2) Creep; (3) Yield; (4) LCF; (5) High-cycle fatigue (HCF); and

(6) Fracture mechanics. Not mentioned as probable failure modes and/or cause for removal of rotating engine components in References 2 and 3 are oxidation, corrosion, and erosion (wear).

Turbine blade metal temperatures frequently reach 1040 to 1090 °C (1900 to 2000 °F), only a few hundred degrees below the melting point of the alloys used. Only because of oxidation-protective coatings and internal forced cooling is it possible for metals to be used under such harsh conditions. All commercial aircraft gas turbine engines use some form of nickel- or cobalt-base superalloy that has been intentionally strengthened and alloyed to resist high stresses in a high-temperature oxidizing environment (Ref. 4).

Aircraft engine turbine blades are not life-limited parts; that is, they can be used until they are no longer repairable, unlike limited life parts that must be removed after a specified amount of time or cycles, even if they appear new. The blades undergo regular inspections that result in no action, repair, or removal for cause. In this paper, a blade is considered failed when it is no longer fit for service and must be either repaired or replaced.

It is believed that the primary failure mechanism in turbine blades is thermal-mechanical fatigue (TMF). TMF cracks usually appear along the leading or trailing edge of the first-stage HPT T-1 blade (Ref. 5). Also, because the turbine blades are exposed to highly corrosive and oxidizing combustion gases, the loss of metal by scaling, spalling, and corrosion can cause rapid failure.

Turbine blade materials have creep-rupture resistance to minimize creep failure at high speed and temperature for extended periods. Initially, the time to removal of these blades is determined by a creep criterion that is deterministic or is not assumed to be probabilistic. Material test data are used to predict rupture life based on calculated stress and temperature. This criterion is dependent on time exposure at stress and temperature (Ref. 1).

Blade coating life is another time-limiting criterion for removal and repair. The blades usually are removed when the engine is removed from service for other reasons, and, as necessary, the remaining coating is removed by chemical stripping or machining and is replaced. The coating life usually does not dictate blade replacement, only repair (Ref. 1).

Besides the time-life limitation of creep, the limiting time for blade replacement is HCF life. As with LCF, HCF is

probabilistic. The blades are subject to vibratory stresses combined with mechanical stresses from centrifugal loads, gas aerodynamic loads, and thermal loads (Ref. 1).

The failure modes for each blade in a turbine blade set are competitive. Knowing the blade failure mode that is most likely to occur minimizes the amount of uncertainty and simplifies failure and blade life analysis. Available data regarding failure mode, although favoring low-cycle, TMF as the controlling mode of failure, are not definitive.

There are several other major contributors besides the competing failure modes that contribute to turbine blade set life uncertainty. First the data are quantal-response data. This means that the data are either censored on the left (sometime after failure occurs) or censored on the right (failure has not occurred by a defined time). This situation arises when each blade is inspected only once and is determined to have failed or not failed. For turbine blade data, this type of information can be useful for reliability studies if the failed blades can be clustered by age (time to failure) at inspection (and the range of ages is large relative to the part life) (Ref. 6).

In 1939, Weibull (Refs. 7 to 9) is credited with being the first to suggest a reasonable way to estimate fracture strength with a statistical distribution function. He also applied the method and equation to fatigue data based on small sample (population) sizes. Johnson (Ref. 10) while with the GM Research Center in the 1950s and 1960s is credited with coming up with a practical engineering analysis based on the Weibull distribution function (Refs. 7 to 9). Johnson, using the Weibull distribution function to evaluate fatigue data, provides a means to evaluate censored data and to extract from these data the lives of the individual components that affect the system life.

In view of the aforementioned, it becomes the objectives of the work reported herein to (1) determine turbine blade life from turbine engine field data using Johnson-Weibull analysis, (2) determine the turbine blade life related to individual blade failure modes, and (3) provide a simplified formula for determining turbine blade life from field data for engine turbine blade sets.

Nomenclature

e	Weibull slope
F	probability of failure, fraction or percent
F_m	mean probability of failure
k	life at operational condition, number of stress cycles or hr
L	life, number of stress cycles or hr
L_β	characteristic life or life at which 63.2 percent of population fails, number of stress cycles or hr

L_{10}	10-percent life or life at which 90 percent of a population survives, number of stress cycles or hr
L_{avg}	average life, total time divided by total number of components, number of stress cycles or hr
L_M	mean time to removal
L_m	mean life of a population, number of stress cycles or hr
M	total number of stress cycles at operating condition where $M = pm$
N	total number of engine operational condition changes over flight profile
N_{eng}	total number of engines in overhaul in field data set
m	number of stress cycles per interval
n	number of blades in a set
n_{blade}	number of blade failures within a specified blade set of the population N_{eng}
p	number of intervals
S	probability of survival, fraction or percent
t	time to blade set removal, cycles or hr
V	volume, m^3 ($in.^3$)
X	fractional percent of components or blades failed from specific cause, or operating variable (Appendix A)
X_n	fractional percent of time at operational condition
σ	stress, Pa (psi)
σ_u	location parameter below which stress no failure will occur, Pa (psi)
σ_β	characteristic stress at which 63.2 percent of population fails, Pa (psi)

Subscripts

avg	designation of average life
blade	turbine blade of a blade set
blade set	turbine blade set
eng	engine
fm	cataloged failure mode
i	i -th component out of n
k	k -th engine operational condition within flight profile

m	designation of mean life or probability of survival at mean life
n	n-th component of a set of blades; number of blades in blade set
mis	mission or operational life
ref	reference life or reference probability of survival
sys	system probability of survival or system life
V	volume
β	designation of characteristic life
1,2	bodies 1, 2, etc.; failure mode 1, 2, etc.

2.0 High-Pressure Turbine T-1 Blade Sets

2.1 Engine Operation and Repair

When a new aircraft engine is introduced into an airline fleet, one of the first questions asked is what will be the average time (hr) between overhaul or refurbishment of the high-pressure turbine (HPT) T-1 blades. Typically, for a new engine program the airlines bring the engines in early for overhaul, for example, approximately at 10 000 hr. As the airlines gain experience and confidence with an engine type, the time to refurbishment is increased for first-run engines, for example, at 22 000 hr. After refurbishment, second-run engines probably get around 15 000 hr on the wing. The hot section is typically overhauled when the engine is removed from service (Ref. 1).

The typical hour-to-cycle ratio depends on the airline operator. Short-haul airline operation typically runs between 1 to less than 4 hr/cycle. Long-haul, coast-to-coast airline operation in the continental United States typically runs between 4 to 6 hr/cycle. For other airline operations, the average can be 6 to 13 hr/cycle. These numbers play an important part in the overhaul process. It is expected that for the shorter cycle engines there will be more deterioration on the hot-section parts on the engines that have a shorter time cycle, implying that the deterioration is cycle dependent rather than time dependent.

When an aircraft engine is removed from service for cause and shipped to the refurbishment shop, the engine and the performance of its individual modules are evaluated and the root cause of removal determined. If the engine is removed for performance or hardware deterioration or major part failure, the engine will be, in most cases, completely broken down into modules: for example, compressor, turbine, auxiliary gearbox, and so forth. Each module will then be refurbished (Ref. 1).

2.2 HPT T-1 Blades

A photograph of the blade type studied in this report is shown in Figure 1(a). The blade is made from a single-crystal nickel-based alloy and plated using plasma vapor deposition

(PVD) to provide oxidation and corrosion resistance. The blade material and coating chemistries are given in Table 1 (Ref. 11). The blade section is approximately 71 mm (2.8 in.) in height and has a cord length at the tip of approximately 37 mm (1.46 in.). The height from the blade root to the blade tip is approximately 118 mm (4.65 in.). The blade weighs approximately 277 g (0.611 lb). There are 82 blades in a T-1 blade set for the particular engine application studied.

A total of 82 blades are inserted around a T-1 turbine disk. The resulting tip-to-tip diameter of the blades is approximately 0.93 m (36.5 in.). The blades are spun at a speed of approximately 9126 rpm during cruise, or 84.5 percent of the maximum speed of 10 800 rpm. Loading on the blades is due to centrifugal load, thermal loads from heating of the blades, aerodynamic loads from impingement of the hot combustion gases against the blade, and vibratory loads due to blade rotation. A load and stress analysis of these blades was beyond the scope of this paper.

An engine is borescoped periodically to determine its health. It is not uncommon to find that the HPT blades deteriorate in service because of the extreme operating conditions they encounter. Even when an engine is operating properly, it can experience some form of hardware deterioration of the HPT T-1 blades. Such a failed blade is shown in Figure 1(b). At the time of removal this blade had run 15 000 hr (2700 cycles). The condition is typical for this time period.

2.3 Blade Failure Criteria

For the purpose of this report, blade failure is defined as the blade being no longer fit for its intended purpose but still capable of functioning for a limited time until being removed from service. Depending on the condition of the deterioration, an engine may be allowed to remain in service on a decreased-cycle inspection interval until it is determined that the deterioration is beyond limits (or its exhaust gas temperature (EGT) margin is too small) and the engine must be removed from service (Ref. 1). Causes of blade failure and/or removal are as follows:

- (1) Creep (stress rupture)
- (2) Yield
- (3) Thermal-mechanical fatigue (TMF)
 - (a) Low-cycle fatigue (LCF)
 - (b) High-cycle fatigue (HCF)
- (4) Fracture mechanics (flaw initiated crack)
- (5) Fretting (wear and fatigue)
- (6) Oxidation
- (7) Corrosion
- (8) Erosion (wear)
- (9) Foreign object damage (FOD)
- (10) Wear (blade tip rub)




Figure 1.—Comparison of unfailed and failed T-1 turbine blades used in study. (a) Example of unfailed T-1 turbine blade. (b) Example of failed T-1 turbine blade.

TABLE 1.—T-1 TURBINE BLADE MATERIAL CHEMISTRY (REF. 11)

Chemical element, wt%											Density, kg/m ³ (lb/in. ³)	
Ni	Cr	Ti	Mo	W	Re	Ta	Al	Co	Hf	Si	Y	8.94×10 ³ (0.323)
Bal.	5	0	2	6	3	8.7	5.6	10	0.1	---	---	
Overlay (coating)												
x1	x3	---	---	---	---	---	x4	x2	x5	x6	x7	-----

x elements of proprietary composition, x1 > x2 ...etc.

For post-operation failure inspection of blade sets, the blade failures were cataloged under three categories:

- (1) Thermal-mechanical fatigue (TMF)
- (2) Oxidation/erosion (O/E)
- (3) Other (creep, yield, fracture mechanics, fretting, corrosion, FOD, and wear)

The blades removed from service can generally be repaired or refurbished two or more times. The blades can be stripped of their coatings and recoated. There is a minimum wall thickness and aerodynamic shape that must be met before the blade can be recoated. They can have minor blend repairs and new abrasive tips installed, and the roots can be shot peened. Of those T-1 blades that are scrapped, approximately 90 percent are due to under-platform stress corrosion.

3.0 Procedure

Sixteen high-pressure turbine (HPT) T-1 blade sets were removed from commercial aircraft engines that had been commercially flown by a single airline. These engines were brought to the maintenance shop for refurbishment or overhaul. The blades on each HPT T-1 blade set were removed and inspected for damage. The damage was cataloged into three categories related to their mode of failure:

- (1) Thermal-mechanical fatigue (TMF)
- (2) Oxidation/erosion (O/E)
- (3) Other

The technician had a preset order in which to look for failure modes. The blades were first inspected for TMF. If cracks were evident on the blade, and even if other failure modes were also evident, the cause for removal was cataloged as TMF. The blades not failed from TMF were inspected for O/E. As with those blades cataloged as being failed by TMF, those blades that exhibited O/E damage were so cataloged even where damage from other failure modes was manifested on the blade. The blades not failed for TMF or

O/E were examined for damage for the other causes discussed previously. These other causes were not separately identified and were categorized and cataloged as "Other."

A list of the engine blade sets, their time at removal, their respective number of failures, and their failure modes are given in Table 2. Of a total of 1312 blades contained in the $N_{eng} = 16$ blade sets, 111 were considered to have failed, or approximately 8.5 percent of the population. Although each of these blade sets was to comprise all new blades when installed in the engine, three blade sets had a mix of new blades with previously run (older) blades. The failures that were reported for the mixed blade sets did not distinguish between the older and newer blades.

Ideally, the time to failure for each blade in a set should be known. More specifically, the time at which the first blade fails in a set should be known based on the assumption that at the time of the first failure, the entire set is no longer fit for its intended purpose. For these type data, these times are not available and will have to be estimated. However, once the time to first failure in a set is determined or estimated, the distributive lives of the blades can be determined as well as the resulting lives from each failure mode.

TABLE 2.—DATA SET FOR T-1 TURBINE BLADE SETS INCLUDING ESTIMATED TIME TO FIRST BLADE FAILURE IN A SET AND CAUSES OF FAILURE
[Number of turbine blades in set, 82.]

Engine number	Time of removal of blade set		Number of failures	Observed failure mode			Estimated time to first blade failure, cycles
	hr	cycles		Oxidation/erosion (O/E)	Thermal-mechanical fatigue (TMF)	Other	
1B	5 898	1327	1	---	---	1	1327
2B	7 318	1404	5	3	2	---	1017
3B	8 188	1675	2	---	---	2	1443
4B	^a 8 333	1747	3	---	1	2	1391
5B	9 049	1827	4	3	---	1	1379
6B	8 717	1843	41	---	1	40	886
7B	9 600	1924	10	---	10	---	1228
8B	10 113	2043	4	1	1	2	1542
9B	7 770	2047	7	7	---	---	1394
10B	10 675	2091	2	---	---	2	1801
11B	7 690	2115	4	1	1	2	1596
12B	11 051	2175	2	---	1	1	1873
13B	10 398	2184	12	4	---	8	1348
14B	11 614	2292	5	1	1	3	1660
15B	10 238	2295	3	3	---	---	1827
16B	14 083	2847	6	---	4	2	1994
Total			111	23	22	66	
L_{avg}	9 421	1990					1482

^aEstimated.

4.0 Statistical Analysis

4.1 Weibull Analysis

In 1939, Weibull (Refs. 8 and 9) is credited with being the first to suggest a reasonable way to estimate fracture strength with a statistical distribution function. He also applied the method and equation to fatigue data based on small sample (population) sizes. The probability distribution function identified by Weibull is as follows:

$$\ln \ln \left(\frac{1}{S} \right) = e \ln \left(\frac{L}{L_\beta} \right) \quad \text{where } 0 < L < \infty; 0 < S < 1 \quad (1)$$

This form of Equation (1) is referred to as the two-parameter Weibull distribution function. The derivation of this equation is given in Reference 12, and in Appendix A.

The variable S is the level of survivability being considered. For example, if 15 percent of the samples have failed, then the survivability would be 0.85. L is the life in cycles or hours at which the fraction $(1 - S)$ of samples have failed. In the case of S equaling 0.9 (90 percent), L is the life at which 10 percent of the samples have failed—typically referred to as the L_{10} life. L_β is the characteristic life of the material, defined as the life at which 63.2 percent of the samples have failed. Finally, e is the Weibull parameter or slope, which is an indicator of the scatter or distribution in the data—the larger the slope, the smaller the amount of scatter.

When plotting the $\ln \ln [1/S]$ as the ordinate against the $\ln L$ as the abscissa, fatigue data are assumed to plot as a straight line (Fig. 2). The ordinate $\ln \ln [1/S]$ is graduated in statistical percent of components failed or removed for cause as a function of $\ln L$, the natural log of the time or cycles to failure. The tangent of the line is the Weibull parameter or slope e , which is indicative of the shape of the cumulative distribution or the amount of scatter of the data. A Weibull slope e of 1.0 is indicative of an exponential distribution of the data, 2.0 is a Rayleigh distribution, and 3.57 is approximately that of a normal distribution of data. For convenience, the ordinate is graduated as the statistical percent of components failed.

There are many examples of the use of the Weibull distribution function to determine the life and strength of materials, structural components, and machines. The first use of the Weibull distribution function outside of Weibull's original reported work (Refs. 8 and 9) was by Lundberg and Palmgren (Ref. 13) for predicting the life of ball and roller bearings.

Burrow et al. (Ref. 14) used Weibull analysis to determine the reliability of tensile strength measurements on dental restorative materials. Ellis and Tordonato (Ref. 15) used Weibull analysis in their failure analysis and life assessment studies of boiler tubes. The fatigue life associated with corrosion fatigue cracking of welded tubing was predicted.




Figure 2.—Weibull plot where (Weibull) slope of tangent of line is e ; probability of survival, S_β , is 36.8 percent at which $L = L_\beta$ or $L/L_\beta = 1$.

Tomimatsu, Kikuchi, and Sakai (Ref. 16) used Weibull analysis in their determination of the fracture toughness of two steels used in reactor pressure vessel fabrication. Weibull analysis and dynamic fatigue slow-crack-growth parameters were used by Osborne, Graves, and Ferber (Ref. 17) to demonstrate a significant difference in the high-temperature behavior of two silicon nitrides (SN-88 and NT164). Ostojic and Berndt (Ref. 18) demonstrated that Weibull parameters such as slope and characteristic life were meaningful parameters when determining the variability of bond strengths of thermally sprayed coatings.

Holland and Zaretsky (Ref. 19) used Weibull statistics to determine the fracture strength of two different batches of cast A357-T6 aluminum. The mean fracture strengths for the two batches were found to differ by an insignificant 1.1 percent. However, using a Weibull analysis they determined at the 99.9999 percent probability of survival (one failure in a million) that the actual fracture strengths differed by 14.3 percent.

Weibull analysis can also be used to evaluate preventive maintenance practices. Williams and Fec (Ref. 20) studying reconditioned railroad roller bearings determined with Weibull analysis that the current practice of inspecting bearings at 200,000 miles was an acceptable practice. Summers-Smith (Ref. 21) applied Weibull analysis to the service life obtained from maintenance records that identified the cause of failure of a hydrodynamically lubricated thrust bearing and a rolling-element bearing, and increased production reliability. Similarly, Vlcek et al. (Ref. 22) used Weibull analysis to rank the relative fatigue lives of PVC coatings used in a printing process. The fatigue life of one PVC coating over another was demonstrated using L_{10} lives, and the ratio of the L_{10} life of a developed PVC coating to the original was found to be 2.3.

The method of using the Weibull distribution function for data analysis for determining component life and reliability was developed and refined by Johnson (Ref. 10). The Johnson (Ref. 10) method was used to analyze the data reported herein.

4.2 Strict-Series System Reliability Blade Life

System life prediction or the life of a single blade set can be determined using strict-series system reliability derived in Appendix B (Refs. 12 and 23). The reliability (or probability of survival), S , and the probability of failure, F , are related by $F = (1 - S)$. For a given time or blade set life, the reliability of an individual blade set S_{sys} of independent blades making up the blade set is the product of the independent reliabilities of each individual blade in the blade set S_i ($i = 1, 2, \dots, n$), as shown in Equation (2):

$$S_{\text{sys}} = S_1 \times S_2 \times \dots \times S_n \quad (2)$$

where S_{sys} is the blade set reliability, and S_1, S_2, \dots, S_n is the reliability of each blade in the blade set. If all components have the same reliability $S_1 = S_2 = \dots = S_n$ (as is assumed here), then Equation (2) reduces to

$$S_{\text{sys}} = S_n^n \quad (3)$$

where n is the number of blades in the blade set. For our case, each engine blade set has a total of 82 blades. Thus, for one blade set, Equation (3) can be written as

$$S_{\text{sys}} = S_n^{82} \quad (4)$$

From Equation (2), the lives of each of the blades at a specified reliability can be combined to determine the calculated system L_{sys} life of the set using the two-parameter Weibull distribution function (Eq. (1)) for the blades comprising the system and strict-series system reliability (Ref. 13) as follows:

$$\frac{1}{L_{\text{sys}}^e} = \left(\frac{1}{L_1^{e_1}} + \frac{1}{L_2^{e_2}} + \dots + \frac{1}{L_n^{e_n}} \right) \quad (5)$$

where L_{sys} is the life of individual blade set and L_1, L_2, \dots, L_n are the lives of the individual blades. The derivation for Equation (5) is given in Appendix B (Ref. 12).

In this work, the 82 blades in a set are each assumed to have the same life, L , where $L_1 = L_2 = \dots = L_n$ and Weibull slope, $e = e_1 = e_2 = \dots = e_n$. Accordingly, Equation (5) can be written for the 82 blades in a single blade set as

$$\frac{1}{L_{\text{sys}}^e} = \left(\frac{82}{L^{e_n}} \right) \quad (6)$$

The calculated system life is dependent on the resultant value of the system Weibull slope e .

4.3 Linear Damage Rule

The blade set life is calculated using Equation (6) for each operating condition of its engine operating profile. In Appendix C is a representation of a short-duration flight profile (Fig. C.1). In order to obtain the operational life of the blade set, the resulting system lives for each of the operating conditions (illustrated in Fig. C.1) are combined in Equation (7) using the linear damage (Palmgren-Langer-Miner) rule discussed in Appendix C (Refs. 24 to 27) where L_{sys_k} is the life for condition k and X_k is the time fraction spent at condition k , ($k = 1, 2, \dots, N$).

$$\frac{1}{L_{\text{mis}}} = \frac{X_1}{L_{\text{sys}_1}} + \frac{X_2}{L_{\text{sys}_2}} + \dots + \frac{X_k}{L_{\text{sys}_k}} + \dots + \frac{X_N}{L_{\text{sys}_N}} \quad (7)$$

It is assumed that each of the blade sets in Table 2 have the same operational cycle. $N = 16$ changes in engine operational conditions over the flight profile for Figure C.1. (Operational cycle N is not to be confused with N_{eng} , the number of engine overhaul blade repairs of Table 2, which also has 16 entries.) The most damaging condition is at takeoff with the cruise condition being the dominant time on the engine.

5.0 Results and Discussion

Sixteen high-pressure turbine (HPT) T-1 blade sets ($N_{\text{eng}} = 16$) were removed from commercial aircraft engines that had been commercially flown by a single airline. These engines were brought to the maintenance shop for refurbishment or overhaul. The blades for these turbines were manufactured from a single-crystal nickel alloy whose chemical composition together with the chemical composition of the blade coating are given in Table 1. The blades on each HPT T-1 blade set were removed and inspected for damage. The damage was cataloged in three categories related to their mode of failure:

- (1) Thermal-mechanical fatigue (TMF)
- (2) Oxidation/erosion (O/E)
- (3) Other (creep, yield, fracture mechanics, fretting, corrosion, FOD, and wear)

The blades were first inspected for TMF. If cracks were evident on the blade even if other failure modes were also evident, the cause for removal was cataloged as TMF. The remaining blades were inspected for O/E. As with those blades cataloged as being failed by TMF, those blades that exhibited O/E damage were so cataloged even where damage from other failure modes was manifested on the blade. The remaining

blades were examined for damage for the other causes. These other causes were not identified and categorized and cataloged as “Other.” The time of removal of the blade sets together with the cataloged failure mode of those blades in each set that failed is summarized in Table 2.

5.1 Field Data Analysis

Weibull plots of these data for $N_{eng} = 16$ based on the time of removal in flight hours and flight cycles are shown in Figure 3.

Theoretically, the time to failure of a turbine blade set is the time at which the first blade in the set fails regardless of the cause. This is analogous to a weak link in a chain. The chain is failed when the first link fails. The problem is that we do not know when the first blade failed nor do we know for sure the time when the most recent blade failure in a particular blade set has occurred. For purpose of the analysis, assume that the most recent blade that has failed in a set fails at the time the set is removed from the engine (Table 2, Time of removal, cycles). From this assumption, we need to determine the time at which the first blade has failed. We assumed the following scenario:

The set starts out with all new (unused) blades.
 The reliability, $S(t)$, of the last blade that fails is

$$S(t) = 1 - F(t) \tag{8}$$

In this calculation, the reliability, $S(t)$ was estimated from the median rank of the failures, according to Equation (9)

(Ref. 21), where i is the failure number and n is the number of individual blades in a set (in this case, $n = 82$):

$$F \approx \frac{i - 0.3}{n + 0.4} \tag{9}$$

Although the time of the last failure in a blade set cannot be known with any reasonable certainty, it can be assumed to have occurred at or shortly before the blade set is removed from service. The time of removal of a blade set is obtained from Table 2. Also, the number of failures in each engine blade set is given in Table 2. As an example, for engine number 2B, the time of removal L is 1404 cycles and there are $n_{blade} = 5$ failures within the blade set.

It is assumed for purposes of calculation that when the first blade failure in a blade set occurs, the blade set is no longer fit for its intended purpose even though it is still functioning. Accordingly, estimation of the time of the first failure in the blade set is a precondition for determining turbine blade life. In order to accomplish this task, it is first necessary to determine the probability of failure out of a large blade population that the most recent failure in the blade set represents. For engine number 2B, solving for F in Equation (9), where $i = 5$ and $n = 82$,

$$F = (5 - 0.3)/(82 + 0.4) = 0.057 \tag{10a}$$

From Equation (8),

$$S = 1 - 0.057 = 0.943 \tag{10b}$$




Figure 3.—Weibull plots of turbine blade set removal time for high-pressure turbine T-1 blade sets from field data. Number of T-1 turbine blades to a set, 82. (a) Flight hours (coefficient of determination, $r^2 = 0.9583$). (b) Flight cycles ($r^2 = 0.954$).

From the field data (Table 2, engine 2B), the time of removal of the blade set is 1404 cycles. From the Weibull plot of Figure 3(b), a Weibull slope e equal to 5.984 is obtained. These Weibull parameters are substituted in Equation (1) to solve for the characteristic life, L_β , of the blades for engine 2B, which is $L_\beta = 2255$ cycles.

Again referring to Equation (9), the value for F of the first failure in that blade set is determined. For $i = 1$, $F = 0.0085$. From Equation (8), $S = 0.9915$. Substituting the value for S together with the Weibull slope $e = 5.984$ and $L_\beta = 2255$ in Equation (1), the estimated time to the first failure is determined to be 1017 cycles. These calculations were repeated for each engine blade set. The resulting values are summarized in the last column of Table 2.

A Weibull plot of the estimated time to first failure of each of the $N_{eng} = 16$ blade sets is shown in Figure 4 and is compared with the time of blade set removal from Figure 3(b). The Weibull parameters for Figure 4, "Time to first blade failure" are summarized in Table 3. The mean time of the turbine blade set, $L_{m \text{ blade set}}$, of 1482 cycles (7016 hr), is based on the first turbine blade failure and is approximately 26 percent less than the average blade set removal time.

These lives are summarized in Table 3. There is an insignificant difference in the Weibull slopes between the two Weibull plots. For purposes of comparison, the slope of 5.984 derived from the time of removal in cycles was used.

5.2 Turbine Blade Life

Knowing the life of the blade set based on the estimated time to the first failure on each blade set, it is possible to determine the distributive lives of the individual blades from Equation (6). It is assumed that the Weibull slope for each of

the individual blades is identical to the Weibull slope for the blade sets based on the time to first failure from Figure 4 and equals 5.235.

Based on the characteristic life, L_β , for the blade set of 1608 cycles (see Table 3 column, "Estimated time to first blade failure"), the calculated characteristic life, L_β , for the individual blade is 3731 cycles (see Table 3 column, "All failure modes").




Figure 4.—Estimated time to first blade failure in set compared to blade set removal time. Number of T-1 turbine blades to a set, 82. For plotted data, coefficient of determination, $r^2 = 0.9734$.

TABLE 3.—SUMMATION OF LIVES OF T-1 TURBINE BLADE SETS AND INDIVIDUAL BLADES BASED ON FAILURE MODE USING JOHNSON-WEIBULL ANALYSIS

Weibull parameters	Blade set life (from Table 2 data)			Individual blade life based on failure mode, cycles			
	Time of removal		Estimated time to first blade failure, cycles	All failure modes	Oxidation/erosion (O/E)	Thermal-mechanical fatigue (TMF)	Other
	hr	cycles					
L_1 life	4 337	993	668	1550	2093	2113	1717
L_5 life	5 873	1304	912	2116	2857	2884	2343
L_{10} life	6 714	1471	1046	2427	3278	3309	2688
L_{50} life	9 529	2015	1499	3478	4698	4742	3852
Mean life	^b 9 406	^c 1987	^d 1482	^d 3434	^d 4638	^d 4582	^d 3803
^a L_β	10 201	2142	1608	3731	5039	5086	4132
Weibull slope	5.379	5.984	5.235	5.235	5.235	5.235	5.235

^aLife at a 63.2 percent probability of failure, characteristic life.

^bLife at a 47.6 percent probability of failure.

^cLife at a 47.2 percent probability of failure.

^dLife at a 47.7 percent probability of failure.




Figure 5.—Calculated individual turbine T-1 blade life from estimated time to first blade failure in blade set. Number of T-1 turbine blades to a set, 82.

From Equation (1) all the other blade lives for each probability of failure (survival) can be calculated. These results are summarized in Table 3 and are represented by the Weibull plot in Figure 5 labeled “Individual blade life.” The mean individual blade life, $L_{m \text{ blade}}$, is 3434 cycles (16 256 hr), or approximately 2.3 times the mean life of the blade set, $L_{m \text{ blade set}}$, of 1482 cycles (7016 hr). The L_{10} individual blade life calculated from Johnson-Weibull analysis is 2427 cycles (11 077 hr) compared to 1046 cycles (4774 hr) for the blade set. The life of the blade set will always be less than the life of an individual blade at the same probability of survival (failure).

5.3 Failure Mode

The time of removal of the blade sets together with the cataloged failure mode of those blades in each set that failed is summarized in Table 2. As previously discussed, the blades were first inspected for TMF. If cracks were evident on the blade even if other failure modes were also evident, the cause for removal was cataloged as TMF. The remaining blades were inspected for O/E. As with those blades cataloged as being failed by TMF, those blades that exhibited O/E damage were cataloged even where damage from other failure modes was manifested on the blade. The remaining blades were examined for damage for the other causes. These other causes were not identified; the cause was categorized and cataloged as “Other.” The “Other” category can include creep (stress rupture), yield, fracture mechanics (flaw initiated crack), fretting (wear and fatigue), corrosion, foreign object damage (FOD), and wear (blade tip rub).

There were 111 cataloged blade failures out of a total of 1312 blades (Table 2). The failed blades comprised 8.5 percent of the total number of blades in the 16 blade sets. TMF accounted for approximately 20 percent of the failures, or 1.7 percent of the blade population. Oxidation/erosion accounted for approximately 21 percent of the failures, or 1.75 percent of the blade population. The highest accounting for blade failures occurs under the “Other” category. This is approximately 59 percent of the failures, or 5 percent of the blade population.

With reference to the strict-series system reliability equation (Eq. (5)), the resulting blade lives associated with the various failure modes with respect to the actual blade life can be derived from the Lundberg-Palmgren model for system failure (Ref. 13) and are expressed by Johnson (Ref. 10) as follows:

$$X = \frac{L_{\text{blade}}^e}{L_{\text{fm}}^e} \quad (11)$$

where X is the fractional percent of components failed from a cataloged failure mode, L_{blade} is the individual blade life, and L_{fm} is the individual blade life resulting from a cataloged failure mode (fm). If each blade failure due to a cataloged failure mode is known as a percentage of the total number of failed blades, then the life of the blade related to that failure mode can be determined from Equation (11) and vice versa. However, a condition precedent for using Equation (11) is that the individual Weibull slopes must be known or assumed with reasonable engineering and statistical certainty.

The results of this analysis are shown in Figure 6 and summarized in Table 3. The resulting blade life attributed to O/E equaled that attributed to TMF. The category that contributed




Figure 6.—Turbine T-1 blade life based on failure mode.

most to blade life was “Other.” That is, if for any reason there were no blade failures attributed to O/E and TMF, the overall blade L_{10} life would increase from 2427 cycles to 2688 cycles, or approximately 11 percent. Because of statistical variance, this increase in life would probably never be noticed in an actual application.

Referring to engine number 6B in Table 2, there are 40 failures attributed to “Other” and a single failure attributed to TMF. Assume for purposes of discussion that at a time of 1843 cycles (from Table 2, engine 6B) a single blade failed from TMF and broke loose, causing secondary damage to 40 other blades in the set. The estimated time to first blade failure for engine 6B would change from 886 to 1843 cycles.

A Weibull analysis of the data was performed with the revised life value (1843 cycles) for engine blade set 6B. From recalculation of the data, the Weibull slope was increased from 5.235 to 6.237 and the blade L_{10} life was decreased from 2427 cycles to 2339 cycles. These changes are considered insignificant.

If the 40 blade failures cataloged under “Other” for engine blade set 6B in Table 2 are discarded, the number of failed blades categorized under “Other” for engine blade set 6B is reduced from 66 to 26. This will reduce the total number of failed blades in Table 2 from 111 to 71. The failed blade fractions for 71 failed blades for the three categories become 0.324, 0.31, and 0.366, for O/E, TMF, and “Other,” respectively.

The respective blade L_{10} life for each failure category in Table 3 was recalculated using Equation (11) based on a Weibull slope $e = 6.237$ and the revised blade L_{10} life of 2339 cycles. For the blade life based on O/E, the L_{10} life decreased from 3278 to 2802 cycles. For TMF, the L_{10} life decreased from 3309 to 2748 cycles. However, for the failure modes cataloged under “Other,” the L_{10} life increased from 2688 to 2822 cycles. In this scenario, if the failure modes related to O/E and TMF are eliminated, the blade L_{10} life would be increased from 2339 to 2748 cycles, or approximately 17 percent. Again, as before, this increase in life would probably never be noticed in an actual application.

5.4 Simplified Life Formula

As previously discussed, there are competing failure modes that affect turbine blade life. Because of this, there was no attempt to analytically perform a life analysis based on any single failure mode to compare with the results presented. We are unaware of any published analysis of the turbine blades discussed in this paper. However, it is possible based on the work presented herein to develop a simplified equation that will allow the user airline to estimate the life of their turbine blades for the purpose of maintenance and replacement.

Of the failure modes discussed, it is our opinion that only the failure mode associated with low-cycle fatigue (LCF) (i.e., TMF) can be measured in terms of cycles to failure with

reasonable engineering certainty. High-cycle fatigue (HCF) is related to the frequency of cycling, which is variable based upon gas velocity and thermal fluctuation. Also, the rate of cycling cannot be assumed with any reasonable engineering certainty much less measured. A prudent approach to the problem of HCF as it relates to a turbine blade application would be to assume that it is time dependent for a given engine application and operating profile. All the other failure modes discussed are also assumed to be time dependent for a given engine application and operating profile.

From Johnson (Ref. 10) the mean time to failure or removal is a function of the Weibull slope e . From the Weibull analysis summarized in Table 3, for a Weibull slope e of 5.379, the mean time to blade set removal ($L_{m\text{-blade set}}$) is 9406 hr (1987 cycles). This occurs at a 47.6 percent probability of failure. The mean time per cycle is equal to 4.73 hr/cycle (9406 hr, or 1987 cycles). Appendix D presents a derivation of a measure of consistency between engine life in cycles and in hours.

For purposes of comparison, as the dispersion or scatter in the data increases, the Weibull slope e decreases (Ref. 10). As an example, for a normal distribution where the mean time to failure occurs at a 50 percent probability of failure, the Weibull slope e equals 3.57. For a Rayleigh distribution where the Weibull slope e equals 2, the probability of failure is 54.4 percent. For an exponential distribution, the probability of failure is 63.2 percent at a Weibull slope e equal to 1. From this trend, an empirical formula can be derived as follows:

$$F_m \approx 0.621e^{-0.172} \quad (12a)$$

where F_m is the mean probability of failure as a fractional percent and e is the Weibull slope. From Equation (1),

$$\ln \ln \left[\frac{1}{(1-F_m)} \right] = e \ln \left[\frac{L_M}{L_\beta} \right] \quad (12b)$$

or

$$L_M = L_\beta \ln \left[\frac{1}{(1-F_m)} \right]^{(1/e)} \quad (12c)$$

where L_M is the mean time to removal and L_β is the characteristic life or the life at a 63.2 percent probability of failure.

From Table 2, the summation of the time of removal of the blade sets divided by the number of blade sets equals the numerical average of the time of blade set removal ($L_{\text{avg-blade set}}$) where $L_{\text{avg-blade set}} = 9421$ hr (1990 cycles). This numerical average of 9421 hr (1990 cycles) correlates to the mean value from the Weibull analysis of 9406 hr (1987 cycles) summarized in Table 3. Accordingly, the numerical average of the blade set removal time ($L_{\text{avg-blade set}}$)

can be substituted for the mean time to blade set removal ($L_{m \text{ blade set}}$) from the Weibull analysis in further calculations.

From Table 3 (column, “Estimated time to first failure”), the mean time to first blade failure in a set is 1482 cycles, or 7016 hr (1482 cycles \times 4.73 hr/cycle). The mean time, $L_{m \text{ blade}}$ to first blade failure in a set in terms of the average blade set time to removal is

$$L_{m \text{ blade}} = (7016 \text{ hr}/9406 \text{ hr}) L_{\text{avg-blade set}} = 0.742 L_{\text{avg-blade set}} \quad (13)$$

An acceptable failure rate needs to be established for blade removal. As discussed, 111 blades (8.5 percent) failed of the 1312 blades comprising the 16 blade sets. It is therefore assumed that a 10-percent failure rate (L_{10}) would be acceptable as an upper failure limit. From Figure 2 and Equation (1),

$$\frac{\ln \ln (1/S_2) - \ln \ln (1/S_1)}{\ln L_2 - \ln L_1} = e \quad (14a)$$

This reduces to

$$[\ln(1/S_1)/\ln(1/S_2)] = [L_1/L_2]^e \quad (14b)$$

In Equation (14b), let

$$S_1 = S_{90} = 0.90$$

$$S_2 = S_m = (1 - 0.477) = 0.523$$

$$L_1 = L_{10}$$

and from Equation (13)

$$L_2 = L_m = 0.742 L_{\text{avg-blade set}}$$

where

$$L_{\text{avg-blade set}} = (\text{Sum of time to removal of blade sets}) / (\text{number of blade sets}) \quad (14c)$$

Substituting the above values into Equation (14b) and solving for the L_{10} blade set life for time to first blade failure in a set where Weibull slope $e = 5.235$ (from Fig. 4),

$$\begin{aligned} L_{10 \text{ blade set}} &= 0.742 L_{\text{avg-blade set}} [\ln(1/S_1)/\ln(1/S_2)]^{1/e} \\ &= 0.742 L_{\text{avg-blade set}} [\ln(1/0.90)/\ln(1/0.523)]^{1/5.235} \quad (15) \\ &= 0.524 L_{\text{avg-blade set}} \end{aligned}$$

Combining Equations (3) and (14), the following empirical equation for the L_{10} individual blade life can be written:

$$L_{10 \text{ blade}} = 0.524 L_{\text{avg-blade set}} (n)^{1/e} = 0.524 L_{\text{avg-blade set}} (n)^{0.191} \quad (16a)$$

Equation (16a) can be further simplified where

$$L_{10 \text{ blade}} \approx (L_{\text{avg-blade set}} / 2) (n)^{0.2} \quad (16b)$$

Substituting $L_{\text{avg-blade set}} = 1990$ cycles and $n = 82$ into Equations (16a) and (16b), $L_{10 \text{ blade}} = 2418$ and 2401 cycles, respectively. This correlates to the individual blade $L_{10 \text{ blade}}$ life from Table 3 of 2427 cycles. Assuming a Weibull slope of 5.235, the value of the characteristic life L_β for individual blades can be calculated from Equation (1). Knowing L_β , the individual blade life at any reliability (probability of survival, S) can be calculated from Equation (1).

6.0 Summary of Results

Sixteen high-pressure turbine (HPT) T-1 blade sets were removed from commercial aircraft engines that had been commercially flown by a single airline. Each blade set contained 82 blades. These engines were brought to the maintenance shop for refurbishment or overhaul. The blades on each HPT T-1 blade set were removed and inspected for damage. The damage found was cataloged into three categories related to their mode of failure. These were (1) Thermal-mechanical fatigue (TMF), (2) Oxidation/erosion (O/E), and (3) Other. From these field data, the turbine blade life was determined as well as the lives related to individual blade failure modes using Johnson-Weibull analysis. From these data and analysis, a simplified formula for calculating turbine blade life and reliability was formulated. The following results were obtained:

1. The following empirical equation for the L_{10} individual blade life was formulated:

$$L_{10 \text{ blade}} \approx (L_{\text{avg-blade set}} / 2) (n)^{0.2}$$

where $L_{\text{avg-blade set}} = (\text{sum of time to removal of blade sets}) / (\text{number of blade sets})$ and n is the number of blades in a set.

2. The individual blade life, $L_{10 \text{ blade}}$, calculated from Johnson-Weibull analysis is 2427 cycles (11 077 hr) compared to L_{10} blade set life of 1046 cycles (4774 hr). The life of the blade set (blade set life is defined as the failure time of first blade in a blade set) will always be less than the life of an individual blade at any given probability of survival (failure).

3. The resulting individual blade life attributed to O/E equaled that attributed to TMF. The category that contributed most to individual blade failure was “Other,” which includes creep (stress rupture), yield, fracture mechanics (flaw initiated crack), fretting (wear and fatigue), corrosion, foreign object damage (FOD), and wear (blade tip rub).
4. If there were no blade failures attributed to O/E and TMF, the overall individual blade life, $L_{10 \text{ blade}}$, would increase approximately 11 to 17 percent.

Glenn Research Center
National Aeronautics and Space Administration
Cleveland, Ohio, April 29, 2013

Appendix A

Derivation of Weibull Distribution Function

According to Weibull (Refs. 7 to 9) and as presented in Reference 12 (see also Ref. 23), any distribution function can be written as

$$F(X) = 1 - \exp\{-[f(X)]\} \quad (\text{A1})$$

where $F(X)$ is the probability of an event (failure) occurring and $f(X)$ is a function of an operating variable X . Conversely, from Equation (A1) the probability of an event not occurring (survival) can be written as

$$1 - F(X) = \exp\{-[f(X)]\} \quad (\text{A2a})$$

or

$$1 - F = \exp\{-[f(X)]\} \quad (\text{A2b})$$

where $F = F(X)$ and $(1 - F) = S$, the probability of survival.

If there are n independent components, each with a probability of the event (failure) not occurring $(1 - F)$, the probability of the event not occurring in the combined total of all components can be expressed from Equation (A2b) as

$$(1 - F)^n = \exp\{-[nf(X)]\} \quad (\text{A3})$$

Equation (A3) gives the appropriate mathematical expression for the principle of the weakest link in a chain or, more generally, for the size effect on failures in solids. The application of Equation (A3) is illustrated by a chain consisting of several links. Testing finds the probability of failure F at any load X applied to a "single" link. To find the probability of failure F_n of a chain consisting of n links, one must assume that if one link has failed the whole chain fails. That is, if any single part of a component fails, the whole component has failed. Accordingly, the probability of nonfailure of the chain $(1 - F_n)$, is equal to the probability of the simultaneous nonfailure of all the links. Thus,

$$1 - F_n = (1 - F)^n \quad (\text{A4a})$$

or

$$S_n = S^n \quad (\text{A4b})$$

Where the probabilities of failure (or survival) of each link are not necessarily equal (i.e., $S_1 \neq S_2 \neq S_3 \dots$), Equation (A4b) can be expressed as

$$S_n = S_1 \cdot S_2 \cdot S_3 \dots \quad (\text{A4c})$$

This is the same as Equation (2) of the main text.

From Equation (A3) for a uniform distribution of stresses σ throughout a volume V ,

$$F_V = 1 - \exp\{-[Vf(\sigma)]\} \quad (\text{A5a})$$

or

$$S = 1 - F_V = \exp\{-[Vf(\sigma)]\} \quad (\text{A5b})$$

Equation (A5b) can be expressed as follows:

$$\ln \ln \left[\frac{1}{S} \right] = \ln f(\sigma) + \ln V \quad (\text{A6})$$

It follows that if $\ln \ln (1/S)$ is plotted as the ordinate and $\ln f(\sigma)$ as the abscissa in a system of rectangular coordinates, a variation of volume V of the test specimen will imply only a parallel displacement but no deformation of the distribution function. Weibull assumed the form

$$f(\sigma) = \left[\frac{\sigma - \sigma_u}{\sigma_\beta - \sigma_u} \right]^e \quad (\text{A7})$$

Where e is the Weibull slope, σ is a stress at a given probability of failure, σ_u is a location parameter below which stress no failure will occur, and σ_β is the characteristic stress at which 63.2 percent of the population will fail. Equation (A6) becomes

$$\ln \ln \left[\frac{1}{S} \right] = e \ln(\sigma - \sigma_u) - e \ln(\sigma_\beta - \sigma_u) + \ln V \quad (\text{A8})$$

If the location parameter σ_u is assumed to be zero, and V is normalized whereby $\ln V$ is zero, Equation (A8) can be written as

$$\ln \ln \left[\frac{1}{S} \right] = e \ln \left[\frac{\sigma}{\sigma_\beta} \right]$$

$$\text{where } 0 < \sigma < \infty \text{ and } 0 < S < 1 \quad (\text{A9})$$

Equation (A9) is identical to Equation (1) of the main text.

The form of Equation (A9) where σ_u is assumed to be zero is referred to as "two-parameter Weibull."

Where σ_u is not assumed to be zero, the form of the equation is referred to as "three-parameter Weibull."

Appendix B

Derivation of Strict Series Reliability

As discussed and presented in References 12 and 23, Lundberg and Palmgren (Ref. 13) in 1947, using the Weibull equation (Appendix A) for rolling-element bearing life analysis, first derived the relationship between individual component lives and system life. The following derivation is based on but is not identical to the Lundberg-Palmgren analysis.

Referring to Figure 2, from Equation (A9) in Appendix A, the Weibull equation can be written as

$$\ln \ln \left[\frac{1}{S_{\text{sys}}} \right] = e \ln \left[\frac{L}{L_{\beta}} \right] \quad (\text{B1})$$

where L is the number of cycles to failure.

Figure B.1 is a sketch of multiple Weibull plots where each Weibull plot represents a cumulative distribution of a component in the system. The system Weibull plot represents the combined Weibull plots 1, 2, 3, and so forth. All plots are assumed to have the same Weibull slope e (Ref. 12). The slope e can be defined as follows:

$$e = \frac{\ln \ln \left[\frac{1}{S_{\text{sys}}} \right] - \ln \ln \left[\frac{1}{S_{\text{ref}}} \right]}{\ln L - \ln L_{\text{ref}}} \quad (\text{B2a})$$

or




Figure B.1.—Sketch of multiple Weibull plots where each numbered plot represents the cumulative distribution of a component in system and system Weibull plot represents combined distribution of plots 1, 2, 3, etc. (all plots are assumed to have same Weibull slope e).

$$\frac{\ln \left[\frac{1}{S_{\text{sys}}} \right]}{\ln \left[\frac{1}{S_{\text{ref}}} \right]} = \left[\frac{L}{L_{\text{ref}}} \right]^e \quad (\text{B2b})$$

From Equations (B1) and (B2b),

$$\ln \left[\frac{1}{S_{\text{sys}}} \right] = \left[\ln \frac{1}{S_{\text{ref}}} \right] \left[\frac{L}{L_{\text{ref}}} \right]^e = \left[\frac{L}{L_{\beta}} \right]^e \quad (\text{B3})$$

and

$$S_{\text{sys}} = \exp \left\{ - \left[\frac{L}{L_{\beta}} \right]^e \right\} \quad (\text{B4})$$

where $S_{\text{sys}} = S$ in Equation (B1). For a given time or life L , each component or stressed volume in a system will have a different reliability S . From Equation (A4c) for a series reliability system

$$S_{\text{sys}} = S_1 \cdot S_2 \cdot S_3 \cdot \dots \quad (\text{B5})$$

Combining Equations (B4) and (B5) gives

$$\exp\left\{-\left[\frac{L}{L_\beta}\right]^e\right\} = \exp\left\{-\left[\frac{L}{L_{\beta 1}}\right]^e\right\} \times \exp\left\{-\left[\frac{L}{L_{\beta 2}}\right]^e\right\} \times \dots \quad (\text{B6a})$$

$$\exp\left\{-\left[\frac{L}{L_\beta}\right]^e\right\} = \exp\left\{-\left[\frac{L}{L_{\beta 1}}\right]^e + \left[\frac{L}{L_{\beta 2}}\right]^e + \left[\frac{L}{L_{\beta 3}}\right]^e + \dots\right\} \quad (\text{B6b})$$

It is assumed that the Weibull slope e is the same for all components. From Equation (B6b)

$$-\left[\frac{L}{L_\beta}\right]^e = -\left\{\left[\frac{L}{L_{\beta 1}}\right]^e + \left[\frac{L}{L_{\beta 2}}\right]^e + \left[\frac{L}{L_{\beta 3}}\right]^e + \dots\right\} \quad (\text{B7a})$$

Factoring out L from Equation (B7a) gives

$$\left[\frac{1}{L_\beta}\right]^e = \left[\frac{1}{L_{\beta 1}}\right]^e + \left[\frac{1}{L_{\beta 2}}\right]^e + \left[\frac{1}{L_{\beta 3}}\right]^e + \dots \quad (\text{B7b})$$

From Equation (B3) the characteristic lives $L_{\beta 1}, L_{\beta 2}, L_{\beta 3},$ etc., can be replaced with the respective lives $L_1, L_2, L_3,$ etc., at S_{ref} (or the lives of each component that have the same probability of survival S_{ref}) as follows:

$$\left[\ln \frac{1}{S_{\text{ref}}}\right] \left[\frac{1}{L_{\text{ref}}}\right]^e = \left[\ln \frac{1}{S_{\text{ref}}}\right] \left[\frac{1}{L_1}\right]^e + \left[\ln \frac{1}{S_{\text{ref}}}\right] \left[\frac{1}{L_2}\right]^e + \left[\ln \frac{1}{S_{\text{ref}}}\right] \left[\frac{1}{L_3}\right]^e + \dots \quad (\text{B8})$$

where, in general, from Equation (B3)

$$\left[\frac{1}{L_\beta}\right]^e = \left[\ln \frac{1}{S_{\text{ref}}}\right] \left[\frac{1}{L_{\text{ref}}}\right]^e \quad (\text{B9a})$$

and

$$\left[\frac{1}{L_{\beta 1}}\right]^e = \left[\ln \frac{1}{S_{\text{ref}}}\right] \left[\frac{1}{L_1}\right]^e, \text{ etc.} \quad (\text{B9b})$$

Factoring out $\ln(1/S_{\text{ref}})$ from Equation (B8) gives

$$\left[\frac{1}{L_{\text{ref}}}\right]^e = \left\{\left[\frac{1}{L_1}\right]^e + \left[\frac{1}{L_2}\right]^e + \left[\frac{1}{L_3}\right]^e + \dots\right\}^{1/e} \quad (\text{B10})$$

or rewriting Equation (B10) results in

$$\left[\frac{1}{L_{\text{ref}}}\right]^e = \sum_{i=1}^n \left[\frac{1}{L_i}\right]^e \quad (\text{B11})$$

Equations (B10) and (B11) are identical to Equation (5) of the text.

Equation (B10) can also be rewritten as follows:

$$1 = \left\{\left[\frac{L_{\text{ref}}}{L_1}\right]^e + \left[\frac{L_{\text{ref}}}{L_2}\right]^e + \left[\frac{L_{\text{ref}}}{L_3}\right]^e + \dots\right\} \quad (\text{B12})$$

From Equation (B12) and according to Johnson (Ref. 10) the fraction of failures due to each cataloged failure mode of a component is expressed as

(1) Percent fraction of failures resulting from cataloged failure mode 1,

$$X_1 = \left[\frac{L_{\text{ref}}}{L_1}\right]^e \quad (\text{B13a})$$

(2) Percent fraction of failures resulting from cataloged failure mode 2,

$$X_2 = \left[\frac{L_{\text{ref}}}{L_2}\right]^e \quad (\text{B13b})$$

(3) Percent fraction of failures resulting from cataloged failure mode 3,

$$X_3 = \left[\frac{L_{\text{ref}}}{L_3}\right]^e \quad (\text{B13c})$$

The form of Equation (B13) is the same as Equation (11) of the text. Substituting Equation (B13) into Equation (B12),

$$X_1 + X_2 + X_3 + \dots = 1 \quad (\text{B14})$$

From Equations (B13a) to (B13c), if the life of the component and the percent fraction of the total failures represented by each cataloged failure mode are known, the life of the component related to each cataloged failure mode can be calculated. Hence, by observation, it is possible to determine the failure modes of a component population and determine the component's life related to each cataloged failure mode. (Refer to Eq. (11) of the text.)

Appendix C

Linear Damage Rule

Most machine components are operated under combinations of variable loading and speed. Figure C.1 shows an example of a typical flight profile for a commercial flight with the time of each segment given.

Palmgren (Ref. 24) working with ball and roller bearings recognized that the variation in both load and speed must be accounted for in order to predict component life. Palmgren (Ref. 24) reasoned: "In order to obtain a value for a calculation, the assumption might be conceivable that (for) a bearing which has a life of k million revolutions under constant load at a certain rpm (speed), a portion M/k of its durability will have been consumed. If the bearing is exposed to a certain load for a run of M_1 million revolutions where it has a life of k_1 million revolutions, and to a different load for a run of M_2 million revolutions where it will reach a life of k_2 million revolutions, and so on, we will obtain

$$\frac{M_1}{k_1} + \frac{M_2}{k_2} + \frac{M_3}{k_3} + \dots = 1 \quad (C1)$$

In the event of a cyclic variable load we obtain a convenient formula by introducing the number of intervals p and designate m as the revolutions in millions that are covered within a single interval. In that case we have

$$(p) \left(\frac{m_1}{k_1} + \frac{m_2}{k_2} + \frac{m_3}{k_3} + \dots \right) = 1 \quad (C2)$$

where k still designates the total life in millions of revolutions under the load and rpm (speed) in question (and $M = pm$)."

Equations (C1) and (C2) were independently proposed for conventional fatigue analysis by Langer (Ref. 25) in 1937 and Miner (Ref. 26) in 1945, 13 and 21 years after Palmgren (Ref. 24), respectively. The equation has been subsequently referred to as the linear damage rule or the Palmgren-Langer-Miner rule. For convenience, the equation can be written as follows:

$$\frac{1}{L} = \frac{X_1}{L_1} + \frac{X_2}{L_2} + \frac{X_3}{L_3} + \dots + \frac{X_k}{L_k} \quad (C3)$$

and

$$X_1 + X_2 + X_3 + \dots + X_k = 1 \quad (C4)$$

where L is the total life in stress cycles or race revolutions, $L_1 \dots L_k$ is the life at a particular load and speed in stress cycles or race revolutions, and $X_1 \dots X_k$ is the fraction of total running time at load and speed. From Equation (C1)

$$M_1 = X_1 L, M_2 = X_2 L, M_3 = X_3 L, \dots M_k = X_k L \quad (C5)$$

Because the flight profile is repeatable, for example, Figure C.1, it is reasonable to use the percent of time in each segment to determine engine component life using Equation (C3).

Equation (C3) is the basis for most variable-load fatigue analysis and is used extensively in bearing life prediction.




Figure C.1.—Example typical flight profile for a commercial gas turbine engine, as shown.

Appendix D

Variation Between Engine Life in Cycles and in Hours

The relationship between engine hours and engine cycles varies depending on engine usage. Therefore, the distribution of failures as a function of hours and as a function of cycles, although closely related, will not necessarily have the same Weibull slope. As a result, the conversion of engine cycles to engine hours may differ with probability of survival.

When the Weibull slopes are equal, the ratio of engine hours to engine cycles is the same at all probabilities of survival. For Weibull analysis,

$$\ln \ln \left(\frac{1}{S} \right) = e \ln \left(\frac{L}{L_\beta} \right) \quad (D1)$$

where $S = 1 - F$ is the probability of component survival with F as the probability of failure; e , the Weibull slope; L_β , the characteristic life at $S = 0.368$ (or $F = 0.632$); and L , component life.

For $S_{\text{hour}} = S_{\text{cycle}}$,

$$\left[e \ln \left(\frac{L}{L_\beta} \right) \right]_{\text{hour}} = \left[e \ln \left(\frac{L}{L_\beta} \right) \right]_{\text{cycle}} \quad (D2a)$$

Therefore,

$$\left(\frac{L}{L_\beta} \right)_{\text{hour}} = \left[\left(\frac{L}{L_\beta} \right)_{\text{cycle}} \right]^p \quad (D2b)$$

where $p = e_{\text{cycle}}/e_{\text{hour}}$. Solving for the ratio of life in hours to life in cycles in terms of characteristic life gives

$$\left(\frac{L_{\text{hour}}}{L_{\text{cycle}}} \right) = \left(\frac{L_{\beta \text{ hour}}}{L_{\beta \text{ cycle}}} \right) \left[\left(\frac{L}{L_\beta} \right)_{\text{cycle}} \right]^{(p-1)} \quad (D3)$$

However, where there is variation between the Weibull slopes, there is also a variation in the ratio of engine hours to cycles at a given probability of survival. This is illustrated in the data in Table 3. From Table 3, for L_1 , L_5 , L_{10} , and L_{50} ($L_{\text{hour}}/L_{\text{cycle}}$) = 4.37, 4.50, 4.56, and 4.73 hours/cycle, respectively.

Note that as the Weibull slopes representing the data for engine cycles and hours approach each other, that is, as $e_{\text{cycle}} \Rightarrow e_{\text{hour}}$, $p \Rightarrow 1$. Thus from Equation (D3), $(L_{\text{hour}}/L_{\text{cycle}}) \Rightarrow (L_{\beta \text{ hour}}/L_{\beta \text{ cycle}}) \Rightarrow \text{Constant (invariant)}$.

The value of $p = e_{\text{cycle}}/e_{\text{hour}}$ provides a metric for consistency between engine cycle and engine hour data.

References

1. Zaretsky, Erwin V.; Hendricks, Robert C.; and Soditus, Sherry: Weibull-Based Design Methodology for Rotating Structures in Aircraft Engines. *Int. J. Rotating Mach.*, vol. 9, 2003, pp. 313–325.
2. Davis, Donald Y.; and Stearns, E. Marshall: Energy Efficient Engine: Flight Propulsion System Final Design and Analysis; Topical Report. NASA CR–168219, 1985.
3. Halila, E.E.; Lenahan, D.T.; and Thomas, T.T.: Energy Efficient Engine High Pressure Turbine Test Hardware: Detailed Design Report. NASA CR–167955, 1982.
4. Manson, S.S.; and Halford, G.R.: *Fatigue and Durability of Structural Materials*. ASM International, Materials Park, OH, 2006, p. 401.
5. Sawyer, John W., ed.: *Gas Turbine Engineering Handbook*. Gas Turbine Publications, Inc., Stamford, CT, 1966, p. 235.
6. Nelson, Wayne: *Applied Life Data Analysis*. John Wiley & Sons, NY, 1982, pp. 405–432.
7. Weibull, Waloddi: A Statistical Theory of the Strength of Materials. *Ingenioersvetenskapskad. Handl.*, no. 151, 1939.
8. Weibull, Waloddi: The Phenomenon of Rupture in Solids. *Ingenioersvetenskapskad. Handl.*, no. 153, 1939.
9. Weibull, Waloddi: A Statistical Distribution of Wide Applicability. *J. Appl. Mech. Trans. ASME*, vol. 18, no. 3, 1951, pp. 293–297.
10. Johnson, L.G.: *The Statistical Treatment of Fatigue Experiments*. Elsevier Publishing Co., Amsterdam, The Netherlands, 1964.
11. Cetal, A.D.; and Duhl, D.N.: Second-Generation Nickel-Base Single Crystal Superalloy. *Superalloys 1988*, The Metallurgical Society, Warrendale, PA, 1988, pp. 235–244.
12. Melis, M.E.; Zaretsky, E.V.; and August, R.: Probabilistic Analysis of Aircraft Gas Turbine Disk Life and Reliability. *J. Propul. Power*, vol. 15, no. 5, 1999, pp. 658–666.
13. Lundberg, G.; and Palmgren, A.: Dynamic Capacity of Rolling Bearings. *Acta Polytech.*, vol. 1, no. 3, 1947.
14. Burrow, M.F., et al.: Analysis of Tensile Bond Strengths Using Weibull Statistics. *Biomat.*, vol. 25, no. 20, 2004, pp. 5031–5035.
15. Ellis, F.V.; and Tordonato, S.: Failure Analysis and Life Assessment Studies for Boiler Tubes. ASME Pressure Vessels and Piping Division Publication, vol. 392, 1999, pp. 3–13.
16. Tomimatsu, M.; Kikuchi, M.; and Sakai, M.: Fracture Toughness Evaluation Based on the Master Curve Procedure. ASME Pressure Vessels and Piping Division Publication, vol. 353, 1997, pp. 343–349.
17. Osborne, N.G.; Graves, G.G.; and Ferber, M.K.: Dynamic Fatigue Testing of Candidate Ceramic Materials for Turbine Engines to Determine Slow Crack Growth Parameters. *J. Eng. Gas Turbines Power, ASME Trans.*, vol. 119, 1997, pp. 273–278.
18. Ostojic, P.; and Berndt, C.C.: Variability in Strength of Thermally Sprayed Coatings. *Surf. Coat. Technol.*, vol. 34, 1988, pp. 43–50.
19. Holland, F.A.; and Zaretsky, E.V.: Investigation of Weibull Statistics in Fracture Analysis of Cast Aluminum. *J. Appl. Mech. Trans. ASME*, vol. 112, 1990, pp. 246–254.
20. Williams, S.R.; and Fec, M.C.: Weibull Analysis of Reconditioned Railroad Roller Bearing Life Test Data. ASME Rail Transportation Division Publication, vol. 5, 1992, pp. 83–87.
21. Summers-Smith, J.D.: Fault Diagnosis as an Aid to Process Machine Reliability. *Qual. Reliab. Eng. Int.*, vol. 5, no. 3, 1989, pp. 203–205.
22. Vlcek, Brian L., et al.: Comparative Fatigue Lives of Rubber and PVC Wiper Cylindrical Coatings. *Tribol. Trans.*, vol. 46, no. 1, 2003, pp. 101–110.
23. Poplawski, Joseph V.; Peters, Steven M.; and Zaretsky, Erwin V.: Effect of Roller Profile on Cylindrical Roller Bearing Life Prediction—Part I: Comparison of Bearing Life Theories. *Tribol. Trans.*, vol. 44, no. 3, 2001, pp. 339–350.
24. Palmgren, A.: The Service Life of Ball Bearings. NASA Technical Translation TT–F–13460, 1971, (from *Zetschrift des Vereines Deutscher Ingenieure*, vol. 68, no. 14, 1924, pp. 339–341).
25. Langer, B.F.: Fatigue Failure From Stress Cycles of Varying Amplitude. *J. Appl. Mech. Trans. ASME*, vol. 4, no. 4, 1937, pp. A160–A162.
26. Miner, Milton A.: Cumulative Damage in Fatigue. *J. Appl. Mech. Trans. ASME*, vol. 12, no. 3, 1945, pp. A159–A164.
27. Kapur, K.C.; and Lamberson, L.R.: *Reliability in Engineering Design*. John Wiley and Sons, Inc., New York, NY, 1977, pp. 8–53.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188		
<p>The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.</p> <p>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.</p>					
1. REPORT DATE (DD-MM-YYYY) 01-04-2013		2. REPORT TYPE Technical Paper		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE Determination of Turbine Blade Life From Engine Field Data			5a. CONTRACT NUMBER		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) Zaretsky, Erwin, V.; Litt, Jonathan, S.; Hendricks, Robert, C.; Soditus, Sherry, M.			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER WBS 561581.02.08.03.16.03		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration John H. Glenn Research Center at Lewis Field Cleveland, Ohio 44135-3191			8. PERFORMING ORGANIZATION REPORT NUMBER E-15972-2		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITOR'S ACRONYM(S) NASA		
			11. SPONSORING/MONITORING REPORT NUMBER NASA/TP-2013-217030		
12. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified-Unlimited Subject Categories: 01, 23, 37, and 38 Available electronically at http://www.sti.nasa.gov This publication is available from the NASA Center for AeroSpace Information, 443-757-5802					
13. SUPPLEMENTARY NOTES Erwin V. Zaretsky is currently a Distinguished Research Associate.					
14. ABSTRACT It is probable that no two engine companies determine the life of their engines or their components in the same way or apply the same experience and safety factors to their designs. Knowing the failure mode that is most likely to occur minimizes the amount of uncertainty and simplifies failure and life analysis. Available data regarding failure mode for aircraft engine blades, while favoring low-cycle, thermal mechanical fatigue as the controlling mode of failure, are not definitive. Sixteen high-pressure turbine (HPT) T-1 blade sets were removed from commercial aircraft engines that had been commercially flown by a single airline and inspected for damage. Each set contained 82 blades. The damage was cataloged into three categories related to their mode of failure: (1) Thermal-mechanical fatigue, (2) Oxidation/Erosion, and (3) Other. From these field data, the turbine blade life was determined as well as the lives related to individual blade failure modes using Johnson-Weibull analysis. A simplified formula for calculating turbine blade life and reliability was formulated. The L10 blade life was calculated to be 2427 cycles (11 077 hr). The resulting blade life attributed to oxidation/erosion equaled that attributed to thermal-mechanical fatigue. The category that contributed most to blade failure was "Other." If there were there no blade failures attributed to oxidation/erosion and thermal-mechanical fatigue, the overall blade L10 life would increase approximately 11 to 17 percent.					
15. SUBJECT TERMS Turbine blade; Failure; Field data; Gas turbine; Weibull					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 30	19a. NAME OF RESPONSIBLE PERSON STI Help Desk (email: help@sti.nasa.gov)
a. REPORT U	b. ABSTRACT U	c. THIS PAGE U			19b. TELEPHONE NUMBER (include area code) 443-757-5802

