



Evaluation Report

RELIABILITY DEPARTMENT

TEST REPORT NO. TR. 7-0057

J.P.L. Task 37

TEST PERFORMED BY
LIBRASCOPE RELIABILITY DEPARTMENT

ON

2N2369, NPN SILICON

EPITAXIAL TRANSISTORS

MANUFACTURED BY

FAIRCHILD SEMICONDUCTOR

950 230

This work was performed for the Jet Propulsion Laboratory,
California Institute of Technology, sponsored by the
National Aeronautics and Space Administration under
Contract NAS7-100.

Prepared by:

Frank E. Haskins
F. Haskins, Electronic Engineering Assoc.

Written by:

L. E. Trempe
L. E. Trempe, Senior Technical Writer

Approved by:

M. McDermott
M. McDermott, Senior Engineer

Approved by:

W. K. Emery
W. K. Emery, Supervisor
Reliability Test Laboratory

Approved by:

H. Meyer
H. Meyer, Manager
Reliability Assurance Department

24 April 1964



GENERAL PRECISION, INC.
INFORMATION SYSTEMS GROUP

REPORT NO. 7-0057

TABLE OF CONTENTS

Section	Page
ABSTRACT	1
INTRODUCTION	
Objectives	5
Test Plan	5
Failure Analysis	9
Degradation Criteria	9
TEST PROCEDURES	
Test Sequence Flow Diagram	10
Initial Electrical Parameter Test	11
Temperature Effects Test	11
Temperature Storage Test	12
Thermal Shock Test	12
Mechanical Shock Test	12
Vibration Test	12
Humidity Test	13
Operating Life Test	13
Acceleration Test	14
Low Temperature Test	14
TEST RESULTS	
Initial Electrical Parameter Test Results	14
Temperature Effects Test Results	15
Temperature Storage Test Results	17
Thermal Shock Test Results	17
Mechanical Shock Test Results	18
Vibration Test Results	18

TABLE OF CONTENTS (Cont.)

Section	Page
Humidity Test Results	18
Operating Life Test Results	19
Acceleration Test Results	21
Low Temperature Test Results	21
FAILURE ANALYSIS	22
STATISTICAL INTERPRETATION OF RESULTS	23
Failures	23
h_{FE1}	24
h_{FE2}	25
$V_{CE(SAT)}$	26
BV_{CBO}	26
BV_{EBO}	26
I_{CBO}	27
CONCLUSIONS	27
APPENDIX	29

ABSTRACT

This report presents the results of a test program requested by Jet Propulsion Laboratory to determine the effects of a sequence of environments on the electrical parameters of the 2N2369 transistors manufactured by Fairchild Semiconductors. The environments consisted of temperature effects, temperature storage, thermal and mechanical shock, vibration, acceleration, humidity, low temperature and operating life.

Parameters monitored were h_{FE1} , h_{FE2} , $V_{CE(SAT)}$, $V_{BE(SAT)}$, I_{CBO} , BV_{CBO} and BV_{EBO} .

One hundred and twenty transistors were received from Jet Propulsion Laboratory for evaluation. Ten units were set aside to check instrumentation. The 110 remaining were divided into five test groups. Group I was used as control group. Group II was subjected to thermal environments, operating life and low temperature storage. Group III was subjected to thermal and mechanical environments, operating life and acceleration. Group IV was subjected to the mechanical environments, operating life and acceleration. Group V was placed immediately into an operational life test.

Initial electrical parameter measurements were made prior to any environmental testing. Four failures were noted during the initial measurements. Two devices were catastrophic failures and two had degradation failures.

Devices in Groups II and III were then subjected to the temperature effects test. Measurements were made of the parameters while the device was at temperature. There were 13 catastrophic failures during the temperature effects test.

ABSTRACT (Cont.)

Following the temperature effects test, the devices in Groups II and III were subjected to a temperature storage test at an ambient temperature of 200° C for a period of 200 hours. Two failures were noted during the post temperature storage environment. One device was a catastrophic failure and one device had a degradation failure.

Devices in Groups II and III were then subjected to ten cycles of temperature cycling from -55° C to +125° C. Two devices were catastrophic failures following the temperature cycling environment.

Devices in Groups III and IV were subjected to ten shocks each with a 1500 G peak amplitude and a duration of $1 \pm .5$ milliseconds in each of two directions for a total of 20 blows. One catastrophic failure was noted at the post environmental data point.

Devices in Groups III and IV were subjected to three, five-minute cycles of 35 G R M S sinusoidal acceleration from 70 to 3000 to 70 cps in each of two axes. One catastrophic failure was noted at the post environmental data point.

Devices in Groups III and IV were subjected to ten cycles of humidity per MIL-STD-202B, Method 106A (excluding Step 7). Six catastrophic failures were noted at the post environmental data point. Surface corrosion was noted on the transistor leads and headers following the humidity test.

All devices were then subjected to 2000 hours of operating life at an ambient temperature of 100° C with a power dissipation of 200 milliwatts. There was a total of sixteen failures during operating life. Seven devices were catastrophic failures and 9 devices had degradation failures. The seven

ABSTRACT (Cont.)

catastrophic failures were primarily due to collector-base breakdown.

The nine degradations were primarily due to I_{CBO} leakage current increasing more than one order of magnitude from the initial value.

Devices in Groups III and IV were then subjected to an acceleration test of 20,000 G's for a period of one minute in each of the three mutually perpendicular axes. Two devices were catastrophic failures following the acceleration test.

The devices in Group II were subjected to a low temperature storage test, -180°C non-operational, for a period of 96 hours. One catastrophic failure was noted during the post environmental data point.

Table 1 is a summary of the failures noted during the environments testing.

TABLE 1

Mode Of Failure Versus Test Group

* NOTE: A device may be a failure on both lead breakage and another parameter.

GROUP	COLLECTOR-BASE CATASTROPHIC	EMITTER-BASE CATASTROPHIC	COLLECTOR-BASE AND EMITTER-BASE CATASTROPHIC	I_{CBO} DEGRADATION	BREAKDOWN VOLTAGE DEGRADATION	BETA DEGRADATION	LEAD BREAKAGE	* TOTAL	%
I	0	1	3	0	0	0	* 2	5	50%
II	9	1	4	0	0	0	0	14	70%
III	1	0	5	0	1	0	1	8	80%
IV	2	0	5	3	1	0	* 2	12	60%
V	2	0	2	4	2	2	0	12	24%
TOTAL	14	2	19	7	4	2	5		

ABSTRACT (Cont.)

Measurement data from this test was analyzed in accordance with JPL Specification ZPP20040. At each measurement point an analysis was performed to determine if a significant change in measurement values had occurred since the measurements were last taken. A significant change could be either a shift in the arithmetic mean and/or the variance (a measure of data dispersion or spread). In the interpretation of the results, it was recognized that a statistically significant finding is not necessarily significant as an engineering result (though significant engineering results based upon measurement data should be statistically significant). In this sense the statistical findings were used to detect possibly significant engineering results, and to confirm engineering results based upon the measurement data.

Histograms were prepared on the initial and final parameter measurements. The histograms provide a quick visualization of the measurement data. They are useful in setting realistic tolerances, and in detecting pronounced non-normality of the measurement distributions (which in turn affect whether or not a statistical result is significant).

This report is engineering oriented. Statistical findings are incorporated with the engineering results.

REPORT DATA

1.0 INTRODUCTION -

1.1 Objectives:

The purpose of testing the Fairchild Semiconductor 2N2369, NPN Silicon Planar Epitaxial Transistor was to gain information on device performance when subjected to a sequence of environment. This information will determine the acceptability of the device.

1.2 Test Plan:

The 120 devices received for testing were inspected for physical anomalies and numbered from 1 to 110 for identification. The remaining ten devices were set aside for use in checking the instrumentation and operating life test circuits.

The devices were inserted into Tektronix transistor adapters during the parameter measurements. No solder connections were made on the devices at any time. A specially designed multiple-package capability fixture made of magnesium was used for the mechanical shock and vibration environments. Extensive research was conducted to determine if any objectionable resonant frequencies existed. Results proved these fixtures had no measureable resonances below 3700 cps.

Parameters monitored after each environmental exposure were as follows:

- | | |
|------------------|---------------|
| 1. h_{FE1} | 5. I_{CBO} |
| 2. h_{FE2} | 6. BV_{CBO} |
| 3. $V_{BE(SAT)}$ | 7. BV_{EBO} |
| 4. $V_{CE(SAT)}$ | |

1.0 INTRODUCTION (Cont.) -

1.2 Test Plan (Cont.):

The preceding parameters will be referred to hereafter in this report as "post environmental measurements".

The initial and final electrical measurements included C_{ob} , $V_{CEO(SUST)}$, the switching times and the post environmental measurements.

Table 1 gives the requirements of these measurements in addition to the electrical characteristics of the devices under test.

All measurements were made at room ambient temperature ($25^{\circ}\text{C} \pm 3^{\circ}\text{C}$) and the devices were allowed to stabilize for a minimum of eight hours before any measurements were made, unless otherwise specified.

Prior to the initial measurements the devices were divided into five groups as follows:

- Group I - Devices numbered 1-10 inclusive were used as control devices and were measured at each data point.
- Group II - Devices numbered 11-30 inclusive were used as thermal environment units.
- Group III - Devices numbered 31-40 inclusive were used as thermal and mechanical environment units.
- Group IV - Devices numbered 41-60 inclusive were used as mechanical environment units.
- Group V - Devices numbered 61-110 inclusive were used as the operating life test units and did not undergo the thermal or mechanical tests.

1.0 INTRODUCTION (Cont.) -

1.2 Test Plan (Cont.):

The devices in Group I through V were subjected to the environments listed in Table 2.

TABLE 1
Electrical Requirements

PARAMETER	SYMBOL	CONDITION	INITIAL		POST ENVI.		UNITS
			MIN.	MAX.	MIN.	MAX.	
Forward Current Gain	h_{FE1}	$I_C=10$ ma Pulse $V_{CE}=1.0$ V	40	120	-	-	-
	h_{FE2}	$I_C=100$ ma Pulse $V_{CE}=2$ V	20	-	-	-	-
Saturation Voltages	$V_{BE(SAT)}$	$I_C=10$ ma $I_B=1.0$ ma	0.7	0.85	-	.935	V
	$V_{CE(SAT)}$	$I_C=10$ ma $I_B=1.0$ ma	-	0.25	-	.275	V
Capacitance	C_{ob}	$V_{CB}=5$ V $I_E=0$	-	4	-	-	pf
Leakage Current	I_{CBO}	$V_{CB}=20$ V	-	0.4	-	-	ua
Breakdown Voltage	BV_{CBO}	$I_C=10$ ua	40	-	38	-	V
	$V_{CEO(SUST)}$	$I_C=10$ ma Pulse $I_B=0$	15	-	14	-	V
	BV_{EBO}	$I_E=10$ ua $I_C=0$	4.5	-	4.0	-	V
Switching Times	τ	$I_C=I_{B1}=I_{B2}=10$ ma	-	13	-	-	n sec.
	T_{on}	$I_C=10$ ma $I_{B1}=3$ ma $I_{B2}=1.5$ ma	-	18	-	-	n sec.
GENERAL PRECISION, INC. INFORMATION SYSTEMS GROUP		PAGE 7 OF 29	REPORT NO. 7-0057				

1.0 INTRODUCTION (Cont.) -

1.2 Test Plan (Cont.):

TABLE 1 (Cont.)

PARAMETER	SYMBOL	CONDITION	INITIAL MIN. MAX.	POST ENVI. MIN. MAX.	UNITS
Switching Times	T_{off}	$I_C = 10 \text{ ma}$ $I_{B1} =$ 3 ma $I_{B2} = 1.5 \text{ ma}$	- 18	- -	n sec.

TABLE 2.

Tests To Which Each Group Was Subjected

	Group I	Group II	Group III	Group IV	Group V
Initial Measurements Paragraph 2. 2	×	×	×	×	×
Temperature Effects Paragraph 2. 3	*	×	×		
Temperature Storage Paragraph 2. 4	*	×	×		
Temperature Cycling Paragraph 2. 5	*	×	×		
Mechanical Shock Paragraph 2. 6	*		×	×	
Vibration Paragraph 2. 7	*		×	×	
Humidity Paragraph 2. 8	*		×	×	
Operating Life (2000 Hours) Paragraph 2. 9	*	×	×	×	×
Final Measurements Paragraph 2. 9	*	×	×	×	×
Low Temperature Paragraph 2. 10	*	×			

1.0 INTRODUCTION (Cont.) -

1.2 Test Plan (Cont.):

TABLE 2. (Cont.)

	Group I	Group II	Group III	Group IV	Group V
Acceleration Paragraph 2.11	*		x	x	

* The devices in Group I were measured at each data point.

1.2.1 Failure Analysis:

Any device which failed catastrophically was removed from the testing sequence and subjected to failure analysis. A failure description for each failure appears in the conclusions section of this report.

1.2.2 Degradation Criteria:

Current Gain: h_{FE1} $\pm 20\%$ of the initial measurement value or a minimum Beta of 36 or a maximum Beta of 132.

h_{FE2} $\pm 20\%$ of the initial measurement value or a minimum Beta of 18.


Leakage Current: $+100\%$ of the maximum specification limit or one order of magnitude change above 10 namps, whichever was smaller.

Breakdown Voltage: 95% of the minimum specification limit.

Saturation Voltage: $+10\%$ increase in maximum specification limit.

2.0 TEST PROCEDURES-

2.1 Test Sequence Flow Diagram:



2.0 TEST PROCEDURES (Cont.)-

2.2 Initial Electrical Parameter Test:

Initial measurements of the electrical parameters were performed per the requirements of Table I, on the Continental Device Corporation test equipment.

2.3 Temperature Effects Test:

The devices in Group II and III were subjected to the temperature effects test as follows: The test devices were mounted into clips on a Continental Device Corporation operating life test board. The board was inserted into a connector on the door of the test chamber. A similar board was inserted into the connector on the outside of the chamber. A shroud was installed over both boards and a flow of dry nitrogen used as a moisture shield.

The devices were subjected to the temperature effects test as shown in Figure 1.




Figure 1. Temperature Effects

2.0 TEST PROCEDURES (Cont.) -

2.4 Temperature Storage Test:

Devices in Group II and III were subjected to an ambient temperature of $200^{\circ}\text{C} \pm 5^{\circ}\text{C}$, non-operating, for a duration of 200 hours. The post environmental measurements were performed at the completion of the temperature storage test.

2.5 Thermal Shock Test:

The transistors in Group II and III were subjected to ten cycles of thermal shock as follows: The devices were exposed to a temperature of $-55^{\circ}\text{C} \begin{smallmatrix} -3^{\circ}\text{C} \\ +0^{\circ}\text{C} \end{smallmatrix}$ for a period of 30 minutes. They were then removed from the extreme cold and immediately placed in a chamber at $+125^{\circ}\text{C} \begin{smallmatrix} +3^{\circ}\text{C} \\ -0^{\circ}\text{C} \end{smallmatrix}$ for a period of 30 minutes.

Transition between chambers was less than two minutes. The sequence from cold to hot is one cycle and was continued for a total of ten cycles. The post environmental measurements were performed at the completion of thermal shock.

2.6 Mechanical Shock Test:

The devices in Group III and IV were subjected to ten impacts, each impact having a 1500 G peak amplitude and a duration of $1 \pm .5$ milliseconds in both a radial and a longitudinal direction for a total of 20 blows. Post environmental measurements were performed at the completion of the mechanical shock test.

2.7 Vibration Test:

The devices in Group III and IV were securely mounted in a specially designed multiple-package fixture made of magnesium. Extensive research was conducted to determine if any objectionable resonant frequencies existed. Results proved these special

2.0 TEST PROCEDURES (Cont.) -

2.7 Vibration Test (Cont.):

fixtures had no measurable resonances below 3700 cps. The devices were subjected to three cycles of 35 G RMS sinusoidal acceleration swept from 70 to 3000 to 70 cps. The transistors were vibrated in both the radial and longitudinal axes. Vibration time was five minutes per sweep for a total of 15 minutes in each plane. Post environmental measurements were performed at the completion of the vibration test.

2.8 Humidity Test:

The devices in Group III and IV were subjected to ten cycles of humidity per MIL-STD-202B, Method 106A, Figure 106-1 (excluding Step 7). Post environmental measurements were performed at the completion of the humidity test.

2.9 Operating Life Test:

The devices in Group II, III, IV and V were subjected to an operating life test for a period of 2000 hours at a ambient temperature of $100^{\circ} \begin{smallmatrix} +3^{\circ} \\ -0^{\circ} \end{smallmatrix}$ C. The devices were operated in a common base mode with a V_{CB} of 30.8 volts and a I_C of 6.5 milliamps for a maximum power dissipation of 200 milliwatts. The operating life test was interrupted at 100 hours, 250 hours, 500 hours, 1000 hours and 2000 hours for electrical parameter measurements. After each interruption a minimum of eight hours was allowed for stabilization at room ambient temperature before the post environmental measurements were made. At the completion of the 2000 hours life test a minimum

2.0 TEST PROCEDURES (Cont.)-

2.9 Operating Life Test (Cont.):

of 48 hours was allowed for stabilization before the final electrical measurements were made. The final measurements were made before Group II was subjected to the low temperature, and Group III and IV were subjected to acceleration. The life test circuit is included in the Appendix of this report.

2.10 Acceleration Test:

At Jet Propulsion Laboratory the devices in Group III and IV were subjected to an acceleration test of 20,000 G for a period of one minute in each of the three mutually perpendicular planes. Post environmental measurements were made at the completion of the acceleration test.

2.11 Low Temperature Test:

The devices in Group II, non-operational, were subjected to a low temperature test at Jet Propulsion Laboratory. The devices were subjected to an ambient temperature of -180°C for a period of 96 hours. Post environmental parameter measurements were made at the completion of the low temperature test.

3.0 TEST RESULTS-

3.1 Initial Electrical Parameter Test Results:

Initial electrical parameter measurements were within the manufacturer's specification with the exception of four devices. Two devices were catastrophic failures and two devices were below the manufacturer's specification on BV_{CBO} . Table 3 is a summary of the failures noted during the initial parameter measurements.

3.0 TEST RESULTS (Cont.)-

3.1 Initial Electrical Parameter Test Results (Cont.):

TABLE 3

Failures Noted During Initial Parameter Measurements

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN FIRST DETECTED	FINAL VALUE
57	Catastrophic	BV _{CBO}	2.4 Volts	--
		BV _{EBO}	2.4 Volts	--
76	Catastrophic	BV _{CBO}	Short	--
		BV _{EBO}	3.4 Volts	--
95	Degradation	BV _{CBO}	34.3 Volts	34.1 Volts
99	Degradation	BV _{CBO}	39.4 Volts	39.6 Volts

3.2 Temperature Effects Test Results:

There were 13 catastrophic failures during the temperature effects test. Secondary breakdown was noted on three of the 13 catastrophic failures. A plot of the mean and 90% confidence limits of the mean is included in the appendix of this report for each of the parameters measured during the temperature effects test. Table 4 is a summary of the failures noted during the temperature effects parameter measurements.

3.0 TEST RESULTS (Cont.)-

3.2 Temperature Effects Test Results (Cont.):

TABLE 4

Failures Noted Following Temperature Effects

DEVICE NO.	FAILURE CLASSIFICATION	WHEN FIRST DETECTED	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED
11	Catastrophic	30° C (1st)	BV _{CBO}	Short
12	Catastrophic	30° C (1st)	BV _{CBO}	Short
13	Catastrophic	75° C	BV _{CBO} BV _{EBO}	Short Short
14	Catastrophic	30° C (1st)	BV _{EBO}	Short
15	Catastrophic	75° C	BV _{CBO}	Short
21	Catastrophic	175° C	BV _{CBO} BV _{EBO}	Open Open
22	Catastrophic	75° C	BV _{CBO}	Short
23	Catastrophic	75° C	BV _{CBO}	Short
26	Catastrophic	75° C	BV _{CBO}	Short
27	Catastrophic	75° C	BV _{CBO}	Short
28	Catastrophic	75° C	BV _{CBO}	Short
31	Catastrophic	150° C	BV _{CBO} BV _{EBO}	7.35 Volts Short
34	Catastrophic	150° C	BV _{CBO} BV _{EBO}	Short Open

3.0 TEST RESULTS (Cont.) -

3.3 Temperature Storage Test Results:

There were two failures noted at the electrical parameter measurement data point following the temperature storage test. Table 5 is a summary of the failures noted.

TABLE 5
Failures Noted Following Temperature Storage

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED
29	Catastrophic	BV _{CBO} BV _{EBO}	Short Short
38	Degradation	BV _{CBO}	37.4 Volts

3.4 Thermal Shock Test Results:

There were two catastrophic failures noted at the electrical parameter measurement data point following the thermal shock test. Table 6 is a summary of the failures noted.

TABLE 6
Failures Noted Following Thermal Shock

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED
8	Catastrophic	BV _{CBO}	Short
17	Catastrophic	BV _{CBO}	Short

3.0 TEST RESULTS (Cont.) -

3.5 Mechanical Shock Test Results:

One catastrophic failure was noted during the post environmental data point. Table 7 is a summary of the failure noted during the mechanical shock test.

TABLE 7
Failures Noted Following Mechanical Shock

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED
35	Catastrophic	BV _{CBO}	Short

3.6 Vibration Test Results:

One degradation failure was noted during the post environmental data point. Table 8 is a summary of the failure noted during the vibration test.

TABLE 8
Failures Noted Following Vibration

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED
41	Degradation	BV _{EBO}	3.81

3.7 Humidity Test Results:

Six catastrophic failures were noted at the post environmental measurements. Table 9 is a summary of the failures noted during the humidity test. The devices subjected to the humidity test also were noted as having surface corrosion on the leads and heads.

3.0 TEST RESULTS (Cont.):

3.7 Humidity Test Results (Cont.):

TABLE 9
Failures Noted Following Humidity

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED
32	Catastrophic	BV_{CBO}	Short
		BV_{EBO}	Short
33	Catastrophic	BV_{CBO}	Short
		BV_{EBO}	Short
42	Catastrophic	BV_{CBO}	Short
		BV_{EBO}	Short
50	Catastrophic	BV_{CBO}	Short
		BV_{EBO}	Short
56	Catastrophic	BV_{CBO}	Short
		BV_{EBO}	Short
59	Catastrophic	BV_{CBO}	Short
		BV_{EBO}	Short

3.8 Operating Life Test Results:

An increase of collector-base leakage (I_{CBO}) was noted throughout the operating life test. There were seven catastrophic and 8 degradation failures during this test. Results of the test are summarized in Table 10 comparing mode of failure versus time.

3.0 TEST RESULTS (Cont.) -

3.8 Operating Life Test Results (Cont.):

TABLE 10
Summary of Operating Life Test Results

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED	FINAL VALUE
100-Hour				
36	Catastrophic	Lead	--	--
107	Degradation	h_{FE2}	26.3	30.3
250-Hour				
47	Degradation	I_{CBO}	150 na	20 na
82	Degradation	I_{CBO}	1030 na	192 na
86	Catastrophic	BV_{CBO}	Short	--
87	Catastrophic	BV_{CBO}	Short	--
500-Hour				
64	Degradation	I_{CBO}	140 na	88 na
108	Degradation	I_{CBO}	140 na	88 na
1000-Hour				
46	Catastrophic	BV_{CBO}	Short	--
49	Catastrophic	BV_{CBO}	Short	--
83	Degradation	I_{CBO}	260 na	4 na
96	Degradation	h_{FE1}	39.4	56.2
2000-Hour				
43	Catastrophic	BV_{CBO}	15 Volts	--
GENERAL PRECISION, INC. INFORMATION SYSTEMS GROUP		PAGE 20 OF 29		REPORT NO. 7-0057

3.0 TEST RESULTS (Cont.) -

3.8 , Operating Life Test Results (Cont.):

TABLE 10 (Cont.)

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED	FINAL VALUE
	2000-Hour (Cont.)			
51	Degradation	I_{CBO}	850 na	--
70	Catastrophic	BV_{CBO}	Short	--

3.9 Acceleration Test Results:

Two catastrophic failures were noted during the post environmental data point. Table 11 is a summary of the failures noted during the acceleration test.

TABLE 11
Failures Noted Following Acceleration

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED
37	Catastrophic	BV_{CBO} BV_{EBO}	Open
52	Catastrophic	Lead	Open

Device No. 37 was opened and it was found that the base lead was broken free of the dice.

3.10 Low Temperature Test Results:

One catastrophic failure was noted during the post environmental data point. Table 12 is a summary of the mode of failure.

3.0 TEST RESULTS (Cont.)-

3.10 Low Temperature Test Results (Cont.):

TABLE 12

Failures Noted Following Low Temperature

DEVICE NO.	FAILURE CLASSIFICATION	PARAMETER FAILURE	MEASURED VALUE WHEN DETECTED
16	Catastrophic	BV_{CBO}	Short

4.0 FAILURE ANALYSIS-

All devices regarded as failures as a result of the test program were checked on the Tektronix 575 Transistor Curve Tracer. Failure analysis appears under the specific environment sections.

5.0

STATISTICAL INTERPRETATION OF RESULTS-

A result which is statistically significant is one which is significant at a confidence level of 95 per cent. That is, we make a statement that the change observed is due to a cause other than change; we expect this statement to be correct to the extent that if the test were repeated with similar units, the same general result would be obtained 95 per cent of the time.

Often the cause of a statistically significant result is due to a shift in accuracy of the measurement instrument rather than an effect of environmental stress. This can usually be determined by examination of the control unit measurements. In such cases, where the cause of change is instrumentation accuracy rather than environmental effect, the result is not reported as being statistically significant.

5.1

Failures:

Thirteen out of 30 units failed during temperature effects. Eleven of the failures occurred in Group II which would indicate that units in Group II are significantly different from units in Group III, yet both groups should be the same.

Out of 33 units subjected to mechanical and/or thermal stress, eight failures occurred during the first 100 hours of life test. It can not be said that the causative factor of failure were the mechanical and/or thermal stresses, for by 250 hours the control group had proportionately the same number of failures as Group II, III, and IV. Of interest is the proportionately few failures in Group V.

5.0 STATISTICAL INTERPRETATION OF RESULTS (Cont.)-

5.1 Failures (Cont.):

Following 1000 hours of life test it was observed that three units out of 14 had failed in Group IV.

During acceleration, five out of fourteen units failed.

There were no significant changes observed on the following parameters: $V_{BE(SAT)}$, C_{ob} , $V_{CEO(SUST)}$, τ , T_{on} , and T_{off} .

5.2 h_{FEI} :

5.2.1 Vibration:

Group IV had a statistically significant mean increase of 1.8 per cent.

5.2.2 Life Test:

100 Hours

Group IV had a statistically significant mean increase of 1.8 per cent. Group V had a statistically significant mean decrease of 4.3 per cent. One unit in Group V had a measurement decrease of 31.3.

250 Hours:

Group IV had a statistically significant mean increase of 2.7 per cent. One unit in Group IV had a measurement increase of 11.9. Group V had a statistically significant mean decrease of 1.5 per cent.

500 Hours

Group II had a statistically significant mean decrease of 2.0 per cent. One unit in Group IV had a decrease of 43.9.

5.0 STATISTICAL INTERPRETATION OF RESULTS (Cont.)-

5.2 h_{FE1} (Cont.):

5.2.2 Life Test (Cont.):

1000 Hours

Groups II, III, and IV had a statistically significant mean increase of 4.3, 3.9, and 5.5 respectively. Group V had a range of change from -25.8 to 14.7.

2000 Hours

Group IV had a statistically significant mean decrease of 3.8 per cent. Group V had a range of change from -36.6 to 27.0.

5.2.3 Acceleration:

Group V had a statistically significant mean decrease of 1.1 per cent.

5.2.4 Low Temperature:

Group II had a statistically significant mean decrease of 1.0 per cent.

5.3 h_{FE2} :

5.3.1 Life Test:

100 Hours

Groups III, IV, and V had a statistically significant mean increase of 0.9, 1.0 and 1.4 per cent respectively.

1000 Hours

Group V had a statistically significant mean increase of 2.7 per cent.

2000 Hours

Groups II, IV, and V had a statistically significant mean decrease of 4.6, 4.4, and 11.1 per cent respectively. The range of

5.0 STATISTICAL INTERPRETATION OF RESULTS (Cont.) -

5.3 h_{FE2} (Cont.):

5.3.1 Life Test (Cont.):

2000 Hours (Cont.)

measurement change for Group V was from -18.1 to 17.0

5.4 $V_{CE(SAT)}$:

5.4.1 Initial:

Group II had one unit with a measurement of 9.3 volts.

5.4.2 Shock:

Group IV had a statistically significant mean increase of 2.5 per cent.

5.4.3 Life Test:

250 Hours

Group V had a statistically significant mean increase of 2.7 per cent.

500 Hours

Group IV had a statistically significant mean increase of 2.8 per cent. Group V had a statistically significant mean decrease of 2.2 per cent.

5.5 BV_{CBO} :

No significant mean changes were observed. Measurement change for individual units ranged from -13.2 volts to 12.4 volts.

5.6 BV_{EBO} :

No significant mean changes were observed. One unit in Group III had an increase of 46.2 volts during or following acceleration.

5.0 STATISTICAL INTERPRETATION OF RESULTS (Cont.) -

5.7 I_{CBO} :

Group V had a significant mean increase of 37.7, 31.9 and 30.9 per cent after 100, 250, and 500 hours of life test respectively.

6.0 CONCLUSIONS-

There was a total of 51 failures noted during the testing program; thirty five were catastrophic failures, seven were degradation failures on I_{CBO} . A summary of mode of failure versus test group is included in Table 13. Of interest is the high percentage of catastrophic failures in the control group (Group I). This group did not see any of the environments the other devices were subjected to, but had four catastrophic failures. A possibility exists that repeated application of breakdown voltages or currents along with the susceptibility of the device to exhibit secondary breakdown may have been the cause of the catastrophic failures. The extremely small geometry of the dice and planar construction prevent anything more than a hypothesis of the cause of the catastrophic failures.

The large percentage of I_{CBO} failures is due to an increase of leakage current greater than one order of magnitude from the initial value.

TABLE 13

Mode Of Failure Versus Test Group

GROUP	COLLECTOR-BASE CATASTROPHIC	EMITTER-BASE CATASTROPHIC	COLLECTOR-BASE AND EMITTER-BASE CATASTROPHIC	I _{CBO} DEGRADATION	BREAKDOWN VOLTAGE DEGRADATION	BETA DEGRADATION	LEAD BREAKAGE	* TOTAL	%
I	0	1	3	0	0	0	2 *	5	50%
II	9	1	4	0	0	0	0	14	70%
III	1	0	5	0	1	0	1	8	80%
IV	2	0	5	3	1	0	2 *	12	60%
V	2	0	2	4	2	2	0	12	24%
TOTAL	14	2	19	7	4	2	5		

* NOTE: A device may be a failure on both lead breakage and another parameter.

APPENDIX 1

This Appendix contains a Description Of Apparatus,
Life Test Circuit, Graphs, J. P. L. Format and,
Histograms

DESCRIPTION OF APPARATUS-

Leakage Tester, MTD-18-1, Continental Device Corporation

Pulsed V_{SAT} Tester, 53014-3, Continental Device Corporation

Beta Tester, 43013, Continental Device Corporation


Beta Tester, 43014-1-1, Continental Device Corporation

LV_{CE} Tester, MT-16-2, Continental Device Corporation

Capacitance Bridge, Model 75A-S8, Boonton Electronics Corporation S/N 602

Digital Voltmeter, Model 7300-A, Cimron Corporation S/N 1342

LIFE TEST CIRCUIT



$$V_{CC} = 64 \text{ Volts}$$

$$V_{EE} = 6.5 \text{ Volts}$$

$$R_L = 5.1 \text{ K}$$

$$R_E = 1.0 \text{ K}$$

$$I_E = 6.5 \text{ ma}$$


$$V_{CB} = 30.8 \text{ Volts}$$

$$P_D = 200 \text{ mw}$$


From a statistical approach the Temperature Effects curves are meaningful. Since the calculations of the mean for each test point include the maverick data points, the mean shows a gross effect. Each curve consists of the parameter "mean" and the upper and lower 90 per cent confidence limits of the mean with respect to temperature.

From an engineering standpoint the curves do not reflect the typical parameter response.

JPL TEST NUMBER A0083 BM (7-0057)
VENDOR FAIRCHILD SEMICONDUCTOR
PART NUMBER 2N2369
PARAMETER h_{FE1} UNIT NONE
TEMPERATURE EFFECTS TEST




JPL TEST NUMBER A0083 BM (7-0057)
VENDOR FAIRCHILD SEMICONDUCTOR
PART NUMBER 2N2369
PARAMETER h_{FE2} UNIT NONE
TEMPERATURE EFFECTS TEST




JPL TEST NUMBER A0083 BM(7-0057)
VENDOR FAIRCHILD SEMICONDUCTOR
PART NUMBER 2N 2369
PARAMETER $V_{CE(SAT)}$ UNIT VOLTS


TEMPERATURE EFFECTS TEST




JPL TEST NUMBER A0083 BM (7-0057)
VENDOR FAIRCHILD SEMICONDUCTOR
PART NUMBER 2N 2369
PARAMETER $V_{BE(SAT)}$ UNIT VOLTS
TEMPERATURE EFFECTS TEST




JPL TEST NUMBER A0083 BM (7-0057)
 VENDOR FAIRCHILD SEMICONDUCTOR
 PART NUMBER 2N 2369
 PARAMETER I_{CBO} UNIT MICROAMPERES
 TEMPERATURE EFFECTS TEST



JPL TEST NUMBER A0083 BM (7-0057)
VENDOR FAIRCHILD SEMICONDUCTOR
PART NUMBER 2N 2369
PARAMETER BV_{EBO} UNIT VOLTS
TEMPERATURE EFFECTS TEST



JPL TEST NUMBER A0083 BM(7-0057)
VENDOR FAIRCHILD SEMICONDUCTOR
PART NUMBER 2N2369
PARAMETER BV_{CBO} UNIT VOLTS
TEMPERATURE EFFECTS TEST



JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Hfe 1

MULTIPLIER: 1 UNIT: None NOMINAL VALUE: None LOWER LIMIT: 40.0 UPPER LIMIT: 120.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NL	NC
57.143	81.466	119.05	5.7210			8-10-63					10	0	0
57.803	81.187	119.05	5.7579	1.013	-1.1793	8-27-63 -.27958	.91579	.21156	-.34437	-1.322	10	0	0
56.497	80.050	119.05	5.7560	1.001	-2.5025	9-5-63 -1.1371	.00000	.23049	-1.4205	-4.933	10	0	0
57.803	81.080	114.94	5.4112	1.132	-4.1052	9-26-63 1.0304	2.5025	.58722	1.2709	1.755	10	0	0
57.803	80.666	113.64	5.3415	1.026	-1.3061	10-8-63 -.41394	.00000	.13827	-.51316	-2.994	10	0	0
56.180	78.232	111.11	5.2079	1.052	-3.5613	10-9-63 -2.4336	-1.5244	.20607	-3.1107	-11.810	10	0	0
57.143	79.559	112.36	5.2802	1.028	.37408	10-14-63 1.3267	2.1011	.16204	1.6676	8.188	10	0	0
56.497	77.670	111.11	5.6387	1.026	-1.2484	10-15-63 -.62805	.00000	.11180	-.80861	-5.617	9	0	1
56.818	78.236	114.94	6.7522	1.275	-.70027	10-16-63 3.2651	3.8314	.51369	.41734	.636	8	0	1
56.497	77.637	111.11	6.3927	1.116	-3.8314	10-29-63 -.59873	.70027	.48875	-.77119	-1.225	8	0	0
56.818	79.729	112.36	7.3879	1.169	.32100	11-5-63 .78622	1.7470	.19844	.98611	3.962	7	0	1
56.818	78.877	111.11	8.5760	1.155	-1.4125	11-12-63 -.80704	.00000	.21754	-1.0232	-3.710	6	0	1
56.180	78.059	111.11	8.5848	1.002	-1.7149	11-26-63 -.81791	.00000	.25469	-1.0478	-3.211	6	0	0
56.818	78.826	112.36	8.6763	1.021	.45346	12-2-63 .76697	1.2484	.10992	.97299	6.978	6	0	0
55.866	76.881	109.89	10.328	1.181	-2.4694	12-17-63 -1.1813	-.73466	.32403	-1.5366	-3.646	5	0	1
56.497	77.101	108.70	10.086	1.049	-1.1945	1-30-64 .21976	.84951	.36324	.28503	.605	5	0	0
56.818	77.742	109.89	10.254	1.034	.32100	2-10-64 .64076	1.1944	.16851	.82422	3.803	5	0	0
56.497	77.513	109.89	10.340	1.017	-.45347	4-2-64 -.22881	.00000	.09578	-.29519	-2.389	5	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Hfe 1

MULTIPLIER: 1 UNIT: None NOMINAL VALUE: None LOWER LIMIT: 40.0 UPPER LIMIT: 120.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD. (8-10-63)	P.C.	t	No.	NU	NL	NC
57.471	79.375	109.89	3.3917							20	0	0	0
62.500	80.940	104.17	5.7969	1.168	-3.5029	-62693	3.3069	.80814	-.77455	8	0	0	12
61.350	79.514	103.09	5.7543	1.015	-1.9608	-1.4268	-.81142	.14067	-1.7944	8	0	0	0
62.112	80.615	103.09	6.8041	1.223	-2.0952	.16937	1.6835	.51431	.21010	7	0	0	1
60.976	79.699	102.04	6.6843	1.036	-1.9225	-.91530	.00000	.24765	-1.1484	7	0	0	0
59.524	77.319	98.039	6.3588	1.105	-4.0238	-2.3806	-.64516	.50799	-3.0790	7	0	0	0
60.606	79.588	102.04	6.4974	1.044	.00000	2.2698	4.0016	.55776	2.8519	7	0	0	0
60.976	79.110	101.01	6.4741	1.007	-1.6234	-.47843	1.3008	.40771	-.60476	7	0	0	0
60.606	81.664	100.00	6.7978	1.058	-1.0101	-.40640	.00000	.15898	-.49766	6	0	0	1

Post Temp. Storage (10-8-63)

Post Temp. Cycling (10-14-63)

Oper. Life Hrs. = 100 (11-5-63)

Oper. Life Hrs. = 250 (11-12-63)

Oper. Life Hrs. = 500 (11-26-63)

Oper. Life Hrs. = 1000 (12-17-63)

Low Temperature (4-2-64)

JPL TEST NUMBER: 7-0057				VENDOR: FAIRCHILD SEMICONDUCTOR				PART NUMBER: 2N 2369				PARAMETER: Hfe 1			
MULTIPLIER: 1				UNIT: None				NOMINAL VALUE: None				UPPER LIMIT: 120.0			
Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC	
Post Temp. Storage (10-8-63)															
61.728	92.431	116.28	6.4146	1.426	-2.6427	1.5812	14.223	1.8728	1.6775	.844	10	0	0	0	
Shock (10-9-63)															
62.112	94.257	126.58	8.5643	1.212	-6.1004	-3.8607	-2.2618	.57872	-4.0925	-6.671	7	1	0	1	
Post Temp. Cycling (10-14-63)															
59.524	94.337	120.48	8.3159	1.053	1.0822	1.7756	2.9748	.27988	1.8474	6.344	7	1	0	0	
Vibration (10-15-63)															
60.606	96.113	123.46	8.5328	1.039	-2.3127	-1.1998	-.36510	.23166	-1.2642	-5.179	7	1	0	0	
Humidity (10-29-63)															
60.241	94.913	121.95	8.3724	1.028	-1.4693	-.98421	-.54466	.12425	-1.0478	-7.921	7	1	0	0	
Oper. Life Hrs. = 100 (11-5-63)															
59.524	93.929	120.48	8.2581	1.260	-3.1069	-1.5804	.00000	.67474	-1.8555	-2.342	4	0	0	3	
Oper. Life Hrs. = 250 (11-12-63)															
58.480	85.173	108.70	12.263	1.029	-1.1687	.58026	3.2901	.98174	.67667	.591	4	0	0	0	
Oper. Life Hrs. = 500 (11-26-63)															
59.172	85.753	107.53	12.439	1.099	-4.3421	-2.2346	-.96454	.75312	-2.6756	-2.967	4	0	0	0	
Oper. Life Hrs. = 1000 (12-17-63)															
57.803	83.518	105.26	11.864	1.074	1.4570	3.0023	5.4860	.87285	3.4701	3.440	4	0	0	0	
Oper. Life Hrs. = 2000 (1-30-64)															
60.606	86.521	107.53	12.292	1.072	-5.4861	-1.8532	.00000	1.2470	-2.1889	-1.486	4	0	0	0	
Acceleration (2-10-64)															
59.172	84.667	107.53	11.873	1.576	.00000	.35432	.70863	.35432	.43764	1.000	2	0	0	2	
Low Temperature (4-2-64)															
59.880	80.961	102.04	21.080	1.051	-1.0567	-.52836	.00000	.52836	-.65690	-1.000	2	0	0	0	
58.824	80.432	102.04	21.609												

JPL TEST NUMBER: 7-0057				VENDOR: FAIRCHILD SEMICONDUCTOR				PART NUMBER: 2N 2369				PARAMETER: Hfe 1							
MULTIPLIER: 1				UNIT: None				NOMINAL VALUE: None				LOWER LIMIT: 40.0				UPPER LIMIT: 120.0			
Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC					
55.249	79.995	103.09	2.8597								19	0	0	1					
52.910	77.242	100.00	2.8046	1.040	-4.5813	-2.7528	-1.9050	.12835	-3.5638	-21.448	19	0	0	0					
53.476	78.096	101.01	2.8299	1.018	.40312	.85425	1.7801	.08168	1.0938	10.458	19	0	0	0					
34.602	75.414	100.00	3.7195	1.637	-31.187	-2.3909	.00000	1.6975	-3.1704	-1.409	18	0	1	1					
53.191	77.751	98.039	3.1321	1.813	-3.2795	-.61646	3.9682	.59720	-.79287	-1.032	14	0	0	4					
52.632	79.101	102.04	3.4921	1.243	-1.7470	1.3505	11.905	.90339	1.7073	1.495	14	0	0	0					
27.027	73.681	99.010	4.8408	1.922	-43.895	-5.4199	-.46597	2.9798	-7.3558	-1.819	14	0	1	0					
52.910	79.764	102.04	4.3017	1.612	1.1655	3.9824	8.9198	.72876	4.9927	5.465	11	0	0	3					
52.083	74.719	92.593	3.6819	1.502	-6.4173	-2.8178	1.3008	.76177	-3.7711	-3.699	10	0	0	1					
51.813	72.918	92.593	5.0932	1.340	-.62491	-.19865	.46596	.14522	-.27242	-1.368	7	0	0	3					

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Hfe 1

MULTIPLIER: 1 UNIT: None NOMINAL VALUE: None LOWER LIMIT: 40.0 UPPER LIMIT: 120.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
54.945	79.076	121.95	2.3006								49	1	0	1
34.014	75.799	117.65	2.4012	1.089	-31.346	-3.2775	3.2938	.65706	-4.3240	-4.988	49	0	1	0
33.445	73.474	113.64	2.3616	1.034	-5.4572	-2.3252	4.2571	.23706	-3.1647	-9.808	49	0	1	0
35.088	74.284	121.95	2.5041	1.078	-1.7004	1.3985	8.3148	.25928	1.8826	5.394	47	1	1	2
39.370	73.046	121.95	2.6581	1.127	-25.769	-1.2378	14.664	.88140	-1.6946	-1.404	47	1	1	0
32.051	74.276	121.95	2.9624	1.216	-36.605	1.4845	27.009	1.4034	1.9987	1.058	46	1	1	1

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Hfe 2

MULTIPLIER: 1 UNIT: None NOMINAL VALUE: None LOWER LIMIT: 20.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
32.258	45.066	66.667	3.1741			8-9-63					10	0	0	0
32.258	45.045	66.667	3.1653	1.006	-1.5385	-0.02157	1.3227	.21375	-.04789	-.101	10	0	0	0
32.258	45.045	66.667	3.1653	1.000	.00000	9-10-63	.00000	.00000	.00000		10	0	0	0
40.000	53.878	76.923	3.4830	1.211	6.5217	9-26-63	.00000	.00000	.00000		10	0	0	0
40.000	53.802	76.923	3.4298	1.031	-2.9240	8.8338	11.111	.48798	16.396	18.103	10	0	0	0
40.000	53.370	76.923	3.5273	1.058	-2.1645	10-8-63	2.1645	.38264	-.14116	-.198	10	0	0	0
40.000	54.660	83.333	3.8836	1.212	.00000	10-9-63	.00000	.28860	-.81114	-1.500	10	0	0	0
40.000	54.173	76.923	3.7724	1.178	-6.4103	10-14-63	1.2904	.65401	2.3607	1.973	10	0	0	0
40.000	54.627	76.923	4.1844	1.094	-2.9240	10-15-63	2.9240	.81896	-.71505	-.473	9	0	0	1
40.000	54.086	76.923	4.3264	1.069	-2.1645	10-16-63	.36550	.36550	-.66908	-1.000	8	0	0	1
41.667	54.841	76.923	4.7939	1.074	.00000	10-29-63	.00000	.35425	-1.0005	-1.528	8	0	0	0
40.000	55.767	76.923	5.6410	1.187	-2.1645	11-5-63	.54731	.35744	.99800	1.531	7	0	0	1
45.455	61.379	83.333	5.7770	1.049	4.5454	11-12-63	.00000	.40892	-1.1450	-1.561	6	0	0	1
45.455	64.102	90.909	6.9762	1.458	.00000	11-26-63	5.6120	.37863	9.1433	14.822	6	0	0	0
40.000	55.809	76.923	6.9086	1.224	-13.986	12-2-63	2.7230	1.3388	4.2480	2.034	6	0	0	0
43.478	60.174	83.333	7.4235	1.155	2.6316	12-17-63	2.7230	1.7049	-15.433	-5.052	5	0	0	1
47.619	65.381	90.909	8.0806	1.185	2.6316	1-30-64	6.4103	.63892	7.2547	6.833	5	0	0	0
47.619	65.381	90.909	8.0806	1.000	.00000	2-10-64	5.2069	.84951	7.9639	6.129	5	0	0	0
						4-2-64	.00000	.00000	.00000		5	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Hfe 2 ..

MULTIPLIER: 1 UNIT: None NOMINAL VALUE: None LOWER LIMIT: 20.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD.	P.C.	t	No.	NU	NL	NC
30.303	41.283	62.500	1.6928							20	0	0	0
34.483	49.068	62.500	3.0781	1.323	2.2247	8.8129	12.500	17.961	8.046	8	0	0	12
34.483	49.068	62.500	3.0781	1.000	.00000	.00000	.00000	.00000		8	0	0	0
34.483	48.523	62.500	3.4598	1.105	-2.6316	-.75188	.00000	.48534	-1.5495	7	0	0	1
34.483	47.956	58.824	3.0603	1.278	-3.6765	-.56698	2.6316	.79793	-1.1823	7	0	0	0
40.000	53.587	66.667	3.4004	1.235	2.1645	5.6310	7.8432	.64847	10.508	7	0	0	0
34.483	49.807	62.500	3.3704	1.018	-6.1919	-3.7799	2.3809	1.0964	-7.5891	7	0	0	0
37.037	51.970	66.667	3.6536	1.175	-2.3809	2.1628	4.1667	.79985	4.1617	7	0	0	0
41.667	57.820	71.429	4.2898	1.182	3.6765	5.1250	6.9444	.49194	8.8637	6	0	0	1

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Hfe 2

MULTIPLIER: 1 UNIT: None NOMINAL VALUE: None LOWER LIMIT: 20.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
37.037	52.967	71.429	3.8193								10	0	0	0
43.478	67.145	100.00	6.8144	2.547	6.4412	13.725	28.571	20.440		5.305	8	0	0	2
43.478	67.349	100.00	7.0989	1.053	-6.4103	-2.5852	.00000	1.0203	-3.8386	-2.534	7	0	0	1
43.478	70.720	100.00	7.2489	1.043	.00000	3.3702	6.4103	.99035	4.7655	3.403	7	0	0	0
43.478	70.720	100.00	7.2489	1.000	.00000	.00000	.00000	.00000			7	0	0	0
40.000	65.127	100.00	8.0043	1.219	-18.824	-5.5924	.00000	2.4173	-8.5869	-2.313	7	0	0	0
43.478	61.115	76.923	7.8491	1.820	.00000	.00000	.00000	.00000			4	0	0	3
43.478	59.925	76.923	7.4054	1.123	-4.7619	-1.1905	.00000	1.1905	-1.9866	-1.000	4	0	0	0
47.619	66.675	83.333	8.2021	1.227	4.1408	6.7498	10.256	1.2757	10.124	5.291	4	0	0	0
43.478	62.718	83.333	9.0036	1.205	-6.1919	-3.9568	.00000	1.3860	-6.3089	-2.855	4	0	0	0
45.455	65.317	83.333	8.8933	1.025	.00000	2.5987	5.4945	1.1413	3.9786	2.277	4	0	0	0
		50.000									1	0	0	3
		47.619									1	0	0	0

Acceleration (2-10-64)

Not Analyzed

Low Temperature (4-2-64)

Not Analyzed

PARAMETER: Hfe 2

PART NUMBER: 2N 2369

VENDOR: FAIRCHILD SEMICONDUCTOR

JPL TEST NUMBER: 7-0057

MULTIPLIER: 1 UNIT: None NOMINAL VALUE: None LOWER LIMIT: 20.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
30.303	45.260	62.500	1.9256	1.370	2.2247	7.7505	11.204	.47674	14.621	16.257	19	0	0	1
34.483	53.011	71.429	2.2538	1.066	.00000	.88544	3.6765	.28757	1.6429	3.079	19	0	0	0
34.483	53.896	71.429	2.1832	1.546	-23.229	-3.4073	.00000	1.6185	-6.7198	-2.105	18	0	0	1
24.390	50.705	71.429	2.7887	1.322	.00000	.00000	.00000	.00000	.00000	.00000	14	0	0	4
34.483	53.662	71.429	2.7507	1.400	.00000	1.2951	10.256	.80373	2.3566	1.611	14	0	0	0
34.483	54.957	76.923	3.2546	1.246	-8.3333	4.8883	7.8432	1.0788	8.1682	4.531	14	0	0	0
38.462	59.846	83.333	3.6333	1.077	-7.8432	-2.6592	3.2680	.90395	-4.6896	-2.942	12	0	0	2
38.462	56.703	83.333	4.0719	1.332	-3.2680	1.9228	7.8432	.97436	3.4211	1.973	11	0	0	1
37.037	56.205	76.923	3.6855	1.755	-7.8432	6.0762	18.797	2.7826	10.021	2.184	8	0	0	3
41.667	60.633	90.909	5.7256											

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Hfe 2

MULTIPLIER: 1 UNIT: None NOMINAL VALUE: None LOWER LIMIT: 20.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
29.412	42.905	66.667	1.1077								49	0	0	1
26.316	43.534	71.429	1.2630	1.300	-10.721	.62803	4.7619	.30925	1.4426	2.031	49	0	0	0
26.316	43.332	71.429	1.2972	1.055	-13.196	-.20176	2.9240	.29760	-.46561	-.678	49	0	0	0
31.250	52.374	90.909	1.6683	1.586	4.9342	9.0048	19.480	.39048	17.193	23.061	47	0	0	2
32.258	53.827	100.00	1.9052	1.304	-10.101	1.4531	10.417	.52465	2.6995	2.770	47	0	0	0
30.303	55.592	100.00	2.0468	1.130	-18.100	1.9533	17.045	.85085	3.5136	2.296	46	0	0	1

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vbe(sat)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: .700 UPPER LIMIT: .935

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.76000	.78500	.80000	.00341			8-21-63					10	0	0	0
.78000	.78800	.80000	.00199	2.929	-.01000	.00300	.03000	.00367	.38071	.818	10	0	0	0
.78000	.78600	.80000	.00221	1.231	-.01000	9-5-63	.00200	.01000	-.25445	-1.000	10	0	0	0
.76000	.76800	.78000	.00249	1.269	-.03000	9-26-63	-.01800	.01000	.00249	-2.3438	10	0	0	0
.77000	.77900	.79000	.00233	1.142	.00000	10-8-63	.01100	.02000	.00180	1.4121	10	0	0	0
.77000	.78000	.79000	.00150	2.433	-.01000	10-9-63	.00100	.01000	.00180	.12820	10	0	0	0
.77000	.77600	.79000	.00221	2.185	-.01000	10-14-63	-.00400	.00000	.00163	-.51546	10	0	0	0
.77000	.77778	.79000	.00222	1.098	.00000	10-15-63	.00222	.01000	.00147	.28571	9	0	0	1
.76000	.77625	.79000	.00324	1.886	-.02000	10-16-63	.00125	.01000	.00295	-.16103	8	0	0	1
.75000	.77500	.79000	.00423	1.702	-.03000	10-29-63	.00125	.02000	.00479	-.16129	8	0	0	0
.77000	.78000	.79000	.00219	4.273	.00000	11-5-63	.00143	.01000	.00143	.18315	7	0	0	1
.77000	.78000	.79000	.00258	1.198	.00000	11-12-63	.00000	.00000	.00000		6	0	0	1
.77000	.77667	.79000	.00333	1.660	-.01000	11-26-63	.00333	.00000	.00211	-.42918	6	0	0	0
.77000	.78000	.79000	.00258	1.660	.00000	12-2-63	.00333	.01000	.00211	.42735	6	0	0	0
.77000	.77800	.79000	.00374	1.745	-.01000	12-17-63	-.00200	.00000	.00200	-.25707	5	0	0	1
.78000	.78600	.80000	.00399	1.141	.00000	1-30-64	.00800	.01000	.00200	1.0178	5	0	0	0
.78000	.78600	.80000	.00399	1.000	.00000	2-10-64	.00000	.00000	.00000	.00000	5	0	0	0
.78000	.78600	.80000	.00399	1.000	.00000	4-2-64	.00000	.00000	.00000	.00000	5	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vbe(sat)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: .700 UPPER LIMIT: .935

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD.	P.C.	t	No.	NU	NL	NC
.31000	.76000	.79000	.02372							20	0	1	0
							Post Temp. Storage (10-8-63)						
.77000	.78250	.79000	.00250	225.611	-.01000	-.00250	.01000	.00313	-.31949	8	0	0	12
							Post Temp. Cycling (10-14-63)						
.78000	.78125	.79000	.00126	3.951	-.01000	-.00125	.01000	.00295	-.16000	8	0	0	0
							Oper. Life Hrs. = 100 (11-5-63)						
.77000	.77857	.78000	.00144	1.152	-.01000	-.00286	.00000	.00184	-.36697	7	0	0	1
							Oper. Life Hrs. = 250 (11-12-63)						
.77000	.78143	.79000	.00260	3.264	-.01000	.00286	.01000	.00286	.36563	7	0	0	0
							Oper. Life Hrs. = 500 (11-26-63)						
.78000	.78429	.79000	.00202	1.667	.00000	.00286	.01000	.00184	.36430	7	0	0	0
							Oper. Life Hrs. = 1000 (12-17-63)						
.77000	.77714	.78000	.00185	1.183	-.01000	-.00714	.00000	.00184	-.91912	7	0	0	0
							Oper. Life Hrs. = 2000 (1-30-64)						
.78000	.79000	.80000	.00217	1.365	.01000	.01286	.02000	.00184	1.6275	7	0	0	0
							Low Temperature (4-2-64)						
.78000	.78833	.79000	.00163	2.050	-.01000	-.00167	.00000	.00167	-.21142	6	0	0	1

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vbe(sat)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: .700 UPPER LIMIT: .935

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD. Initial (8-10-63)	P.C.	t	No.	NU	NL	NC
.77000	.78000	.79000	.00258							10	0	0	0
.76000	.77500	.78000	.00328	1.292	-.01000	-.00500	.00000	.00189	-2.646	8	0	0	2
.77000	.78000	.79000	.00309	1.290	.00000	.00571	.01000	.00202	2.828	7	0	0	1
.76000	.77143	.78000	.00340	1.217	-.02000	-.00857	.00000	.00261	-3.286	7	0	0	0
.76000	.79143	.84000	.00962	7.986	-.01000	.02000	.07000	.00976	2.049	7	0	0	0
.76000	.77571	.78000	.00298	10.433	-.06000	-.01571	.01000	.00922	-1.704	7	0	0	0
.77000	.77750	.78000	.00252	2.453	.00000	.00000	.00000	.00000		4	0	0	3
.76000	.77750	.79000	.00750	8.902	-.01000	.00000	.01000	.00577	.000	4	0	0	0
.77000	.77500	.78000	.00289	6.724	-.01000	-.00250	.01000	.00479	-.522	4	0	0	0
.76000	.77000	.78000	.00578	3.989	-.01000	-.00500	.00000	.00289	-1.732	4	0	0	0
.78000	.78750	.79000	.00249	5.376	.01000	.01750	.03000	.00479	3.656	4	0	0	0
.77000	.77250	.77500	.00248	2.014	-.02000	-.01750	-.01500	.00250	-7.000	2	0	0	2
.77000	.78000	.79000	.00998	16.147	-.00500	.00750	.02000	.01250	.600	2	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vbe(sat)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: .700 UPPER LIMIT: .935

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD. Vibration (10-15-63)	P.C.	t	No.	NU	NL	NC
.77000	.78158	.79000	.00175				- Shock (10-9-63)						
.77000	.77842	.79000	.00158	1.223	-.02000	-.00316	.01000	.00172	-1.837	19	0	0	1
.76000	.78631	.82000	.00414	6.830	-.01000	.00789	.05000	.00463	1.707	19	0	0	0
.76000	.77722	.79000	.00178	5.698	-.05000	-.00944	.01000	.00446	-2.116	18	0	0	1
.76000	.77214	.79000	.00281	1.940	-.02000	-.00643	.01000	.00269	-2.386	14	0	0	4
.77000	.77643	.79000	.00170	2.740	-.01000	.00429	.02000	.00202	2.121	14	0	0	0
.77000	.77571	.79000	.00173	1.032	-.02000	-.00071	.01000	.00195	-.366	14	0	0	0
.64000	.76417	.78000	.01138	37.214	-.13000	-.01167	.01000	.01093	-1.067	12	0	1	2
.77000	.78182	.79000	.00182	42.643	-.01000	.01818	.14000	.01234	1.473	11	0	0	1
.76000	.78500	.80000	.00500	5.487	-.02000	.00125	.02000	.00441	.284	8	0	0	3

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vbe(sat)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: .700 UPPER LIMIT: .935

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.77000	.78673	.81000	.00114								49	0	0	1
.77000	.78796	.80000	.00108	1.106	-.02000	.00122	.02000	.00122	.1540	1.000	49	0	0	0
.77000	.78816	.80000	.00146	1.813	-.03000	.00020	.01000	.00141	.02589	.144	49	0	0	0
.76000	.77000	.78000	.00089	2.819	-.03000	-.01894	.01000	.00133	-2.4593	-14.196	47	0	0	2
.77000	.78064	.79000	.00093	1.088	.00000	.01064	.02000	.00077	1.3628	13.821	47	0	0	0
.77000	.77935	.79000	.00105	1.258	-.01000	-.00130	.00000	.00050	-.16736	-2.598	46	0	0	1

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vce(sat)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: .275

Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.12000	.14300	.16000	.00396			8-21-63					10	0	0	0
.12000	.14300	.17000	.00423	1.142	-.01000	-.00000	.01000	.00149	-.00001	-.000	10	0	0	0
.11000	.13200	.16000	.00442	1.093	-.02000	-.01100	.00000	.00180	-8.3333	-6.128	10	0	0	0
.13000	.14800	.17000	.00389	1.294	.01000	.01600	.02000	.00163	10.811	9.798	10	0	0	0
.13000	.14300	.17000	.00367	1.124	-.01000	-.00500	.00000	.00167	-3.4965	-3.000	10	0	0	0
.12000	.14300	.17000	.00423	1.330	-.01000	-.00000	.01000	.00149	-.00000	-.000	10	0	0	0
.12000	.14200	.16000	.00359	1.388	-.01000	-.00100	.00000	.00100	-.70423	-1.000	10	0	0	0
.12000	.14222	.17000	.00465	1.509	.00000	.00111	.01000	.00111	.78125	1.000	9	0	0	1
.12000	.14000	.16000	.00423	1.361	-.01000	-.00125	.00000	.00125	-.89286	-1.000	8	0	0	1
.12000	.14000	.16000	.00423	1.000	.00000	.00000	.00000	.00000	.00000		8	0	0	0
.12000	.14000	.16000	.00488	1.167	.00000	.00000	.00000	.00000	.00000		7	0	0	1
.12000	.13333	.16000	.00615	1.360	-.01000	-.00667	.00000	.00211	-5.0000	-3.162	6	0	0	1
.12000	.13500	.16000	.00619	1.015	.00000	.00167	.01000	.00167	1.2346	1.000	6	0	0	0
.12000	.13667	.16000	.00667	1.159	.00000	.00167	.01000	.00167	1.2195	1.000	6	0	0	0
.11000	.13000	.16000	.00837	1.312	-.01000	-.00400	.00000	.00245	-3.0769	-1.633	5	0	0	1
.12000	.13600	.16000	.00748	1.250	.00000	.00600	.01000	.00245	4.4117	2.449	5	0	0	0
.12000	.13600	.16000	.00748	1.000	.00000	.00000	.00000	.00000	.00000		5	0	0	0
.13000	.14000	.16000	.00548	1.867	.00000	.00400	.01000	.00245	2.8571	1.633	5	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vce(sat) UPPER LIMIT: .275
 MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.12000	.60850	9.3300	.45904								20	1	0	0
.14000	.15375	.16000	.00324	50217.4	-.01000	-.00125	.00000	.00125	-.81301	-1.000	8	0	0	12
.14000	.15375	.16000	.00324	1.000	.00000	.00000	.00000	.00000	.00000		8	0	0	0
.14000	.15143	.16000	.00340	1.037	-.01000	-.00143	.00000	.00143	-.94340	-1.000	7	0	0	1
.13000	.14286	.15000	.00360	1.118	-.01000	-.00857	.00000	.00143	-6.0000	-6.000	7	0	0	0
.13000	.14571	.15000	.00297	1.461	.00000	.00286	.01000	.00184	1.9608	1.549	7	0	0	0
.13000	.14286	.15000	.00360	1.461	-.01000	-.00286	.00000	.00184	-2.0000	-1.549	7	0	0	0
.13000	.14714	.16000	.00359	1.000	.00000	.00429	.01000	.00202	2.9126	2.121	7	0	0	0
.13000	.14833	.16000	.00401	1.069	.00000	.00000	.00000	.00000	.00000		6	0	0	1

Post Temp. Storage (10-8-63)
 Oper. Life Hrs. = 100 (11-5-63)
 Oper. Life Hrs. = 250 (11-12-63)
 Oper. Life Hrs. = 500 (11-26-63)
 Oper. Life Hrs. = 1000 (12-17-63)
 Oper. Life Hrs. = 2000 (1-30-64)
 Low Temperature (4-2-64)

JPL TEST NUMBER: 7-0057 UNIT: Volts VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vce(sat) UPPER LIMIT: .275

MULTIPLIER: 1 MINOMIAL VALUE: None LOWER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	Meand. Initial (8-10-63)	MaxD. StdD.	P.C.	t	No.	NU	NL	NC
.12000	.17100	.45000	.03125				Post Temp. Storage (10-8-63)			10	1	0	0
.12000	.14125	.16000	.00581	36.218	.00000	.00250	.01000	.00164	1.7699	8	0	0	2
.12000	.13714	.16000	.00522	1.416	-.01000	-.00143	.00000	.00143	-1.0417	7	0	0	1
.12000	.13714	.16000	.00522	1.000	.00000	.00000	.00000	.00000		7	0	0	0
.13000	.17000	.22000	.01431	7.525	.00000	.03286	.10000	.01629	19.328	7	0	0	0
.13000	.14286	.18000	.00747	3.671	-.09000	-.02714	.01000	.01643	-19.000	7	0	0	0
.13000	.13750	.16000	.00750	1.735	-.01000	-.00250	.00000	.00250	-1.8182	4	0	0	3
.12000	.13000	.15000	.00707	1.125	-.01000	-.00750	.00000	.00250	-3.000	4	0	0	0
.13000	.13750	.16000	.00750	1.125	.00000	.00750	.01000	.00250	3.000	4	0	0	0
.11000	.12750	.15000	.00854	1.296	-.02000	-.01000	.00000	.00408	-2.449	4	0	0	0
.13000	.14000	.16000	.00707	1.458	.01000	.01250	.02000	.00250	5.000	4	0	0	0
.13000	.14500	.16000	.01500	2.250	.00000	.00000	.00000	.00000		2	0	0	2
.13000	.14500	.16000	.01500	1.000	.00000	.00000	.00000	.00000		2	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vce(sat)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: .275

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD.	P.C.	t	No.	NU	NL	NC
.13000	.14158	.16000	.00233				Shock (10-9-63)						
.13000	.14526	.17000	.00221	1.107	.00000	.00368	.01000	.00114	3.240	19	0	0	1
.13000	.15789	.23000	.00629	8.071	-.01000	.01263	.09000	.00634	1.991	19	0	0	0
.13000	.14778	.19000	.00358	3.263	-.09000	.01167	.05000	.00805	-1.449	18	0	0	1
.12000	.14143	.17000	.00345	1.378	-.02000	.00286	.01000	.00194	-1.472	14	0	0	4
.11000	.13429	.15000	.00327	1.118	-.02000	.00714	.00000	.00163	-4.372	14	0	0	0
.13000	.14000	.16000	.00332	1.029	.00000	.00571	.02000	.00173	3.309	14	0	0	0
.12000	.13636	.15000	.00310	1.459	-.01000	.00273	.00000	.00141	-1.936	11	0	0	3
.13000	.14100	.16000	.00314	1.066	.00000	.00400	.01000	.00163	2.449	10	0	0	1
.13000	.15000	.17000	.00617	2.696	-.01000	.00857	.03000	.00595	1.441	7	0	0	3

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vce(sat)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: .275

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.13000	.14592	.16000	.00133					Initial (8-10-63)			49	0	0	1
.12000	.14735	.17000	.00145	1.184	-.01000	.00143	.01000	.00071	.96953	2.000	49	0	0	0
.12000	.14020	.16000	.00192	1.756	-.02000	-.00714	.02000	.00127	-5.0946	-5.620	49	0	0	0
.13000	.15277	.17000	.00154	1.622	.00000	.01277	.03000	.00104	8.3565	12.270	47	0	0	2
.13000	.14638	.16000	.00137	1.258	-.01000	-.00638	.01000	.00077	-4.3605	-8.279	47	0	0	0
.12000	.14152	.16000	.00161	1.349	-.02000	-.00478	.01000	.00086	-3.3794	-5.531	46	0	0	1

Oper. Life Hrs. = 100 (8-27-63)
 Oper. Life Hrs. = 250 (9-5-63)
 Oper. Life Hrs. = 500 (9-26-63)
 Oper. Life Hrs. = 1000 (10-16-63)
 Oper. Life Hrs. = 2000 (12-3-63)

JPL TEST NUMBER: 7-0057

VENDOR: FAIRCHILD SEMICONDUCTOR

PART NUMBER: 2N 2369

PARAMETER: BVcbo

MULTIPLIER: 1

UNIT: Volts

NOMINAL VALUE: None

LOWER LIMIT: 38.0

UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
50.190	57.961	81.370	2.7502			8-10-63					10	0	0	0
49.200	56.880	80.200	2.7054	1.033	-4.1400	-1.0810	.40000	.37402	-1.9005	-2.890	10	0	0	0
50.000	57.620	81.100	2.7549	1.037	-1.8000	.74000	4.1000	.45023	1.2843	1.644	10	0	0	0
51.300	58.740	82.200	2.7668	1.009	.30000	1.1200	3.5000	.34667	1.9067	3.231	10	0	0	0
50.700	58.010	81.100	2.7198	1.035	-1.4000	-7.3000	-.20000	.10333	-1.2584	-7.065	10	0	0	0
51.100	58.340	81.100	2.6930	1.020	.00000	10-9-63	.60000	.06155	.56565	5.361	10	0	0	0
51.100	58.389	81.100	3.0109	1.125	-.50000	-1.1111	.00000	.05386	-.19029	-2.063	9	0	0	1
51.100	58.444	81.100	3.0100	1.001	.00000	10-15-63	.29999	.03768	.09505	1.474	9	0	0	0
51.100	58.675	81.000	3.3912	1.128	-.10000	10-16-63	.20000	.03504	.02130	.357	8	0	0	1
51.100	58.650	81.100	3.4083	1.010	-.20000	10-29-63	.10000	.03660	-.04263	-.683	8	0	0	0
51.200	58.557	81.200	3.9287	1.163	-.20000	11-5-63	.20000	.05216	.12198	1.369	7	0	0	1
51.100	54.750	60.300	1.3150	10.445	-.10000	11-12-63	.19999	.04944	-.06088	-.674	6	0	0	1
50.400	54.333	58.900	1.1987	1.200	-1.4000	11-26-63	.10000	.21972	-.76687	-1.896	6	0	0	0
51.000	54.633	60.100	1.2987	1.174	.00000	12-3-63	1.2000	.20494	.54911	1.464	6	0	0	0
51.100	53.600	55.500	.83571	2.898	-.10000	12-17-63	.10000	.04000	.11194	1.500	5	0	0	1
51.200	53.680	55.700	.85308	1.042	.00000	1-30-64	.19999	.03742	.14903	2.138	5	0	0	0
51.100	53.660	55.800	.87109	1.043	-.10000	2-10-64	.10000	.03742	-.03727	-.535	5	0	0	0
51.000	53.560	55.700	.87102	1.000	-.10000	4-2-64	-.10000	.00000	-.18671	.000	5	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR

PART NUMBER: 2N 2369

PARAMETER: BVcbo

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 38.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD.	P.C.	t	No.	NU	NL	NC
41.590	59.444	84.220	2.6832	1.002	-.74000	Post Temp. Storage (10-8-63) .28625	4.5000 .67522 .44902		.424	8	0	0	12
48.500	63.750	83.500	4.2386	1.152	.19999	Post Temp. Cycling (10-14-63) .38571	.60000 .05084 .59747		7.586	7	0	0	1
48.800	64.557	83.800	4.8633	1.259	.19999	Oper. Life Hrs. = 100 (11-5-63) 1.5857	9.2000 1.2693 2.3974		1.249	7	0	0	0
51.900	66.143	84.200	4.3346	1.009	-.60000	Oper. Life Hrs. = 250 (11-12-63) -.20000	-.10000 .06901 -.30329		-2.898	7	0	0	0
51.800	65.943	84.100	4.3550	1.009	-.3.5000	Oper. Life Hrs. = 500 (11-26-63) -.92857	.40000 .63008 -1.4283		-1.474	7	0	0	0
51.700	65.014	83.900	4.3745	1.004	-.40000	Oper. Life Hrs. = 1000 (12-17-63) .87143	3.5000 .63423 1.3226		1.374	7	0	0	0
51.800	65.886	84.000	4.3653	1.011	.00000	Oper. Life Hrs. = 2000 (1-30-64) .20000	.90000 .11952 .30263		1.673	7	0	0	0
56.300	68.317	83.900	4.2624	1.210	-.30000	Low Temperature (4-2-64) -.15000	.00000 .04282 -.21956		-3.503	6	0	0	1

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: BVcbo

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 38.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
41.700	56.001	69.030	3.2785								10	0	0	0
37.400	53.275	67.700	3.9826	1.181	-4.3000	-0.26250	3.1000	.71912	-.49273	-.365	8	0	1	2
38.000	54.571	68.300	4.4886	1.111	.20000	.45714	.60000	.05281	.83769	8.656	7	0	0	1
40.100	54.800	68.200	4.3087	1.085	-.10000	.22857	2.1000	.31222	.41710	.732	7	0	0	0
37.500	54.500	68.300	4.5344	1.107	-2.6000	-.30000	.10000	.38359	-.55046	-.782	7	0	1	0
40.400	50.580	66.300	4.5956	1.363	-.20000	.66000	2.9000	.58873	1.3049	1.121	5	0	0	2
37.400	48.825	66.500	6.2128	1.462	-3.0000	-.62500	.20000	.79202	-1.2801	-.789	4	0	1	1
37.100	48.675	66.400	6.2436	1.010	-.30000	-.15000	-.10000	.05000	-.30817	-3.000	4	0	1	0
37.900	47.650	61.900	5.0724	1.515	-4.5000	-1.0250	.80000	1.1828	-2.1511	-.867	4	0	1	0
39.800	49.325	66.400	5.8551	1.332	.10000	1.6750	4.5000	1.0282	3.3958	1.629	4	0	0	0
38.100	48.975	66.500	6.1109	1.089	-1.7000	-.35000	.10000	.45000	-.71465	-.778	4	0	0	0
36.900	40.950	45.000	4.0500	4.553	-1.2000	-.65000	-.10000	.55000	-1.5873	-1.182	2	0	1	2
36.700	40.850	45.000	4.1500	1.050	-.20000	-.10000	.00000	.10000	-.24480	-1.000	2	0	1	0

JPL TEST NUMBER: 7-0057

VENDOR: FAIRCHILD SEMICONDUCTOR

PART NUMBER: 2N 2369

PARAMETER: BVCbo

MULTIPLIER: 1 UNIT: Volts

LOWER LIMIT: 30.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
38.140	53.969	80.260	2.4434					Initial (8-10-63)			19	0	0	1
								Shock (10-9-63)						
38.000	54.189	80.000	2.4915	1.040	-1.1000	.22000	3.2000	.22323	.40598	.986	19	0	0	0
								Vibration (10-15-63)						
38.100	53.921	80.200	2.5788	1.071	-2.6000	-.26842	.30000	.18888	-.49781	-1.421	19	0	0	0
								Humidity (10-29-63)						
38.100	56.093	80.000	3.1894	1.127	-.20000	.41429	3.3000	.26120	.73857	1.586	14	0	0	5
								Oper. Life Hrs. = 100 (11-5-63)						
38.200	56.064	80.200	3.1053	1.055	-3.9000	-.02857	1.7000	.31890	-.05097	-.090	14	0	0	0
								Oper. Life Hrs. = 250 (11-12-63)						
38.100	55.393	80.100	3.2623	1.104	-5.8000	-.67143	-.10000	.40280	-1.2121	-1.667	14	0	0	0
								Oper. Life Hrs. = 500 (11-26-63)						
38.000	55.457	79.900	3.0430	1.149	-2.7000	.06428	7.4000	.59583	.11592	.108	14	0	0	0
								Oper. Life Hrs. = 1000 (12-17-63)						
38.100	55.883	80.100	3.5571	1.171	-.90000	.50833	2.6000	.24816	.90963	2.048	12	0	0	2
								Oper. Life Hrs. = 2000 (1-30-64)						
38.100	56.964	80.200	3.7907	1.041	-1.1000	.09091	1.5000	.17810	.15959	.510	11	0	0	1
								Acceleration (2-10-64)						
38.100	60.787	80.000	4.7079	1.122	-.20000	.57500	4.7000	.59032	.94592	.974	8	0	0	3

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: BVcbo

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 38.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
34.320	53.628	70.620	1.0587								49	0	1	1
								Oper. Life Hrs. = 100 (8-27-63)						
34.200	53.249	70.700	1.0257	1.065	-9.6600	-.37898	1.6800	.21186	-.71171	-1.789	49	0	1	0
								Oper. Life Hrs. = 250 (9-5-63)						
34.000	53.466	69.700	1.1012	1.106	-2.1000	.33829	5.5000	.18517	.63273	1.827	47	0	1	2
								Oper. Life Hrs. = 500 (9-26-63)						
34.700	54.486	75.900	1.1436	1.078	-3.1000	1.0204	12.400	.32408	1.8728	3.149	47	0	1	0
								Oper. Life Hrs. = 1000 (10-16-63)						
34.200	53.898	75.700	1.1454	1.003	-13.200	-.58851	.19999	.28164	-1.0919	-2.090	47	0	1	0
								Oper. Life Hrs. = 2000 (12-3-63)						
39.600	54.284	75.500	1.0969	1.139	-.80000	-.09111	1.1000	.04043	-.16784	-2.254	45	0	0	2

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Bvebo

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 4.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
5.0000	5.9160	6.1800	.11019			8-10-63					10	0	0	0
4.9900	5.9270	6.1800	.11237	1.040	-.01000	8-27-63	.06000	.00623	.18559	1.766	10	0	0	0
4.9800	5.9280	6.1800	.11422	1.033	-.01000	9-9-63	.02000	.00314	.01687	.318	10	0	0	0
5.5700	6.0270	6.2000	.06086	3.522	.01000	9-26-63	.59000	.05638	1.6426	1.756	10	0	0	0
4.9900	5.8080	6.1600	.14109	5.375	-1.0400	10-8-63	-.03000	.10530	-3.7707	-2.080	10	0	0	0
5.0000	5.9380	6.1900	.11285	1.563	.01000	10-9-63	.13000	.10006	2.1893	1.299	10	0	0	0
4.9800	5.9350	6.1900	.11508	1.040	-.02000	10-14-63	.01000	.00300	-.05055	-1.000	10	0	0	0
5.0200	5.9378	6.1900	.12451	1.054	.00000	10-15-63	.04000	.00444	.09356	1.250	9	0	0	1
5.0300	5.9587	6.1900	.13746	1.083	-.01000	10-16-63	.01000	.00227	-.02098	-.552	8	0	0	1
5.0200	5.9575	6.1900	.13866	1.018	-.01000	10-29-63	.00000	.00125	-.02098	-1.000	8	0	0	0
5.0100	5.9633	6.1900	.19180	1.435	-.01000	11-5-63	.01000	.00333	.05590	1.000	6	0	0	2
5.0400	5.9683	6.1900	.18683	1.054	.00000	11-12-63	.03000	.00500	.08378	1.000	6	0	0	0
5.0100	5.9583	6.1900	.19094	1.044	-.03000	11-26-63	.00000	.00447	-.16784	-2.236	6	0	0	0
5.0000	5.9567	6.1900	.19260	1.018	-.01000	12-2-63	.00000	.00167	-.02798	-1.000	6	0	0	0
5.0000	5.9200	6.2000	.23144	1.203	.00000	12-17-63	.02000	.00316	.16892	3.162	5	0	0	1
5.0100	5.9160	6.1900	.22777	1.032	-.01000	1-30-64	.01000	.00400	-.06762	-1.000	5	0	0	0
5.0100	5.9200	6.2000	.22915	1.012	-.01000	2-10-64	.01000	.00400	.06757	1.000	5	0	0	0
5.0400	5.9220	6.1900	.22181	1.067	-.01000	4-2-64	.03000	.00800	.03377	.250	5	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Bvebo

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 4.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
4.6900	5.9445	6.3500	.07713								20	0	0	0
5.6300	5.9787	6.3400	.07642	2.547	-.08000	-.02875	.00000	.00854	-.48087	-3.365	8	0	0	12
5.6500	6.0062	6.3600	.07653	1.003	.02000	.02750	.04000	.00250	.45785	11.000	8	0	0	0
5.5800	6.0057	6.3700	.09693	1.404	-.07000	.00143	.02000	.01204	.02378	.119	7	0	0	1
5.7300	6.0229	6.3600	.08070	1.443	-.02000	.01714	.15000	.02265	.28463	.757	7	0	0	0
5.7000	6.0014	6.3500	.07880	1.049	-.11000	-.02143	.04000	.01724	-.35706	-1.243	7	0	0	0
5.6600	6.0114	6.3600	.08779	1.241	-.04000	.01000	.11000	.01799	.16635	.556	7	0	0	0
5.6900	6.0186	6.3500	.08429	1.085	-.01000	.00714	.04000	.00778	.11868	.918	7	0	0	0
5.7100	6.0283	6.3600	.09931	1.190	.00000	.00833	.02000	.00307	.13823	2.712	6	0	0	1

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Bvebo

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 4.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD. (10-9-63)	P.C.	t	No.	NU	NL	NC
5.6800	5.9100	6.0900	.04708				Post Temp. Storage (10-8-63)						
5.5700	5.8287	5.9900	.05460	1.076	-.15000	-.03750	.00000	.01709	-.64336	8	0	0	2
5.6100	5.8586	6.0300	.06058	1.077	.02000	.03571	.06000	.00528	.60960	7	0	0	1
5.6400	5.8443	6.0300	.05788	1.095	-.08000	-.01429	.03000	.01343	-.24444	7	0	0	0
5.6400	5.8543	6.0300	.05645	1.052	.00000	.01000	.04000	.00655	.17081	7	0	0	0
5.6400	5.9000	6.0300	.06839	1.048	-.01000	-.00200	.00000	.00200	-.03390	5	0	0	2
5.6400	5.9200	6.0200	.09346	1.494	-.01000	.02750	.11000	.02780	.46453	4	0	0	1
5.6200	5.9100	6.0200	.09675	1.072	-.02000	-.01000	.00000	.00577	-.16921	4	0	0	0
5.6600	5.9250	6.0400	.08894	1.183	-.01000	.01500	.04000	.01041	.25316	4	0	0	0
5.6000	5.9100	6.0300	.10370	1.359	-.06000	-.01500	.02000	.01708	-.25381	4	0	0	0
5.6200	5.9050	6.0300	.09559	1.177	-.05000	-.00500	.02000	.01555	-.08468	4	0	0	0
6.0000	6.0200	6.0400	.01990	46.172	.01000	.01000	.01000	.00000	.16611	2	0	0	2
6.0000	6.0150	6.0300	.01518	1.717	-.01000	-.00500	.00000	.00500	-.08312	2	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: BVEBO

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 4.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
4.5000	5.7837	6.1700	.09629					Initial (8-10-63)			19	0	0	1
4.5600	5.7847	6.1800	.09363	1.058	-.04000	.00105	.06000	.00464	.01819	.227	19	0	0	0
3.8100	5.7016	6.1900	.13939	2.216	-1.7800	-.08316	.04000	.09430	-1.4585	-.882	19	0	1	0
4.3600	5.7800	6.1600	.13501	1.447	-.24000	-.02500	.00000	.01676	-.43253	-1.491	14	0	0	5
5.1000	5.8514	6.1900	.10057	1.802	-.01000	.07143	.74000	.05222	1.2207	1.368	14	0	0	0
5.1600	5.8308	6.1600	.10221	1.043	-.08000	-.00923	.09000	.01034	-.15831	-.892	13	0	0	1
5.1500	5.8900	6.1900	.09074	1.269	-.01000	.05923	.53000	.04055	1.0056	1.461	13	0	0	0
5.1700	5.8636	6.1600	.10104	1.049	-.46000	-.05727	.02000	.04193	-.97675	-1.366	11	0	0	2
5.1700	5.8810	6.1900	.10132	1.094	-.01000	.02800	.20000	.01999	.47611	1.401	10	0	0	1
5.1700	5.9014	6.1400	.12527	1.070	.00000	.01429	.05000	.00612	.24207	2.336	7	0	0	3

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: BVEBO

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 4.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
4.8400	5.9251	6.2900	.03852								49	0	0	1
5.2100	5.9561	6.2900	.03194	1.454	-.14000	.03102	.37000	.01314	.52081	2.361	49	0	0	0
5.2100	5.9534	6.3000	.03164	1.019	-.71000	-.00265	.21000	.01606	-.04456	-.165	49	0	0	0
5.0300	5.8972	6.3100	.04886	2.287	-.99000	-.06532	.35000	.04594	-1.1076	-1.422	47	0	0	2
5.1800	5.9723	6.2800	.02931	2.779	-.25000	.07511	1.0000	.04682	1.2576	1.604	47	0	0	0
5.1000	5.9217	6.2700	.03716	1.573	-1.0100	-.04891	.08000	.02395	-.82599	-2.042	46	0	0	1

Oper. Life Hrs. = 100 (8-27-63)
 Oper. Life Hrs. = 250 (9-5-63)
 Oper. Life Hrs. = 500 (9-26-63)
 Oper. Life Hrs. = 1000 (10-16-63)
 Oper. Life Hrs. = 2000 (12-3-63)

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Icbo
 MULTIPLIER: 1 UNIT: Micro-amperes NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: .4

Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.01000	.04300	.20000	.01764			8-10-63					10	0	0	0
.00300	.04150	.21300	.02164	1.504	-.03500	8-27-63 -.00150	.09000	.01162	-3.6145	-.129	10	0	0	0
.00100	.03310	.23800	.02296	1.126	-.10100	9-5-63 -.00840	.02500	.01061	-25.378	-.792	10	0	0	0
.00400	.04730	.32000	.03065	1.782	.00300	9-26-63 .01420	.08200	.00772	30.021	1.840	10	0	0	0
.00300	.03670	.25000	.02390	1.645	-.07000	10-8-63 -.01060	.00000	.00679	-28.883	-1.561	10	0	0	0
.00400	.04140	.28100	.02687	1.264	.00000	10-9-63 .00470	.03100	.00299	11.353	1.574	10	0	0	0
.00600	.03390	.23000	.02195	1.499	-.05100	10-14-63 -.00750	.00400	.00497	-22.124	-1.508	10	0	0	0
.00300	.03689	.24000	.02557	1.222	-.00500	10-15-63 -.0089	.01000	.00130	2.4096	.686	9	0	0	1
.00300	.03562	.23000	.02779	1.050	-.01000	10-16-63 -.00162	.00000	.00121	-4.5614	-1.344	8	0	0	1
.00300	.03375	.21800	.02634	1.113	-.01200	10-29-63 -.00188	.00000	.00146	-5.5556	-1.287	8	0	0	0
.00300	.04443	.26000	.03595	1.629	.00000	11-5-63 .00700	.04200	.00585	15.756	1.197	7	0	0	1
.00300	.00750	.01200	.00152	650.765	-.00300	11-12-63 -.00108	.00000	.00052	-13.333	-1.936	6	0	0	1
.00110	.00585	.01300	.00167	1.207	-.01090	11-26-63 -.00165	.00100	.00186	-28.205	-.888	6	0	0	0
.00300	.00717	.01100	.00119	1.958	-.00300	12-3-63 .00132	.00990	.00180	18.372	.730	6	0	0	0
.00300	.00820	.01500	.00193	2.183	.00000	12-17-63 .00180	.00500	.00086	21.951	2.092	5	0	0	1
.00300	.00760	.01400	.00181	1.147	-.00100	1-30-64 -.00060	.00000	.00024	-7.8947	-2.449	5	0	0	0
.00300	.00760	.01400	.00181	1.000	.00000	2-10-64 .00000	.00000	.00000	.00000		5	0	0	0
.00300	.00680	.01300	.00169	1.148	-.00100	4-2-64 -.00080	.00000	.00020	-11.765	-4.000	5	0	0	0

JPL TEST NUMBER: 7-0057				VENDOR: FAIRCHILD SEMICONDUCTOR				PART NUMBER: 2N 2369				PARAMETER: Icbo				
MULTIPLIER: 1				UNIT: Micro-amperes				NOMINAL VALUE: None				UPPER LIMIT: .4				
Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL			
.00090	.01403	.09000	.00445			Initial (8-10-63)								20	0	0
						Post Temp. Storage (10-8-63)										
.00300	.02887	.11000	.01198	2.900	.00200	.00676	.02000	.00221	23.420	3.065	8	0	0			
						Post Temp. Cycling (10-14-63)										
.00400	.02600	.10800	.01202	1.006	-.00800	-.00288	.00100	.00101	-11.058	-2.853	8	0	0			
						Oper. Life Hrs. = 100 (11-5-63)										
.00700	.03014	.09600	.01245	1.064	-.05600	.00229	.07600	.01479	7.5829	.155	7	0	0			
						Oper. Life Hrs. = 250 (11-12-63)										
.00600	.03143	.12200	.01586	1.621	-.00900	.00129	.02600	.00426	4.0909	.302	7	0	0			
						Oper. Life Hrs. = 500 (11-26-63)										
.00700	.03257	.12900	.01677	1.119	-.00100	.00114	.00700	.00101	3.5088	1.131	7	0	0			
						Oper. Life Hrs. = 1000 (12-17-63)										
.00900	.03986	.15800	.02064	1.514	.00000	.00729	.02900	.00389	18.280	1.873	7	0	0			
						Oper. Life Hrs. = 2000 (1-30-64)										
.00900	.04214	.16000	.02110	1.045	.00000	.00229	.01200	.00166	5.4237	1.379	7	0	0			
						Low Temperature (4-2-64)										
.00800	.04467	.15000	.02263	1.015	-.01000	-.00267	.00100	.00161	-5.9702	-1.661	6	0	0			

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Icbo

MULTIPLIER: 1 UNIT: Micro-amperes NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: .4

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-10-63)	MaxD. StdD. (10-8-63)	P.C.	t	No.	NU	NL	NC
.00090	.01109	.03000	.00329				Post Temp. Storage (10-8-63)						
.00600	.01575	.03700	.00362	1.036	-.00900	.00326	.01160	.00208	20.714	8	0	0	2
.00600	.01300	.02400	.00258	2.245	-.00100	.00029	.00300	.00052	2.1978	7	0	0	1
.00500	.01814	.06200	.00758	8.625	-.00200	.00514	.03800	.00550	28.346	7	0	0	0
.00500	.01257	.02300	.00255	8.823	-.04200	-.00557	.00200	.00608	44.318	7	0	0	0
.00700	.01940	.04200	.00623	4.259	.00000	.00740	.02200	.00438	38.144	5	0	0	2
.00900	.02325	.04600	.00831	1.422	.00200	.00950	.02300	.00497	40.860	4	0	0	1
.00900	.02300	.04700	.00876	1.110	-.00200	-.00025	.00100	.00063	-1.0870	4	0	0	0
.00900	.02550	.05200	.00987	1.271	.00000	.00250	.00500	.00119	9.8039	4	0	0	0
.01000	.03375	.07300	.01421	2.074	.00100	.00825	.02100	.00442	24.444	4	0	0	0
.01200	.03600	.07800	.01472	1.072	-.00200	.00225	.00500	.00155	6.2500	4	0	0	0
.03200	.05100	.07000	.01900	1.200	-.00800	-.00500	-.00200	.00300	-9.8039	2	0	0	2
.03100	.05150	.07200	.02050	1.164	-.00100	.00050	.00200	.00150	.97087	2	0	0	0

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Icbo

MULTIPLIER: 1 UNIT: Micro-amperes NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: .4

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.00300	.03226	.16000	.01057								19	0	0	1
.00700	.03974	.17400	.01139	1.162	-.00400	.00747	.02100	.00131-18.808		5.706	19	0	0	0
.00700	.03847	.16000	.01062	1.151	-.01400	-.00126	.01800	.00141-3.2832		-.899	19	0	0	0
.00800	.03336	.15200	.01051	1.385	-.14600	-.00421	.04200	.01157-12.634		-.364	14	0	0	5
.01800	.10471	.50000	.03478	10.947	-.01900	.07136	.34800	.02742 68.145		-2.602	14	1	0	0
.02000	.11443	.68000	.04611	1.757	-.05300	.00971	.18000	.01422 8.4894		.683	14	1	0	0
.01800	.12757	.78000	.05262	1.302	-.01800	.01314	.10000	.00840 10.302		1.564	14	1	0	0
.02300	.14942	.79900	.06307	1.232	-.00300	.01583	.06500	.00627 10.597		-2.526	12	1	0	2
.01100	.14773	.85000	.07461	1.283	-.11000	-.01091	.05100	.01227 -7.3846		-.889	11	1	0	1
.00600	.07900	.22800	.03217	7.397	-.03200	-.00812	.00100	.00381-10.285		-2.130	8	0	0	3

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Icbo

MULTIPLIER: 1 UNIT: Micro-amperes NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: .4

Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.00090	.03551	.39000	.01005								49	0	0	1
				1.953	-.05500	.02145	.26000	.00698	37.664	3.076	49	1	0	0
.00000	.05696	.65000	.01404											
				2.433	-.00800	.02732	.38000	.00815	31.893	3.353	47	1	0	2
.00600	.08566	1.0300	.02236											
				1.215	.00300	.03832	.11600	.00433	30.908	8.847	47	1	0	0
.01300	.12398	1.1000	.02465											
				1.037	-.25500	-.01332	.39500	.01230	-12.036	-1.083	47	2	0	0
.00800	.11066	.96000	.02421											
				6.431	-.76800	-.04313	.20700	.02166	-63.610	-1.991	46	0	0	1
.00300	.06780	.23200	.00965											

Oper. Life Hrs. = 100 (8-27-63)
 Oper. Life Hrs. = 250 (9-5-63)
 Oper. Life Hrs. = 500 (9-26-63)
 Oper. Life Hrs. = 1000 (10-16-63)
 Oper. Life Hrs. = 2000 (12-3-63)

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Cob

MULTIPLIER: 1 UNIT: Pico-farads NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 4.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
2.3000	2.4200	2.6000	.03888								10	0	0	0
2.3000	3.0833	5.9000	.56593	127.139	.00000	.63333	3.6000	.59367	20.541	1.067	6	1	0	4

Initial (8-12-63)

Final (1-30-64)

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Cob

MULTIPLIER: 1 UNIT: Pico-farads NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 4.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
2.2000	2.3850	2.6000	.03102				Initial (8-8-63)				20	0	0	0
2.2000	2.4000	2.7000	.06172	1.386	.00000	.04286	.10000	.02020	1.7857	2.121	7	0	0	13

Final (1-30-64)

Group No. 3

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Cob

MULTIPLIER: 1 UNIT: Pico-farads NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 4.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
2.2000	2.4300	2.6000	.03959			Initial (8-8-63)					10	0	0	0
2.3000	2.4750	2.6000	.06292	1.010	-.10000	-.02500	.00000	.02500	-1.0101	-1.000	4	0	0	6

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Cob

MULTIPLIER: 1 UNIT: Pico-farads NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 4.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
2.2000	2.4158	2.5000	.01914			Initial (8-8-63)					19	0	0	1
2.2000	2.6462	4.5000	.17083	54.508	.00000	Final (1-30-64)	.23846	2.1000	.16662	9.0116	13	1	0	6

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Cob

MULTIPLIER: 1 UNIT: Pico-farads NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 4.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
2.2000	2.4714	2.8000	.01913			Initial (8-8-63)					49	0	0	1
2.2000	2.5042	3.7000	.03247	2.764	-.40000	Final (1-30-64)					47	0	0	2
						.03404	1.0000	.02457	1.3594	1.385				

Group No. 1

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vceo(sust)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 14.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
15.700	20.740	33.300	1.7259			Initial (8-8-63)					10	0	0	0
18.900	21.160	27.900	1.7087	2.041	2.9000	3.0800	3.2000	.05832	14.556	52.816	5	0	0	5

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vceo(sust)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 14.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
15.500	21.165	31.200	1.1481								20	0	0	0
18.600	25.314	33.600	2.3903	1.517	2.3000	2.7429	3.2000	.13427	10.835	20.428	7	0	0	13

Final (1-30-64)

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vceo(sust)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 14.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
15.500	18.090	23.000	.83887			Initial (8-8-63)					10	0	0	0
18.800	20.825	25.500	1.5676	1.397	3.0000	3.1500	3.3000	.06453	15.126	48.813	4	0	0	6

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vceo(sust)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 14.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	P.C.	t	No.	NU	NL	NC
						Initial (8-8-63)							
16.200	19.805	31.800	.89167			Final (1-30-64)				19	0	0	1
12.500	22.415	34.600	1.5238	1.998	4.7000	2.1154	4.5000	.67765	9.4372	13	0	1	6

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Vceo(sust)

MULTIPLIER: 1 UNIT: Volts NOMINAL VALUE: None LOWER LIMIT: 14.0 UPPER LIMIT: None

Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
14.700	18.341	26.700	.35793								49	0	0	1
17.800	21.587	29.600	.36773	1.009	1.8000	3.2065	4.9000	.06553	14.854	48.928	46	0	0	3

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: T

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 13.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.70000	.96000	1.0000	.03055			Initial (8-12-63)					10	0	0	0
.90000	.98000	1.0000	.02000	4.667	.00000	Final (2-5-64)	.04000	.20000	.04000	4.0816	5	0	0	5

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: T

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 13.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.90000	.98500	1.1000	.01313			Initial (8-12-63)					20	0	0	0
1.0000	1.0143	1.1000	.01429	2.414	-.10000	Final (2-5-64)	.01429	.10000	.02608	.548	7	0	0	13

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: T

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 13.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.90000	.99000	1.1000	.01795			Initial (8-12-63)					10	0	0	0
1.0000	1.0250	1.1000	.02500	1.289	.00000	Final (2-5-64)	.10000	.02887	4.8780	1.732	4	0	0	6

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: T

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 13.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.90000	1.0105	1.1000	.01509			Initial (8-12-63)					19	0	0	1
.90000	.98889	1.0000	.01111	3.895	-.10000	-.00000	.10000	.02357	-.00000	-.000	9	0	0	10

Final (2-5-64)

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: T

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 13.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
.90000	.99592	1.1000	.00770			Initial	(8-12-63)				49	0	0	1
.90000	.99348	1.1000	.00787	1.019	-.20000	-.00217	.10000	.01098	-.21882	-.198	46	0	0	3

Final (2-5-64)

JPL TEST NUMBER: 7-0057

VENDOR: FAIRCHILD SEMICONDUCTOR

PART NUMBER: 2N 2369

PARAMETER: Ton

MULTIPLIER: 1

UNIT: Nano-seconds

NOMINAL VALUE: None

LOWER LIMIT: None

UPPER LIMIT: 12.0

	Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
--	------	------	------	------	---	-------	--------	-------	-------	------	---	-----	----	----	----

4.9000	5.2300	5.7000	.07310
--------	--------	--------	--------

Initial (8-12-63)

Final (2-5-64)

10 0 0 0

[illegible]

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Ton

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 12.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
4.7000	5.2050	5.7000	.06004			Initial (8-12-63)					20	0	0	0
6.7000	7.0857	7.5000	.11430	1.269	1.8000	1.9857	2.1000	.04040	28.024	49.146	7	0	0	13

Final (2-5-64)

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Ton

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 12.0

Min.	Mean	Max.	Std.	F	MinD.	Meand.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
5.0000	5.1400	5.5000	.04762			Initial (8-12-63)					10	0	0	0
5.9000	6.9000	7.4000	.33912	20.289	.90000	Final (1-30-64)	1.7500	2.1000	.28723	25.362	4	0	0	6

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Ton

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 12.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
4.7000	5.1895	5.8000	.05967			Initial (8-12-63)					19	0	0	1
7.0000	7.2400	7.7000	.05999	1.880	1.8000	2.0200	2.4000	.05538	27.901	36.476	10	0	0	9

Final (2-5-64)

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Ton
 MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 12.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD. Initial (8-12-63)	MaxD. StdD.	P.C.	t	No.	NU	NL	NC
4.6000	5.0877	5.6000	.04275							49	0	0	1
7.0000	7.3298	7.7000	.03163	1.904	1.7000	2.2340	2.5000	.02321	30.479	96.239	0	0	2

Final (1-30-64)

Group No. 1

JPL TEST NUMBER: 7-0057

VENDOR: FAIRCHILD SEMICONDUCTOR

PART NUMBER: 2N 2369

PARAMETER: Toff

MULTIPLIER: 1

UNIT: Nano-seconds

NOMINAL VALUE: None

LOWER LIMIT: None

UPPER LIMIT: 18.0

Min. Mean

Max. Std.

五

MIND.

Meand.

nd. MaxD. StdD.
Initial (8-12-63)

†

No.

NTU

IN

INC

5.1000 6.2900 9.4000 .37960

Final (2-5-64)

1

8.7000	9.9833	10.800	.34777
--------	--------	--------	--------

1.986

57 4.5000 .28829

13.759

9

0

0

✱

PARAMETER: Toff

PART NUMBER: 2N 2369

VENDOR: FAIRCHILD SEMICONDUCTOR

JPL TEST NUMBER: 7-0057

UPPER LIMIT: 18.0

LOWER LIMIT: None

NOMINAL VALUE: None

MULTIPLIER: 1 UNIT: Nano-seconds

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
4.8000	6.3000	8.4000	.22361			Initial (8-12-63)					20	0	0	0
9.8000	11.314	12.900	.41658	1.215	4.3000	4.8429	5.6000	.16310	42.803	29.692	7	0	0	13

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Toff

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 18.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
4.6000	6.1100	8.0000	.39199			Initial (8-12-63)					10	0	0	0
8.0000	9.5500	11.800	.81803	1.742	3.4000	Final (2-5-64)	4.6000	.25290	42.147	15.915	4	0	0	6
							4.0250							

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Toff

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 18.0

Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxD.	StdD.	P.C.	t	No.	NU	NL	NC
4.6000	5.7632	8.1000	.24783								19	0	0	1
7.7000	10.433	14.200	.52949	2.883	3.1000	4.5250	6.1000	.24219	43.371	18.684	12	0	0	7

Final (2-5-64)

JPL TEST NUMBER: 7-0057 VENDOR: FAIRCHILD SEMICONDUCTOR PART NUMBER: 2N 2369 PARAMETER: Toff

MULTIPLIER: 1 UNIT: Nano-seconds NOMINAL VALUE: None LOWER LIMIT: None UPPER LIMIT: 18.0


Min.	Mean	Max.	Std.	F	MinD.	MeanD.	MaxB.	StdD.	P.C.	t	No.	NU	NL	NC
4.4000	5.4143	7.6000	.12171			Initial (8-12-63)					49	0	0	1
7.5000	10.228	13.900	.23382	3.540	1.9000	4.8106	6.4000	.12830	47.036	37.495	47	0	0	2

Final (2-5-64)

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- Hfe 1 -- None



7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369


FINAL HISTOGRAM -- Hfe 1 -- None

t	x	n
-4.75	-.1751451 e 02	0
-4.25	-.7778454 e 01	0
-3.75	.1957592 e 01	0
-3.25	.1169364 e 02	0
-2.75	.2142970 e 02	0
-2.25	.3116575 e 02	2
-1.75	.4090180 e 02	0
-1.25	.5063785 e 02	4
-.75	.6037390 e 02	22
-.25	.7010995 e 02	11
.25	.7984599 e 02	14
.75	.8958204 e 02	9
1.25	.9931809 e 02	3
1.75	.1090541 e 03	4
2.25	.1187901 e 03	4
2.75	.1285262 e 03	0
3.25	.1382623 e 03	0
3.75	.1479983 e 03	0
4.25	.1577343 e 03	0
4.75	.1674704 e 03	0
5.25	.1772064 e 03	0
mean	.7497796 e 02	
standard deviation	.1947210 e 02	
failures	37	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- life 2 -- None



7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Hfe 2 -- None

t	x	n
-4.75	-.9790922 e 01	0
-4.25	-.2872383 e 01	0
-3.75	.4046152 e 01	0
-3.25	.1096469 e 02	0
-2.75	.1788323 e 02	0
-2.25	.2480177 e 02	0
-1.75	.3172031 e 02	2
-1.25	.3863884 e 02	9
-.75	.4555738 e 02	14
-.25	.5247592 e 02	19
.25	.5939446 e 02	12
.75	.6631300 e 02	6
1.25	.7323153 e 02	2
1.75	.8015007 e 02	8
2.25	.8706859 e 02	0
2.75	.9398713 e 02	0
3.25	.1009057 e 03	1
3.75	.1078242 e 03	0
4.25	.1147427 e 03	0
4.75	.1216612 e 03	0
5.25	.1285798 e 03	0
mean	.5593519 e 02	
standard deviation	.1383708 e 02	
failures	37	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- Vbe(sat) -- Volts

t	x	n
-4.75	.5598512 e 00	1
-4.25	.5830344 e 00	0
-3.75	.6062175 e 00	0
-3.25	.6294007 e 00	0
-2.75	.6525839 e 00	0
-2.25	.6757671 e 00	0
-1.75	.6989502 e 00	0
-1.25	.7221334 e 00	0
-.75	.7453166 e 00	0
-.25	.7684997 e 00	57
.25	.7916829 e 00	49
.75	.8148661 e 00	1
1.25	.8380493 e 00	0
1.75	.8612324 e 00	0
2.25	.8844155 e 00	0
2.75	.9075987 e 00	0
3.25	.9307819 e 00	0
3.75	.9539650 e 00	0
4.25	.9771481 e 00	0
4.75	.1000331 e 01	0
5.25	.1023514 e 01	0

mean .7800913 e 00
standard deviation .4636634 e-01
failures 2

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Vbe(sat) -- Volts

t	x	n
-4.75	.7453586 e 00	0
-4.25	.7491779 e 00	0
-3.75	.7529972 e 00	0
-3.25	.7568166 e 00	0
-2.75	.7606359 e 00	0
-2.25	.7644553 e 00	0
-1.75	.7682746 e 00	14
-1.25	.7720940 e 00	0
-.75	.7759133 e 00	0
-.25	.7797326 e 00	35
.25	.7835519 e 00	0
.75	.7873713 e 00	0
1.25	.7911906 e 00	22
1.75	.7950100 e 00	0
2.25	.7988293 e 00	2
2.75	.8026487 e 00	0
3.25	.8064679 e 00	0
3.75	.8102873 e 00	0
4.25	.8141066 e 00	0
4.75	.8179260 e 00	0
5.25	.8217453 e 00	0
mean	.7816423 e 00	
standard deviation	.7638679 e-02	
failures	37	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- Vce(sat) -- Volts

t	x	n
-4.75	-.3966641 e 01	0
-4.25	-.3524588 e 01	0
-3.75	-.3082534 e 01	0
-3.25	-.2640480 e 01	0
-2.75	-.2198427 e 01	0
-2.25	-.1756373 e 01	0
-1.75	-.1314319 e 01	0
-1.25	-.8722659 e 00	0
-.75	-.4302124 e 00	0
-.25	.1184109 e-01	106
.25	.4538947 e 00	1
.75	.8959482 e 00	0
1.25	.1338001 e 01	0
1.75	.1780055 e 01	0
2.25	.2222108 e 01	0
2.75	.2664161 e 01	0
3.25	.3106214 e 01	0
3.75	.3548267 e 01	0
4.25	.3990320 e 01	0
4.75	.4432373 e 01	0
5.25	.4874427 e 01	1

mean .2328674 e 00
standard deviation .8841071 e 00
failures 2

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Vce(sat) -- Volts

t	x	n
-4.75	.8788939 e-01	0
-4.25	.9356213 e-01	0
-3.75	.9923485 e-01	0
-3.25	.1049076 e 00	0
-2.75	.1105803 e 00	0
-2.25	.1162531 e 00	0
-1.75	.1219258 e 00	6
-1.25	.1275985 e 00	13
-.75	.1332713 e 00	0
-.25	.1389440 e 00	26
.25	.1446167 e 00	0
.75	.1502895 e 00	18
1.25	.1559622 e 00	0
1.75	.1616349 e 00	10
2.25	.1673076 e 00	0
2.75	.1729804 e 00	0
3.25	.1786531 e 00	0
3.75	.1843258 e 00	0
4.25	.1899986 e 00	0
4.75	.1956713 e 00	0
5.25	.2013440 e 00	0
mean	.1417804 e 00	
standard deviation	.1134546 e-01	
failures	37	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- BVcbo -- Volts

t	x	n
-4.75	.1027877 e 02	0
-4.25	.1502671 e 02	0
-3.75	.1977466 e 02	0
-3.25	.2452259 e 02	0
-2.75	.2927053 e 02	0
-2.25	.3401847 e 02	1
-1.75	.3876641 e 02	3
-1.25	.4351435 e 02	12
-.75	.4826229 e 02	19
-.25	.5301023 e 02	28
.25	.5775817 e 02	15
.75	.6250611 e 02	12
1.25	.6725405 e 02	11
1.75	.7200198 e 02	3
2.25	.7674992 e 02	1
2.75	.8149785 e 02	2
3.25	.8624579 e 02	1
3.75	.9099372 e 02	0
4.25	.9574166 e 02	0
4.75	.1004896 e 03	0
5.25	.1052375 e 03	0

mean .5538420 e 02
 standard deviation .9495879 e 01
 failures 2

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- BVcbo -- Volts

t	x	n
-4.75	.1083612 e 02	0
-4.25	.1553800 e 02	0
-3.75	.2023987 e 02	0
-3.25	.2494174 e 02	0
-2.75	.2964362 e 02	0
-2.25	.3434550 e 02	0
-1.75	.3904737 e 02	4
-1.25	.4374924 e 02	5
-.75	.4845112 e 02	13
-.25	.5315300 e 02	19
.25	.5785487 e 02	13
.75	.6255674 e 02	7
1.25	.6725861 e 02	7
1.75	.7196049 e 02	0
2.25	.7666235 e 02	2
2.75	.8136423 e 02	1
3.25	.8606610 e 02	1
3.75	.9076796 e 02	0
4.25	.9546983 e 02	0
4.75	.1001717 e 03	0
5.25	.1048736 e 03	0
mean	.5550393 e 02	
standard deviation	.9403748 e 01	
failures	38	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2569

INITIAL HISTOGRAM -- Bvebo -- Volts


t	x	n
-4.75	.450807 e 01	0
-4.25	.4518457 e 01	1 x
-3.75	.46800067 e 01	1 x
-3.25	.4841097 e 01	1 x
-2.75	.5002227 e 01	5 xxx
-2.25	.5164956 e 01	1 x
-1.75	.5326586 e 01	1 x
-1.25	.5488216 e 01	5 xxx
-.75	.5649046 e 01	9 xxxxxxxxxx
-.25	.5811476 e 01	14 xxxxxxxxxx
.25	.5973105 e 01	45 xxxxxxxxxx
.75	.6134735 e 01	25 xxxxxxxxxx
1.25	.6296365 e 01	4 xxxxx
1.75	.6457994 e 01	0
2.25	.6619624 e 01	0
2.75	.6781253 e 01	0
3.25	.6942883 e 01	0
3.75	.7104512 e 01	0
4.25	.7266142 e 01	0
4.75	.7427772 e 01	0
5.25	.7589401 e 01	0

mean .5892290 e 01
standard deviation .2222777 e 00
failures 2

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Bvebo -- Volts



7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- Icbo -- Micro Amperes

t	x	n
4.75	-.2322775 e 00	0
4.25	-.2047438 e 00	0
3.75	-.1772102 e 00	0
3.25	-.1496764 e 00	0
2.75	-.1221428 e 00	0
2.25	-.9460906 e-01	0
1.75	-.6707541 e-01	0
1.25	-.3954173 e-01	0
.75	-.1200805 e-01	12
.25	.1552562 e-01	66
.75	.4305929 e-01	18
1.25	.7059296 e-01	2
1.75	.9812663 e-01	2
2.25	.1256603 e 00	1
2.75	.1531939 e 00	2
3.25	.1807275 e 00	2
3.75	.2082612 e 00	2
4.25	.2357948 e 00	0
4.75	.2633285 e 00	0
5.25	.2908621 e 00	0
	.3183958 e 00	1
mean	.2929242 e-01	
standard deviation	.5506735 e-01	
failures	2	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Icbo -- Micro-amperes

t	x	n
-4.75	-.4661177 e 00	0
-4.25	-.4095243 e 00	0
-3.75	-.3529307 e 00	0
-3.25	-.2963372 e 00	0
-2.75	-.2397438 e 00	0
-2.25	-.1831503 e 00	0
-1.75	-.1265568 e 00	0
-1.25	-.6996327 e-01	0
-.75	-.1336982 e-01	21
-.25	.4322366 e-01	32
.25	.9981714 e-01	9
.75	.1564106 e 00	3
1.25	.2130041 e 00	6
1.75	.2695975 e 00	1
2.25	.3261909 e 00	0
2.75	.3827844 e 00	0
3.25	.4393778 e 00	0
3.75	.4959712 e 00	0
4.25	.5525646 e 00	0
4.75	.6091580 e 00	0
5.25	.6657515 e 00	1
mean	.7152033 e-01	
standard deviation	.1131870 e 00	
failures	37	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- Cob -- Pico-farads

t	x	n
-4.75	.1828392 e 01	0
-4.25	.1892458 e 01	0
-3.75	.1956524 e 01	0
-3.25	.2020590 e 01	0
-2.75	.2084657 e 01	0
-2.25	.2148723 e 01	0
-1.75	.2212789 e 01	7
-1.25	.2276856 e 01	22
-.75	.2340922 e 01	0
-.25	.2404988 e 01	28
.25	.2469054 e 01	32
.75	.2533121 e 01	0
1.25	.2597187 e 01	14
1.75	.2661253 e 01	0
2.25	.2725319 e 01	4
2.75	.2789385 e 01	1
3.25	.2853451 e 01	0
3.75	.2917517 e 01	0
4.25	.2981583 e 01	0
4.75	.3045650 e 01	0
5.25	.3109716 e 01	0

mean .2457021 e 01
 standard deviation .1281224 e 00
 failures 2

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Cob -- Pico-farads

t	x	n
-4.75	.2033111 e 00	0
-4.25	.4516283 e 00	0
-3.75	.6999448 e 00	0
-3.25	.9482619 e 00	0
-2.75	.1196579 e 01	0
-2.25	.1444895 e 01	0
-1.75	.1693212 e 01	0
-1.25	.1941529 e 01	0
-.75	.2189845 e 01	17
-.25	.2438163 e 01	37
.25	.2686479 e 01	19
.75	.2934796 e 01	0
1.25	.3183113 e 01	1 x
1.75	.3431429 e 01	0
2.25	.3679746 e 01	1 x
2.75	.3928062 e 01	0
3.25	.4176378 e 01	0
3.75	.4424595 e 01	1 x
4.25	.4673011 e 01	0
4.75	.4921328 e 01	0
5.25	.5169645 e 01	1 x
mean	.2562321 e 01	
standard deviation	.4966335 e 00	
failures	33	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- Vce0(sust) -- Volts

t	x	n
-4.75	.1120517 e 01	0
-4.25	.3034327 e 01	0
-3.75	.4948131 e 01	0
-3.25	.6861940 e 01	0
-2.75	.8775750 e 01	0
-2.25	.1068956 e 02	0
-1.75	.1260336 e 02	0
-1.25	.1451717 e 02	1
-.75	.1643098 e 02	38
-.25	.1834478 e 02	30
.25	.2025859 e 02	19
.75	.2217240 e 02	6
1.25	.2408621 e 02	5
1.75	.2600001 e 02	3
2.25	.2791381 e 02	1
2.75	.2982762 e 02	1
3.25	.3174142 e 02	3
3.75	.3365523 e 02	1
4.25	.3556904 e 02	0
4.75	.3748284 e 02	0
5.25	.3939664 e 02	0
mean	.1930169 e 02	
standard deviation	.3827614 e 01	
failures	2	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Vceo(sust) -- Volts

t	x	n
-4.75	.3978656 e 01	0
-4.25	.5876604 e 01	0
-3.75	.7774559 e 01	0
-3.25	.9672514 e 01	0
-2.75	.1157047 e 02	1 x
-2.25	.1346842 e 02	0
-1.75	.1536638 e 02	0
-1.25	.1726433 e 02	1 x
-.75	.1916228 e 02	22 xxxxxxxxxxxxxxxxxxxxxxx
-.25	.2106023 e 02	24 xxxxxxxxxxxxxxxxxxxxxxx
.25	.2295819 e 02	12 xxxxxxxxxxxxxxx
.75	.2485614 e 02	7 xxxxxxx
1.25	.2675409 e 02	0
1.75	.2865205 e 02	4 xxx
2.25	.3055000 e 02	1 x
2.75	.3244795 e 02	1 x
3.25	.3434590 e 02	2 xx
3.75	.3624386 e 02	0
4.25	.3814180 e 02	0
4.75	.4003975 e 02	0
5.25	.4193771 e 02	0
mean	.2200921 e 02	
standard deviation	.3795906 e 01	
failures	35	

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- T -- Nano-seconds

t	x	n
-4.75	.6969861 e 00	1 x
-4.25	.7281022 e 00	0
-3.75	.7592184 e 00	0
-3.25	.7903346 e 00	0
-2.75	.8214507 e 00	0
-2.25	.8525670 e 00	0
-1.75	.8836830 e 00	0
-1.25	.9147992 e 00	19
-.75	.9459153 e 00	0
-.25	.9770315 e 00	0
.25	.1008148 e 01	74
.75	.1039264 e 01	0
1.25	.1070380 e 01	0
1.75	.1101496 e 01	14
2.25	.1132612 e 01	0
2.75	.1163728 e 01	0
3.25	.1194844 e 01	0
3.75	.1225961 e 01	0
4.25	.1257077 e 01	0
4.75	.1288193 e 01	0
5.25	.1319309 e 01	0

mean .9925896 e 00
standard deviation .6223230 e-01
failures 2

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- T -- Nano-seconds


t	x	n
-4.75	.7624699 e 00	0
-4.25	.7870281 e 00	0
-3.75	.8115864 e 00	0
-3.25	.8361446 e 00	0
-2.75	.8607028 e 00	0
-2.25	.8852611 e 00	0
-1.75	.9098193 e 00	10
-1.25	.9343775 e 00	0
-.75	.9589357 e 00	0
-.25	.9834940 e 00	0
.25	.1008052 e 01	54
.75	.1032611 e 01	0
1.25	.1057169 e 01	0
1.75	.1081727 e 01	0
2.25	.1106285 e 01	0
2.75	.1130843 e 01	7
3.25	.1155401 e 01	0
3.75	.1179960 e 01	0
4.25	.1204518 e 01	0
4.75	.1229076 e 01	0
5.25	.1253634 e 01	0

mean .9957731 e 00
standard deviation .4911644 e-01
failures 39

7-0057

FAIRCHILD SEMICONDUCTOR --- 2N 2369

INITIAL HISTOGRAM --- Ton --- Nano-seconds



7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Ton -- Nano-seconds

t	x	n
-4.75	.5312537 e 01	1 x
-4.25	.5512637 e 01	0
-3.75	.5712738 e 01	0
-3.25	.5912839 e 01	1 x
-2.75	.6112939 e 01	0
-2.25	.6313040 e 01	0
-1.75	.6513141 e 01	0
-1.25	.6713241 e 01	2 xx
-.75	.6913342 e 01	10 xxxxxxxx
-.25	.7113442 e 01	27 xxxxxxxxxxxxxxxxxx
.25	.7313543 e 01	12 xxxxxxxxxxxxxx
.75	.7513643 e 01	17 xxxxxxxxxxxxxxxxxx
1.25	.7713744 e 01	4 xxx
1.75	.7913845 e 01	0
2.25	.8113945 e 01	0
2.75	.8314045 e 01	0
3.25	.8514146 e 01	0
3.75	.8714246 e 01	0
4.25	.8914346 e 01	0
4.75	.9114447 e 01	0
5.25	.9314547 e 01	0
mean	.7213493 e 01	
standard deviation	.4002011 e 00	
failures	36	

7-0C57

FAIRCHILD SEMICONDUCTOR -- 2N 2369

INITIAL HISTOGRAM -- Toff -- Nano-seconds

t	x	n
-4.75	.8117279 e 00	0
-4.25	.1335247 e 01	0
-3.75	.1858767 e 01	0
-3.25	.2382286 e 01	0
-2.75	.2905805 e 01	0
-2.25	.3429325 e 01	0
-1.75	.3952844 e 01	0
-1.25	.4476363 e 01	11
-.75	.4999883 e 01	30
-.25	.5523402 e 01	20
.25	.6046921 e 01	21
.75	.6570441 e 01	7
1.25	.7093959 e 01	9
1.75	.7627478 e 01	6
2.25	.8140997 e 01	3
2.75	.8664515 e 01	0
3.25	.9188034 e 01	1
3.75	.9711553 e 01	0
4.25	.1023407 e 02	0
4.75	.1075859 e 02	0
5.25	.1128211 e 02	0

mean .5785161 e 01
standard deviation .1047038 e 01
failures 2

7-0057

FAIRCHILD SEMICONDUCTOR -- 2N 2369

FINAL HISTOGRAM -- Toff -- Nano-seconds

t	x	n
-4.75	.2851599 e 01	0
-4.25	.3636193 e 01	0
-3.75	.4420786 e 01	0
-3.25	.5205379 e 01	0
-2.75	.5989972 e 01	0
-2.25	.6774565 e 01	0
-1.75	.7559160 e 01	2
-1.25	.8343753 e 01	10
-.75	.9128346 e 01	14
-.25	.9912939 e 01	19
.25	.1069753 e 02	8
.75	.1148213 e 02	11
1.25	.1226672 e 02	5
1.75	.1305131 e 02	4
2.25	.1383590 e 02	3
2.75	.1462049 e 02	0
3.25	.1540509 e 02	0
3.75	.1618968 e 02	0
4.25	.1697427 e 02	0
4.75	.1775886 e 02	0
5.25	.1854346 e 02	0

mean .1030524 e 02
standard deviation .1569186 e 01
failures 34