

MONTHLY PROGRESS REPORT THROUGH 31 MAY 1965

LIFE CYCLE TESTS

1. Status of Cycling Program: The cycling program has included cells from the following manufacturers: General Electric Company (G.E.), Gould-National Batteries, Inc. (Gould), Sonotone Corporation (Sonotone), Yardney Electric Corporation (Yardney), Gulton Industries, Inc. (Gulton) and Delco-Remy (Delco).

TOTAL NUMBER OF PACKS IN PROGRAM: 121

Cell Type	Total Number of Packs			Cells Failed*	
	Cycled To Late	Still Cycling	Failed	Since Last Report	Total To Date
NICKEL CADMIUM (10-cell packs)					
G.E. 3.0 a.h.	12	9	3	3	27
Gould 3.5 a.h.	12	5	7	2	54
Sonotone 5.0 a.h.	12	10	2	3	27
Gulton 6.0 a.h.	12	5	7	0	58
TOTAL	48	29	19	8	166
NICKEL CADMIUM (5-cell packs)					
G.E. 5.0 a.h. NIMBUS	3	3	0	0	0
G.E. 12 a.h.	13	10	3	2	12
Gulton 4.0 a.h.	6	6	0	0	0
Gulton 5.0 a.h. NIMBUS	3	3	0	0	0
Gulton 6.0 a.h.	1	1	0	0	2
Gulton 6.0 a.h. HSI	3	3	0	0	0
Gulton 6.0 a.h. 3rd Elect.	5	5	0	0	0
Gulton 12 a.h.	6	6	0	0	1
Gulton 20 a.h.	12	6	6	1	26
Gulton 50 a.h.	2	0	2	0	6
Gould 20 a.h.	12	6	6	0	19
TOTAL	66	49	17	3	66
SILVER CADMIUM (10-cell packs)					
Yardney 12 a.h.	3	1	2	0	16
TOTAL	3	1	2	0	16
SILVER ZINC (5-cell packs)					
Delco 25 a.h.	3	0	3	5	10
Delco 40 a.h.	1	0	1	0	2
TOTAL	4	0	4	0	12

*All failure analysis results are cumulative. These results are shown on pages 4 through 33.

N65-28871

GPO PRICE \$ _____

CFSTI PRICE(S) \$ _____

(ACCESSION NUMBER)

(THRU)

125

(PAGE)

(CODE)

663867

03

Hard copy (HC) \$4.00

Microfiche (MF) \$1.00

2. Test Parameters:

a. Ambient Temperatures:

- (1) 0° C.
- (2) 25° C.
- (3) 40° C.

b. Voltage limits per pack on charge:

- (1) 1.55 ± 0.03 volts per cell at 0° C.
- (2) 1.49 ± 0.03 volts per cell at 25° C.
- (3) 1.45 ± 0.03 volts per cell at 40° C.
- (4) 1.97 ± 0.03 volts per cell at 25° C. on the silver zinc packs.

c. Depth of Discharge:

- (1) 90-minute and 3-hour orbits:
 - (a) 15 percent and 25 percent at 0° C.
 - (b) 25 percent and 40 percent at 25° C.
 - (c) 15 percent and 25 percent at 40° C.
- (2) 24-hour orbits:
 - (a) 50 percent at 0° C, 25° C and 40° C.
 - (b) 40 percent at 25° C on the silver zinc packs.

d. Orbit Times:

- (1) 90 minutes--30-minute-discharge and 60-minute charge.
- (2) 3 hours--30-minute discharge and 150-minute charge.
- (3) 24 hours--1-hour discharge and 23-hour charge.

3. Data:

a. Normal operation schedules complete data to be recorded on 90-minute and 3-hour packs every 32 cycles. On 24-hour cycles, complete data is taken every eight cycles.

b. The attached data sheets give end of discharge and end of charge voltage readings for each cell on each cycle recorded.

4. Capacity Tests:

a. Prior to cycling, each pack was given a capacity test at its respective cycling temperature. This check consisted of a c/10 charge for 16 hours followed by a c/2 discharge to 1.0 volt/cell average. After each 88 days of cycling, each pack was discharged at the c/2 rate to 1.0 volt/cell average following a charge at the cycle rate. The pack was then recharged at the c/10 rate for 16 hours and discharged at the c/2 rate to 1.0 volt/cell average. The pack was then recharged at the c/10 rate for 48 hours, voltage limited to the cycle limits. Data of capacity tests is tabulated on pages 34 through 39.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: General Electric 3.0 Ampere-Hour	
							FAILURE	ANALYSIS
16	40%	1.5	25°	427	7	3985		Low Volt Disch, Normal Volt Chg, Pos Tab Broken and Touching Case. Burned Tape on Tab Caused by Overheating From Poor Tab Weld.
				58	6	4473		Low Volt Disch, Normal Volt Chg, Short on One Edge of Plates, Neg Plate Material Penetrated Separator.
				361	1	4741		Low Volt Disch, Normal Volt Chg, Shorted, Separator Deteriorated, Neg Plate Material Penetrated Separator.
				522	5	4917		Low Volt Disch, Low Volt Chg, Separator Impregnated with Neg Plate Material, Separator Deteriorated.
				456	10	4917		Low Volt Disch, Low Volt Chg, Separator Impregnated with Neg Plate Material, Separator Deteriorated.
				719	4	5013		Low Volt Disch, Low Volt Chg, Separator Impregnated with Neg Plate Material, Separator Deteriorated, Several Small Burned Areas on Separator.
		1.5	50°	541	2	779		Low Volt Disch, High Volt Chg, Leaked, Shorted at Top of Core, Separator Too Short, Pos Tab Burned.
			40°	540	6	2083		Low Volt Disch, High Volt Chg, Leaked, Shorted at Top of Core, Separator Too Short, Pos Tab Burned.
			40°	549	7	2523		Low Volt Disch, High Volt Chg, Pos Tab Burned.
39	15%							

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: General Electric 3.0 Ampere-Hour FAILURE ANALYSIS
40	25%	1.5	40°	484	3	2073	Low Volt Disch, High Volt Chg, Shorted at Top of Core, Separator Too Short, Pos Tab Burned.
			40°	3131	8	2182	Low Volt Disch, Normal Volt Chg, Leaked, Loose Plate Material on Separator.
			40°	47	7	2182	Low Volt Disch, High Volt Chg, Shorted at Top of Core, Separator Too Short, Pos Tab Burned and Broken.
			40°	49	5	2446	Low Volt Disch, High Volt Chg, Pos Weld to Terminal Stud Burned, Poor Weld.
			40°	45	10	2461	Low Volt Disch, High Volt Chg, Loose Plate Material on Separator, Short at Outside End of Pos Plate.
			40°	466	2	2509	Low Volt Disch, High Volt Chg, Leaked, Pos Tab Burned and Shorted to Neg Tab.
			40°	441	6	2509	Low Volt Disch, High Volt Chg, Leaked, Shorted at Top of Core, Separator Too Short, Pos Tab Burned.
43	15%	3.0	40°	416	4	1182	Low Volt Disch, Low Volt Chg, Shorted at Top of Core, Separator Too Short, Pos Tab Burned.
			40°	499	3	1515	Low Volt Disch, High Volt Chg, Shorted at Top of Core, Separator Too Short, Pos Tab Burned and Broken.
			40°	412	6	1911	Showed Open Circuit at Start of Cycle, Pos Tab Broken, Burned Tape on Tab Caused by Overheating From Poor Tab Weld.
			40°	426	9	2298	Showed Open at Start of Cycle, Pos Tab Corroded, Pos Tab Broken, Top of Separator Burned, Separator Impregnated with Neg Plate Material, Separator Deteriorated.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: General Electric 3.0 Ampere-Hour FAILURE ANALYSIS
43	15%	3.0	40°	436	7	2515	Showed Open at Start of Cycle, Pos Tab Corroded, Pos Tab Broken, Poor Roll, Uneven Wind at End of Roll, Shorts at Top of Roll, Separator Deteriorated.
				435	10	2656	Showed Open at Start of Cycle, Pos Tab Corroded, Pos Tab Broken, Separator Impregnated with Neg Plate Material, Separator Deteriorated.
44	25%	3.0	40°	222	6	1672	Showed Open Circuit at Start of Cycle, Pos Tab Broken, Burned Tape on Tab Caused By Overheating From Poor Tab Weld.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gould 3.5 Ampere-Hour FAILURE ANALYSIS
3	25%	1.5	25°	73	5	2785	Low Volt Disch, High Volt Chg, Short Near Center of Core, Piece of Pos Plate Material Between Plates Causing Short Through Separator.
				54	2	3090	Low Volt Disch, Low Volt Chg, Leaked, Lost 1.7 gm, Weak Weld on Neg Tab to Plate.
				165	9	4081	Low Volt Disch, Normal Volt Chg, Leaked, Lost 1.7 gm, Deposit on Glass Seal, Short Through Separator, Short at Pos Tab Near Center of Core, Neg Tab Weld to Plate Weak.
				93	6	4289	Low Volt Disch, Normal Volt Chg, Leaked Around Glass Seal, Lost 2.6 gm, Separator Deteriorated, Neg Plate Material Penetrated Separator.
				97	7	4401	Low Volt Disch, Normal Volt Chg, Leaked Around Glass Seal, Lost 2.5 gm, Separator Deteriorated, Neg Plate Material Penetrated Separator.
				77	4	4751	Low Volt Disch, Normal Volt Chg, Separator Deteriorated, Separator Impregnated with Neg Plate Material, Blistering on Pos Plates.
4	40%	1.5	25°	188	10	4751	Low Volt Disch, Normal Volt Chg, Leaked, Lost 2.1 gm, Neg Plate Material on Separator.
				81	7	1609	Low Volt Disch, Normal Volt Chg, Leaked, Lost 3.2 gm, High Pres Bulge Top.
				90	8	1827	Low Volt Disch, Low Volt Chg, Leaked, Lost 2.7 gm, High Pres Bulge Top.
				2	1	2110	Low Volt Disch, Low Volt Chg, Separator Deteriorated at Center of Core, Under Pressure When Opened.

PAGE NUMBER	DEPTH OF DISCHARGE	CHARGE PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gould 3.5 Ampere-Hour FAILURE ANALYSIS
4	40%	1.5	25°	43	6	2954	Low Volt Disch, Low Volt Chg, Leaked, Lost 1.3 gm, Plate Material on Separator.
			25°	27	3	3029	Low Volt Disch, Normal Volt Chg, Deposit on Glass Seal, Separator Deteriorated.
			25°	198	10	3164	Low Volt Disch, Low Volt Chg, Leaked, Lost 1.5 gm, Separator Deteriorated, Pos Plate Material Between Plates.
7	25%	3.0	25°	49	2	3007	Low Volt Disch, Normal Volt Chg, Leaked Around Glass Seal, Lost 2.7 gm, Neg Plate Material Migrated Through Separator, Separator Deteriorated, One Weak Weld Pos Tab to Plate.
			25°	37	1	3130	Low Volt Disch, Normal Volt Chg, Leaked, Lost 1.1 gm, Glass Seal Broken, Separator Very Dry, Neg Plate Material Migration, Pinpoint Penetration, Loose Neg Plate Material on Separator, Separator Deteriorated, All Tab Welds to Plates Weak.
			25°	109	6	3483	Low Volt Disch, Low Volt Chg, Leaked, Lost 2.0 gm, Deposit on Glass Seal, Separator Deteriorated, Pinpoint Penetration, Neg Plate Material on Separator, Weak Weld on One Tab to Pos Plate Weld.
			25°	104	5	*3736	Shorted on Cycling, Deposit on Glass Seal, Leaked, Lost 1.1 gm, Weak Weld Pos Tab to Plate, Neg Plate Material on Separator, Pinpoint Penetration, Separator Deteriorated.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gould 3.5 Ampere-Hour FAILURE ANALYSIS
8	40%	3.0	25°	68	6	1346	Low Volt Disch, Low Volt Chg, Leaked, Lost 1.5 gm, Plate Material on Separator.
				112	8	1704	Low Volt Disch, Normal Volt Chg, Leaked, Lost 2.0 gm, Pos Tab Weld to Bottom of Can Weak, Pos Tab Weld to Plate Weak.
				39	1	1985	Low Volt Disch, Normal Volt Chg, Deposit on Glass Seal, Separator Deteriorated, Neg Plate Material on Separator.
				170	10	1985	Low Volt Disch, Normal Volt Chg, Leaked, Lost 1.8 gm, Pos and Neg Tab Weld Weak to Plates Near Center of Core, Separator Deteriorated at Center of Core.
				78	7	2138	Low Volt Disch, Low Volt Chg, Leaked Around Glass Seal, Lost 1.4 gm, Pos Tab Weld to Case Weak, Separator Deteriorated, Neg Plate Material Penetrated Separator.
				41	2	2494	Low Volt Disch, Low Volt Chg, Leaked Around Glass Seal, Lost 1.7 gm, Separator Deteriorated, Neg Plate Material Impregnated Separator, One Bad Weld Neg Tab to Plate.
				130	9	2494	Low Volt Disch, Low Volt Chg, Leaked Around Glass Seal, Lost 2.1 gm, Separator Deteriorated, Pos and Neg Plate Material Impregnated Separator.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gould 3.5 Ampere-Hour FAILURE ANALYSIS
27	15%	1.5	40°	13	3	2901	Low Volt Disch, Low Volt Chg, Leaked, Lost 1.5 gm, Separator Deteriorated, Pos Plate Material on Separator.
			40°	195	8	2901	Low Volt Disch, Normal Volt Chg, Leaked, Lost 3.6 gm, Short Through Separator, Separator Burned at Center of Core, Pos Plate Material on Separator.
			40°	103	7	2998	Low Volt Disch, Normal Volt Chg, High Pres, Short Through Separator, Pieces of Pos Plate Material Between Plates.
			40°	200	10	3270	Low Volt Disch, Normal Volt Chg, Leaked, Lost 2.5 gm, Short Through Separator, Separator Deteriorated at Center of Core, Pos Tab Weld to Case Weak.
			40°	197	9	4102	Low Volt Disch, High Volt Chg, Leaked Around Glass Seal, Lost 1.4 gm, Short at Pos Tab, Separator Deteriorated, Neg Plate Material Penetrated Separator.
			40°	11	2	4485	Low Volt Disch, Normal Volt Chg, Deposit on Glass Seal, Separator Deteriorated, Separator Impregnated with Neg Plate Material.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CHILL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Could 3.5 Ampere-Hour FAILURE ANALYSIS
28	25%	1.5	50°	122	2	408	Low Volt Disch, Normal Volt Chg, Leaked, Lost 1.8 gm, Weak Bottom Weld Suspicious Spot but not Definite.
			40°	157	7	484	Low Volt Disch, Normal Volt Chg, Leaked, Lost 2.0 gm, High Pres Bulge.
			40°	158	8	484	Low Volt Disch, Normal Volt Chg, Leaked, Lost 1.9 gm, High Pres Pulge Top.
			40°	141	5	860	Low Volt Disch, High Volt Chg, Leaked, Lost 3.5 gm.
			40°	168	10	1293	Low Volt Disch, High Volt Chg, Weak Weld to Bottom of Case.
			40°	121	1	1811	Low Volt Disch, Low Volt Chg, Short at Outside End of Plates, Grid Wire Penetrated Separator.
			40°	133	3	1811	Low Volt Disch, High Volt Chg, Weak Weld on Pos Tab to Case.
			40°	140	4	1811	Low Volt Disch, Low Volt Chg, Short Around Pos Tab, Blistering on Pos Plate, Active Neg Plate Material on Separator.
			40°	155	6	1811	Low Volt Disch, Low Volt Chg, Short Through Separator, Weak Weld to Bottom of Case.
			40°	163	9	1811	Low Volt Disch, Low Volt Chg, Short Through Separator, Weak Weld to Bottom of Case, Deposit on Glass Seal.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	ORBIT NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gould 3.5 Ampere-Four FAILURE ANALYSIS
31	15%	3.0	40°	RL66	9	1500	Low Volt Disch, Low Volt Chg, Leaked, Lost 7.1 gm, Separator Deteriorated.
			40°	RL79	10	1500	Low Volt Disch, Low Volt Chg, Leaked, Lost 1.5 gm, Short Through Separator, Separator Deteriorated, One Weak Tab.
			40°	R92	2	1696	Low Volt Disch, High Volt Chg, Pieces of Plate Material Shorted Through Separator, Separator Deteriorated.
			40°	126	3	2411	Low Volt Disch, Low Volt Chg, Leaked Around Glass Seal, Lost 2.1 gm, Short Through Separator by Piece of Pos Plate Material Between Plates, Separator Deteriorated, Neg Plate Material Impregnated Separator, Tab to Plate Weld Poor.
			40°	RL62	8	2477	Low Volt Disch, High Volt Chg, Leaked Around Glass Seal, Lost 2.4 gm, Separator Deteriorated, Neg Plate Material Impregnated Separator, Pinpoint Penetration, Poor Weld Pos Tab to Case.
			40°	72	1	2517	Low Volt Disch, Low Volt Chg, Leaked Around Glass Seal, Lost 1.8 gm, Short Between Plates, Extra Piece of Pos Plate Between Plates, Separator Deteriorated, Pos Tabs to Plate Weld Both Weak.
			40°	143	6	2517	Low Volt Disch, Low Volt Chg, Short Through Separator at Start of Core, Extra Piece of Pos Plate Material, Separator Impregnated with Neg Plate Material, Separator Deteriorated, Neg Tab Weld to Pigtail Weak, One Tab to Pos Plate Weld Weak, Still Under Pressure When Opened.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Could 3.5 Ampere-Hour FAILURE ANALYSIS
32	25%	3.0	40°	125	6	138	Low Volt Disch, Normal Volt Chg, Bottom Weld Weak, Greenish Corrosion Inside at Neg Lead.
			40°	65	3	495	Low Volt Disch, Normal Volt Chg, Leaked, Lost 1.5 gm, Bad Glass Seal Around Neg Terminal.
			40°	1	1	800	Low Volt Disch, Normal Volt Chg, Leaked, Lost 3.2 gm, Shorts Near Center of Core.
			40°	67	4	875	Low Volt Disch, Low Volt Chg, Leaked, Lost 2.2 gm, Short Around Tabs, Pos Tab Weld Weak to Case.
			40°	132	7	875	Failed During Shut Down to Move to Another Chamber, Leaked, Lost 4.4 gm, High Pres. Neg Tabs Pushed Out of Cell, Short at Center and Outside Edge of Core.
			40°	149	9	974	Low Volt Disch, High Volt Chg, Leaked, Lost 1.1 gm, Piece of Pos Plate Material Shorted Through Separator, Weak Welds to Case and Plates.
52	25%	1.5	0°	116	8	*7858	Low Volt Disch, Low Volt Chg, Still Under Pressure When Opened, Neg Plate Material on Separator, Excess Migration of Neg Plate Material, Separator Deteriorated.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Sonotone 5.0 Ampere-Hour FAILURE ANALYSIS
1	25%	1.5	25°	4361	4	2995	Low Volt Disch, High Volt Chg, Inclusion on Surface of Outside Pos Plate Wore Hole Through Separator and Thin Outside Wrap, Separator Sticking to Neg Plate, Glass Seal Leaked.
			25°	4335	1	4423	Low Volt Disch, High Volt Chg, Neg Tabs Weak Weld to Plates, Separator Melted at Center of Core, Extreme Pressure Points on Separator From Scoring Causing High Resistance Shorts.
2	40%	1.5	25°	811	10	3155	Shorted on Cycling, Leaked Around Seal, High Pressure Bulge on Bottom, Insulators Eruptive, Exposed Grid Wires at Center of Core Penetrated Separator Causing Large Burned Area at Short, Pos and Neg Tab Weld Poor.
			25°	3628	5	3992	Low Volt Disch, Normal Volt Chg, Leaked Around Seal, High Pres Bulge on Bottom, Hole in Separator Exposing Pos and Neg Plates, Neg Plate Material Penetrated Separator.
			25°	3613	2	4411	Low Volt Disch, Low Volt Chg, Two Pieces of Neg Plate Material Wore Hole in Separator at Scoring Mark, Burned Through Plates, Neg Tab Welds Poor, Separator Beginning to Deteriorate.
			25°	3630	6	5262	Low Volt Disch, Normal Volt Chg, Deposit on Glass Seal, Pos and Neg Plate Material on Separator, Separator Deteriorated, Neg Tab to Plate Welds Weak, Burn Marks on Separator at Tabs, High Pressure Bulge.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: <u>Sonotone 5.0 Ampere-Hour</u> FAILURE ANALYSIS
2	40%	1.5	25°	3631	7	5262	Low Volt Disch, Low Volt Chg, Uncoined Plate Edges Pierced Separator Causing Partial Shorts, Burn Marks Around Tab Areas, Weak Weld on All Tab to Plate Welds, Deep Pressure Points Caused by Scoring, Separator Torn at Start of Core Exposing Pos and Neg Plate, Separator Deteriorated, Neg Plate Material on Separator.

PACK NUMBER	DEPTH OF DISCHARGE	CHARGE PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Sonotone 5.0 Ampere-Hour	
							FAILURE	ANALYSIS
6	40%	3.0	25°	4324	8	1069	Low Volt Disch, Normal Volt Chg, Separator Impregnated With Active Material, Separator Sticking to Neg Plate.	
							Low Volt Disch, Low Volt Chg, Small Hole in Separator at Start of Coil, Pos Plate Edge Broken Allowing Grid Wire to Penetrate Separator.	
							Grid Wires of Pos Plate Penetrated Separator and Shorted to Neg Plate, Active Plate Material Penetrated Separator at Three Points, Bad Tab Welds.	
							Low Volt Disch, High Volt Chg, Separator Deteriorated, Large Burned Area at Center of Core, Pinpoint Penetration, Deep Scoring Caused Hole in Separator, Partial Shorts Around Edge of Plates Deep Pressure Points Caused by Scoring.	
25	15%	1.5	40°	4852	5	6348	Grid Wire Penetrated Separator at Tabs.	
							Shorted on Cycling, Slight Burn Adjacent to Neg Tab, Separator Deteriorated, Neg Plate Material Penetrated Separator, Tab Welds Weak.	
26	25%	1.5	40°	4323	1	2487	Low Volt Disch, Normal Volt Chg, High Pres Bulge, Deposit Around Seal, Neg Tab Weld Weak, Neg Plate Material Penetrated Separator.	
							Low Volt Disch, Normal Volt Chg, High Pres Bulge, Deposit Around Seal, Pos Tab Weld Weak, Plate Broken at Pos Tab, Deep Pressure Points From Scoring, Separator Completely Deteriorated.	
							Shorted on Cycling, Complete Short From Deep Scoring, Plate Shorted Through Outer Wrap.	
							Low Volt Disch, Low Volt Chg, Separator Deteriorated, Plate Material Penetrated Separator.	
3625	40°	4	40°	4881	3	3344		

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Sonotone 5.0 Ampere Hour FAILURE ANALYSIS
29	15%	3.0	40°	3626	1	1418	Shorted on Cycling, Neg.Tab Welds Poor, Active Plate Material Penetrated Separator at Scoring Marks.
30	25%	3.0	40°	3657	7	855	Hole in Separator Allowing Pos Plate to Hit Case, Separator Damaged at Center of Cell Allowing Pos and Neg Plate to Short Together.
			40°	3643	4	3068	Low Volt Disch, Low Volt Chg, Separator Completely Deteriorated, Neg Tab to Plate Welds Weak, Burn Spots Around Tabs, Deep Scoring Caused Burn Spots on Separator.
			40°	809	9	3068	Low Volt Disch. Low Volt Chg, Deposit Around Glass Seal, Burn Spots Around Edge of Separator Caused By Uncoined Edge of Plates, Deep Scoring Caused Burn Spots on Separator, Burn Spots Around Tab Areas, Separator Deteriorated.
49	15%	1.5	0°	6887	9	2010	Low Volt Disch, Low Volt Chg, Burn on Separator Opposite Pos Tab.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: <u>Gulton 6.0 Ampere-Hour</u> FAILURE ANALYSIS
13	25%	1.5	25°	2305	1	308	Low Volt Disch, High Volt Chg, Lost 12 gm, CO ₂ Top Ceramic, High Pres Bulge.
			25°	2355	10	502	Low Volt Disch, High Volt Chg, Lost 10 gm, High Pres Bulge.
			25°	3134	5	2969	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plates.
			25°	3211	7	3084	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plates.
			25°	2613	4	3598	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plate, Separator Deteriorated.
14	40%	1.5	25°	2324	2	4021	Low Volt Disch, Low Volt Chg, Ceramic Short, Separator Deteriorated, Separator Impregnated with Neg Plate Material, Blistering on Pos Plates, High Pres Bulge.
			25°	1623	4	262	Low Volt Disch, High Volt Chg, Lost 12 gm, High Pres Bulge.
			25°	1635	5	262	Voltage Fell Off During Charge, Went Flat in 3 Min. on Disch, Lost 6 gm, Concave Wall, High Pres. Bulge, Ceramic Broken Inside Case, CO ₂ on Outside of Ceramic, Pos Terminal Loose.
			25°	2356	1	450	Low Volt Disch, High Volt Chg, Lost 12 gm, High Pres.
			25°	2387	2	1113	Low Volt Disch, High Volt Chg, Ceramic Short.
			25°	2391	3	1618	Low Volt Disch, Low Volt Chg, Ceramic Short.
			25°	3208	7	2036	Low Volt Disch, Normal Volt Chg, Ceramic Short.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gulton 6.0 Ampere-Hour	
							FAILURE ANALYSIS	
17	25%	3.0	25°	1862	5	721	Low Volt Disch, High Volt Chg, Ceramic Short.	
				1823	3	721	Low Volt Disch, High Volt Chg, High Pres Bulge, Burnt Spot on Neg Plate Near Bottom Second From End, Ceramic Short.	
				2348	10	1688	Low Volt Disch, Low Volt Chg, Ceramic Short.	
				1757	1	2375	Low Volt Disch, Low Volt Chg, Ceramic Short, Deposit Around Ceramic Seal, High Pres Bulge.	
				1598	2	2449	Low Volt Disch, Low Volt Chg, Pinpoint Penetration of Separator, Blistering on Pos Plate, High Pres Bulge.	
				2347	9	2885	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plates, High Pressure Bulge, Still Under Pressure When Opened.	
				1826	6	365	Low Volt Disch, Chg Volt Normal, Lost 3 gm, Concave Wall, Ceramic Short.	
				1615	3	608	Low Volt Disch, Normal Volt Chg, Deposit on Top of Pos Terminal, Lost 5.1 gm, High Pres Bulge.	
				1827	7	643	Low Volt Disch, High Volt Chg, High Pres Bulge, Ceramic Short.	
				2228	9	643	Low Volt Disch, High Volt Chg, Ceramic Short.	
13	40%	3.0	25°	1562	5	1145	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plates.	
				1233	1	1550	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plate, Neg Plate Material on Separator.	

PACK NUMBER	DEPTH OF DISCHARGE	CHARGE PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gulton 6.0 Ampere-Hour FAILURE ANALYSIS
37	15%	1.5	50°	1764	3	238	Low Volt Disch, Volt Did Not Increase on Following Chg, (1.00 V) Lost 4 gm, Ceramic Short.
			40°	1784	8	1566	Low Volt Disch, Low Volt Chg, Lost 10.5 gm, Ceramic Short.
			40°	1802	4	2819	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plate.
			40°	2333	10	2981	Low Volt Disch, Normal Volt Chg, Ceramic Short, Blistering on Pos Plates.
			40°	1769	7	4897	Low Volt Disch, Normal Volt Chg, Ceramic Short, Leaked, Lost 1 gm, Blistering on Pos Plate, Separator Deteriorated.
			40°	1814	6	6064	Low Volt Disch, High Volt Chg, Deposit on Pos Terminal, Separator Deteriorated, Neg Plate Material on Separator, Blistering on Pos Plates, Ceramic Short.
38	25%	1.5	50°	1454	8	37	No Volt on Chg or Disch, Ceramic Short.
			50°	1815	6	114	Volt Fell Off During Disch, Chg Volt Slightly Low, Lost 3.5 gm, Ceramic Short.
			40°	1853	9	187	Rev on Disch, Chg Volt Normal, Lost 4 gm, Deposits Around Pos Terminal (Outside), Ceramic Short.
			40°	1627	3	225	Low Volt Disch, High Volt Chg on Cycle 219, Dead on 225, Lost 3.5 gm.
			40°	2405	5	1333	Low Volt Disch, Normal Volt Chg, Pos Bus Shorted to Case.
			40°	1626	2	1377	Low Volt Disch, Low Volt Chg, High Pres Bulge, Ceramic Short.

PACK NUMBER	DEPTH OF DISCHARGE	CHARGE PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	FAILURE ANALYSIS	CELL TYPE: Gulton 6.0 Ampere-Hour
41	15%	3.0	40°	1771	9	649	Low Volt Disch, High Volt Chg, Ceramic Short.	
			40°	1801	6	1062	Low Volt Disch, Normal Volt Chg, Ceramic Short.	
			40°	3135	2	1132	Low Volt Disch, Normal Volt Chg, Ceramic Short.	
			40°	1852	7	1157	Low Volt Disch, Normal Volt Chg, Ceramic Short, Blistering on Pos Plates.	
			40°	2221	8	1157	Low Volt Disch, Normal Volt Chg, Ceramic Short.	
			40°	1632	3	1689	Low Volt Disch, Normal Volt Chg, Ceramic Short, Blistering on Pos Plates.	
42	25%	3.0	50°	2309	8	96	Low Volt Disch, Normal Volt Chg, Ceramic Short.	
			40°	2346	7	332	Low Volt Disch, Low Volt Chg, CO ₃ on Bottom of Case, Ceramic Short.	
			40°	2306	9	416	Low Volt Disch, High Volt Chg, Ceramic Short.	
			40°	918	1	484	Low Volt Disch, Low Volt Chg, High Pres Bulge, Deposit on Bottom of Case, Ceramic Short, Lost 3.1 gm.	

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: <u>Gulton 6.0 Ampere-Hour</u> FAILURE ANALYSIS
61	15%	1.5	0°	1622	2	1	Volt Between 0.25 and 0.3 V Throughout Cycle, Side Concave, Burnt Case, End Neg Pushed Into Pos Tab. Cell Replaced in Pack Due to Early Failure.
				1845	8	6	Lost 5 gm, Leak at Weld on Bottom, High Pres Bulge, Cell Replaced in Pack Due to Early Failure.
				2397	5	2762	Low Volt Disch, Low Volt Chg, Ceramic Short.
				1825	4	4094	Low Volt Disch, Low Volt Chg, Ceramic Short, Separator Impregnated with Neg Plate Material, Blistering on Pos Plates, High Pres Bulge.
				2311	10	4285	Low Volt Disch, Low Volt Chg, Ceramic Short, Separator Impregnated with Neg Plate Material, Blistering on Pos Plates, High Pres Bulge.
				2400	6	4413	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plates, High Pres Bulge.
62	25%	1.5	0°	1630	10	2995	Low Volt Disch, High Volt Chg, Leaked, Lost 6.8 gm, Ceramic Seal Broke, Deposit on Inside of Ceramic, High Pres Bulge, Blistering on Pos Plates.
				1792	4	4066	Low Volt Disch, Low Volt Chg, Small Shorts Through Separator Near Pos Tab, Blistering on Pos Plate, Separator Deteriorated.
				1806	5	4441	Low Volt Disch, Low Volt Chg, Ceramic Short, Blistering on Pos Plates, High Pres Bulge.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	GELT NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Galton 6.0 Ampere-Hour FAILURE ANALYSIS
66	25%	3.0	0°	1794	6	1045	Low Volt Disch, High Volt Chg, High Pres Bulge, Concave Side, Ceramic Broken, No Seal, Lost 5.1 gm, Pos Bus Against Case.
			0°	1843	8	1173	Low Volt Disch, Low Volt Chg, Wall Concave, Ceramic Short.
			0°	1781	5	1237	Low Volt Disch, High Volt Chg, High Pres Bulge, Deposit Around Pos Terminal, Ceramic Broken on Pos Terminal, Blisters on Pos Plate, Burnt Spot on Separator at Blisters, Lost 1.3 gm.
			0°	1634	3	1417	Low Volt Disch, Normal Volt Chg, Ceramic Short, High Pres Bulge, One Side Concave Other Convex, Pos Plates Blistered, Lost 2.3 gm.
			0°	1823	7	2122	Low Volt Disch, Low Volt Chg, Leaked, Lost 7.8 gm, Separator Impregnated with Neg Plate Material, Blistering on Pos Plates, High Pres Bulge, One Side Concave.

CELL TYPE: General Electric 12.0 Ampere-Hour									
PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	FAILURE ANALYSIS		
93	50%	24.0	40°	204	1	266	Cell Lost Capacity on Cycling But Came Back When Removed From Pack, So It Was Put Back on Cycling in Same Pack.		
96	40%	1.5	40°	208	2	266	Low Volt Disch, Normal Volt Chg, Was Opened Up But Did Not Show Anything to be Wrong With Cell, Failure Due to Loss of Capacity.		
			25°	445	3	3822	Low Volt Disch, Low Volt Chg, Separator Penetrated by Neg Plate Material, Pinpoint Shorts Through Separator.		
			25°	446	2	4020	Low Volt Disch, Low Volt Chg, Separator Penetrated by Neg Plate Material, Pinpoint Shorts Through Separator.		
99	25%	1.5	25°	442	4	4020	Low Volt Disch, Low Volt Chg, Separator Penetrated by Neg Plate Material, Pinpoint Shorts Through Separator.		
			40°	429	3	3841	Shorted on Cycling, Separator Penetrated by Neg Plate Material, Pinpoint Shorts Through Separator, Leaked at Neg Terminal, Epoxy Lifted Up.		
			40°	432	2	3841	Failed During Shut Down of Pack, Separator Deteriorated, Separator Impregnated with Neg Plate Material.		
124	25%	1.5	40°	440	1	4853	Low Volt Disch, Low Volt Chg, Separator Deteriorated, Separator Impregnated with Neg Plate Material.		
			0°	410	5	3037	Cell Lost Capacity on Cycling But Came Back When Removed From Pack, So It Was Put Back On Cycling In Same Pack.		

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: <u>Gulton 20 Ampere-Hour</u> FAILURE ANALYSIS
73	25%	1.5	25°	396	3	1776	Low Volt Disch, Normal Volt Chg, Concave Side, Neg Ceramic Seal Broken, Lost 23.7 gm.
			25°	387	1	6120	Low Volt Disch, Low Volt Chg, Lost 13.2 gm, Separator Completely Deteriorated, Neg Plate Material Migration, Pinpoint Penetration, Blistering on Pos Plates, High Pressure Bulge.
74	25%	3.0	25°	458	4	1134	Low Volt Disch, Low Volt Chg, Leaked, Lost 14.2 gm, Blistering on Pos Plates.
			25°	419	3	1302	Low Volt Disch, Normal Volt Chg, Leaked, Lost 21.9 gm.
			25°	440	2	1754	Low Volt Disch, Normal Volt Chg, Leaked Around Both Terminals, Ceramic Broken on Neg Terminal, lost 18.0 gm, Neg Plate Material Penetrated Separator, Sides Concaved, Shorting Case to Bus.
87	40%	1.5	25°	468	1	163	Low Volt Disch, High Volt Chg, High Pres Bulge, Lost 8 gm.
			25°	388	2	208	Low Volt Disch, High Volt Chg, Lost 26.7 gm, Ceramic Short Around Pos Terminal.
			25°	394	3	627	Low Volt Disch, High Volt Chg, Lost 16.4 gm, High Pres Bulge, Deposit on Both Terminals, Ceramic Short Neg to Case.
			25°	454	4	627	Low Volt Disch, Low Volt Chg, Lost 21.6 gm, Deposit on Both Terminals, Sides Concave Hit Bus on Both Sides.
			25°	386	5	627	Low Volt Disch, Low Volt Chg, Lost 18.1 gm, High Pres Bulge, Burnt Separator 5th or 6th Neg Plate Near Top, Ceramic Short.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gulton 20 Ampere-Hour FAILURE ANALYSIS
88	40%	3.0	25°	422	2	151	Low Volt Disch, High Volt Chg, High Pres Bulge, Bottom Ceramic Leak, Lost 25 gm.
				404	1	151	Low Volt Disch, High Volt Chg, High Pres Bulge, Bottom Ceramic Leak, Lost 25 gm.
				466	3	358	Low Volt Disch, High Volt Chg, High Pres Bulge, Lost 16.4 gm.
				429	5	358	Low Volt Disch, Low Volt Chg, Ceramic Short Around Pos Terminal.
				452	4	2824	Low Volt Disch, Low Volt Chg, Short Through Separator at Top of Plates, High Pres Bulge on Sides, High Pres, Separator Deteriorated.
90	25%	1.5	40°	457	5	2824	Low Volt Disch, Normal Volt Chg, Short Through Separator, Blistering on Pos Plate, High Pres Bulge on Sides, High Pres.
				378	3	4045	Normal Volt Disch, Went Dead on Chg During Cap Check, Ceramic Short, Separator Completely Deteriorated.
				395	4	2862	Shorted Out Following Capacity Check, Leaked, Lost 6.8 gm, Deposit on Both Terminals, Both Ceramic Seals Broken, Separator Completely Deteriorated, Neg Plate Material Migration, Separator Very Wet, Plastic Wrap Burned, Ceramic Short.
				412	3	*3385	Shorted on Cycling, High Pressure Bulge, Pos and Neg Plate Material on Separator, Separator Completely Deteriorated.
				435	2	3111	Low Volt Disch, High Volt Chg, Leaked, Lost 24.6 gm, High Pres Bulge, Separator Very Dry.
101	15%	1.5	0°	407	5	3111	Low Volt Disch, High Volt Chg, Leaked, Lost 20.4 gm, Separator Very Dry.
				438	4	3629	Low Volt Disch, High Volt Chg, Leaked, Lost 13.2 gm, High Pres Bulge, Sides Concave, Blistering on Pos Plates.

CELL TYPE: Gulton 20 Ampere-Hour

FAILURE
ANALYSIS

Volt Fell Suddenly at End of Chg, Burn Spots at Busses, Concave Around Spots, End Neg Pushed into Pos Tab.

Low Volt Disch, Normal Volt Chg, Walls Concave, Busses Shorted to Case, Lost 26.9 gm.

High Pres Bulge, Blisters on Pos Plate, Busses Shorted to Case.

Black Deposit on Outside on Neg Terminal, High Pres Bulge, Busses Shorted to Case, Blisters on Pos Plate, Burnt Spot on Separator.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED
102	15%	3.0	0°	449	2	135
115	25%	1.5	0°	490	3	2107
			0°	508	2	2203
			0°	467	4	2291

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gould 20 Ampere-Hour
							FAILURE ANALYSIS
98	25%	1.5	0°	77	5	3556	Low Volt Disch, Low Volt Chg, Separator Deteriorated, Neg Plate Material Penetrated Separator, Two Pos Plates Not Welded to Tabs.
104	25%	1.5	25°	69	1	2672	Low Volt Disch, Low Volt Chg, Shorted at Bottom of Pos Plate, Pos Grid Wire Penetrated Separator, Short at Top Between Pos Grid and Neg Tab, High Pressure.
			25°	R36	5	2826	Low Volt Disch, Low Volt Chg, Short Between Plates, Grid Wire Penetrated Separator, Pos Plate Material Between Plates, High Pressure.
			25°	5	3	2980	Low Volt Disch, Low Volt Chg, Separator Completely Deteriorated, Short Between Plates, High Pressure.
112	15%	1.5	40°	17	1	5005	Low Volt Disch, Low Volt Chg, Short Between Plates, Short About One Inch From Bottom of Plates, Separator Completely Deteriorated, High Pressure.
			40°	25	2	5005	Low Volt Disch, Low Volt Chg, Shorted Through Separator, Shorted on Bottom Corner of Plates, Separator Completely Deteriorated, High Pressure.
			40°	38	5	5213	Low Volt Disch, Low Volt Chg, Short at Top Corner of Plate Where Pos Tabs are Connected to Plates, Separator Deteriorated Allowing Plates to Come Together, Elistering on Pos Plates.
118	40%	1.5	25°	61	2	1747	Low Volt Disch, Low Volt Chg, Short at Bottom of Pos Plate, Grid Wires Penetrated Separator Where Tape Holds Plates Together, High Pressure.
			25°	R91	4	1963	Low Volt Disch, Low Volt Chg, Shorted at Bottom Corner of Pos Plates, Grid Wires Through Separator, Rough Grid Showing Through at Top and Bottom of Most Plates, High Pressure.
			25°	92	5	2937	Low Volt Disch, Low Volt Chg, Short Through Separator on Side of Plates, Pos Plate Material Penetrated Separator, High Pressure.

PAGE NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Gould 20 Ampere-Hour FAILURE ANALYSIS
119	40%	3.0	25°	73	5	222	Normal Volt Disch, Low Volt Chg, Short Near Bottom of 5th or 6th Pos, No Obvious Cause.
			25°	80	2	1793	Low Volt Disch, Normal Volt Chg, Neg Plate Material Penetrated Separator, High Pressure, Blistering on Pos Plate.
			25°	86	3	1793	Low Volt Disch, Normal Volt Chg, Neg Plate Material Penetrated Separator, High Pressure, Blistering on Pos Plate.
122	25%	3.0	40°	16	2	801	Low Volt Disch, Low Volt Chg, Blistering on Pos Plates, Separator Deteriorated, Plate Material on Both Sides of Separator, High Pressure.
			40°	58	3	801	Low Volt Disch, Low Volt Chg, Blistering on Pos Plates, Separator Deteriorated, Plate Material on Both Sides of Separator, High Pressure.
			40°	18	5	983	Low Volt Disch, Low Volt Chg, Plate Material Penetrated Separator, Pos Plates Blistered, High Pressure.
126	25%	1.5	40°	9	3	1273	Low Volt Disch, Low Volt Chg, Shorted at Bottom Corner of Neg Plate, Grid Wire Penetrated Separator, Several Other Plates Had Grid Wires Sticking Out, High Pressure.
			40°	R29	4	1509	Low Volt Disch, Low Volt Chg, Shorted at Bottom Corner of Pos Plate, Grid Wire Penetrated Separator, Blistering on Pos Plates, Separator Deteriorated, High Pressure.
			40°	11	5	1569	Low Volt Disch, Low Volt Chg, Shorted on Side of Pos Plate, Grid Wire Penetrated Separator, High Pressure.

PACK NUMBER	DEPTH OF DISCHARGE	CHARGE PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: <u>Gulton 50 Ampere-Hour</u> FAILURE ANALYSIS
95	25%	1.5	0°	109	3	2643	Shorted Out While Cycling, All Plates Shorted at Bottom Center, Separator Very Dry and Stiff From Heat, Blistering on Pos Plate.
			0°	107	5	2938	Shorted Out While Cycling, Short Between Plates at Center Near Bottom of Plates, Separator Dry, Small Amount of Neg Plate Material Migration on Separator.
			0°	115	1	3227	Low Volt Disch, High Volt Chg, Separator Impregnated with Neg Plate Material, Large Blisters on Pos Plate, One Neg Plate Stuck to Can.
123	15%	1.5	40°	119	2	1873	Low Volt Disch, Low Volt Chg, Separator Decomposed, Hot Spots Through Separator Shorted Out Several Plates, High Pres Bulge, Still Under Pressure When Opened.
			40°	118	3	1873	Went Dead During Shutdown, Separator Decomposed, Several Small Hot Spots on Each Plate, Outside Neg Plates Stuck to Case, High Pres Bulge, Deposit Around Ceramic Seal of Pos Terminal.
			40°	117	4	1873	Went Dead During Shutdown, Separator Decomposed, Neg Plate Stuck to Case, High Pres Bulge, Still Under Pressure When Opened.

PACK NUMBER	DEPTH OF DISCHARGE	ORBIT PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: Yardney 10 x YS-12	
							FAILURE ANALYSIS	
33	50%	24	40°		3	58	Leaked, Dried Out	
					2	126	Leaked, Dried Out	
					1	152	Leaked, Dried Out	
					8	197	Leaked, Dried Out	
					4	210	Leaked, Dried Out	
					10	210	Leaked, Dried Out	
57	50%	24	0°		1	162	Leaked, Electrolyte Shorted Out Cell	
					2	162	Leaked, Electrolyte Shorted Out Cell	
					10	162	Leaked, Electrolyte Shorted Out Cell	
					3	166	Leaked, Electrolyte Shorted Out Cell	
					4	166	Leaked, Electrolyte Shorted Out Cell	
					5	166	Leaked, Electrolyte Shorted Out Cell	
					6	166	Leaked, Electrolyte Shorted Out Cell	
					7	166	Leaked, Electrolyte Shorted Out Cell	
					8	166	Leaked, Electrolyte Shorted Out Cell	
					9	166	Leaked, Electrolyte Shorted Out Cell	

PACK NUMBER	DEPTH OF DISCHARGE	CHARGE PERIOD (HOURS)	TEST TEMPERATURE	CELL NUMBER	POSITION IN PACK	CYCLES COMPLETED	CELL TYPE: <u>Delco 25 Ampere-Hour</u> FAILURE ANALYSIS
75	40%	24	25°			32	Cell Blew-up, Pack Returned to Manufacturer
89	40%	24	25°			80	Returned to Manufacturer for Analysis.
298	40%	3.0	25°			120	Returned to Manufacturer for Analysis.

PACK NUMBER	275	DEPTH OF DISCHARGE	25%	ORBIT PERIOD (HOURS)	42	TEST TEMPERATURE	25°	CELL NUMBER		POSITION IN		CYCLES COMPLETED	139	CELL TYPE: Delco 40 Ampere-Hour FAILURE ANALYSIS	Returned to Manufacturer for Analysis.
----------------	-----	-----------------------	-----	-------------------------	----	---------------------	-----	----------------	--	----------------	--	---------------------	-----	--	--

AMPERE-HOUR CAPACITIES ON PRECONDITIONING AND CAPACITY CHECK CYCLES

TYPE	PACK NUMBER	ORBIT PERIOD (Hours)	DEPTH OF DISCHARGE	TEMPERATURE °C	PRECONDITIONING*		CAPACITY CHECKS AFTER 86-DAY INTERVALS								CYCLES TO PACK FAILURE	
					INITIAL	(See Note)	1 st DAY 88	SECOND 88 DAYS	THIRD 88 DAYS	FOURTH 88 DAYS	FIFTH 88 DAYS	SIXTH 88 DAYS	SEVENTH 88 DAYS	EIGHTH 88 DAYS		
G.E. 3 A.H.	63	1.5	15	0	3.48		3.12	3.12	3.05	3.03	3.05					
	64		25	0	3.50		3.33	3.70	3.30	3.25	3.42					
	15		25	25	4.00		3.38	2.93	2.33	1.95	1.47					
	16		40	25	4.05		2.75	2.10	1.35							5013
	39		15	50/40	1.65	3.42 (772)	2.10	1.53	1.25	1.17	0.70					2569
	40		25	50/40	1.80	3.50 (7440)	0.88*	0.88								
G.E. 3 A.H.	67	3	15	0	3.62		3.55	3.10	3.53	2.97	3.25					
	68		25	0	3.60		3.17	3.53	3.40	3.10	3.25					
	19		25	25	3.60		3.78	2.48	3.15	2.00	2.78					
	20		40	25	3.70		3.00	2.35	2.07	1.03	2.00					
	43		15	50/40	1.74	2.62 (771)	2.20	1.61	1.15							
	44		25	50/40	1.70	2.5 (771)	1.25	1.19	1.12	1.10	0.95					
Gould 3.5 A.H.	51	1.5	15	0	3.60		4.15	3.32	3.41	3.21	3.35					
	52		25	0	3.60		3.15	3.52	3.40	3.50	3.24					
	53		25	25	4.01		3.22	2.90	2.30							
	54		40	25	3.70		2.75	2.37								
	27		15	50/40	1.52	2.62 (772)	2.07	1.95	1.60							
	28		25	50/40	1.55	2.61 (7444)	2.86									
Gould 3.5 A.H.	55	3	15	0	3.27		3.59	3.15	3.38	3.33	3.27					
	56		25	0	3.50		2.91	3.53	3.65	3.41	3.38					
	71		25	25	4.32		4.03	2.79	3.53	2.77	2.28					2464
	8		40	25	4.29		3.65	3.35	3.03							5524
	31		15	50/40	1.60	1.31 (3281)	1.75	1.98	2.16							975
	32		25	50/40	1.55	1.66 (405)	1.49									

* Preconditioning at change to 40° C. Number of cycles completed at 50° C is in parentheses.

** Still at 40° C.

AMPERE-HOUR CAPACITIES ON PRECONDITIONING AND CAPACITY CHECK CYCLES

TYPE	PACK NUMBER	ORBIT PERIOD (Hours)	DEPTH OF DISCHARGE	TEMPERATURE °C	PRECONDITIONING		CAPACITY CHECKS AFTER 88-DAY INTERVALS								CYCLES TO PACK FAILURE
					INITIAL	*	FIRST 88 DAYS	SECOND 88 DAYS	THIRD 88 DAYS	FOURTH 88 DAYS	FIFTH 88 DAYS	SIXTH 88 DAYS	SEVENTH 88 DAYS	EIGHTH 88 DAYS	
Sonotone 5 A.H.	49	1.5	15	0	5.45		5.54	5.50	4.96	4.79	4.71				
	50		25	0	5.04		4.96	4.58	4.25	3.79	3.67				
	1		25	25	5.42		3.67	2.33	2.88	2.79	2.21				
	2		40	25	6.42		4.38	4.17	3.25	3.00					6671
	25		15	50/40	3.08	3.63 (703)	2.25	1.83	2.04	1.17	1.17				
	26		25	50/40	3.17	3.17 (445)	2.75	2.93							3625
Sonotone 5 A.H.	53	3	15	0	5.67		5.79	5.67	5.42	5.33	5.50				
	54		25	0	4.92		3.96	3.96	4.13	3.96	3.75				
	5		25	25	5.71		4.28	3.04	2.04	2.13	2.13				
	6		40	25	5.83		4.50	3.29	3.25	2.92	2.33				
	29		15	50/40	3.33	4.92 (223)	2.75	2.38	2.42	2.08	1.96				
	30		25	50/40	3.75	3.50 (183)	1.88	2.88	2.38	1.67	1.21				
Gulton 6 A.H.	61	1.5	15	0	5.00		5.10	5.40	4.45	3.15	2.60				
	62		25	0	5.00		4.75	3.80	4.35	3.55	3.30				
	13		25	25	5.80		2.95	2.85	2.70						4021
	14		40	25	6.40		3.45								2086
	37		15	50/40	2.75	3.60 (234)	1.70	2.95	1.85	2.00					6064
	38		25	50/40	2.65	2.90 (114)	1.55								1377
Gulton 6 A.H.	65	3	15	0	1.50		5.45	5.35	5.15	4.50	4.50				
	66		25	0	4.25		5.00	3.50	2.50	3.80	3.90				
	17		25	25	5.80		3.65	3.45	2.50	2.30					2825
	18		40	25	4.55		4.95	3.16							1550
	41		15	50/40	2.75	4.55 (234)	2.05	1.63							1684
	42		25	50/40	2.60	3.80 (96)	2.15	2.10	2.35	1.85	1.50				

* Preconditioning at change to 40° C. Number of cycles completed at 50° C is in parentheses.

AMPERE-HOUR CAPACITIES ON PRECONDITIONING AND CAPACITY CHECK CYCLES

TYPE	PACK NUMBER	ORBIT PERIOD (Hours)	DEPTH OF DISCHARGE	TEMPERATURE °C	PRECONDITIONING		CAPACITY CHECKS AFTER 88-DAY INTERVALS								CYCLES TO PACK FAILURE
					INITIAL	*	FIRST 88 DAYS	SECOND 88 DAYS	THIRD 88 DAYS	FOURTH 88 DAYS	FIFTH 88 DAYS	SIXTH 88 DAYS	SEVENTH 88 DAYS	EIGHTH 88 DAYS	
G.E. 12 A.H.	110	1.5	15	0	13.9		12.7	10.4	13.0	12.5	14.1				
	124		25	0	14.2		13.5	12.9	12.8	11.4	11.5				
	88		25	25	15.2		8.00	5.55	5.50	5.40	5.70				
	98		40	25	14.8		6.00	7.65							4020
	85		15	50/40	6.80	8.20 (33%)	5.00	4.70	5.00	4.90	5.00				
	99		25	50/40	6.90	6.00 (19%)	4.90	5.20	4.40						4853
G.E. 12 A.H.	111	3	15	0	14.2		13.2	10.7	11.0	12.1	12.9				
	125		25	0	14.6		13.0	12.1	11.9	12.2	12.9				
	83		25	25	15.2		11.7	8.20	6.13	5.20	4.80				
	97		40	25	14.9		5.60	5.86	7.90	8.20	6.80				
	86		15	50/40	7.10	8.20 (40%)	6.30	3.70	4.00	3.50	2.90				
	100		25	50/40	7.60	9.80 (70%)	3.80	4.70	5.70	5.10					
Gould 20 A.H.	84	1.5	15	0	22.5		27.7	26.5	24.2	24.7	21.7				
	98		25	0	23.1		21.2	15.2	18.7	17.2	17.5				2980
	104		25	25	25.0		18.5	14.0							2937
	118		40	25	24.7		23.3								5213
	112		15	50/40	9.67	6.83 (18%)	15.7	15.3	12.5	12.4					1574
	126		25	50/40	9.00	13.9 (132%)	15.2								
Gould 20 A.H.	80	3	15	0	23.0		23.2	21.5	20.3	25.8					
	94		25	0	23.0		17.5	25.0	18.2	18.8	16.8				
	105		25	25	23.3		23.5	22.2	21.3	21.2	20.7				
	119		40	25	24.8		24.7	21.7							1793
	108		15	50/40	9.50	9.67 (47%)	11.8	14.8	16.8	15.2					
	122		25	50/40	9.33	7.50 (75%)	8.17								983

* Preconditioning at change to 40° C. Number of cycles completed at 50° C is in parentheses.

** Still at 50° C.

AMPERE-HOUR CAPACITIES ON PRECONDITIONING AND CAPACITY CHECK CYCLES

TYPE	PACK NUMBER	ORBIT PERIOD (Hours)	DEPTH OF DISCHARGE	TEMPERATURE °C	PRECONDITIONING		CAPACITY CHECKS AFTER 88-DAY INTERVALS								CYCLES TO PACK FAILURE
					INITIAL	* (See Note)	FIRST 88 DAYS	SECOND 88 DAYS	THIRD 88 DAYS	FOURTH 88 DAYS	FIFTH 88 DAYS	SIXTH 88 DAYS	SEVENTH 88 DAYS	EIGHTH 88 DAYS	
Gulton 20 A.H.	101	1.5	15	0	17.2		12.5	5.67							3631
	115		25	0	17.7		11.2								2283
	73		25	25	23.3		7.17	9.50	7.83	8.67	8.83				627
	87		40	25	23.3										
	76		15	50/40	10.3	13.8 (172)	6.50	4.83	5.50	4.67	5.00				4045
	90		25	50/40	9.00	11.3 (65)	6.00	10.3	7.33						
Gulton 20 A.H.	102	3	15	0	16.7		19.8	25.2	20.3	19.5	17.3				
	116		25	0	21.7		20.7	21.8	19.3	17.5	15.2				1754
	74		25	25	20.3		6.17	7.17							358
	88		40	25	19.8										
	77		15	50/40	9.50	12.7 (71)	7.33	5.33	4.83	5.33	4.67				
	91		25	50/40	9.17	10.3 (47)	6.67	6.67	7.67	6.83	7.17				
Yardney 12 A.H.	57	24	50	0	13.8		8.60								166
	33		50	40	13.5		12.0								210
Gulton 6 A.H.	79	24	50	25	6.60		3.55	4.40	4.25						
G.E. 12 A.H.	93	24	50	40	13.0		7.60	6.50	5.00						349
Gulton 50 A.H.	95	1.5	25	0	57.6		59.6	45.4							3227

* Preconditioning at change to 40° C. Number of cycles completed at 50° C is in parentheses.
 ** Two cells only; pack failed during capacity check.
 *** Changed from 25° to 40° C ambient after 173 cycles.

AMPERE-HOUR CAPACITIES ON PRECONDITIONING AND CAPACITY CHECK CYCLES

TYPE	PACK NUMBER	ORBIT PERIOD (Hours)	DEPTH OF DISCHARGE	TEMPERATURE °C	INITIAL PRECONDI- TIONING	CAPACITY CHECKS AFTER 88-DAY INTERVALS										CYCLES TO PACK FAILURE	
						FIRST 88 DAYS	SECOND 88 DAYS	THIRD 88 DAYS	FOURTH 88 DAYS	FIFTH 88 DAYS	SIXTH 88 DAYS	SEVENTH 88 DAYS	EIGHTH 88 DAYS	NINTH 88 DAYS	TENTH 88 DAYS		
Gulton (Comm.) 4 A.H.	815	1.5	15	0	5.04	3.57	4.03	4.00									
	826		25	0	4.37	4.00	3.37	3.73									
	204		25	25	4.63	2.47	2.07	1.83									
	214		40	25	5.00	2.00	2.07	1.87									
	228		15	40	4.20	1.77	1.67	1.47									
	240		25	40	3.37	1.17	1.13	1.30									
Gulton 12 A.H.	216	1.5	15	0	14.0	14.0											
	301		25	0	14.2	14.5											
	227		25	25	14.1	5.90											
	296		40	25	13.3	4.70											
	78		15	40	6.80	4.30											
	290		25	40	11.4	5.40											
Gulton (HSI) 6 A.H.	213	1.5	25	0	7.30	7.30											
	218		40	25	6.90	3.00											
	238		25	40	5.00	1.75											
Yardney (AgZn)	9	24	42	25	14.0												

AMPERE-HOUR CAPACITIES ON PRECONDITIONING AND CAPACITY CHECK CYCLES

PACK NUMBER	ORBIT PERIOD (Hours)	DEPTH OF DISCHARGE	TEMPERATURE °C	INITIAL PRECONDI- TIONING	CAPACITY CHECKS AFTER 88-DAY INTERVALS										CYCLES TO PACK FAILURE	
					FIRST 88 DAYS	SECOND 88 DAYS	THIRD 88 DAYS	FOURTH 88 DAYS	FIFTH 88 DAYS	SIXTH 88 DAYS	SEVENTH 88 DAYS	EIGHTH 88 DAYS	NINTH 88 DAYS	TENTH 88 DAYS		
Gulton (Nimbus) 5 A.H.	1.5	15	0	5.00												
		25	0													
		15	25	5.25												
		25	25													
		15	40	3.29												
		25	40													
Gulton 6 A.H. (Third elec- trode)	1.5	25	0	7.15												
		40	0	7.25												
		25	25	7.10	3.15											
		40	25	5.95	3.85											
		15	40													
		25	40													
G.S. (Nimbus) 5 A.H.	1.5	15	0	5.42												
		25	0													
		15	25	4.67												
		25	25													
		15	25	3.67												
		25	40													

MFR	CAPACITY A.H.	PACK NO.	TEMP °C	ORBIT PERIOD (HRS)		PERCENT DEPTH OF DISCHARGE	PERCENT OF RECHARGE	CHARGE VOLTAGE LIMIT	CYCLES COVERED			CELLS REMAIN- ING IN PACK	
				DISCHARGE	CHARGE				INITIAL	FINAL	DIFFERENCE	INITIAL	FINAL
G.E. (pages 47-55)	3	63	0	0.5	1.0	15	115	1.55	7804	8004	200	10	10
		64	0	"	"	25	"	"	7751	8254	503	10	10
		15	25	"	"	25	125	1.49	7800	8314	514	10	10
		16	25	"	"	40	"	"	FAILED				
		39	40	"	"	15	160	1.45	7895	7959	64	6	6
		40	40	"	"	25	"	1.41	FAILED				
		67	0	"	2.5	15	115	1.55	5703	5903	200	10	10
		68	0	"	"	25	"	"	5740	5903	163		
		19	25	"	"	25	125	1.49	5712	5903	191	10	10
		20	25	"	"	40	"	"	5557	5903	346	10	10
		43	40	"	"	15	160	1.45	FAILED				
		44	40	"	"	25	"	"	5717	5903	186		
Gould (pages 55-60)	3.5	51	0	"	1.0	15	115	1.55	7321	7714	393	10	10
		52	0	"	"	25	"	"	7321	7714	393	10	10
		3	25	"	"	25	125	1.49	FAILED				
		4	25	"	"	40	"	"	FAILED				
		27	40	"	"	15	160	1.45	FAILED				
		28	40	"	"	25	"	"	FAILED				
		55	0	"	2.5	15	115	1.55	5703	6103	400	10	10
		56	0	"	"	25	"	"	5713	6103	390	10	10
		7	25	"	"	25	125	1.49	5557	6103	546	7	6
		8	25	"	"	40	"	"	FAILED				
		31	40	"	"	15	160	1.45	FAILED				
		32	40	"	"	25	"	1.41	FAILED				

MFR.	CAPACITY A.H.	PACK NO.	TEMP. °C.	ORBIT PERIOD (HRS.)		PERCENT DEPTH OF DISCHARGE	PERCENT OF RECHARGE	CHARGE VOLTAGE LIMIT	CYCLES COVERED		CELLS REMAIN- ING IN PACK		
				DISCHARGE	CHARGE				INITIAL	FINAL	INITIAL	FINAL	
SONOTONE (11/15/54)	5	49	0	0.5	1.0	15	115	1.55	7500	500	1	1	
		50	0	"	"	25	"	"	7400	500	11	11	
		1	25	"	"	25	125	1.49	"	500	"	"	
		2	25	"	"	40	"	"	FAILED	"	"	"	
		25	40	"	"	15	160	1.45	7300	500	1	1	
		26	40	"	"	25	"	"	FAILED	"	"	"	
		53	0	"	2.5	15	115	1.55	5000	500	1	1	
		54	0	"	"	25	"	"	"	"	"	"	
		5	25	"	"	25	125	1.49	"	"	"	"	
		6	25	"	"	40	"	"	"	"	"	"	
		37	40	"	"	15	160	1.45	7300	500	1	1	
		29	40	"	"	25	"	"	"	"	"	"	
GULSON (Pages 7/15)	6	61	0	"	1.0	15	115	1.55	"	500	1	1	
		62	0	"	"	25	"	"	"	"	"	"	
		13	25	"	"	25	125	1.49	FAILED	"	"	"	
		14	25	"	"	40	"	"	FAILED	"	"	"	
		37	40	"	"	15	160	1.45	FAILED	"	"	"	
		38	40	"	"	25	"	"	FAILED	"	"	"	
		65	0	"	2.5	15	115	1.55	"	500	200	1	1
		66	0	"	"	25	"	"	"	500	500	11	11
		17	25	"	"	25	125	1.49	FAILED	"	"	"	"
		18	25	"	"	40	"	"	FAILED	"	"	"	"
		41	40	"	"	15	160	1.45	FAILED	"	"	"	"
		42	40	"	"	25	"	"	"	500	500	1	1

MFR.	CAPACITY A. H.	PACK NO.	TEMP °C.	ORBIT PERIOD (HRS)		PERCENT DEPTH OF DISCHARGE	PERCENT OF RECHARGE	CHARGE VOLTAGE LIMIT	CYCLES COVERED		CELLS REMAIN- ING IN PACK		
				DISCHARGE	CHARGE				INITIAL	FINAL	DIFFERENCE	INITIAL	FINAL
G.E. (pages 76-85)	12	110	0	0.5	1.0	15	115	1.55	7171	7171		5	5
		124	0	"	"	25	"	"	6946	7430	293	5	5
		82	25	"	"	25	125	1.49	7202	7050	479	5	4
		96	25	"	"	40	"	"		FAILED			
		85	40	"	"	15	160	1.45	7060	7553	473	5	5
		99	40	"	"	25	"	"		FAILED			
		111	0	"	2.5	15	115	1.55	3567	3047	239	5	5
		125	0	"	"	25	"	"	3533	3031	222	5	5
		83	25	"	"	25	125	1.49	3011	3000	23	5	5
		97	25	"	"	40	"	"		3010	200	5	5
		36	40	"	"	15	160	1.45	3547	3000	222	5	5
		100	40	"	"	25	"	"	3000	3000	0	5	5
GOULD (pages 94-99)	20	84	0	"	1.0	15	115	1.55	7430	7430		5	5
		98	0	"	"	25	"	"	6700	7000	200	5	5
		104	25	"	"	25	125	1.49		FAILED			
		118	25	"	"	40	"	"		FAILED			
		112	40	"	"	15	160	1.45		FAILED			
		126	40	"	"	25	"	1.41		FAILED			
		90	0	"	2.5	15	115	1.55	3531	3030	239	5	5
		94	0	"	"	25	"	"	3532	3031	222	5	5
		105	25	"	"	25	125	1.49	3571	3000	222	5	5
		119	25	"	"	40	"	"		FAILED			
		108	40	"	"	15	160	1.45	3000	3000	0	5	5
		122	40	"	"	25	"	1.41		FAILED			

MFR	CAPACITY A.H.	PACK NO.	TEMP °C	ORBIT PERIOD (HRS)		PERCENT DEPTH OF DISCHARGE	PERCENT OF RECHARGE	CHARGE VOLTAGE LIMIT	CYCLES COVERED		CELLS REMAIN- ING IN PACK	
				DISCHARGE	CHARGE				INITIAL	FINAL	INITIAL	FINAL
GULTON (pages 72-75)	20	101	0	0.5	1.0	15	115	1.55		FAILED		
		115	0	"	"	25	"	"		FAILED		
		73	25	"	"	25	125	1.49			3	5
		87	25	"	"	40	"	"		FAILED		
		76	40	"	"	15	160	1.45			5	5
		90	40	"	"	25	"	"		FAILED		
		102	0	"	2.5	15	115	1.55			4	4
		116	0	"	"	25	"	"			5	5
		74	25	"	"	25	125	1.49		FAILED		
		88	25	"	"	40	"	"		FAILED		
G.E. NIMBUS (pages 98-101)	5	77	40	"	"	15	160	1.45				
		91	40	"	"	25	"	"			4	5
		103	0	"	1.0	15	110	1.49			5	5
				"	"	25	"	"				
		106	25	"	"	15	120	"			5	5
				"	"	25	"	"				
		113	40	"	"	15	130	"	1.5	533	5	5
				"	"	25	"	"				
		117	0	"	"	15	110	"	1	364	5	5
				"	"	25	"	"				
GULTON NIMBUS (pages 101-103)	5	120	25	"	"	15	120	"	1	465	5	5
				"	"	25	"	"				
		127	40	"	"	15	130	"	1	511	5	5
				"	"	25	"	"				

MFR.	CAPACITY A. H.	PACK NO.	TEMP °C	ORBIT PERIOD (HRS)		PERCENT DEPTH OF DISCHARGE	PERCENT OF RECHARGE	CHARGE VOLTAGE LIMIT	CYCLES COVERED		CELLS REMAIN- ING IN PACK	
				DISCHARGE	CHARGE				INITIAL	FINAL	INITIAL	FINAL
YARDNEY	12	57	0	1.0	23.0	50	*	1.50		FAILED		
		33	40	"	"	"	*	1.50		FAILED		
	6	79	25	1.0	23.0	50	200	1.49	382	427	3	3
G.E. (page 104)	12	93	25*	1.0	23.0	50	200**	1.49**		FAILED		
GULTON (page 105)	50	95	0	0.5	1.0	25	115	1.55		FAILED		
		123	40	"	"	15	160	1.45		FAILED		
DELCO (pages 105)	25	75	25	1.0	23.0	40	*	1.97		FAILED		
		89	25	"	"	"	*	"		FAILED		
		288	25	0.5	2.5	"	*	"		DISCONTINUED		
	(MOON) →	188	25	"	"	"	*	"	24	225	5	0
DELCO (pages 106)	40	275	25	1.0	23.0	25	*	1.97		DISCONTINUED		
YARDNEY (page 106)	12	9	25	1.0	23.0	42 (5 amp)	500 no.	1.97	1	13	10	10

* DOES NOT APPLY.
 ** CHANGED TO 40°C, 1.45 V/CELL LIMIT AFTER CYCLE 173.
 *** CHANGED TO 25°C, 1.45 V/CELL LIMIT AFTER CYCLE 27.

MFR.	CAPACITY A.M.	PACK NO.	TEMP. °C.	ORBIT		PERIOD (HRS.) CHARGE	PERCENT DEPTH OF DISCHARGE	PERCENT OF RECHARGE	CHARGE VOLTAGE LIMIT	CYCLES COVERED		DIFFERENCE	CELLS REMAIN- ING IN PACK	
				DISCHARGE	CHARGE					INITIAL	FINAL		INITIAL	FINAL
GULTON (pages 167-172)	4	315	0	0.5	1.0	15	115	1.55	4/33	4/34	0.01	5	5	
		326	0	"	"	25	"	"	4/35	4/36	0.01	5	5	
		204	25	"	"	25	125	1.49	4/35	4/36	0.01	5	5	
		214	25	"	"	40	"	"	3/35	4/36	0.01	5	5	
		228	40	"	"	15	160	1.45	4/34	4/35	0.01	5	5	
		240	40	"	"	25	"	"	4/34	4/35	0.01	5	5	
GULTON (pages 173-178)	12	216	0	"	"	15	115	1.55	1/34	1/35	0.01	5	5	
		201	0	"	"	25	115	1.55	1/34	1/35	0.01	5	5	
		227	25	"	"	25	125	1.49	1/34	1/35	0.01	5	5	
		296	25	"	"	40	125	1.44	1/34	1/35	0.01	5	5	
		78	40	"	"	15	160	1.45	1/34	1/35	0.01	5	5	
		290	40	"	"	25	160	1.45	1/34	1/35	0.01	5	5	
GULTON (pages 179-181)	(HSI) 6	213	0	"	"	25	115	1.55	1/34	1/35	0.01	5	5	
		218	25	"	"	40	125	1.49	1/34	1/35	0.01	5	5	
		238	40	"	"	25	160	1.45	1/34	1/35	0.01	5	5	
						</								

A.F.R.	CAPACITY A.H.	PACK NO.	TEMP °C.	ORBIT PERIOD (HRS.)		PERCENT DEPTH OF DISCHARGE	PERCENT OF RECHARGE	CHARGE VOLTAGE LIMIT	CYCLES COVERED		DIFFERENCE	CELLS REMAINING IN PACK	
				DISCHARGE	CHARGE				INITIAL	FINAL		INITIAL	FINAL
CATION	6 (T11180 ELECTRODE)	59	1	0.5	1.0	25	—	—	171	654	483	5	5
		7	0	"	"	40	—	—	177	656	479	5	5
		11	35	"	"	40	—	—	1023	1624	531	5	5
		23	3	"	"	25	—	—	1051	1625	554	5	5
		35	40	"	"	15	—	—					
		47	40	"	"	25	—	—	1	218	219	5	5

PACK NO. 63
G.E. 3 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115
TEST TEMPERATURE 0 C
ORIENT PERIOD 90 MIN.

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES										END OF DISCHARGE
			1	2	3	4	5	6	7	8	9	10	
7846.	12.43	.90	1.25	1.14	1.26	1.24	1.23	1.25	1.24	1.24	1.25	1.25	1.25
7887.	12.31	.90	1.23	1.23	1.23	1.21	1.22	1.23	1.23	1.25	1.23	1.22	1.22
7925.	12.32	.90	1.23	1.23	1.23	1.22	1.23	1.23	1.23	1.25	1.23	1.22	1.22
7999.	12.29	.90	1.23	1.23	1.24	1.22	1.22	1.23	1.23	1.25	1.22	1.22	1.22
8031.	12.28	.90	1.23	1.23	1.23	1.21	1.22	1.22	1.23	1.25	1.22	1.22	1.22
8073.	12.27	.90	1.22	1.23	1.23	1.21	1.22	1.23	1.22	1.26	1.22	1.22	1.22
8119.	12.29	.90	1.23	1.23	1.23	1.22	1.22	1.23	1.23	1.26	1.22	1.22	1.22
8143.	12.23	.90	1.23	1.23	1.23	1.22	1.22	1.23	1.23	1.26	1.22	1.22	1.22
8207.	12.31	.90	1.23	1.23	1.23	1.22	1.22	1.23	1.23	1.26	1.23	1.22	1.22
8239.	12.28	.90	1.23	1.23	1.23	1.21	1.22	1.22	1.23	1.25	1.22	1.22	1.22
8271.	12.32	.90	1.23	1.23	1.24	1.22	1.22	1.22	1.23	1.26	1.22	1.22	1.23
8301.	12.27	.90	1.23	1.23	1.23	1.21	1.22	1.22	1.22	1.25	1.22	1.22	1.22
8327.	12.26	.90	1.23	1.23	1.23	1.21	1.22	1.22	1.22	1.25	1.22	1.22	1.22
7846.	15.49	.52	1.61	1.43	1.60	1.55	1.63	1.62	1.52	1.51	1.47	1.53	1.53
7887.	15.50	.23	1.59	1.47	1.59	1.54	1.62	1.61	1.52	1.55	1.47	1.53	1.53
7925.	15.52	.22	1.59	1.46	1.60	1.54	1.63	1.62	1.52	1.57	1.47	1.52	1.52
7999.	15.48	.22	1.59	1.46	1.59	1.54	1.62	1.61	1.51	1.60	1.46	1.51	1.51
8031.	15.50	.22	1.59	1.46	1.59	1.54	1.62	1.61	1.51	1.60	1.46	1.51	1.51
8073.	15.49	.23	1.59	1.46	1.59	1.54	1.62	1.60	1.51	1.60	1.46	1.52	1.52
8119.	15.49	.22	1.60	1.46	1.59	1.54	1.62	1.61	1.51	1.60	1.46	1.52	1.52
8143.	15.49	.21	1.60	1.47	1.60	1.55	1.62	1.61	1.52	1.61	1.47	1.53	1.53
8207.	15.50	.22	1.60	1.46	1.59	1.54	1.62	1.61	1.50	1.60	1.46	1.52	1.52
8239.	15.49	.22	1.60	1.46	1.59	1.54	1.62	1.61	1.51	1.60	1.46	1.52	1.52
8271.	15.50	.22	1.60	1.46	1.59	1.54	1.62	1.61	1.50	1.61	1.46	1.52	1.52
8301.	15.49	.24	1.60	1.46	1.59	1.54	1.62	1.61	1.50	1.61	1.46	1.51	1.51
8327.	15.49	.23	1.60	1.46	1.59	1.54	1.62	1.61	1.50	1.60	1.46	1.52	1.52

PACK NO. 64
G.E. 3 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES										END OF DISCHARGE
			1	2	3	4	5	6	7	8	9	10	
7816.	12.01	1.50	1.20	1.21	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.19
7854.	12.05	1.49	1.20	1.21	1.20	1.20	1.20	1.20	1.21	1.21	1.22	1.20	1.19
7916.	12.05	1.50	1.20	1.21	1.20	1.21	1.20	1.20	1.21	1.21	1.22	1.21	1.19
7928.	12.00	1.50	1.20	1.21	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.19
7951.	12.00	1.50	1.20	1.20	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.18
8002.	12.02	1.50	1.20	1.20	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.19
8047.	12.03	1.50	1.20	1.21	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.19
8072.	11.93	1.49	1.20	1.21	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.19
8103.	12.05	1.49	1.21	1.21	1.20	1.21	1.20	1.20	1.21	1.21	1.22	1.21	1.20
8134.	12.00	1.50	1.20	1.20	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.19
8156.	12.00	1.49	1.20	1.21	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.19
8200.	11.98	1.50	1.20	1.20	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.18
8254.	11.99	1.50	1.20	1.20	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.18
8256.	11.99	1.50	1.20	1.20	1.20	1.20	1.20	1.19	1.20	1.20	1.21	1.20	1.19
7816.	15.52	.86	1.56	1.51	1.54	1.60	1.52	1.49	1.49	1.49	1.63	1.55	1.60
7854.	15.52	.33	1.55	1.55	1.53	1.59	1.53	1.49	1.49	1.49	1.65	1.53	1.59
7916.	15.52	.30	1.55	1.56	1.54	1.61	1.51	1.49	1.48	1.48	1.66	1.55	1.60
7928.	15.53	.32	1.55	1.56	1.54	1.60	1.52	1.48	1.48	1.48	1.65	1.54	1.60
7951.	15.54	.30	1.55	1.56	1.54	1.61	1.51	1.48	1.48	1.48	1.65	1.54	1.60
8002.	15.52	.31	1.55	1.56	1.54	1.61	1.50	1.49	1.48	1.48	1.65	1.54	1.60
8047.	15.51	.31	1.55	1.56	1.54	1.60	1.50	1.48	1.48	1.48	1.65	1.54	1.60
8072.	15.50	.32	1.56	1.57	1.55	1.61	1.51	1.49	1.49	1.49	1.66	1.55	1.61
8103.	15.51	.31	1.55	1.57	1.54	1.60	1.51	1.48	1.48	1.48	1.65	1.54	1.61
8134.	15.50	.31	1.55	1.57	1.54	1.60	1.51	1.48	1.48	1.48	1.65	1.54	1.60
8166.	15.53	.30	1.56	1.57	1.54	1.60	1.52	1.48	1.48	1.48	1.65	1.54	1.61
8200.	15.46	.29	1.55	1.56	1.54	1.60	1.51	1.47	1.47	1.47	1.63	1.54	1.60
8234.	15.45	.29	1.55	1.57	1.54	1.60	1.50	1.48	1.48	1.47	1.62	1.54	1.60
8256.	15.40	.32	1.55	1.56	1.54	1.59	1.51	1.48	1.48	1.47	1.61	1.53	1.58

PACK NO. 15
G.E. 3 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES					END OF DISCHARGE				
			1	2	3	4	5	6	7	8	9	10
7842.	11.60	1.51	1.18	1.06	1.18	1.17	1.14	1.19	1.12	1.13	1.18	1.15
7883.	11.11	1.52	1.15	1.15	1.13	1.13	1.06	1.16	1.09	.99	1.14	1.08
7921.	11.07	1.52	1.15	1.15	1.14	1.13	1.06	1.16	1.01	1.03	1.14	1.07
7995.	10.99	1.51	1.15	1.15	1.13	1.13	1.08	1.16	1.01	.96	1.13	1.07
8027.	10.90	1.51	1.15	1.15	1.13	1.12	1.04	1.16	.95	.96	1.14	1.06
8064.	10.36	1.51	1.16	1.16	1.14	1.14	1.08	1.17	.26	1.00	1.15	1.03
8124.	10.39	1.52	1.15	1.15	1.16	1.13	1.16	1.16	.00	1.15	1.17	1.14
8156.	10.33	1.51	1.15	1.15	1.16	1.14	1.15	1.16	.00	1.12	1.17	1.13
8188.	10.32	1.51	1.16	1.16	1.16	1.15	1.16	1.17	.00	1.04	1.17	1.14
8218.	9.14	1.51	1.15	1.15	1.15	1.15	1.15	1.16	.00	.11	1.17	1.12
8244.	9.04	1.51	1.14	1.15	1.16	1.14	1.13	1.16	.00	.11	1.16	1.09
7842.	14.65	.94	1.49	1.46	1.45	1.46	1.44	1.49	1.43	1.44	1.46	1.51
7883.	14.59	.93	1.48	1.51	1.44	1.44	1.42	1.49	1.43	1.44	1.45	1.48
7921.	14.57	.94	1.48	1.50	1.44	1.45	1.42	1.49	1.42	1.44	1.44	1.47
7995.	14.59	.93	1.48	1.51	1.44	1.45	1.42	1.49	1.42	1.44	1.44	1.48
8027.	14.58	.93	1.49	1.50	1.44	1.45	1.42	1.49	1.42	1.44	1.45	1.47
8064.	14.61	.94	1.49	1.50	1.44	1.45	1.42	1.49	1.42	1.45	1.45	1.48
8124.	13.20	.94	1.48	1.50	1.44	1.45	1.42	1.49	.00	1.45	1.45	1.50
8156.	13.22	.94	1.48	1.51	1.44	1.46	1.45	1.49	.00	1.44	1.46	1.50
8188.	13.18	.94	1.48	1.50	1.44	1.45	1.44	1.48	.00	1.43	1.45	1.50
8218.	13.20	.94	1.48	1.50	1.44	1.45	1.44	1.49	.00	1.43	1.45	1.50
8244.	13.23	.94	1.49	1.51	1.45	1.46	1.44	1.49	.00	1.44	1.46	1.50

PACK NO. 39
G.E. 3 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE .90

CELL VOLTAGES

	1	2	3	4	5	6	7	8	9	10	END OF DISCHARGE
7378.	.00	.00	1.20	1.17	1.15	.00	.00	1.16	1.13	1.20	
7419.	.00	.00	1.13	1.04	1.14	.00	.00	1.11	.94	1.16	
7505.	.00	.00	1.14	1.10	1.15	.00	.00	1.13	1.08	1.13	
7531.	.00	.00	1.11	1.06	1.13	.00	.00	1.12	1.11	1.13	
7563.	.00	.00	1.10	.99	1.13	.00	.00	1.13	1.10	1.12	
7695.	.00	.00	1.12	1.01	1.13	.00	.00	1.11	1.11	1.11	
7651.	.00	.00	1.11	1.12	1.14	.00	.00	1.11	1.07	1.08	
7675.	.00	.00	1.11	1.07	1.15	.00	.00	1.10	1.09	1.07	
7739.	.00	.00	1.13	1.07	1.16	.00	.00	1.13	1.12	1.11	
7771.	.00	.00	1.10	1.05	1.13	.00	.00	1.08	1.13	1.09	
7803.	.00	.00	1.15	1.11	1.13	.00	.00	1.15	1.11	1.12	
7833.	.00	.00	1.12	1.13	1.13	.00	.00	1.12	1.12	1.16	
7859.	.00	.00	1.10	1.05	1.11	.00	.00	1.09	.97	1.06	
.72	.00	.00	1.41	1.40	1.41	.00	.00	1.42	1.40	1.43	END OF CHARGE
7378.	.00	.00	1.40	1.40	1.41	.00	.00	1.41	1.41	1.43	
7419.	.00	.00	1.42	1.41	1.41	.00	.00	1.42	1.41	1.42	
7505.	.00	.00	1.41	1.41	1.41	.00	.00	1.42	1.41	1.42	
7531.	.00	.00	1.41	1.41	1.41	.00	.00	1.42	1.41	1.42	
7563.	.00	.00	1.41	1.41	1.41	.00	.00	1.42	1.41	1.42	
7605.	.00	.00	1.41	1.42	1.42	.00	.00	1.42	1.42	1.42	
7651.	.00	.00	1.42	1.42	1.42	.00	.00	1.43	1.42	1.42	
7675.	.00	.00	1.42	1.42	1.42	.00	.00	1.42	1.42	1.42	
7739.	.00	.00	1.42	1.41	1.42	.00	.00	1.43	1.42	1.43	
7771.	.00	.00	1.41	1.41	1.42	.00	.00	1.42	1.41	1.41	
7803.	.00	.00	1.41	1.41	1.40	.00	.00	1.42	1.40	1.41	
7833.	.00	.00	1.41	1.41	1.41	.00	.00	1.41	1.40	1.42	
7859.	.00	.00	1.40	1.41	1.40	.00	.00	1.41	1.40	1.42	

PACK NO. 67
G.E. 3 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 3 HOURS

CYCLE PACK CURRENT
NO. VOLTAGE 0.90

CELL VOLTAGES

6 7 8 9 10

END OF
DISCHARGE

3763.	12.30	.89	1.23	1.23	1.21	1.22	1.23	1.23	1.23	1.25	1.22	1.23
3782.	12.30	.89	1.23	1.23	1.21	1.23	1.23	1.24	1.23	1.23	1.22	1.23
3822.	12.28	.89	1.23	1.23	1.21	1.23	1.22	1.24	1.23	1.24	1.21	1.23
3854.	12.34	.90	1.24	1.13	1.22	1.23	1.23	1.25	1.24	1.24	1.23	1.25
3894.	12.25	.90	1.23	1.24	1.22	1.23	1.23	1.24	1.24	1.25	1.22	1.23
3927.	12.27	.90	1.22	1.23	1.21	1.22	1.22	1.24	1.23	1.24	1.21	1.23
3958.	12.29	.89	1.23	1.23	1.21	1.23	1.22	1.23	1.23	1.25	1.22	1.23
3985.	12.39	.90	1.24	1.25	1.25	1.24	1.24	1.25	1.24	1.26	1.23	1.24

3763.	15.10	.21	1.56	1.43	1.43	1.51	1.56	1.55	1.52	1.43	1.51	1.54
3782.	15.14	.06	1.57	1.42	1.42	1.55	1.57	1.54	1.54	1.46	1.55	1.52
3822.	15.78	.04	1.52	1.42	1.41	1.47	1.54	1.51	1.48	1.46	1.49	1.50
3854.	15.10	.06	1.56	1.43	1.43	1.51	1.57	1.55	1.52	1.47	1.51	1.55
3894.	15.09	.05	1.55	1.44	1.43	1.50	1.56	1.57	1.53	1.49	1.51	1.57
3927.	15.04	.05	1.55	1.42	1.42	1.50	1.56	1.55	1.52	1.47	1.52	1.54
3958.	15.48	.09	1.53	1.44	1.45	1.58	1.58	1.59	1.57	1.54	1.57	1.58
3985.	15.53	.08	1.50	1.45	1.47	1.53	1.60	1.60	1.57	1.54	1.56	1.59

END OF
CHARGE

PACK NO. 68
G.E. 3 A.H.

DEPTH OF DISCHARGE 25 TEST TEMPERATURE 0 C
PERCENT OF RECHARGE 115 ORBIT PERIOD 3 HOURS

CYCLE PACK CURRENT
NO. VOLTAGE 1.50

CELL VOLTAGES

1	2	3	4	5	6	7	8	9	10
3824. 12.02 1.50	1.19	1.20	1.20	1.20	1.20	1.21	1.21	1.20	1.20
3861. 12.01 1.50	1.19	1.20	1.20	1.20	1.20	1.21	1.21	1.19	1.20
3898. 12.01 1.50	1.19	1.19	1.20	1.20	1.20	1.21	1.21	1.19	1.20
3933. 12.00 1.50	1.19	1.20	1.20	1.21	1.20	1.21	1.22	1.20	1.20
3966. 12.03 1.50	1.19	1.20	1.20	1.20	1.20	1.21	1.22	1.20	1.20
3997. 12.02 1.50	1.19	1.19	1.20	1.20	1.20	1.21	1.22	1.19	1.20

END OF
DISCHARGE

34
3824. 15.38 .08
3861. 15.45 .10
3898. 15.46 .10
3933. 15.42 .10
3966. 15.45 .10
3997. 15.47 .11

END OF
CHARGE

1.61	1.62	1.51	1.58	1.57	1.57	1.45	1.62	1.41	1.44
1.61	1.62	1.53	1.58	1.58	1.59	1.46	1.62	1.41	1.44
1.61	1.62	1.54	1.58	1.58	1.58	1.46	1.62	1.41	1.45
1.60	1.62	1.55	1.58	1.58	1.59	1.46	1.62	1.42	1.45
1.61	1.62	1.56	1.57	1.58	1.58	1.46	1.62	1.41	1.45
1.60	1.62	1.56	1.58	1.59	1.59	1.46	1.62	1.40	1.45

PACK NO. 19
G.E. 3 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES										END OF DISCHARGE
			1	2	3	4	5	6	7	8	9	10	
3772.	12.03	1.51	1.20	1.20	1.20	1.20	1.20	1.20	1.20	1.21	1.20	1.20	
3791.	12.05	1.50	1.20	1.20	1.20	1.20	1.20	1.21	1.20	1.22	1.20	1.20	
3831.	12.04	1.51	1.20	1.20	1.20	1.21	1.20	1.21	1.20	1.21	1.20	1.20	
3863.	12.10	1.50	1.21	1.11	1.21	1.22	1.20	1.22	1.21	1.21	1.22	1.22	
3903.	12.03	1.51	1.21	1.21	1.21	1.21	1.21	1.22	1.21	1.22	1.20	1.21	
3936.	12.01	1.52	1.20	1.20	1.20	1.21	1.20	1.21	1.20	1.21	1.19	1.20	
3967.	11.97	1.52	1.19	1.20	1.19	1.20	1.19	1.20	1.19	1.21	1.19	1.20	
3995.	12.00	1.51	1.20	1.20	1.20	1.21	1.20	1.21	1.20	1.21	1.19	1.20	
3772.	14.59	.38	1.44	1.44	1.43	1.44	1.43	1.51	1.43	1.50	1.44	1.51	
3791.	14.59	.25	1.44	1.44	1.43	1.44	1.43	1.51	1.44	1.50	1.44	1.51	
3831.	14.62	.26	1.44	1.44	1.44	1.44	1.44	1.52	1.44	1.50	1.44	1.51	
3863.	14.62	.26	1.44	1.42	1.44	1.44	1.44	1.51	1.44	1.48	1.45	1.52	
3903.	14.58	.27	1.45	1.45	1.44	1.44	1.44	1.52	1.44	1.51	1.44	1.52	
3936.	14.58	.29	1.44	1.44	1.44	1.43	1.44	1.51	1.43	1.50	1.43	1.51	
3967.	14.46	.18	1.43	1.43	1.43	1.43	1.42	1.50	1.43	1.46	1.43	1.49	
3995.	14.49	.16	1.43	1.43	1.43	1.44	1.43	1.51	1.43	1.49	1.43	1.51	

PACK NO. 20
G.E. 3 A.H.
DEPTH OF DISCHARGE 40
PERCENT OF RECHARGE 125
TEST TEMPERATURE 25 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES										DISCHARGE END OF
			1	2	3	4	5	6	7	8	9	10	
3618.	11.15	2.39	1.15	1.10	1.08	1.11	1.10	1.11	1.12	1.11	1.14	1.12	
3639.	10.97	2.38	1.14	1.08	1.05	1.09	1.09	1.11	1.08	1.13	1.13	1.11	
3676.	10.70	2.40	1.14	1.06	1.02	1.07	.94	1.06	1.09	1.12	1.12	1.11	
3704.	9.55	2.39	1.14	.91	1.01	1.07	.11	1.05	1.09	1.13	1.13	1.12	
3734.	10.06	2.40	1.14	1.11	1.09	1.11	.00	1.13	1.12	1.13	1.12	1.12	
3765.	9.39	2.40	1.13	1.00	.94	1.03	.00	.97	1.09	1.00	1.13	1.11	
3793.	10.16	2.40	1.14	1.12	1.13	1.13	.00	1.14	1.12	1.14	1.13	1.12	

6C	1.49	1.47	1.44	1.46	1.44	1.48	1.49	1.47	1.47	1.49	END OF CHARGE
3618.	1.49	1.47	1.44	1.46	1.44	1.48	1.49	1.47	1.47	1.49	1.49
3639.	1.49	1.47	1.44	1.46	1.44	1.49	1.49	1.47	1.47	1.49	1.49
3676.	1.50	1.47	1.44	1.46	1.43	1.48	1.50	1.47	1.48	1.50	1.50
3704.	1.50	1.45	1.45	1.47	1.43	1.49	1.50	1.46	1.48	1.51	1.51
3734.	1.48	1.48	1.45	1.47	.00	1.49	1.49	1.47	1.46	1.49	1.49
3765.	1.46	1.49	1.40	1.40	.00	1.42	1.43	1.42	1.47	1.45	1.45
3793.	1.48	1.48	1.45	1.46	.00	1.49	1.48	1.46	1.48	1.50	1.50

PACK NO. 44
G.E. 3 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 3 HOURS

CYCLE NO. PACK CURRENT
VOLTAGE 1.50

CELL VOLTAGES
1 2 3 4 5

6 7 8 9 10

END OF
DISCHARGE

3548.	10.01	1.50	1.10	1.13	1.10	1.12	1.12	.00	1.14	1.10	1.12	1.07
3569.	9.92	1.50	1.09	1.12	1.08	1.12	1.10	.00	1.13	1.09	1.12	1.05
3606.	9.77	1.50	1.06	1.11	1.05	1.11	1.08	.00	1.12	1.07	1.10	1.03
3643.	9.67	1.50	1.05	1.10	1.04	1.10	1.07	.00	1.11	1.06	1.10	1.00
3678.	9.70	1.50	1.07	1.11	1.05	1.12	1.08	.00	1.12	1.05	1.11	1.02
3711.	9.81	1.50	1.08	1.11	1.08	1.12	1.09	.00	1.12	1.05	1.12	1.04
3742.	9.76	1.50	1.07	1.11	1.03	1.11	1.08	.00	1.12	1.06	1.10	1.07
3770.	9.42	1.50	1.03	1.09	.98	1.10	1.06	.00	1.10	.95	1.08	1.03

END OF
CHARGE

3548.	12.86	.48	1.41	1.45	1.43	1.41	1.41	.00	1.43	1.46	1.41	1.43
3569.	12.87	.43	1.41	1.46	1.43	1.41	1.41	.00	1.43	1.46	1.41	1.43
3606.	12.83	.45	1.41	1.45	1.43	1.41	1.41	.00	1.42	1.46	1.40	1.43
3643.	12.84	.44	1.41	1.45	1.43	1.41	1.41	.00	1.43	1.46	1.41	1.43
3678.	12.83	.43	1.41	1.46	1.42	1.41	1.41	.00	1.43	1.46	1.41	1.43
3711.	12.86	.44	1.42	1.46	1.44	1.42	1.41	.00	1.43	1.46	1.41	1.44
3742.	12.72	.45	1.42	1.46	1.44	1.42	1.41	.00	1.41	1.44	1.40	1.42
3770.	12.71	.46	1.40	1.44	1.41	1.40	1.39	.00	1.41	1.44	1.40	1.42

55

PACK NO. 51
GOULD 3.5 A.H.

DEPTH OF DISCHARGE	15
PERCENT OF RECHARGE	115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK VOLTAGE CURRENT

CELL VOLTAGES

1	2	3	4	5	6	7	8	9	10
1	2	3	4	5	6	7	8	9	10

**END OF
DISCHARGE**

**END OF
CHARGE**

7863.	12.60	1.06	1.26	1.14	1.23	1.23	1.29	1.24	1.26	1.26	1.25	1.25	1.29
7904.	12.44	1.05	1.24	1.23	1.22	1.22	1.26	1.23	1.24	1.26	1.25	1.25	1.29
7942.	12.43	1.05	1.24	1.23	1.22	1.22	1.25	1.23	1.24	1.26	1.25	1.25	1.29
8016.	12.39	1.05	1.24	1.23	1.22	1.22	1.25	1.23	1.25	1.24	1.23	1.23	1.29
8048.	12.37	1.05	1.24	1.23	1.22	1.22	1.24	1.23	1.24	1.23	1.24	1.24	1.29
8090.	12.38	1.05	1.24	1.23	1.21	1.21	1.26	1.23	1.24	1.22	1.25	1.25	1.29
8136.	12.38	1.05	1.24	1.23	1.22	1.22	1.25	1.23	1.24	1.21	1.25	1.26	1.29
8160.	12.52	1.05	1.24	1.23	1.22	1.22	1.25	1.23	1.24	1.21	1.25	1.26	1.29
8224.	12.39	1.05	1.24	1.23	1.22	1.22	1.26	1.23	1.24	1.20	1.25	1.26	1.29
8256.	12.32	1.05	1.24	1.23	1.22	1.22	1.24	1.23	1.24	1.19	1.25	1.24	1.29
8288.	12.33	1.05	1.24	1.23	1.22	1.22	1.76	1.23	1.25	1.20	1.25	1.26	1.29
8318.	12.32	1.05	1.24	1.23	1.22	1.22	1.44	1.23	1.24	1.19	1.25	1.24	1.29
8344.	12.32	1.05	1.23	1.23	1.21	1.21	1.25	1.23	1.24	1.19	1.25	1.25	1.29

[illegible]

PACK NO. 52
GOULD 3.5 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 1.75

CELL VOLTAGES

1 2 3 4 5 6 7 8 9 10

7714.	10.48	1.76	1.18	1.11	1.18	1.19	1.19	1.16	.12	1.14	1.22
7752.	10.14	1.76	1.20	.74	1.19	1.19	1.20	1.17	.12	1.13	1.21
7826.	12.22	1.76	1.22	1.22	1.20	1.21	1.21	1.23	.120	1.24	1.23
7858.	10.75	1.76	1.21	1.21	1.19	1.20	1.20	1.21	.21	1.23	1.22
7916.	10.86	1.76	1.21	1.22	1.19	1.20	1.20	1.19	.00	1.22	1.21
7940.	10.93	1.75	1.21	1.22	1.20	1.21	1.21	1.19	.00	1.23	1.22
7982.	10.86	1.75	1.20	1.21	1.20	1.20	1.20	1.19	.00	1.21	1.21
8016.	10.87	1.76	1.21	1.21	1.20	1.20	1.21	1.21	.00	1.21	1.21
8038.	10.86	1.77	1.21	1.20	1.20	1.20	1.21	1.21	.00	1.21	1.21

END OF
DISCHARGE

7714.	14.83	1.00	1.46	1.43	1.56	1.54	1.55	1.48	1.44	1.44	1.52
7752.	14.83	.57	1.50	1.43	1.55	1.52	1.54	1.47	1.45	1.43	1.48
7826.	15.44	.60	1.59	1.46	1.58	1.56	1.57	1.66	1.47	1.51	1.54
7858.	15.47	.60	1.57	1.48	1.58	1.55	1.57	1.53	1.46	1.59	1.52
7916.	13.95	.59	1.57	1.53	1.58	1.55	1.57	1.50	.00	1.55	1.50
7940.	13.96	.58	1.56	1.50	1.58	1.56	1.57	1.50	.00	1.57	1.52
7982.	13.99	.57	1.58	1.54	1.59	1.56	1.58	1.52	.00	1.55	1.53
8016.	13.96	.62	1.57	1.5	1.59	1.56	1.58	1.55	.00	1.54	1.52
8038.	13.93	.65	1.57	1.55	1.59	1.56	1.58	1.54	.00	1.54	1.52

END OF
CHARGE

DEPTH OF DISCHARGE	15	TEST TEMPERATURE	0 C
PERCENT OF RECHARGE	115	ORBIT PERIOD	3 HOURS

CELL VOLTAGES

TEST TEMPERATURE 0 C
ORBIT PERIOD 3 HOURS

3793.	12.35	1.05	1.23	1.24	1.23	1.22	1.23	1.23	1.23	1.23	1.25	1.23	1.23	1.23
3812.	12.36	1.05	1.23	1.24	1.24	1.22	1.23	1.23	1.23	1.23	1.25	1.23	1.23	1.23
3852.	12.35	1.05	1.23	1.24	1.24	1.23	1.23	1.23	1.23	1.23	1.25	1.23	1.23	1.23
3884.	12.41	1.05	1.24	1.13	1.24	1.24	1.24	1.23	1.23	1.24	1.24	1.25	1.25	1.25
3924.	12.32	1.05	1.24	1.24	1.24	1.23	1.23	1.23	1.23	1.23	1.24	1.23	1.23	1.24
3957.	12.35	1.06	1.23	1.24	1.24	1.23	1.23	1.23	1.23	1.23	1.25	1.23	1.23	1.24
3988.	12.39	1.05	1.24	1.24	1.24	1.23	1.23	1.23	1.23	1.23	1.25	1.23	1.23	1.24
4016.	12.41	1.05	1.24	1.24	1.24	1.24	1.23	1.23	1.23	1.24	1.26	1.24	1.24	1.24

[illegible]

U
C
C
U
U

PACK NO. 56
GOULD 3.5 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 3 HOURS

CYCLE NO. PACK CURRENT
VOLTAGE 1.75

CELL VOLTAGES

1	2	3	4	5	6	7	8	9	10	END OF DISCHARGE
3774. 12.10 1.76	1.20	1.21	1.21	1.20	1.20	1.21	1.22	1.20	1.21	
3795. 12.07 1.76	1.20	1.21	1.21	1.20	1.20	1.21	1.22	1.20	1.21	
3832. 12.03 1.78	1.20	1.20	1.20	1.19	1.19	1.20	1.22	1.19	1.20	
3869. 12.01 1.78	1.19	1.20	1.20	1.19	1.19	1.20	1.21	1.19	1.20	
3904. 11.98 1.78	1.20	1.20	1.20	1.20	1.20	1.20	1.22	1.19	1.20	
3937. 12.04 1.78	1.20	1.20	1.20	1.20	1.20	1.20	1.22	1.20	1.20	
3968. 12.15 1.78	1.21	1.22	1.22	1.21	1.21	1.21	1.23	1.21	1.22	
3996. 12.12 1.78	1.21	1.22	1.22	1.20	1.21	1.21	1.23	1.20	1.21	

40										END OF CHARGE
3774. 15.51	1.54	1.56	1.57	1.54	1.54	1.56	1.57	1.54	1.55	
3795. 15.57	1.54	1.58	1.59	1.55	1.55	1.58	1.56	1.54	1.54	
3832. 15.50	1.54	1.55	1.57	1.54	1.55	1.56	1.56	1.54	1.54	
3869. 15.50	1.54	1.55	1.58	1.54	1.55	1.56	1.57	1.54	1.54	
3904. 15.62	1.56	1.57	1.60	1.56	1.56	1.58	1.58	1.56	1.56	
3937. 15.50	1.54	1.55	1.58	1.55	1.55	1.56	1.57	1.54	1.55	
3968. 15.43	1.52	1.51	1.60	1.55	1.55	1.57	1.55	1.52	1.56	
3996. 15.45	1.53	1.53	1.59	1.54	1.54	1.55	1.56	1.53	1.55	

PACK NO. 7
GOULD 3.5 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 3 HOURS

CYCLE PACK CURRENT
NO. VOLTAGE 1.75

CELL VOLTAGES
1 2 3 4 5

6 7 8 9 10

END OF
DISCHARGE

END OF
CHARGE

3625.	7.75	1.73	.00	1.17	1.10	.86	.00	1.06	1.19	1.19	1.18
3644.	7.76	1.73	.00	1.17	1.10	.87	.00	1.05	1.19	1.20	1.18
3684.	7.51	1.74	.00	1.16	1.06	.75	.00	.97	1.20	1.19	1.17
3716.	7.55	1.73	.00	1.17	1.06	.77	.00	.93	1.17	1.22	1.20
3756.	6.55	1.74	.00	1.16	1.04	.00	.00	.89	1.20	1.20	1.18
3789.	6.49	1.75	.00	1.14	1.03	.00	.00	.83	1.20	1.19	1.17
3820.	6.41	1.74	.00	1.13	1.00	.00	.00	.79	1.20	1.19	1.16
3848.	6.17	1.74	.00	1.13	1.01	.00	.00	.56	1.20	1.19	1.17

3625.	10.14	.44	.00	1.47	1.43	1.43	.00	1.44	1.46	1.47	1.46
3644.	10.14	.43	.00	1.47	1.43	1.43	.00	1.44	1.46	1.46	1.46
3684.	10.13	.43	.00	1.47	1.42	1.44	.00	1.44	1.47	1.46	1.46
3716.	10.15	.43	.00	1.47	1.41	1.43	.00	1.44	1.46	1.47	1.47
3756.	8.67	.43	.00	1.47	1.42	.00	.00	1.45	1.47	1.47	1.46
3789.	8.69	.43	.00	1.47	1.42	.00	.00	1.44	1.46	1.46	1.46
3820.	8.71	.43	.00	1.47	1.42	.00	.00	1.45	1.47	1.47	1.46
3848.	8.73	.43	.00	1.47	1.42	.00	.00	1.45	1.47	1.47	1.47

PACK NO. 49
SONOTONE 5 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 1.50

CELL VOLTAGES

	1	2	3	4	5	6	7	8	9	10
7587.	11.00	1.48	1.21	1.21	1.20	1.21	1.22	1.24	1.25	.00 1.23
7621.	10.88	1.51	1.19	1.21	1.19	1.19	1.22	1.22	1.24	.00 1.21
7667.	11.02	1.52	1.21	1.23	1.20	1.21	1.23	1.24	1.24	.00 1.24
7695.	10.93	1.53	1.20	1.22	1.19	1.20	1.22	1.23	1.24	.00 1.22
7727.	10.93	1.53	1.20	1.21	1.19	1.20	1.22	1.23	1.24	.00 1.22
7759.	10.93	1.53	1.20	1.21	1.19	1.20	1.22	1.23	1.24	.00 1.22
7845.	10.94	1.49	1.21	1.21	1.21	1.21	1.23	1.24	1.25	.00 1.23
7877.	10.97	1.50	1.20	1.20	1.20	1.21	1.23	1.24	1.25	.00 1.23
7909.	10.97	1.49	1.20	1.20	1.20	1.21	1.23	1.24	1.25	.00 1.23
7943.	10.92	1.51	1.20	1.20	1.20	1.20	1.22	1.23	1.24	.00 1.22
7967.	10.93	1.50	1.20	1.21	1.20	1.20	1.22	1.23	1.24	.00 1.22
8007.	10.92	1.52	1.20	1.21	1.19	1.20	1.22	1.23	1.24	.00 1.22
8029.	10.92	1.53	1.20	1.22	1.19	1.20	1.21	1.23	1.23	.00 1.22

END OF
DISCHARGE

.86

7587.	13.94	1.54	1.53	1.57	1.54	1.52	1.59	1.54	1.56	.00 1.53
7621.	13.97	1.55	1.54	1.61	1.53	1.50	1.66	1.52	1.54	.00 1.51
7667.	13.89	.55	1.54	1.56	1.54	1.52	1.58	1.54	1.56	.00 1.53
7695.	13.89	.56	1.54	1.57	1.54	1.51	1.59	1.54	1.56	.00 1.52
7727.	13.89	.58	1.54	1.55	1.54	1.51	1.58	1.54	1.56	.00 1.52
7759.	13.89	.59	1.54	1.53	1.54	1.52	1.59	1.54	1.56	.00 1.53
7845.	13.90	.56	1.56	1.51	1.56	1.53	1.59	1.56	1.58	.00 1.54
7877.	13.89	.58	1.55	1.47	1.56	1.53	1.59	1.55	1.57	.00 1.54
7909.	13.88	.58	1.55	1.48	1.56	1.53	1.57	1.55	1.57	.00 1.54
7943.	13.87	.52	1.55	1.49	1.54	1.52	1.63	1.54	1.56	.00 1.53
7967.	13.86	.55	1.54	1.54	1.55	1.52	1.58	1.54	1.56	.00 1.53
8007.	13.87	.55	1.54	1.53	1.54	1.52	1.61	1.54	1.56	.00 1.53
8029.	13.87	.58	1.54	1.54	1.54	1.51	1.59	1.54	1.55	.00 1.52

END OF
CHARGE

PACK NO. 50
SONOTONE 5 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 2.50

CELL VOLTAGES

1 2 3 4 5 6 7 8 9 10

END OF
DISCHARGE

7610.	11.57	2.48	1.09	1.18	1.14	1.11	1.12	1.18	1.18	1.20	1.18	1.17
7654.	11.64	2.50	1.11	1.09	1.16	1.12	1.12	1.20	1.19	1.19	1.20	1.19
7690.	11.58	2.51	1.11	1.18	1.15	1.12	1.10	1.19	1.19	1.20	1.18	1.17
7724.	11.54	2.51	1.10	1.18	1.15	1.12	1.07	1.19	1.19	1.20	1.18	1.18
7754.	11.51	2.50	1.11	1.09	1.16	1.12	.99	1.20	1.20	1.19	1.20	1.19
7812.	14.82	2.37	1.52	1.46	1.49	1.52	1.47	1.47	1.46	1.49	1.45	1.47
7866.	11.70	2.50	1.11	1.18	1.16	1.13	1.16	1.19	1.19	1.21	1.19	1.19
7898.	11.23	2.50	1.11	1.18	1.16	1.13	1.16	1.19	1.19	1.20	1.18	1.18
7930.	11.16	2.50	1.09	1.18	1.15	1.12	1.15	1.18	1.18	1.20	1.18	1.17
7994.	11.80	2.50	1.12	1.20	1.17	1.14	1.16	1.21	1.21	1.22	1.20	1.19
8018.	11.80	2.50	1.12	1.19	1.17	1.14	1.15	1.20	1.20	1.22	1.20	1.19

END OF
CHARGE

7610.	15.30	1.44	1.54	1.47	1.55	1.52	1.53	1.53	1.47	1.56	1.48	1.67
7654.	15.30	.66	1.52	1.43	1.54	1.52	1.50	1.53	1.48	1.55	1.49	1.63
7690.	15.27	.69	1.53	1.48	1.54	1.52	1.48	1.53	1.48	1.55	1.48	1.67
7724.	15.26	.71	1.53	1.48	1.54	1.52	1.45	1.53	1.48	1.56	1.49	1.67
7754.	15.26	.73	1.53	1.45	1.54	1.52	1.43	1.53	1.48	1.54	1.49	1.68
7812.	15.26	1.19	1.53	1.48	1.54	1.53	1.44	1.53	1.48	1.56	1.49	1.68
7866.	15.53	.78	1.54	1.50	1.56	1.55	1.52	1.56	1.50	1.59	1.51	1.70
7898.	15.55	.79	1.54	1.49	1.56	1.54	1.55	1.56	1.50	1.58	1.50	1.69
7930.	15.52	.45	1.48	1.44	1.47	1.47	1.47	1.46	1.44	1.48	1.44	1.48
7994.	15.41	.70	1.53	1.49	1.54	1.53	1.53	1.56	1.49	1.59	1.50	1.68
8018.	15.40	.71	1.53	1.49	1.54	1.53	1.53	1.54	1.49	1.57	1.49	1.68

PACK NO. 1
SONOTONE 5 A.H.

CYCLE NO. PACK VOLTAGE CURRENT

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CELL VOLTAGES

1	2	3	4	5	6	7	8	9	10
.00	1.17	1.13	.00	1.05	.67	1.17	1.17	1.15	1.14
.00	1.18	1.14	.00	1.06	.77	1.17	1.18	1.16	1.15
.00	1.17	1.12	.00	1.04	.64	1.16	1.16	1.14	1.13
.00	1.17	1.13	.00	1.04	.65	1.16	1.17	1.14	1.13
.00	1.16	1.12	.00	1.04	.51	1.16	1.16	1.15	1.13
.00	1.16	1.12	.00	1.04	.40	1.16	1.16	1.14	1.13
.00	1.18	1.14	.00	1.06	.64	1.17	1.17	1.15	1.14
.00	1.18	1.13	.00	1.06	.44	1.17	1.17	1.15	1.14
.00	1.17	1.12	.00	1.05	.03	1.16	1.16	1.14	1.13

END OF
DISCHARGE

Q

END OF
CHARGE

7460.	8.66	2.49	.00	1.17	1.13	.00	1.05	.67	1.17	1.17	1.15	1.14
7494.	8.79	2.49	.00	1.18	1.14	.00	1.06	.77	1.17	1.18	1.16	1.15
7568.	8.56	2.50	.00	1.17	1.12	.00	1.04	.64	1.16	1.16	1.14	1.13
7600.	8.59	2.50	.00	1.17	1.13	.00	1.04	.65	1.16	1.17	1.14	1.13
7632.	8.45	2.49	.00	1.16	1.12	.00	1.04	.51	1.16	1.16	1.15	1.13
7651.	8.32	2.49	.00	1.16	1.12	.00	1.04	.40	1.16	1.16	1.14	1.13
7718.	8.59	2.52	.00	1.18	1.14	.00	1.06	.64	1.17	1.17	1.15	1.14
7750.	8.45	2.52	.00	1.18	1.13	.00	1.06	.44	1.17	1.17	1.15	1.14
7782.	7.96	2.49	.00	1.17	1.12	.00	1.05	.03	1.16	1.16	1.14	1.13

63

PACK NO. 25 SONOTONE 5 A.H.		DEPTH OF DISCHARGE 15 PERCENT OF RECHARGE 16G		TEST TEMPERATURE 40 C ORBIT PERIOD 90 MIN.															
CYCLE NO.		PACK CURRENT VOLTAGE 1.50		CELL VOLTAGES															
		1	2	3	4	5	6	7	8	9	10								
7098.	9.08	1.49	1.12	1.14	.00	.00	1.05	1.17	1.18	1.14	1.16								
7130.	9.04	1.50	1.12	1.13	.00	.00	1.03	1.17	1.17	1.13	1.15								
7162.	9.05	1.49	1.12	1.13	.00	.00	1.04	1.17	1.17	1.13	1.15								
7181.	9.09	1.48	1.12	1.14	.00	.00	1.05	1.17	1.18	1.14	1.16								
7248.	9.01	1.50	1.11	1.14	.00	.00	1.04	1.17	1.18	1.13	1.15								
7280.	9.10	1.51	1.12	1.14	.00	.00	1.06	1.18	1.18	1.14	1.16								
7312.	8.99	1.48	1.11	1.13	.00	.00	1.04	1.16	1.17	1.13	1.14								
7346.	8.84	1.50	1.11	1.11	.00	.00	1.00	1.15	1.16	1.11	1.13								
7370.	8.82	1.50	1.11	1.11	.00	.00	.99	1.15	1.16	1.11	1.12								
7410.	8.86	1.51	1.11	1.12	.00	.00	1.01	1.15	1.16	1.11	1.12								
7432.	8.87	1.50	1.11	1.11	.00	.00	1.01	1.15	1.15	1.11	1.12								
1.20																			
7098.	11.65	1.44	1.42	1.43	.00	.00	1.47	1.41	1.44	1.42	1.62								
7130.	11.66	1.44	1.42	1.43	.00	.00	1.48	1.41	1.44	1.42	1.62								
7162.	11.68	1.44	1.43	1.43	.00	.00	1.48	1.42	1.45	1.42	1.63								
7181.	11.66	1.44	1.42	1.43	.00	.00	1.47	1.41	1.45	1.42	1.62								
7248.	11.65	1.45	1.43	1.43	.00	.00	1.48	1.42	1.45	1.43	1.63								
7280.	11.66	1.44	1.43	1.42	.00	.00	1.47	1.41	1.45	1.42	1.62								
7312.	11.63	1.44	1.42	1.42	.00	.00	1.47	1.41	1.44	1.42	1.62								
7346.	11.61	1.44	1.42	1.42	.00	.00	1.47	1.41	1.44	1.42	1.61								
7370.	11.63	1.44	1.42	1.42	.00	.00	1.47	1.41	1.45	1.42	1.62								
7410.	11.60	1.44	1.42	1.42	.00	.00	1.46	1.41	1.44	1.42	1.61								
7432.	11.61	1.44	1.42	1.42	.00	.00	1.46	1.41	1.44	1.41	1.61								

PACK NO. 53 SONOTONE 5 A.H.	CYCLE NO.	PACK VOLTAGE	CURRENT	DEPTH OF DISCHARGE 15 PERCENT OF RECHARGE 115					TEST TEMPERATURE 0 C ORBIT PERIOD 3 HOURS					END OF DISCHARGE
				1	2	3	4	5	6	7	8	9	10	
				CELL VOLTAGES										
3663.	12.46	1.50	1.22	1.24	1.24	1.25	1.25	1.25	1.25	1.25	1.25	1.26	1.25	
3704.	12.41	1.50	1.22	1.23	1.24	1.24	1.24	1.24	1.24	1.24	1.25	1.25	1.24	
3736.	12.45	1.50	1.22	1.17	1.24	1.24	1.24	1.25	1.25	1.24	1.24	1.25	1.25	
3778.	12.40	1.50	1.21	1.23	1.24	1.24	1.24	1.24	1.24	1.24	1.26	1.24	1.23	
3811.	12.37	1.50	1.21	1.23	1.24	1.24	1.24	1.24	1.24	1.24	1.25	1.25	1.23	
3840.	12.10	1.50	1.19	1.20	1.21	1.21	1.21	1.21	1.22	1.21	1.22	1.22	1.20	
3871.	12.50	1.50	1.22	1.24	1.25	1.25	1.25	1.25	1.25	1.25	1.26	1.26	1.25	
3663.	15.30	.35	1.53	1.52	1.50	1.55	1.55	1.52	1.48	1.55	1.66	1.53	1.47	
3704.	15.34	.21	1.53	1.52	1.50	1.56	1.56	1.52	1.48	1.55	1.66	1.53	1.51	
3736.	15.36	.22	1.52	1.51	1.50	1.55	1.55	1.51	1.47	1.55	1.67	1.53	1.55	
3778.	15.41	.20	1.53	1.52	1.51	1.56	1.56	1.52	1.48	1.56	1.66	1.54	1.55	
3811.	15.39	.19	1.52	1.51	1.50	1.56	1.56	1.52	1.48	1.56	1.68	1.53	1.56	
3840.	14.18	.20	1.44	1.44	1.45	1.40	1.40	1.41	1.43	1.41	1.43	1.40	1.39	
3871.	15.72	.26	1.53	1.54	1.53	1.59	1.59	1.55	1.51	1.58	1.68	1.57	1.63	

PACK NO. 54 SONOTONE 5 A.H.		DEPTH OF DISCHARGE 25 PERCENT OF RECHARGE 115		TEST TEMPERATURE 0 C ORBIT PERIOD 3 HOURS									
CYCLE NO.	PACK VOLTAGE	CURRENT 2.50	CELL VOLTAGES										END OF DISCHARGE
			1	2	3	4	5	6	7	8	9	10	
3643.	11.62	2.51	1.18	1.15	1.01	1.15	1.19	1.18	1.18	1.20	1.19	1.19	1.19
3694.	11.61	2.50	1.17	1.15	1.02	1.14	1.19	1.18	1.17	1.20	1.19	1.19	1.19
3763.	11.57	2.50	1.17	1.14	1.00	1.14	1.18	1.18	1.17	1.19	1.19	1.18	1.18
3806.	11.55	2.50	1.18	1.15	.99	1.15	1.19	1.19	1.18	1.20	1.19	1.19	1.19
3838.	11.62	2.51	1.17	1.15	1.01	1.15	1.19	1.19	1.17	1.20	1.19	1.19	1.19
3898.	11.72	2.51	1.18	1.15	1.04	1.16	1.20	1.19	1.18	1.20	1.20	1.20	1.20
.58													
3643.	15.65	.41	1.51	1.54	1.54	1.52	1.53	1.63	1.68	1.70	1.53	1.52	END OF CHARGE
3694.	15.70	.39	1.50	1.56	1.60	1.51	1.52	1.64	1.68	1.68	1.52	1.50	
3763.	15.58	.40	1.50	1.47	1.55	1.52	1.53	1.61	1.65	1.63	1.53	1.51	
3806.	15.57	.33	1.51	1.55	1.57	1.52	1.53	1.61	1.67	1.67	1.53	1.51	
3838.	15.50	.35	1.50	1.53	1.54	1.51	1.51	1.60	1.66	1.67	1.51	1.50	
3898.	15.49	.40	1.50	1.53	1.54	1.52	1.52	1.59	1.62	1.65	1.52	1.51	

PACK NO. 5
SOMOTONE 5 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 3 HOURS

CYCLE NO. PACK CURRENT
VOLTAGE 2.50

CELL VOLTAGES
1 2 3 4 5

6 7 8 9 10

END OF
DISCHARGE

END OF
CHARGE

3676.	11.35	2.51	1.16	.98	1.05	1.16	1.16	1.16	1.17	1.18	1.17	1.16
3717.	11.12	2.51	.13	.92	1.05	1.14	1.14	1.14	1.16	1.15	1.15	1.14
3749.	11.26	2.51	1.15	.86	1.06	1.15	1.16	1.16	1.17	1.16	1.17	1.15
3791.	11.13	2.51	1.14	.86	1.05	1.15	1.15	1.15	1.16	1.16	1.16	1.14
3824.	11.05	2.49	1.14	.82	1.04	1.14	1.15	1.15	1.16	1.16	1.16	1.14
3853.	10.87	2.49	1.14	.74	1.01	1.13	1.14	1.14	1.16	1.15	1.16	1.13
3884.	10.68	2.49	1.12	.67	.99	1.11	1.13	1.13	1.15	1.11	1.14	1.11
3676.	14.27	.62	1.42	1.44	1.44	1.42	1.42	1.43	1.43	1.45	1.42	1.42
3717.	14.21	.62	1.41	1.44	1.43	1.42	1.41	1.42	1.42	1.44	1.41	1.41
3749.	14.25	.62	1.41	1.44	1.43	1.42	1.42	1.42	1.42	1.44	1.41	1.41
3791.	14.26	.62	1.42	1.44	1.43	1.42	1.42	1.43	1.42	1.44	1.42	1.42
3824.	14.27	.61	1.42	1.45	1.44	1.42	1.42	1.43	1.42	1.44	1.42	1.42
3853.	14.27	.61	1.42	1.45	1.44	1.42	1.42	1.43	1.43	1.45	1.42	1.42
3884.	14.03	.34	1.39	1.41	1.41	1.40	1.39	1.40	1.40	1.42	1.39	1.40

PACK NO. 6
SOMOTONE 5 A.H.

DEPTH OF DISCHARGE 40
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES					TEST TEMPERATURE 25 C				END OF DISCHARGE
			1	2	3	4	5	6	7	8	9	
3543.	7.56	4.03	1.13	1.13	1.14	.00	1.14	1.09	1.09	.00	.85	.00
3594.	7.55	3.99	1.14	1.13	1.14	.00	1.14	1.10	1.06	.00	.82	.00
3663.	7.13	3.98	1.12	1.11	1.12	.00	1.13	1.06	1.01	.00	.57	.00
3706.	7.25	3.97	1.14	1.13	1.14	.00	1.14	1.09	1.02	.00	.64	.00
3738.	7.21	3.94	1.13	1.12	1.13	.00	1.14	1.08	1.00	.00	.60	.00
3798.	6.54	3.93	1.12	1.11	1.13	.00	1.13	1.06	.99	.00	.04	.00
3543.	10.94	1.00	1.48	1.64	1.47	.00	1.63	1.47	1.63	.00	1.61	.00
3594.	10.82	.96	1.48	1.63	1.47	.00	1.63	1.47	1.50	.00	1.61	.00
3663.	10.86	.73	1.48	1.57	1.46	.00	1.62	1.47	1.58	.00	1.59	.00
3706.	10.70	.71	1.48	1.59	1.47	.00	1.62	1.47	1.52	.00	1.59	.00
3738.	10.61	.66	1.47	1.55	1.45	.00	1.58	1.46	1.51	.00	1.57	.00
3798.	10.76	.67	1.47	1.59	1.46	.00	1.60	1.47	1.59	.00	1.57	.00

END OF CHARGE

PACK NO. 29 SONOTONE 5 A.H.	CYCLE NO.	PACK CURRENT VOLTAGE 1.50	DEPTH OF DISCHARGE 15 PERCENT OF RECHARGE 160					TEST TEMPERATURE 40 C ORBIT PERIOD 3 HOURS					END OF DISCHARGE
			1	2	3	4	5	6	7	8	9	10	
			CELL VOLTAGES										
3605.	10.27	1.51	.00	1.19	1.18	1.12	1.16	1.15	1.15	1.01	1.13	1.18	
3646.	10.22	1.51	.00	1.19	1.18	1.12	1.15	1.15	1.14	.99	1.12	1.17	
3695.	10.41	1.49	.00	1.20	1.19	1.17	1.18	1.16	1.17	1.01	1.13	1.18	
3728.	10.34	1.48	.00	1.20	1.19	1.15	1.17	1.16	1.17	1.00	1.13	1.18	
3757.	9.95	1.48	.00	1.18	1.16	1.01	1.16	1.10	1.15	.93	1.11	1.17	
3788.	10.35	1.49	.00	1.20	1.19	1.18	1.17	1.17	1.15	.96	1.13	1.18	
		.48											
3605.	12.61	.47	.00	1.40	1.38	1.37	1.41	1.39	1.40	1.46	1.41	1.40	
3646.	12.59	.47	.00	1.40	1.38	1.37	1.40	1.39	1.40	1.46	1.41	1.39	
3695.	12.55	.47	.00	1.39	1.38	1.37	1.40	1.38	1.40	1.45	1.40	1.39	
3728.	12.50	.47	.00	1.39	1.37	1.37	1.39	1.38	1.40	1.45	1.40	1.39	
3757.	12.48	.33	.00	1.39	1.37	1.36	1.40	1.37	1.40	1.45	1.40	1.39	
3788.	12.50	.47	.00	1.38	1.37	1.37	1.39	1.37	1.39	1.44	1.40	1.38	
													END OF CHARGE

PACK NO. 30
SONOTONE 5 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT 2.50	CELL VOLTAGES						8	9	10	END OF DISCHARGE
			1	2	3	4	5	6	7			
3454.	7.47	2.55	.97	1.11	1.11	.00	1.09	1.13	.00	.96	.00	1.09
3505.	7.53	2.53	.99	1.11	1.11	.00	1.09	1.13	.00	.96	.00	1.11
3617.	7.66	2.52	1.05	1.13	1.14	.00	1.11	1.16	.00	1.02	.00	1.11
3624.	7.04	2.47	.87	1.08	1.10	.00	1.08	1.13	.00	.67	.00	1.09
3684.	6.05	2.43	.90	1.01	1.10	.00	1.08	1.11	.00	.15	.00	.95
3454.	10.17	.80	1.41	1.44	1.49	.00	1.49	1.45	.60	1.43	.00	1.47
3505.	10.18	.55	1.41	1.43	1.49	.00	1.47	1.45	.00	1.42	.00	1.50
3617.	10.15	.62	1.41	1.44	1.53	.00	1.47	1.47	.00	1.43	.00	1.47
3624.	10.17	.61	1.40	1.42	1.51	.00	1.46	1.48	.00	1.41	.00	1.48
3684.	9.96	.54	1.39	1.39	1.48	.00	1.43	1.44	.00	1.40	.00	1.41

END OF CHARGE

PACK NO. 61
GULTON 6 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115
TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 1.80

CELL VOLTAGES

1	2	3	4	5	6	7	8	9	10	END OF DISCHARGE
6727. 79	1.22	1.13	.00	.00	.00	1.21	1.22	1.22	.00	.00
6761. 84	1.21	1.11	.00	.00	.00	1.20	1.22	1.22	.00	.00
6835. 73	1.21	1.11	.00	.00	.00	1.20	1.22	1.22	.00	.00
6867. 72	1.21	1.10	.00	.00	.00	1.20	1.21	1.22	.00	.00
6899. 72	1.21	1.10	.00	.00	.00	1.20	1.21	1.22	.00	.00
6985. 71	1.22	1.09	.00	.00	.00	1.21	1.22	1.22	.00	.00
7017. 77	1.22	1.10	.00	.00	.00	1.21	1.22	1.22	.00	.00
7049. 72	1.21	1.09	.00	.00	.00	1.21	1.21	1.22	.00	.00
7107. 70	1.22	1.08	.00	.00	.00	1.20	1.22	1.22	.00	.00
7147. 69	1.11	1.10	.00	.00	.00	1.21	1.22	1.22	.00	.00
7169. 69	1.15	1.09	.00	.00	.00	1.21	1.22	1.22	.00	.00

6727. 04	1.51	1.50	.00	.00	.00	1.51	1.50	1.59	.00	.00
6761. 50	1.50	1.50	.00	.00	.00	1.49	1.49	1.62	.00	.00
6835. 48	1.51	1.49	.00	.00	.00	1.50	1.50	1.58	.00	.00
6867. 49	1.50	1.49	.00	.00	.00	1.50	1.50	1.59	.00	.00
6899. 50	1.50	1.48	.00	.00	.00	1.51	1.50	1.59	.00	.00
6985. 46	1.51	1.49	.00	.00	.00	1.51	1.50	1.58	.00	.00
7017. 51	1.50	1.48	.00	.00	.00	1.50	1.50	1.58	.00	.00
7049. 47	1.50	1.48	.00	.00	.00	1.51	1.50	1.59	.00	.00
7107. 50	1.51	1.49	.00	.00	.00	1.51	1.51	1.58	.00	.00
7147. 56	1.32	1.50	.00	.00	.00	1.53	1.53	1.67	.00	.00
7169. 57	1.37	1.51	.00	.00	.00	1.52	1.52	1.61	.00	.00

PACK NO. 62 GULTON 6 A.H.		DEPTH OF DISCHARGE 25 PERCENT OF RECHARGE 115		TEST TEMPERATURE 0 C ORBIT PERIOD 90 MIN.								
CYCLE NO.	PACK VOLTAGE 3.00	CURRENT	CELL VOLTAGES					END OF DISCHARGE				
			1	2	3	4	5	6	7	8	9	10
7207.	8.31	3.02	1.19	1.18	1.17	.00	.00	1.17	1.19	1.20	1.20	.00
7240.	8.28	3.03	1.19	1.18	1.17	.00	.00	1.17	1.19	1.20	1.19	.00
7320.	8.26	3.03	1.19	1.17	1.16	.00	.00	1.16	1.18	1.19	1.19	.00
7354.	8.25	3.03	1.19	1.17	1.16	.00	.00	1.16	1.18	1.19	1.19	.00
7384.	8.31	3.01	1.20	1.09	1.17	.00	.00	1.17	1.19	1.19	1.20	.00
7442.	8.23	3.01	1.19	1.17	1.16	.00	.00	1.16	1.18	1.19	1.19	.00
7464.	8.16	3.01	1.19	1.17	1.16	.00	.00	1.15	1.17	1.19	1.19	.00
7496.	8.21	2.99	1.19	1.17	1.16	.00	.00	1.15	1.17	1.19	1.19	.00
7528.	8.24	3.01	1.19	1.17	1.16	.00	.00	1.16	1.18	1.19	1.19	.00
7560.	8.20	3.01	1.19	1.17	1.16	.00	.00	1.15	1.17	1.19	1.19	.00
7592.	8.19	3.02	1.18	1.17	1.15	.00	.00	1.15	1.17	1.19	1.18	.00
7624.	8.18	3.02	1.18	1.17	1.15	.00	.00	1.15	1.16	1.19	1.19	.00
7648.	8.21	3.01	1.19	1.17	1.16	.00	.00	1.16	1.17	1.19	1.19	.00
1.72												
7207.	10.96	.83	1.55	1.63	1.55	.00	.00	1.64	1.53	1.55	1.51	.00
7240.	10.98	.81	1.55	1.62	1.56	.00	.00	1.68	1.53	1.55	1.51	.00
7320.	10.98	.78	1.55	1.62	1.56	.00	.00	1.66	1.54	1.55	1.51	.00
7354.	11.00	.76	1.55	1.63	1.56	.00	.00	1.66	1.54	1.55	1.51	.00
7384.	11.00	.80	1.55	1.63	1.55	.00	.00	1.66	1.54	1.54	1.51	.00
7442.	10.99	.77	1.55	1.63	1.55	.00	.00	1.67	1.54	1.55	1.51	.00
7464.	10.98	.72	1.55	1.68	1.57	.00	.00	1.64	1.54	1.56	1.51	.00
7496.	10.96	.82	1.55	1.60	1.56	.00	.00	1.66	1.54	1.56	1.51	.00
7528.	10.98	.79	1.55	1.62	1.55	.00	.00	1.65	1.54	1.56	1.51	.00
7560.	10.85	.76	1.54	1.57	1.56	.00	.00	1.61	1.53	1.56	1.51	.00
7592.	10.86	.73	1.54	1.57	1.55	.00	.00	1.62	1.53	1.55	1.50	.00
7624.	10.86	.71	1.54	1.58	1.56	.00	.00	1.63	1.52	1.56	1.50	.00
7648.	10.87	.70	1.54	1.58	1.55	.00	.00	1.62	1.53	1.55	1.50	.00

PACK NO. 65 GULTON 6 A.H.	CYCLE NO.	PACK VOLTAGE	CURRENT	DEPTH OF DISCHARGE 15 PERCENT OF RECHARGE 115										TEST TEMPERATURE 0 C ORBIT PERIOD 3 HOURS	END OF DISCHARGE
				CELL VOLTAGES											
				1	2	3	4	5	6	7	8	9	10		
	3795.	12.32	1.81	1.23	1.24	1.23	1.24	1.24	1.27	1.27	1.21	1.25	1.24	1.18	
	3836.	12.31	1.82	1.23	1.23	1.23	1.23	1.23	1.27	1.27	1.21	1.24	1.23	1.18	
	3868.	12.34	1.82	1.23	1.15	1.23	1.24	1.24	1.27	1.27	1.21	1.23	1.25	1.19	
	3910.	12.30	1.82	1.23	1.24	1.23	1.24	1.23	1.26	1.26	1.21	1.24	1.24	1.18	
	3943.	12.26	1.81	1.23	1.24	1.22	1.24	1.23	1.25	1.25	1.21	1.24	1.24	1.18	
	3972.	12.08	1.80	1.21	1.22	1.21	1.22	1.21	1.21	1.21	1.19	1.23	1.22	1.16	
	4003.	12.33	1.82	1.23	1.24	1.23	1.24	1.24	1.26	1.26	1.21	1.24	1.24	1.18	
	3795.	15.45	.41	1.60	1.60	1.53	1.52	1.50	1.42	1.62	1.52	1.49	1.64		
	3836.	15.48	.32	1.60	1.59	1.53	1.52	1.50	1.48	1.62	1.51	1.49	1.65		
	3868.	15.55	.31	1.61	1.61	1.53	1.52	1.50	1.48	1.63	1.52	1.49	1.65		
	3910.	15.49	.31	1.60	1.60	1.53	1.52	1.50	1.49	1.61	1.52	1.49	1.64		
	3943.	15.44	.28	1.60	1.60	1.52	1.52	1.50	1.45	1.62	1.51	1.49	1.65		
	3972.	14.57	.26	1.48	1.49	1.48	1.48	1.40	1.37	1.47	1.48	1.46	1.47		
	4003.	15.24	.32	1.55	1.55	1.52	1.52	1.50	1.45	1.57	1.51	1.49	1.57		

PACK NO. 66
GULTON 6 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES					TEST TEMPERATURE 0 C				END OF DISCHARGE	
			1	2	3	4	5	6	7	8	9		10
3465.	5.84	3.03	1.17	1.19	.00	1.10	.00	.00	.00	.00	1.19	1.21	
3516.	5.78	3.02	1.16	1.19	.00	1.07	.00	.00	.00	.00	1.17	1.19	
3585.	5.68	3.02	1.16	1.19	.00	.99	.00	.00	.00	.00	1.17	1.13	
3628.	5.69	3.02	1.17	1.20	.00	1.00	.00	.00	.00	.00	1.18	1.19	
3660.	5.69	3.02	1.16	1.19	.00	1.00	.00	.00	.00	.00	1.18	1.18	
3720.	5.80	3.03	1.16	1.19	.00	1.07	.00	.00	.00	.00	1.18	1.20	
3465.	7.82	.69	1.59	1.59	.00	1.55	.00	.00	.00	.00	1.58	1.53	END OF CHARGE
3516.	7.80	.66	1.59	1.61	.00	1.54	.00	.00	.00	.00	1.56	1.50	
3585.	7.86	.66	1.59	1.59	.00	1.54	.00	.00	.00	.00	1.58	1.53	
3628.	7.85	.66	1.60	1.61	.00	1.56	.00	.00	.00	.00	1.60	1.54	
3660.	7.74	.60	1.57	1.57	.00	1.54	.00	.00	.00	.00	1.57	1.51	
3720.	7.80	.69	1.59	1.59	.00	1.55	.00	.00	.00	.00	1.60	1.47	

74

8

PACK NO. 42 GULTON 6 A.H.		DEPTH OF DISCHARGE 25 PERCENT OF RECHARGE 160					TEST TEMPERATURE 40 C ORBIT PERIOD 3 HOURS					
CYCLE NO.	PACK VOLTAGE 3.00	CURRENT	CELL VOLTAGES									
			1	2	3	4	5	6	7	8	9	10
3358.	6.27	2.96	.00	1.12	1.05	.99	1.14	.89	.00	.00	.00	1.06
3427.	5.95	2.93	.00	1.07	1.01	.89	1.09	.82	.00	.00	.00	1.05
3477.	5.58	3.01	.00	1.06	.92	.90	1.04	.67	.00	.00	.00	.98
3537.	5.86	2.91	.00	1.11	.92	.94	1.10	.74	.00	.00	.00	1.02
END OF DISCHARGE												
3358.	9.09	.96	.00	1.54	1.48	1.50	1.44	1.56	.00	.00	.00	1.54
3427.	9.01	.80	.00	1.43	1.49	1.49	1.43	1.53	.00	.00	.00	1.56
3477.	8.78	.69	.00	1.43	1.49	1.49	1.42	1.46	.00	.00	.00	1.47
3537.	8.73	.90	.00	1.45	1.42	1.48	1.42	1.49	.00	.00	.00	1.46
END OF CHARGE												

PACK NO. 110
G.E. 12 A.H.

TEST TEMPERATURE 0° C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 3.60

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

7310.	6.32	3.55	1.27	1.27	1.25	1.27	1.27
7338.	6.21	3.56	1.25	1.25	1.25	1.24	1.25
7370.	6.23	3.66	1.24	1.24	1.24	1.24	1.24
7402.	6.22	3.64	1.24	1.24	1.24	1.23	1.24
7488.	6.20	3.58	1.24	1.25	1.25	1.24	1.24
7520.	6.21	3.59	1.25	1.25	1.25	1.25	1.25
7552.	6.20	3.58	1.25	1.24	1.25	1.24	1.25
7586.	6.19	3.59	1.24	1.24	1.25	1.24	1.24
7610.	6.21	3.59	1.24	1.24	1.24	1.24	1.24
7650.	6.21	3.61	1.24	1.24	1.25	1.24	1.24
7672.	6.20	3.62	1.24	1.24	1.24	1.24	1.24

2.37

7310.	7.72	1.10	1.56	1.55	1.54	1.54	1.53
7338.	7.71	.97	1.56	1.56	1.53	1.54	1.53
7370.	7.70	1.09	1.56	1.56	1.52	1.54	1.52
7402.	7.69	1.05	1.56	1.55	1.52	1.54	1.51
7488.	7.68	.95	1.57	1.56	1.53	1.55	1.52
7520.	7.70	1.04	1.57	1.56	1.53	1.55	1.52
7552.	7.72	1.01	1.57	1.56	1.53	1.55	1.52
7586.	7.70	1.05	1.57	1.56	1.53	1.54	1.52
7610.	7.68	1.11	1.56	1.56	1.52	1.54	1.52
7650.	7.75	1.07	1.58	1.57	1.53	1.55	1.53
7672.	7.73	1.12	1.57	1.57	1.53	1.54	1.52

PACK NO. 124
G.E. 12 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK VOLTAGE 6.00 CURRENT

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

7031.	5.91	6.11	1.20	1.20	1.14	1.20	1.19
7077.	5.99	5.93	1.20	1.12	1.15	1.21	1.21
7109.	5.92	5.91	1.20	1.20	1.14	1.20	1.19
7105.	5.91	5.94	1.19	1.20	1.14	1.20	1.19
7137.	5.93	5.91	1.20	1.20	1.14	1.20	1.19
7255.	5.92	6.04	1.20	1.20	1.14	1.20	1.19
7287.	5.93	6.05	1.19	1.20	1.14	1.20	1.18
7319.	5.87	6.04	1.19	1.19	1.14	1.19	1.18
7353.	5.89	6.05	1.19	1.19	1.14	1.19	1.18
7377.	5.89	6.04	1.19	1.19	1.14	1.19	1.19
7417.	5.89	6.05	1.18	1.19	1.14	1.19	1.18

7031.	3.45	1.55	1.52	1.61	1.52	1.55
7077.	1.28	1.55	1.52	1.62	1.51	1.56
7105.	1.34	1.55	1.52	1.61	1.51	1.56
7109.	1.24	1.55	1.52	1.63	1.51	1.58
7137.	1.25	1.56	1.52	1.62	1.51	1.57
7255.	1.30	1.56	1.52	1.64	1.51	1.61
7287.	1.25	1.58	1.51	1.62	1.50	1.57
7319.	1.35	1.55	1.50	1.61	1.50	1.58
7353.	1.28	1.55	1.50	1.62	1.50	1.57
7377.	1.25	1.54	1.50	1.64	1.50	1.57
7417.	1.35	1.55	1.50	1.62	1.50	1.57
7417.	1.24	1.54	1.49	1.62	1.49	1.57

PACK NO. G.E. 12 A.H.	CYCLE NO.	PACK VOLTAGE	CURRENT 6.00	DEPTH OF DISCHARGE 25 PERCENT OF RECHARGE 125					TEST TEMPERATURE 25 C ORBIT PERIOD 90 MIN.	END OF DISCHARGE
				1	2	3	4	5		
7269.	5.58	5.88	1.17	.99	1.14	1.16	1.13			
7303.	5.56	5.92	1.18	.97	1.15	1.17	1.14			
7349.	5.50	5.89	1.18	.89	1.12	1.17	1.14			
7377.	5.30	5.88	1.16	.80	1.11	1.15	1.11			
7409.	5.29	5.84	1.16	.75	1.11	1.14	1.11			
7441.	5.16	5.71	1.16	.65	1.11	1.14	1.10			
7527.	4.95	5.59	1.17	.39	1.13	1.16	1.14			
7528.	4.82	5.85	1.22	.00	1.20	1.22	1.23			
7560.	4.63	5.73	1.18	.00	1.16	1.18	1.15			
7594.	4.12	5.86	1.11	.00	1.00	1.05	.99			
7618.	4.70	5.62	1.17	.00	1.18	1.18	1.18			
7658.	4.08	5.82	1.12	.00	.88	1.08	1.06			
7680.	4.69	5.73	1.18	.00	1.17	1.18	1.18			
7269.	7.33	3.75	1.49	1.45	1.46	1.47	1.45			END OF CHARGE
7303.	7.34	3.70	1.50	1.46	1.47	1.49	1.46			
7349.	7.34	3.60	1.50	1.46	1.47	1.48	1.45			
7377.	7.34	3.66	1.50	1.46	1.47	1.47	1.45			
7409.	7.33	3.68	1.49	1.45	1.46	1.47	1.44			
7441.	7.32	3.71	1.49	1.45	1.46	1.47	1.44			
7527.	7.33	3.71	1.50	1.46	1.47	1.49	1.45			
7528.	5.79	3.45	1.46	.00	1.45	1.45	1.45			
7560.	5.91	3.19	1.51	.00	1.48	1.48	1.46			
7594.	5.71	2.34	1.44	.00	1.44	1.44	1.42			
7618.	5.84	2.60	1.49	.00	1.47	1.47	1.44			
7658.	5.77	3.28	1.46	.00	1.45	1.45	1.44			
7680.	5.87	2.92	1.49	.00	1.47	1.47	1.45			

PACK NO. 85
G.E. 12 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 3.60

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

7102.	6.38	3.23	1.29	1.27	1.27	1.27	1.27	1.28
7181.	5.80	3.58	1.18	1.16	1.16	1.16	1.15	1.17
7255.	5.79	3.54	1.18	1.15	1.16	1.15	1.15	1.17
7287.	5.78	3.55	1.18	1.16	1.16	1.14	1.14	1.16
7341.	5.91	3.54	1.20	1.18	1.18	1.18	1.18	1.19
7349.	5.88	3.48	1.20	1.17	1.18	1.18	1.18	1.19
7413.	5.92	3.55	1.20	1.18	1.18	1.18	1.15	1.17
7445.	5.76	3.46	1.18	1.14	1.15	1.15	1.17	1.18
7477.	5.85	3.45	1.19	1.17	1.16	1.17	1.15	1.16
7507.	5.78	3.60	1.18	1.16	1.15	1.15	1.15	1.16
7533.	5.84	3.58	1.19	1.18	1.16	1.16	1.16	1.17

7102.	2.88	1.43	1.42	1.45	1.42	1.42	1.42	1.42
7181.	2.80	1.45	1.44	1.47	1.44	1.44	1.44	1.43
7255.	2.80	1.45	1.43	1.47	1.44	1.44	1.44	1.43
7287.	2.79	1.45	1.44	1.47	1.44	1.44	1.44	1.44
7341.	2.54	1.45	1.44	1.47	1.44	1.44	1.44	1.44
7349.	2.40	1.45	1.43	1.46	1.44	1.44	1.44	1.44
7413.	2.67	1.45	1.43	1.47	1.44	1.44	1.44	1.44
7445.	1.59	1.42	1.42	1.44	1.43	1.43	1.42	1.42
7477.	1.94	1.42	1.42	1.44	1.42	1.42	1.42	1.42
7507.	2.55	1.44	1.44	1.46	1.44	1.44	1.44	1.42
7533.	2.85	1.44	1.43	1.44	1.43	1.43	1.43	1.43

PACK NO. 111
G.E. 12 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES					
			1	2	3	4	5	
3602.	6.23	3.68	1.25	1.26	1.24	1.25	1.25	END OF DISCHARGE
3757.	6.18	3.65	1.25	1.25	1.24	1.25	1.24	
3789.	6.21	3.63	1.25	1.25	1.24	1.25	1.25	
3849.	6.21	3.67	1.24	1.25	1.23	1.25	1.24	
3602.	7.30	.83	1.46	1.46	1.48	1.45	1.46	END OF CHARGE
3757.	7.85	.77	1.63	1.54	1.64	1.53	1.57	
3789.	7.77	.60	1.61	1.52	1.61	1.50	1.55	
3849.	7.86	.64	1.63	1.54	1.62	1.52	1.58	

PACK NO. 125 G.E. 12 A.H.		DEPTH OF DISCHARGE 25 PERCENT OF RECHARGE 115					TEST TEMPERATURE 0 C ORBIT PERIOD 3 HOURS		END OF DISCHARGE	END OF CHARGE
CYCLE NO.	PACK VOLTAGE	CURRENT	1	2	3	4	5			
3664.	6.00	6.00	1.20	1.20	1.20	1.20	1.20			
3771.	5.97	5.97	1.19	1.20	1.20	1.20	1.19			
3831.	5.96	6.04	1.19	1.19	1.19	1.19	1.19			
3664.	7.70	1.38	1.54	1.54	1.53	1.57	1.55			
3771.	7.69	.68	1.56	1.55	1.56	1.52	1.51			
3831.	7.70	.57	1.57	1.55	1.58	1.52	1.50			

PACK NO. 83
G.E. 12 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES					
			1	2	3	4	5	
3651.	5.63	6.05	1.13	1.13	1.13	1.13	1.11	END OF DISCHARGE
3771.	5.53	5.98	1.12	1.12	1.12	1.11	1.07	
3814.	5.62	5.99	1.15	1.15	1.15	1.14	1.11	
3847.	5.68	5.98	1.15	1.14	1.14	1.14	1.11	
3906.	5.54	6.06	1.12	1.12	1.11	1.11	1.06	
3651.	7.18	1.50	1.44	1.43	1.44	1.43	1.43	END OF CHARGE
3771.	7.15	1.51	1.43	1.41	1.43	1.42	1.42	
3814.	7.11	1.50	1.44	1.43	1.44	1.43	1.42	
3847.	7.17	1.51	1.44	1.43	1.43	1.43	1.42	
3906.	7.16	1.53	1.43	1.42	1.43	1.42	1.42	

PACK NO. G.E. 12 A.H.	CYCLE NO.	PACK VOLTAGE	CURRENT 9.60	DEPTH OF DISCHARGE 40 PERCENT OF RECHARGE 125					TEST TEMPERATURE 25 C ORBIT PERIOD 3 HOURS	
				1	2	3	4	5		
	3641.	5.44	9.01	1.11	1.05	1.09	1.06	1.10		END OF DISCHARGE
	3804.	5.31	8.69	1.12	.95	1.09	1.10	1.11		
	3836.	5.07	8.39	1.09	.75	1.06	1.07	1.09		
	3894.	4.66	8.41	1.06	.47	.99	1.05	1.06		
			2.40							END OF CHARGE
	3641.	7.64	2.42	1.51	1.49	1.60	1.53	1.52		
	3804.	7.57	2.29	1.51	1.46	1.63	1.50	1.51		
	3836.	7.52	2.23	1.48	1.43	1.62	1.50	1.49		
	3894.	7.35	1.14	1.45	1.41	1.55	1.48	1.46		

PACK NO. 86
G.E. 12 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES					END OF DISCHARGE
			1	2	3	4	5	
3657.	5.64	3.56	1.15	1.11	1.12	1.14	1.12	
3666.	5.63	3.60	1.15	1.11	1.12	1.14	1.12	
3676.	5.67	3.55	1.15	1.12	1.13	1.14	1.13	
3710.	5.73	3.64	1.17	1.15	1.15	1.16	1.15	
3743.	5.69	3.61	1.16	1.13	1.14	1.15	1.13	
3774.	5.64	3.61	1.15	1.11	1.12	1.14	1.12	
3802.	5.59	3.58	1.14	1.10	1.11	1.14	1.12	
3657.	6.99	1.15	1.40	1.40	1.40	1.39	1.39	END OF CHARGE
3666.	6.97	1.14	1.40	1.40	1.40	1.40	1.39	
3676.	6.98	1.15	1.40	1.39	1.39	1.39	1.39	
3710.	7.01	1.16	1.40	1.40	1.40	1.40	1.40	
3743.	6.97	1.16	1.40	1.40	1.40	1.39	1.39	
3774.	6.90	1.17	1.38	1.38	1.38	1.38	1.38	
3802.	6.91	1.16	1.38	1.39	1.39	1.38	1.38	

84

PACK NO. 100
G.E. 12 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 3 HOURS

CYCLE PACK CURRENT
NO. VOLTAGE 6.00

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

3484.	5.53	5.96	1.13	1.12	1.12	1.09	1.10
3515.	5.50	5.96	1.12	1.12	1.12	1.08	1.09
3524.	5.50	5.97	1.12	1.12	1.11	1.08	1.09
3596.	5.56	5.99	1.13	1.13	1.13	1.10	1.11
3629.	5.49	5.96	1.12	1.11	1.11	1.09	1.10
3660.	5.61	5.99	1.13	1.12	1.12	1.12	1.14
3688.	5.41	5.96	1.12	1.10	1.10	1.05	1.07

3484.	7.18	1.92	1.44	1.45	1.45	1.42	1.43
3515.	7.19	1.83	1.44	1.45	1.45	1.43	1.44
3524.	7.18	1.85	1.45	1.45	1.45	1.42	1.43
3596.	7.23	1.84	1.44	1.45	1.45	1.43	1.44
3629.	7.20	1.82	1.44	1.45	1.45	1.43	1.44
3660.	7.08	1.94	1.42	1.43	1.43	1.41	1.42
3688.	7.10	1.92	1.43	1.43	1.43	1.41	1.42

PACK NO. 84
GOULD 20 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK CURRENT
VOLTAGE 6.00

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

7294.	6.20	6.06	1.26	1.25	1.24	1.24	1.23
7328.	6.12	6.04	1.24	1.23	1.22	1.22	1.22
7416.	6.20	6.03	1.26	1.25	1.24	1.24	1.24
7470.	6.14	6.00	1.24	1.24	1.23	1.23	1.22
7502.	6.17	6.01	1.25	1.24	1.24	1.23	1.23
7534.	6.09	6.06	1.23	1.23	1.22	1.22	1.21
7566.	6.17	6.02	1.24	1.24	1.23	1.22	1.22
7598.	6.21	6.03	1.25	1.24	1.24	1.23	1.23
7622.	6.17	6.04	1.25	1.24	1.24	1.23	1.23

3.45

END OF
CHARGE

7294.	7.95	3.03	1.61	1.57	1.61	1.57	1.59
7328.	7.71	2.38	1.54	1.56	1.55	1.52	1.56
7416.	7.89	2.79	1.58	1.59	1.60	1.56	1.59
7470.	7.89	2.41	1.61	1.57	1.62	1.55	1.57
7502.	7.84	2.61	1.58	1.57	1.59	1.55	1.57
7534.	7.63	2.28	1.52	1.55	1.54	1.50	1.54
7566.	7.84	2.78	1.56	1.59	1.58	1.54	1.57
7598.	7.84	2.58	1.57	1.57	1.59	1.55	1.57
7622.	7.83	2.66	1.56	1.57	1.58	1.55	1.57

PACK NO. 98
GOULD 20 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115
TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 10.00 1 2 3 4 5

END OF
DISCHARGE

7101.	4.56	9.92	1.09	1.20	1.13	1.16	.00
7189.	4.62	9.81	1.09	1.20	1.14	1.17	.00
7243.	4.52	9.97	1.08	1.19	1.13	1.16	.00
7275.	4.53	9.97	1.07	1.20	1.13	1.17	.00
7307.	4.35	8.33	1.00	1.17	1.09	1.12	.00
7315.	4.61	9.94	1.10	1.21	1.15	1.18	.00

5.75

END OF
CHARGE

7101.	6.22	3.83	1.58	1.52	1.56	1.59	.00
7189.	6.24	3.34	1.58	1.52	1.56	1.58	.00
7243.	6.18	3.81	1.57	1.51	1.56	1.58	.00
7275.	6.16	3.89	1.57	1.51	1.55	1.57	.00
7307.	6.00	5.59	1.55	1.46	1.50	1.52	.00
7315.	6.17	2.99	1.57	1.52	1.55	1.57	.00

PACK NO. 80 GOULD 20 A.H.		DEPTH OF DISCHARGE 15 PERCENT OF RECHARGE 115					TEST TEMPERATURE 0 C ORBIT PERIOD 3 HOURS		END OF DISCHARGE
CYCLE NO.	PACK VOLTAGE	CURRENT 6.00	CELL VOLTAGES						
			1	2	3	4	5		
3627.	6.04	6.05	1.22	1.21	1.17	1.23	1.22		
3668.	6.01	6.07	1.22	1.21	1.16	1.23	1.22		
3700.	6.06	6.09	1.22	1.16	1.17	1.23	1.22		
3742.	6.02	6.07	1.22	1.21	1.17	1.23	1.22		
3775.	6.02	6.05	1.22	1.21	1.17	1.23	1.22		
3804.	6.09	6.06	1.24	1.21	1.19	1.24	1.23		
3835.	6.24	6.10	1.26	1.25	1.22	1.27	1.26		
3627.	7.25	1.38	1.43	1.46	1.48	1.43	1.43		
3663.	7.24	1.06	1.43	1.47	1.48	1.44	1.43		
3700.	7.26	1.05	1.43	1.46	1.48	1.44	1.43		
3742.	7.26	1.02	1.43	1.47	1.48	1.44	1.43		
3775.	7.42	1.40	1.45	1.53	1.52	1.47	1.45		
3804.	7.31	.93	1.44	1.48	1.49	1.45	1.45		
3835.	7.72	1.04	1.50	1.58	1.56	1.53	1.54		

PACK NO. 94 GOULD 20 A.H.		DEPTH OF DISCHARGE 25 PERCENT OF RECHARGE 115					TEST TEMPERATURE 0 C ORBIT PERIOD 3 HOURS				
CYCLE NO.	PACK VOLTAGE 10.00	CURRENT	CELL VOLTAGES					END OF DISCHARGE			
			1	2	3	4	5				
3498.	6.03	10.24	1.23	1.21	1.20	1.22	1.21				
3539.	5.98	10.23	1.22	1.20	1.19	1.20	1.20				
3571.	6.00	10.28	1.23	1.20	1.18	1.21	1.20				
3621.	6.12	9.60	1.25	1.23	1.22	1.24	1.23				
3650.	5.73	9.29	1.19	1.15	1.13	1.16	1.14				
3681.	6.12	9.63	1.25	1.23	1.21	1.23	1.22				
									END OF CHARGE		
3498.	7.86	2.30	1.52	1.52	1.62	1.62	1.61				
3539.	7.84	1.59	1.51	1.51	1.63	1.60	1.61				
3571.	7.84	1.55	1.51	1.51	1.63	1.61	1.61				
3621.	7.92	1.60	1.54	1.53	1.63	1.62	1.63				
3650.	7.05	1.29	1.41	1.40	1.42	1.42	1.42				
3681.	8.01	1.44	1.54	1.54	1.64	1.66	1.64				

TEST TEMPERATURE 25 C
ORBIT PERIOD 3 HOURS

PACK NO. 105
GOLD 20 A.H.

CYCLE NO.	PACK VOLTAGE	CURRENT 10.00	DEPTH OF DISCHARGE 25 PERCENT OF RECHARGE 125					CELL VOLTAGES				
			1	2	3	4	5	1	2	3	4	5
3431.	5.86	9.99	1.11	1.17	1.18	1.19	1.17	1.11	1.17	1.18	1.19	1.17
3432.	6.22	10.03	1.08	1.17	1.18	1.18	1.17	1.08	1.17	1.18	1.18	1.17
3568.	5.88	10.03	1.13	1.19	1.20	1.21	1.20	1.13	1.19	1.20	1.21	1.20
3600.	5.87	10.02	1.09	1.18	1.18	1.19	1.18	1.09	1.18	1.18	1.19	1.18
3660.	5.79	10.21	1.03	1.17	1.18	1.18	1.18	1.03	1.17	1.18	1.18	1.18
3431.	7.30	2.50	1.42	1.46	1.46	1.46	1.47	1.42	1.46	1.46	1.46	1.47
3482.	7.29	2.57	1.40	1.46	1.46	1.45	1.46	1.40	1.46	1.46	1.45	1.46
3568.	7.28	2.58	1.42	1.47	1.47	1.48	1.50	1.42	1.47	1.47	1.48	1.50
3600.	7.25	2.61	1.38	1.45	1.46	1.45	1.46	1.38	1.45	1.46	1.45	1.46
3660.	7.29	2.61	1.37	1.46	1.46	1.46	1.46	1.37	1.46	1.46	1.46	1.46

END OF
DISCHARGE

END OF
CHARGE

PACK NO. 108
GOULD 20 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 3 HOURS

CYCLE PACK CURRENT
NO. VOLTAGE 6.00

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

3457.	5.85	5.97	1.18	1.15	1.20	1.15	1.15	1.20
3498.	5.83	6.07	1.17	1.14	1.20	1.15	1.15	1.20
3572.	5.85	6.02	1.18	1.14	1.20	1.15	1.15	1.20
3605.	5.83	5.93	1.17	1.14	1.20	1.14	1.14	1.20
3634.	5.65	5.75	1.14	1.10	1.17	1.09	1.09	1.18
3665.	5.79	6.05	1.16	1.13	1.19	1.13	1.13	1.19

3457.	7.19	1.92	1.44	1.47	1.42	1.46	1.43
3498.	7.18	1.72	1.43	1.47	1.42	1.46	1.43
3572.	7.22	1.77	1.44	1.48	1.43	1.45	1.44
3605.	7.14	1.73	1.43	1.47	1.41	1.44	1.42
3634.	7.07	.93	1.42	1.44	1.41	1.41	1.41
3665.	7.08	1.39	1.41	1.44	1.41	1.41	1.41

PACK NO. 73
GULTON 20 A.H.

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK VOLTAGE 10.00 CURRENT

END OF
DISCHARGE

6831.	3.29	9.89	.00	1.12	.00	1.07	1.08
6865.	3.34	9.94	.00	1.14	.00	1.10	1.09
6939.	3.33	9.61	.00	1.12	.00	1.09	1.09
6971.	3.35	9.68	.00	1.13	.00	1.10	1.09
7003.	3.33	9.61	.00	1.12	.00	1.09	1.09
7089.	3.31	9.87	.00	1.13	.00	1.10	1.10
7121.	3.40	9.81	.00	1.15	.00	1.12	1.11
7153.	3.32	9.82	.00	1.12	.00	1.10	1.09
7187.	3.30	9.80	.00	1.12	.00	1.09	1.08
7211.	3.29	9.77	.00	1.11	.00	1.09	1.08
7251.	3.33	9.83	.00	1.13	.00	1.10	1.09
7273.	3.31	9.76	.00	1.12	.00	1.09	1.08

END OF
CHARGE

6831.	4.36	6.25	.00	1.48	.00	1.44	1.45
6865.	4.41	3.48	.00	1.50	.00	1.45	1.46
6939.	4.41	4.04	.00	1.50	.00	1.45	1.46
6971.	4.42	3.99	.00	1.49	.00	1.45	1.46
7003.	4.42	4.05	.00	1.49	.00	1.45	1.47
7089.	4.42	3.96	.00	1.51	.00	1.46	1.48
7121.	4.43	4.46	.00	1.49	.00	1.46	1.47
7153.	4.44	4.38	.00	1.50	.00	1.46	1.47
7187.	4.42	4.10	.00	1.49	.00	1.45	1.46
7211.	4.44	3.90	.00	1.51	.00	1.46	1.47
7251.	4.43	3.48	.00	1.51	.00	1.46	1.46
7273.	4.41	3.89	.00	1.49	.00	1.45	1.45

PACK NO. 76
GULTON 20 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE NO. VOLTAGE 6.00 CURRENT

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

6942.	5.22	6.02	1.14	.90	1.02	1.07	1.08
6975.	5.16	6.00	1.13	.87	1.01	1.05	1.08
7019.	5.11	6.05	1.13	.75	.98	1.04	1.07
7089.	5.10	6.04	1.13	.86	1.00	1.01	1.08
7149.	5.03	5.99	1.13	.83	1.04	.96	1.10
7181.	4.96	5.94	1.13	.82	1.01	.89	1.10
7213.	5.14	6.00	1.13	.81	1.01	1.08	1.10
7245.	5.68	6.06	1.16	1.03	1.18	1.16	1.15
7277.	5.34	6.05	1.13	.87	1.11	1.12	1.09
7309.	5.29	5.98	1.13	.83	1.11	1.13	1.09
7333.	5.30	5.97	1.13	.83	1.11	1.13	1.10

6942.	4.80	1.45	1.47	1.41	1.45	1.42
6975.	3.62	1.44	1.47	1.42	1.44	1.41
7019.	3.68	1.45	1.47	1.42	1.44	1.42
7089.	3.89	1.45	1.47	1.42	1.43	1.43
7149.	3.69	1.46	1.47	1.43	1.44	1.42
7181.	3.26	1.45	1.46	1.42	1.42	1.42
7213.	3.24	1.45	1.46	1.42	1.45	1.42
7245.	3.12	1.46	1.46	1.43	1.45	1.42
7277.	3.36	1.47	1.50	1.45	1.50	1.43
7309.	4.03	1.44	1.45	1.42	1.44	1.41
7333.	3.99	1.45	1.46	1.42	1.46	1.41
	4.06	1.45	1.45	1.43	1.46	1.41

PACK NO. 102
GULTON 20 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C

CYCLE NO. PACK CURRENT
VOLTAGE 6.00

CELL VOLTAGES
1 2 3 4 5

3429. 4.86 6.02 1.22 1.22 1.23 1.21 1.20
3470. 4.88 6.04 1.22 1.22 1.23 1.23 1.21
3502. 4.92 6.06 1.22 1.22 1.23 1.23 1.22
3552. 4.90 6.07 1.23 1.23 1.23 1.23 1.21

END OF
DISCHARGE

3612. 4.87 6.03 1.25 1.25 1.22 1.22 1.16

3429. 5.96 1.07 1.55 1.55 1.42 1.42 1.42
3470. 6.02 .95 1.54 1.54 1.46 1.46 1.48
3502. 6.03 .97 1.54 1.55 1.46 1.46 1.47
3552. 6.03 .80 1.59 1.61 1.42 1.42 1.44

END OF
CHARGE

3612. 5.96 1.38 1.60 1.59 1.39 1.39 1.39

TEST TEMPERATURE 0 C
ORBIT PERIOD 3 HOURS

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

PACK NO. 116
GULTON 20 A.H.

CYCLE NO. PACK VOLTAGE 10.00 CURRENT 1 2 3 4 5 CELL VOLTAGES

END OF
DISCHARGE

END OF
CHARGE

3285.	5.85	10.04	1.18	1.19	1.14	1.20	1.17
3326.	5.82	10.05	1.18	1.18	1.13	1.19	1.16
3358.	5.86	10.04	1.19	1.19	1.12	1.20	1.17
3408.	5.92	10.03	1.20	1.20	1.15	1.21	1.19
3437.	5.86	10.06	1.17	1.19	1.15	1.21	1.18

3285.	7.80	2.30	1.46	1.62	1.61	1.59	1.56
3326.	7.86	1.83	1.47	1.66	1.61	1.59	1.56
3358.	7.88	1.71	1.49	1.66	1.60	1.59	1.56
3408.	7.88	1.74	1.45	1.64	1.64	1.61	1.58
3437.	7.85	2.23	1.42	1.66	1.63	1.62	1.58

PACK NO. 77
GULTON 20 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 3 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT	CELL VOLTAGES					END OF DISCHARGE
			1	2	3	4	5	
3392.	5.45	6.01	1.10	1.09	1.07	1.08	1.12	
3443.	5.44	5.99	1.10	1.09	1.06	1.08	1.12	
3512.	5.38	6.01	1.09	1.07	1.04	1.10	1.12	
3555.	5.47	6.00	1.12	1.11	1.08	1.11	1.14	
3587.	5.43	5.99	1.10	1.09	1.05	1.09	1.12	
3622.	5.24	6.06	1.06	1.03	1.01	1.05	1.12	
		1.92						
3392.	6.99	1.93	1.41	1.40	1.40	1.41	1.41	END OF CHARGE
3443.	7.00	1.92	1.41	1.40	1.40	1.40	1.41	
3512.	7.01	1.92	1.42	1.39	1.40	1.41	1.40	
3555.	6.97	1.93	1.42	1.41	1.41	1.42	1.42	
3587.	7.01	1.94	1.42	1.40	1.40	1.41	1.41	
3622.	6.91	1.87	1.39	1.38	1.38	1.39	1.39	

PACK NO. 91 GULTON 20 A.H.		DEPTH OF DISCHARGE 25 PERCENT OF RECHARGE 160					TEST TEMPERATURE 40 C ORBIT PERIOD 3 HOURS					END OF DISCHARGE	END OF CHARGE	
CYCLE NO.	PACK VOLTAGE	CURRENT 10.00	1	2	3	4	5							
3264.	4.29	10.05	1.11	1.11	1.00	.00	1.09							
3315.	4.24	10.20	1.10	1.11	.98	.00	1.09							
3384.	3.27	9.86	1.12	1.12	.06	.00	1.11							
3404.	3.29	10.04	1.11	1.11	.00	.00	1.10							
3439.	3.15	10.33	1.05	1.07	.00	.00	1.04							
3264.	5.78	2.87	1.47	1.47	1.43	.00	1.46							
3315.	5.80	2.85	1.47	1.48	1.42	.00	1.46							
3384.	4.49	3.18	1.49	1.52	.00	.00	1.49							
3404.	4.34	2.32	1.46	1.48	.00	.00	1.45							
3439.	4.27	2.34	1.43	1.44	.00	.00	1.43							

PACK NO. 103
G.E. 5 A.H. NIMBUS

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 110

TEST TEMPERATURE 0 °C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 1.50

CELL VOLTAGES
1 2 3 4 5

143. 6.16 1.49
176. 6.14 1.51
220. 6.21 1.50
256. 6.16 1.51
290. 6.16 1.51
320. 6.18 1.52
383. 6.17 1.54
400. 6.13 1.53
432. 6.16 1.52
464. 6.17 1.52
496. 6.11 1.52
528. 6.14 1.52
560. 6.15 1.52

1.23 1.23 1.23 1.24 1.24
1.23 1.23 1.23 1.23 1.23
1.16 1.24 1.24 1.24 1.24
1.23 1.23 1.23 1.23 1.23
1.23 1.23 1.23 1.23 1.23
1.24 1.21 1.25 1.25 1.25
1.23 1.23 1.24 1.24 1.23
1.23 1.24 1.24 1.24 1.23
1.23 1.73 1.24 1.24 1.23
1.23 1.24 1.24 1.24 1.23
1.22 1.22 1.22 1.23 1.22
1.22 1.23 1.23 1.23 1.23
1.23 1.23 1.23 1.24 1.23

END OF
DISCHARGE

143. 7.42 .83
176. 7.41 .43
220. 7.41 .43
256. 7.43 .44
290. 7.43 .44
320. 7.54 .60
383. 7.59 .65
400. 7.55 .69
432. 7.56 .73
464. 7.53 .71
496. 7.44 .60
528. 7.52 .58
560. 7.59 .71

1.48 1.48 1.50 1.48 1.48
1.48 1.48 1.50 1.48 1.48
1.48 1.48 1.50 1.48 1.48
1.48 1.48 1.50 1.48 1.48
1.50 1.53 1.53 1.50 1.50
1.51 1.51 1.53 1.51 1.51
1.52 1.52 1.53 1.52 1.51
1.51 1.51 1.52 1.51 1.50
1.51 1.50 1.52 1.50 1.49
1.50 1.49 1.50 1.48 1.48
1.51 1.50 1.52 1.50 1.49
1.52 1.52 1.53 1.51 1.51

END OF
CHARGE

PACK NO. 106 G.E. 5 A.H. NIMBUS		DEPTH OF DISCHARGE 15 PERCENT OF RECHARGE 120					TEST TEMPERATURE 25 C ORBIT PERIOD 90 MIN.		END OF DISCHARGE
CYCLE NO.	PACK VOLTAGE	CELL VOLTAGES							
		1	2	3	4	5			
107.	6.20	1.54	1.25	1.22	1.25	1.26			
148.	6.12	1.55	1.22	1.23	1.23	1.22			
186.	6.14	1.50	1.23	1.24	1.23	1.23			
234.	6.14	1.50	1.23	1.23	1.23	1.23			
260.	6.13	1.50	1.23	1.23	1.22	1.22			
292.	6.12	1.49	1.23	1.23	1.22	1.22			
34.	6.11	1.49	1.23	1.23	1.22	1.22			
380.	6.12	1.49	1.23	1.23	1.22	1.22			
404.	6.14	1.49	1.23	1.24	1.23	1.23			
469.	6.10	1.50	1.22	1.23	1.22	1.22			
500.	6.12	1.49	1.23	1.24	1.23	1.23			
532.	6.14	1.49	1.23	1.24	1.23	1.23			
562.	6.14	1.48	1.23	1.23	1.22	1.23			
588.	6.12	1.49	1.23	1.23	1.22	1.22			
107.	7.15	.90	1.44	1.43	1.43	1.43	1.43		
148.	7.09	.89	1.43	1.42	1.42	1.42	1.42	1.42	
186.	7.11	.89	1.44	1.42	1.42	1.42	1.42	1.42	
234.	7.11	.89	1.44	1.42	1.42	1.42	1.42	1.42	
260.	7.12	.89	1.44	1.43	1.43	1.43	1.43	1.43	
292.	7.12	.89	1.44	1.43	1.42	1.42	1.42	1.42	
334.	7.11	.89	1.44	1.43	1.42	1.42	1.42	1.42	
380.	7.12	.89	1.44	1.43	1.42	1.42	1.42	1.42	
404.	7.13	.89	1.45	1.43	1.43	1.43	1.43	1.43	
468.	7.10	.90	1.44	1.43	1.42	1.42	1.42	1.42	
500.	7.12	.89	1.44	1.43	1.43	1.43	1.43	1.43	
532.	7.12	.89	1.44	1.43	1.42	1.42	1.42	1.42	
562.	7.13	.89	1.44	1.43	1.42	1.42	1.42	1.42	
588.	7.13	.89	1.44	1.43	1.43	1.43	1.43	1.43	

PACK NO. 113
G.E. 5 A.H. NIMBUS

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 130

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 1.50

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

107.	6.10	1.30	1.23	1.18	1.24	1.24	1.24
148.	6.00	1.30	1.19	1.20	1.20	1.20	1.20
186.	6.01	1.49	1.19	1.20	1.20	1.20	1.20
260.	5.98	1.49	1.19	1.20	1.20	1.20	1.20
292.	5.98	1.49	1.19	1.20	1.20	1.20	1.19
334.	5.97	1.46	1.20	1.20	1.20	1.20	1.20
380.	6.01	1.49	1.20	1.21	1.21	1.21	1.20
404.	5.95	1.49	1.19	1.20	1.20	1.20	1.20
468.	5.96	1.49	1.19	1.20	1.20	1.20	1.19
500.	5.94	1.48	1.19	1.20	1.20	1.20	1.19
532.	5.94	1.48	1.19	1.20	1.20	1.20	1.19
562.	5.92	1.49	1.18	1.19	1.19	1.19	1.19
588.	5.90	1.49	1.18	1.18	1.19	1.19	1.18

107.	7.05	.98	1.40	1.41	1.40	1.40	1.41
148.	7.01	.84	1.40	1.40	1.39	1.40	1.40
186.	7.01	.97	1.40	1.40	1.40	1.40	1.40
260.	7.01	.99	1.40	1.40	1.40	1.40	1.40
292.	7.02	.99	1.40	1.40	1.40	1.40	1.40
334.	7.02	.99	1.41	1.41	1.41	1.41	1.41
380.	7.04	.99	1.41	1.41	1.41	1.41	1.40
404.	7.00	.98	1.41	1.41	1.40	1.40	1.40
468.	7.01	.99	1.40	1.40	1.40	1.40	1.40
500.	7.01	.98	1.40	1.40	1.40	1.40	1.40
532.	6.96	.98	1.39	1.39	1.39	1.38	1.38
562.	6.96	.99	1.39	1.39	1.39	1.39	1.39
588.	6.95	.99	1.39	1.39	1.39	1.39	1.39

PACK NO. 117
GULTON 5 A.M. NINJUS

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 110

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 1.50

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

1.	6.28	1.26	1.26	1.26	1.26	1.26
37.	6.12	1.26	1.23	1.22	1.22	1.22
70.	6.01	1.26	1.23	1.22	1.22	1.21
102.	5.96	1.26	1.23	1.22	1.22	1.21
180.	5.12	1.26	1.23	1.22	1.22	1.22
212.	6.10	1.26	1.23	1.22	1.22	1.22
244.	6.17	1.26	1.24	1.24	1.24	1.23
270.	6.10	1.26	1.22	1.22	1.22	1.22
302.	6.12	1.26	1.23	1.23	1.23	1.23

1.	7.28	1.47	1.48	1.46	1.46	1.46
37.	7.23	1.54	1.50	1.50	1.51	1.51
70.	7.23	1.47	1.44	1.44	1.45	1.45
102.	7.21	1.47	1.43	1.43	1.43	1.43
180.	7.48	1.50	1.48	1.48	1.48	1.48
212.	7.48	1.50	1.48	1.48	1.48	1.48
244.	7.49	1.49	1.48	1.48	1.48	1.48
270.	7.51	1.49	1.48	1.48	1.48	1.48
302.	7.60	1.50	1.50	1.50	1.50	1.50

PACK NO. 120
GULTON 5 A.H. NIMBUS

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 120

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CYCLE NO.	PACK VOLTAGE	CURRENT 1.50	CELL VOLTAGES					END OF DISCHARGE
			1	2	3	4	5	
25.	6.26	1.52	1.26	1.26	1.25	1.25	1.24	
63.	6.17	1.51	1.25	1.24	1.24	1.24	1.23	
137.	6.14	1.50	1.24	1.24	1.23	1.23	1.22	
169.	6.14	1.50	1.24	1.23	1.23	1.23	1.22	
211.	6.13	1.50	1.24	1.23	1.22	1.23	1.22	
257.	6.13	1.49	1.24	1.23	1.23	1.23	1.22	
281.	6.12	1.48	1.25	1.24	1.23	1.24	1.23	
319.	6.27	1.48	1.27	1.26	1.26	1.26	1.25	
345.	6.11	1.49	1.24	1.23	1.23	1.23	1.22	
377.	6.11	1.48	1.24	1.23	1.23	1.23	1.22	
409.	6.13	1.48	1.24	1.23	1.23	1.23	1.22	
439.	6.11	1.49	1.24	1.22	1.22	1.23	1.22	
465.	6.11	1.49	1.24	1.22	1.22	1.23	1.22	
25.	7.14	.90	1.42	1.43	1.42	1.43	1.42	
63.	7.14	.89	1.43	1.43	1.42	1.43	1.42	
137.	7.15	.89	1.43	1.44	1.42	1.44	1.42	
169.	7.15	.89	1.43	1.43	1.42	1.43	1.42	
211.	7.16	.89	1.43	1.44	1.42	1.43	1.42	
257.	7.15	.89	1.43	1.43	1.42	1.43	1.42	
281.	7.14	.89	1.43	1.44	1.43	1.44	1.43	
319.	7.15	.89	1.43	1.44	1.42	1.43	1.42	
345.	7.13	.89	1.42	1.43	1.42	1.43	1.42	
377.	7.15	.88	1.43	1.44	1.42	1.43	1.42	
409.	7.15	.89	1.43	1.44	1.42	1.43	1.42	
439.	7.15	.89	1.43	1.44	1.42	1.43	1.42	
465.	7.15	.88	1.43	1.44	1.56	1.43	1.42	

END OF CHARGE

PACK NO. 127
GILTON 5 A.H. NIMBUS

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 130

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK VOLTAGE 1.50 CURRENT

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

71.	5.96	1.57	1.20	1.19	1.20	1.21	1.20	1.20
109.	5.97	1.47	1.20	1.19	1.20	1.21	1.20	1.20
157.	5.95	1.48	1.20	1.19	1.20	1.20	1.19	1.19
183.	5.93	1.47	1.19	1.18	1.20	1.20	1.19	1.19
215.	5.91	1.48	1.19	1.18	1.19	1.20	1.18	1.18
257.	5.89	1.47	1.17	1.17	1.19	1.19	1.17	1.17
303.	5.93	1.47	1.19	1.19	1.20	1.20	1.19	1.19
327.	5.91	1.47	1.18	1.18	1.20	1.20	1.19	1.19
365.	6.12	1.47	1.23	1.22	1.23	1.24	1.23	1.23
391.	5.88	1.48	1.18	1.17	1.19	1.19	1.18	1.18
423.	5.88	1.47	1.18	1.17	1.19	1.20	1.18	1.18
455.	5.87	1.47	1.17	1.17	1.19	1.19	1.18	1.18
485.	5.84	1.49	1.16	1.16	1.18	1.19	1.17	1.17
511.	5.82	1.48	1.16	1.15	1.18	1.19	1.17	1.17

71.	7.00	.98	1.40	1.41	1.40	1.40	1.40	1.40
109.	7.00	1.01	1.41	1.41	1.40	1.40	1.40	1.40
157.	6.96	.97	1.40	1.40	1.39	1.39	1.39	1.39
183.	7.01	.97	1.41	1.41	1.40	1.40	1.40	1.40
215.	7.00	.97	1.41	1.41	1.40	1.40	1.40	1.40
257.	6.98	.97	1.40	1.40	1.39	1.39	1.39	1.39
303.	7.04	.97	1.42	1.42	1.41	1.41	1.41	1.41
327.	7.04	.97	1.42	1.42	1.41	1.40	1.40	1.40
365.	7.03	.97	1.41	1.41	1.41	1.40	1.40	1.40
391.	7.03	.97	1.41	1.41	1.40	1.40	1.40	1.40
423.	7.03	.97	1.41	1.41	1.39	1.39	1.39	1.39
455.	6.97	.97	1.40	1.40	1.39	1.39	1.39	1.39
485.	6.99	.97	1.40	1.40	1.39	1.39	1.39	1.39
511.	6.98	.97	1.40	1.40	1.39	1.39	1.39	1.39

PACK NO. 79
GULTON 6 A.H.

TEST TEMPERATURE 25 C
ORBIT PERIOD 24 HOURS

CYCLE NO.	PACK VOLTAGE	CURRENT 3.0	DEPTH OF DISCHARGE 50 PERCENT OF RECHARGE 200					END OF DISCHARGE
			1	2	3	4	5	
390.	3.38	3.03	.00	1.14	.00	1.11	1.12	
399.	3.21	2.93	.00	1.02	.00	1.00	1.02	
407.	2.98	2.99	.00	.99	.00	.96	1.00	
		.26						
390.	4.19	.24	.00	1.45	.00	1.38	1.43	END OF CHARGE
399.	4.20	.27	.00	1.40	.00	1.40	1.40	
407.	4.21	.26	.00	1.40	.00	1.40	1.39	

PACK NO. 188 DELCO 25 A.H. NAOH		DEPTH OF DISCHARGE 40 PERCENT OF RECHARGE					TEST TEMPERATURE 25 C ORBIT PERIOD 3 HRS.		
CYCLE NO.	PACK CURRENT VOLTAGE 20.00	1	2	3	4	5			
299.	5.64 19.88	1.19	1.05	1.22	1.00	1.21			END OF DISCHARGE
302.	4.20 19.92	1.11	.55	.96	.35	1.15			
323.	5.21 19.93	1.18	.81	1.20	.77	1.20			
325.	3.52 19.92	1.12	.48	.96	.41	.52			
299.	9.76 15.00	1.95	2.00	1.94	1.94	1.94			END OF CHARGE
302.	9.87 .86	1.95	1.99	1.95	1.94	1.94			
323.	9.88 .71	1.96	1.98	1.94	1.95	1.97			
325.	9.79 .74	1.95	1.97	1.94	1.95	1.99			

PACK NO. 9 YARDLEY 12 A.H. AGZN			DEPTH OF DISCHARGE 42 PERCENT OF RECHARGE			TEST TEMPERATURE 25 C ORBIT PERIOD 24 HRS.								
CYCLE NO.	PACK VOLTAGE	CURRENT	1	2	CELL VOLTAGES	3	4	5	6	7	8	9	10	END OF DISCHARGE
1.	15.25	4.94	1.52	1.53	1.53	1.53	1.53	1.52	1.53	1.53	1.55	1.52	1.52	
10.	15.00	4.94	1.49	1.50	1.50	1.50	1.50	1.48	1.51	1.50	1.52	1.50	1.49	
18.	14.90	4.95	1.49	1.49	1.49	1.49	1.49	1.48	1.50	1.49	1.52	1.50	1.49	
		.50												END OF CHARGE
1.	19.76	.01	2.00	2.01	2.00	2.00	2.00	2.02	1.87	2.01	2.08	1.86	2.00	
10.	19.81	.01	2.00	2.00	2.00	2.00	2.00	2.01	1.91	2.01	2.04	1.88	2.00	
13.	19.97	.00	2.00	2.00	2.00	2.00	2.00	2.00	2.01	2.01	2.04	1.98	2.00	

PACK NO. 315
GULTON 4 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 1.2

CELL VOLTAGES
1 2 3 4 5

4250.	5.11	1.19	1.23	1.23	1.23	1.23	1.22
4269.	6.16	1.19	1.24	1.15	1.23	1.24	1.23
4324.	6.10	1.19	1.23	1.23	1.23	1.22	1.22
4457.	6.15	1.19	1.24	1.24	1.24	1.24	1.23
4489.	6.13	1.18	1.24	1.24	1.24	1.24	1.23
4523.	6.09	1.18	1.23	1.23	1.23	1.23	1.22
4545.	6.21	1.19	1.25	1.25	1.25	1.25	1.25

END OF
DISCHARGE

4250.	7.74	.69	1.54	1.56	1.53	1.56	1.55
4269.	7.70	.70	1.54	1.55	1.52	1.55	1.55
4324.	7.72	.69	1.54	1.55	1.53	1.56	1.54
4457.	7.75	.70	1.54	1.58	1.53	1.56	1.55
4489.	7.74	.68	1.54	1.57	1.53	1.56	1.55
4523.	7.57	.41	1.51	1.54	1.49	1.52	1.51
4545.	7.72	.64	1.53	1.56	1.53	1.55	1.54

END OF
CHARGE

PACK NO. 326
GULTON 4 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 2.0

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

4420.	5.97	1.98	1.19	1.20	1.19	1.18	1.19	1.19
4453.	5.94	1.98	1.19	1.20	1.19	1.18	1.19	1.19
4497.	5.95	1.98	1.19	1.11	1.19	1.19	1.19	1.19
4533.	5.90	1.98	1.18	1.19	1.18	1.18	1.18	1.18
4548.	6.10	1.99	1.23	1.24	1.20	1.22	1.24	1.24
4606.	6.02	2.00	1.20	1.21	1.20	1.19	1.20	1.20
4628.	5.94	1.98	1.20	1.21	1.20	1.20	1.20	1.20
4660.	5.95	1.98	1.20	1.20	1.19	1.19	1.19	1.19
4692.	5.97	1.99	1.20	1.20	1.19	1.20	1.19	1.19
4724.	5.96	1.97	1.20	1.20	1.19	1.19	1.19	1.19
4756.	5.99	1.98	1.20	1.20	1.20	1.19	1.20	1.20
4788.	5.99	1.99	1.20	1.20	1.20	1.19	1.20	1.20
4812.	5.94	1.99	1.20	1.20	1.19	1.19	1.19	1.19

END OF
CHARGE

4420.	7.79	1.15	1.56	1.54	1.56	1.57	1.54	1.54
4453.	7.76	.83	1.57	1.54	1.56	1.56	1.55	1.55
4497.	7.68	.84	1.56	1.53	1.55	1.56	1.54	1.54
4533.	7.72	.75	1.56	1.53	1.55	1.56	1.54	1.54
4548.	7.49	.83	1.50	1.48	1.50	1.50	1.48	1.48
4606.	7.81	.82	1.58	1.54	1.57	1.58	1.55	1.55
4628.	7.71	.88	1.56	1.54	1.56	1.57	1.55	1.55
4660.	7.70	.76	1.55	1.52	1.55	1.56	1.54	1.54
4692.	7.07	.79	1.42	1.42	1.42	1.42	1.41	1.41
4724.	7.74	.43	1.56	1.54	1.55	1.57	1.55	1.55
4756.	7.77	.84	1.57	1.54	1.56	1.57	1.55	1.55
4788.	7.78	.84	1.57	1.54	1.57	1.57	1.56	1.56
4812.	7.75	.84	1.56	1.53	1.56	1.57	1.54	1.54

PACK NO. 204
GULTON 4 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 2.0

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

4270.	5.76	1.99	1.14	1.13	1.14	1.14	1.14	1.15
4320.	5.94	2.00	1.19	1.17	1.19	1.17	1.17	1.18
4332.	5.90	2.00	1.18	1.16	1.18	1.16	1.17	1.17
4364.	5.88	2.01	1.17	1.15	1.18	1.16	1.17	1.17
4406.	5.88	2.00	1.18	1.15	1.17	1.16	1.17	1.17
4451.	5.90	2.00	1.18	1.16	1.18	1.17	1.17	1.17
4476.	5.84	2.00	1.17	1.15	1.17	1.16	1.17	1.17
4512.	5.94	1.99	1.19	1.17	1.19	1.17	1.18	1.18
4538.	5.83	2.00	1.17	1.14	1.17	1.16	1.16	1.16
4570.	5.87	1.99	1.18	1.15	1.17	1.16	1.17	1.17
4604.	5.85	2.00	1.17	1.15	1.17	1.16	1.16	1.16
4638.	5.90	2.00	1.18	1.16	1.18	1.17	1.17	1.17
4660.	5.89	2.00	1.18	1.16	1.18	1.16	1.17	1.17

4270.	7.28	1.25	1.45	1.45	1.43	1.46	1.47
4320.	7.34	1.23	1.46	1.46	1.44	1.48	1.47
4332.	7.34	1.25	1.45	1.46	1.44	1.48	1.47
4364.	7.33	1.26	1.45	1.45	1.44	1.47	1.47
4406.	7.32	1.26	1.45	1.45	1.44	1.47	1.47
4451.	7.30	1.26	1.45	1.45	1.44	1.47	1.47
4476.	7.31	1.26	1.46	1.46	1.44	1.48	1.47
4512.	7.33	1.25	1.45	1.46	1.44	1.48	1.47
4538.	7.31	1.26	1.45	1.45	1.44	1.47	1.46
4570.	7.34	1.25	1.46	1.46	1.44	1.48	1.47
4604.	7.32	1.26	1.45	1.45	1.44	1.48	1.47
4638.	7.34	1.26	1.45	1.45	1.44	1.48	1.47
4660.	7.34	1.25	1.46	1.46	1.44	1.48	1.47

PACK NO. 214
GULTON 4 A.H.

DEPTH OF DISCHARGE 40
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 3.2

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

3986.	5.67	3.20	1.12	1.01	1.13	1.11	1.13
4022.	5.53	3.20	1.09	1.11	1.11	1.09	1.10
4056.	5.56	3.20	1.09	1.11	1.11	1.10	1.10
4086.	5.59	3.18	1.08	.99	1.11	1.10	1.10
4144.	5.44	3.19	1.06	1.09	1.09	1.09	1.08
4166.	5.51	3.20	1.09	1.12	1.11	1.11	1.10
4198.	5.37	3.19	1.05	1.08	1.08	1.07	1.06
4230.	5.56	3.21	1.09	1.12	1.11	1.11	1.10
4262.	5.61	3.20	1.11	1.13	1.11	1.11	1.11
4294.	5.63	3.20	1.11	1.13	1.12	1.12	1.11
4326.	5.63	3.21	1.12	1.13	1.12	1.11	1.12
4350.	5.62	3.21	1.10	1.13	1.12	1.11	1.11

END OF
CHARGE

3986.	7.35	2.00	1.45	1.45	1.51	1.46	1.45
4022.	7.35	1.50	1.45	1.45	1.51	1.47	1.44
4056.	7.36	1.40	1.45	1.44	1.51	1.47	1.45
4086.	7.39	1.51	1.44	1.45	1.51	1.47	1.45
4144.	7.35	1.47	1.44	1.45	1.51	1.47	1.45
4166.	7.35	1.43	1.45	1.45	1.51	1.48	1.45
4198.	7.37	1.45	1.45	1.45	1.51	1.47	1.45
4230.	7.35	1.45	1.44	1.44	1.50	1.47	1.44
4262.	7.39	1.66	1.45	1.46	1.52	1.48	1.45
4294.	7.42	1.62	1.46	1.46	1.52	1.49	1.45
4326.	7.46	1.83	1.46	1.47	1.53	1.50	1.46
4350.	7.39	1.58	1.45	1.46	1.52	1.48	1.45

PACK NO. 228
GULTON 4 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 1.2

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

4259.	5.94	1.19	1.20	1.19	1.18	1.14	1.18
4301.	6.03	1.19	1.21	1.20	1.20	1.19	1.20
4313.	5.99	1.20	1.20	1.20	1.20	1.17	1.19
4345.	5.99	1.20	1.20	1.19	1.19	1.17	1.19
4387.	6.00	1.20	1.20	1.19	1.19	1.17	1.19
4457.	5.95	1.19	1.20	1.20	1.19	1.17	1.19
4493.	6.03	1.19	1.21	1.20	1.20	1.18	1.20
4519.	5.96	1.19	1.20	1.19	1.19	1.16	1.19
4551.	6.01	1.18	1.20	1.20	1.20	1.17	1.20
4564.	6.14	1.20	1.23	1.23	1.22	1.20	1.23

END OF
CHARGE

4259.	7.12	.96	1.43	1.42	1.41	1.42	1.42
4301.	7.08	.97	1.41	1.40	1.40	1.41	1.41
4313.	7.08	.97	1.42	1.40	1.41	1.41	1.41
4345.	7.09	.98	1.42	1.41	1.41	1.41	1.41
4387.	7.09	.96	1.42	1.41	1.41	1.41	1.41
4457.	7.05	.78	1.42	1.41	1.41	1.41	1.41
4493.	7.05	.78	1.41	1.40	1.40	1.41	1.40
4519.	7.05	.76	1.41	1.40	1.40	1.41	1.40
4551.	7.07	.82	1.41	1.40	1.41	1.41	1.40
4564.	7.01	.97	1.40	1.40	1.40	1.40	1.40

PACK NO. 240
GULTON 4 A. H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK CURRENT VOLTAGE 2.0 1 2 3 4 5 CELL VOLTAGES

END OF
DISCHARGE

END OF
CHARGE

CYCLE NO.	PACK CURRENT	VOLTAGE 2.0	1	2	3	4	5	CELL VOLTAGES
4273.	5.50	2.00	1.09	1.10	1.09	1.09	1.07	
4324.	5.66	2.01	1.13	1.12	1.13	1.13	1.12	
4336.	5.49	2.01	1.10	1.08	1.09	1.09	1.08	
4368.	5.46	2.02	1.09	1.08	1.08	1.08	1.08	
4410.	5.46	2.02	1.08	1.09	1.09	1.08	1.08	
4455.	5.58	2.02	1.11	1.11	1.12	1.11	1.10	
4480.	5.38	2.01	1.07	1.08	1.08	1.08	1.07	
4516.	5.62	2.00	1.12	1.12	1.12	1.12	1.11	
4542.	5.43	2.02	1.08	1.08	1.08	1.08	1.07	
4574.	5.75	2.01	1.15	1.14	1.15	1.15	1.12	
4608.	5.46	2.01	1.09	1.08	1.09	1.10	1.06	
4642.	5.59	2.01	1.12	1.10	1.12	1.12	1.09	
4664.	5.50	2.00	1.10	1.09	1.10	1.10	1.08	
4273.	7.12	1.60	1.42	1.43	1.42	1.42	1.42	
4324.	7.11	.96	1.41	1.42	1.41	1.42	1.41	
4336.	7.12	1.02	1.41	1.42	1.42	1.42	1.41	
4368.	7.13	1.01	1.41	1.42	1.42	1.42	1.41	
4410.	7.13	.99	1.42	1.42	1.42	1.42	1.42	
4455.	7.12	.98	1.42	1.42	1.42	1.42	1.41	
4480.	7.12	.98	1.42	1.43	1.42	1.43	1.42	
4516.	7.13	.95	1.42	1.42	1.42	1.42	1.41	
4542.	7.13	.96	1.42	1.42	1.42	1.42	1.41	
4574.	7.15	1.06	1.42	1.43	1.43	1.43	1.42	
4608.	7.10	1.25	1.41	1.42	1.42	1.41	1.41	
4642.	7.12	1.27	1.41	1.42	1.42	1.42	1.41	
4664.	7.19	1.60	1.43	1.44	1.43	1.43	1.43	

PACK NO. 216
GULTON 12 A.11.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 115

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK CURRENT
VOLTAGE 3.6

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

1151.	6.17	3.61	1.23	1.23	1.22	1.22	1.22	1.22
1189.	6.17	3.62	1.23	1.23	1.23	1.23	1.23	1.22
1251.	6.17	3.62	1.23	1.23	1.23	1.23	1.23	1.22
1263.	6.16	3.62	1.22	1.23	1.22	1.22	1.22	1.22
1295.	6.16	3.61	1.22	1.23	1.22	1.22	1.22	1.22
1337.	6.17	3.60	1.23	1.23	1.23	1.22	1.22	1.22
1382.	6.18	3.54	1.23	1.23	1.23	1.23	1.23	1.23
1407.	6.17	3.54	1.23	1.24	1.23	1.23	1.23	1.23
1418.	6.25	3.54	1.24	1.25	1.24	1.25	1.24	1.24
1450.	6.24	3.64	1.24	1.25	1.24	1.24	1.24	1.24
1484.	6.24	3.60	1.24	1.25	1.24	1.24	1.24	1.24
1518.	6.24	3.59	1.24	1.25	1.24	1.24	1.24	1.24
1540.	6.23	3.61	1.24	1.25	1.24	1.24	1.24	1.24

1151.	2.07	1.58	1.49	1.48	1.48	1.48	1.48	1.50
1189.	1.55	1.58	1.48	1.48	1.48	1.48	1.49	1.50
1251.	1.58	1.59	1.49	1.48	1.48	1.48	1.49	1.50
1263.	1.05	1.59	1.49	1.48	1.48	1.48	1.49	1.50
1295.	1.07	1.59	1.49	1.48	1.48	1.48	1.49	1.50
1337.	1.08	1.59	1.49	1.48	1.48	1.48	1.49	1.50
1382.	1.07	1.59	1.49	1.48	1.48	1.48	1.49	1.50
1407.	1.04	1.59	1.46	1.45	1.45	1.46	1.47	1.47
1418.	0.02	1.49	1.47	1.47	1.47	1.47	1.47	1.50
1450.	1.02	1.48	1.49	1.47	1.47	1.47	1.47	1.51
1484.	1.11	1.54	1.49	1.47	1.47	1.47	1.48	1.50
1484.	1.02	1.56	1.49	1.47	1.47	1.47	1.47	1.50
1518.	0.99	1.58	1.49	1.47	1.47	1.47	1.47	1.50
1540.	1.06	1.57	1.49	1.47	1.47	1.47	1.47	1.50

PACK NO. 301
GULTON 12 A.H.

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK CURRENT
VOLTAGE 6.00

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

CELL VOLTAGES
1 2 3 4 5

2094.	6.05	6.01	1.21	1.22	1.21	1.20	1.21
2128.	6.02	6.01	1.21	1.21	1.21	1.20	1.20
2202.	6.03	6.01	1.21	1.21	1.21	1.20	1.20
2234.	6.02	6.02	1.21	1.21	1.21	1.20	1.20
2266.	6.03	6.00	1.21	1.21	1.21	1.20	1.20
2352.	6.06	5.98	1.22	1.22	1.22	1.21	1.21
2384.	6.06	6.00	1.22	1.22	1.22	1.21	1.21
2416.	6.04	5.98	1.21	1.21	1.21	1.20	1.21
2450.	6.01	5.99	1.21	1.21	1.21	1.20	1.20
2474.	6.02	5.97	1.21	1.21	1.21	1.20	1.20
2514.	6.03	5.97	1.21	1.21	1.21	1.20	1.20
2536.	6.04	6.00	1.21	1.21	1.21	1.20	1.20

END OF
DISCHARGE

2094.	3.45	1.55	1.54	1.55	1.65	1.56
2128.	7.81	1.56	1.54	1.55	1.65	1.54
2202.	7.82	1.55	1.55	1.55	1.64	1.54
2234.	7.83	1.55	1.55	1.55	1.63	1.55
2266.	7.80	1.55	1.54	1.54	1.64	1.54
2352.	7.83	1.57	1.55	1.55	1.66	1.56
2384.	7.87	1.55	1.54	1.55	1.64	1.55
2416.	7.81	1.55	1.53	1.53	1.64	1.55
2450.	7.82	1.53	1.53	1.53	1.59	1.53
2474.	7.70	1.54	1.54	1.54	1.63	1.54
2514.	7.74	1.55	1.54	1.54	1.64	1.54
2536.	7.83	1.55	1.53	1.53	1.63	1.54
2536.	7.78	1.55	1.53	1.53	1.63	1.54

END OF
CHARGE

PACK NO. 227
GULTON 12 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 6.0

CELL VOLTAGE
3 4 5

END OF
DISCHARGE

END OF
CHARGE

1463. 5.82 6.55 1.17 1.15 1.15 1.15 1.16
1501. 5.92 5.98 1.18 1.17 1.18 1.18 1.18
1575. 5.73 5.93 1.14 1.13 1.14 1.14 1.15
1607. 5.62 5.95 1.13 1.12 1.13 1.13 1.14
1649. 5.60 5.96 1.11 1.10 1.10 1.12 1.13
1695. 5.63 5.95 1.12 1.11 1.11 1.13 1.13
1719. 5.59 5.95 1.12 1.11 1.11 1.13 1.13

1783. 5.56 5.94 1.11 1.10 1.09 1.11 1.12
1815. 5.54 6.00 1.10 1.10 1.09 1.11 1.11
1847. 5.70 5.95 1.14 1.13 1.13 1.14 1.13
1877. 5.66 5.93 1.13 1.12 1.12 1.13 1.13
1903. 5.59 5.90 1.12 1.11 1.11 1.12 1.12

1463. 7.20 3.75 1.43 1.43 1.42 1.42 1.44
1501. 7.21 3.80 1.43 1.43 1.43 1.43 1.44
1575. 7.21 3.77 1.43 1.43 1.43 1.43 1.44
1607. 7.20 3.77 1.43 1.43 1.43 1.43 1.44
1649. 7.20 3.79 1.43 1.43 1.42 1.43 1.44
1695. 7.21 3.79 1.43 1.43 1.43 1.43 1.44

1757. 7.22 3.79 1.43 1.44 1.43 1.44 1.45
1783. 7.19 3.78 1.43 1.43 1.42 1.43 1.44
1815. 7.21 3.81 1.43 1.44 1.43 1.43 1.44
1847. 7.20 3.80 1.43 1.43 1.43 1.43 1.44
1877. 7.21 3.82 1.43 1.43 1.43 1.43 1.44
1903. 7.23 3.81 1.44 1.44 1.43 1.44 1.45

PACK NO. 296
GULTON 12 A.H.

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK CURRENT
VOLTAGE 9.60

DEPTH OF DISCHARGE 40
PERCENT OF RECHARGE 125

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

CYCLE NO.	PACK CURRENT VOLTAGE 9.60	1	2	3	4	5	END OF DISCHARGE
2316.	5.23	1.06	1.06	1.06	1.04	1.05	
2350.	5.37	1.08	1.09	1.07	1.06	1.07	
2396.	5.25	1.05	.97	1.05	1.03	1.04	
2424.	5.07	1.02	1.04	1.02	.99	1.00	
2456.	5.18	1.04	1.06	1.04	1.03	1.02	
2488.	5.09	1.03	1.04	1.02	1.01	1.02	
2574.	5.34	1.09	1.09	1.08	1.05	1.07	
2606.	5.46	1.10	1.10	1.10	1.07	1.09	
2638.	5.54	1.11	1.11	1.12	1.10	1.11	
2672.	5.05	1.02	1.01	1.02	1.00	1.01	
2693.	5.46	1.11	1.11	1.10	1.08	1.10	
2733.	5.49	1.11	1.11	1.10	1.07	1.09	
2755.	5.34	1.08	1.07	1.06	1.04	1.07	
2316.	7.37	1.48	1.49	1.47	1.47	1.49	
2350.	7.39	1.48	1.48	1.46	1.46	1.48	
2396.	7.37	1.48	1.48	1.46	1.46	1.48	
2424.	7.37	1.47	1.48	1.46	1.46	1.48	
2456.	7.38	1.48	1.49	1.47	1.46	1.49	
2488.	7.37	1.48	1.48	1.47	1.46	1.49	
2574.	7.42	1.49	1.49	1.48	1.48	1.50	
2606.	7.37	1.47	1.48	1.46	1.47	1.48	
2638.	7.44	1.49	1.50	1.47	1.47	1.50	
2672.	7.32	1.47	1.47	1.46	1.46	1.46	
2693.	7.35	1.48	1.48	1.47	1.47	1.48	
2733.	7.35	1.47	1.47	1.46	1.46	1.47	
2755.	7.37	1.47	1.48	1.46	1.46	1.47	

PACK NO. 78
GULTON 12 A.H.

DEPTH OF DISCHARGE 15
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK CURRENT
VOLTAGE 3.60

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

2028.	4.65	3.39	1.15	1.14	1.16	.00	1.16
2066.	4.60	3.55	1.14	1.13	1.15	.00	1.15
2114.	4.64	3.55	1.15	1.14	1.17	.00	1.16
2140.	4.58	3.57	1.13	1.13	1.16	.00	1.14
2172.	4.62	3.51	1.14	1.14	1.16	.00	1.15
2214.	4.59	3.50	1.13	1.13	1.15	.00	1.14
2260.	4.68	3.59	1.16	1.16	1.17	.00	1.17
2284.	4.58	3.58	1.14	1.14	1.16	.00	1.15
2348.	4.60	3.59	1.13	1.14	1.16	.00	1.15
2380.	4.58	3.53	1.13	1.13	1.15	.00	1.14
2412.	4.56	3.60	1.13	1.13	1.15	.00	1.13
2442.	4.55	3.51	1.13	1.12	1.15	.00	1.13
2468.	4.43	3.66	1.10	1.09	1.12	.00	1.10

2028.	5.60	2.88	1.40	1.40	1.40	.00	1.40
2066.	5.61	2.86	1.40	1.40	1.40	.00	1.41
2114.	5.61	2.93	1.40	1.40	1.40	.00	1.41
2140.	5.61	2.92	1.40	1.40	1.40	.00	1.41
2172.	5.61	2.93	1.40	1.40	1.40	.00	1.41
2214.	5.61	2.93	1.40	1.40	1.40	.00	1.40
2260.	5.63	2.93	1.41	1.41	1.41	.00	1.41
2284.	5.59	2.92	1.41	1.41	1.41	.00	1.41
2348.	5.60	2.92	1.41	1.40	1.40	.00	1.40
2380.	5.61	2.90	1.41	1.40	1.40	.00	1.41
2412.	5.55	2.90	1.39	1.39	1.39	.00	1.39
2442.	5.56	2.92	1.39	1.39	1.39	.00	1.39
2468.	5.56	2.92	1.39	1.39	1.39	.00	1.39

PACK NO. 290
GULTON 12 A.H.

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 160

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 6.00

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

2320.	5.51	5.91	1.09	1.12	1.11	1.12	1.08
2353.	5.44	5.91	1.08	1.11	1.10	1.11	1.07
2397.	5.39	6.00	1.07	1.09	1.07	1.12	1.06
2467.	5.47	6.04	1.09	1.10	1.10	1.11	1.09
2497.	6.36	5.28	1.27	1.27	1.26	1.27	1.26
2555.	6.40	5.58	1.28	1.28	1.28	1.28	1.28
2577.	5.44	5.98	1.10	1.10	1.11	1.10	1.06
2609.	6.35	5.13	1.27	1.27	1.27	1.27	1.27
2641.	6.39	5.14	1.28	1.28	1.28	1.28	1.28
2673.	6.29	5.35	1.26	1.26	1.26	1.26	1.26
2705.	5.45	6.00	1.10	1.10	1.10	1.08	1.10
2737.	6.29	5.13	1.26	1.25	1.25	1.25	1.26
2761.	5.41	6.00	1.08	1.10	1.09	1.07	1.08

END OF
CHARGE

2320.	7.24	4.80	1.44	1.45	1.44	1.45	1.44
2353.	7.22	3.93	1.44	1.45	1.44	1.44	1.45
2397.	7.23	4.00	1.44	1.44	1.44	1.44	1.44
2467.	7.23	3.96	1.45	1.44	1.44	1.43	1.45
2497.	7.23	4.17	1.44	1.44	1.43	1.43	1.44
2555.	7.22	4.28	1.44	1.45	1.45	1.44	1.44
2577.	7.24	4.08	1.45	1.45	1.45	1.44	1.45
2609.	7.27	4.07	1.45	1.46	1.45	1.45	1.45
2641.	7.24	4.08	1.45	1.45	1.45	1.45	1.45
2673.	7.25	4.19	1.45	1.45	1.45	1.45	1.45
2705.	7.29	4.16	1.45	1.45	1.47	1.47	1.45
2737.	7.13	4.36	1.43	1.43	1.43	1.42	1.42
2761.	7.16	4.31	1.43	1.43	1.43	1.43	1.43
	7.16	4.34	1.43	1.43	1.44	1.42	1.44

PACK NO. 213
GULTON HSI 6 A.H.

TEST TEMPERATURE 0 C
ORBIT PERIOD 90 MIN.

CYCLE NO. PACK VOLTAGE 3.0 CURRENT

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 115

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

1145.	6.17	3.00	1.22	1.22	1.22	1.22	1.22	1.22
1191.	6.25	3.00	1.23	1.13	1.23	1.23	1.23	1.24
1219.	6.16	3.01	1.22	1.22	1.22	1.22	1.22	1.22
1251.	6.15	3.01	1.22	1.22	1.22	1.22	1.22	1.22
1283.	6.17	3.01	1.22	1.22	1.22	1.22	1.22	1.22
1369.	6.15	3.02	1.22	1.23	1.22	1.23	1.23	1.22
1382.	6.30	3.03	1.25	1.25	1.25	1.25	1.25	1.25
1416.	6.16	3.02	1.23	1.23	1.23	1.23	1.23	1.22
1440.	6.14	3.02	1.22	1.22	1.22	1.22	1.22	1.22
1480.	6.16	3.04	1.22	1.22	1.22	1.22	1.22	1.22
1502.	6.14	3.04	1.22	1.22	1.22	1.22	1.22	1.22

1145.	7.76	1.73	1.53	1.53	1.52	1.57	1.57	1.57
1191.	7.73	1.30	1.53	1.53	1.52	1.56	1.56	1.56
1219.	7.75	1.34	1.53	1.53	1.53	1.57	1.56	1.56
1251.	7.77	1.27	1.53	1.53	1.52	1.57	1.56	1.56
1283.	7.77	1.25	1.53	1.53	1.52	1.56	1.56	1.56
1369.	7.76	1.26	1.54	1.54	1.53	1.58	1.57	1.57
1382.	7.68	1.50	1.53	1.52	1.53	1.53	1.53	1.53
1416.	7.69	1.17	1.52	1.52	1.52	1.56	1.55	1.55
1440.	7.69	1.13	1.52	1.52	1.51	1.56	1.56	1.56
1480.	7.69	1.12	1.52	1.52	1.51	1.56	1.56	1.56
1502.	7.70	1.15	1.52	1.52	1.51	1.56	1.56	1.56

PACK NO. 218
GULTON HSI 6 A.H.

DEPTH OF DISCHARGE 40
PERCENT OF RECHARGE 125

TEST TEMPERATURE 25 C
ORBIT PERIOD 90 MIN.

CYCLE NO.	PACK VOLTAGE	CURRENT 4.8	CELL VOLTAGES				
			1	2	3	4	5
1116.	5.45	4.70	1.09	1.07	1.08	1.09	1.08
1149.	5.42	4.69	1.08	1.07	1.07	1.08	1.07
1229.	5.29	4.80	1.07	1.05	1.04	1.06	1.05
1263.	5.46	4.76	1.10	1.08	1.09	1.09	1.08
1293.	5.29	4.71	1.05	.94	1.04	1.05	1.02
1351.	5.15	4.69	1.03	1.03	1.02	1.04	1.01
1373.	5.37	4.78	1.09	1.08	1.07	1.08	1.07
1387.	5.18	4.83	1.04	1.05	1.03	1.01	1.04
1419.	5.42	4.82	1.09	1.09	1.07	1.09	1.07
1451.	5.56	4.81	1.12	1.12	1.09	1.11	1.11
1483.	5.62	4.72	1.13	1.13	1.12	1.13	1.12
1507.	5.57	4.71	1.12	1.11	1.10	1.11	1.11
1116.	7.26	3.00	1.44	1.45	1.43	1.44	1.44
1149.	7.27	2.99	1.44	1.46	1.44	1.45	1.45
1229.	7.27	3.01	1.44	1.45	1.44	1.45	1.45
1263.	7.27	3.01	1.44	1.45	1.44	1.45	1.45
1293.	7.29	3.01	1.44	1.45	1.44	1.45	1.45
1351.	7.27	3.01	1.44	1.45	1.44	1.46	1.45
1373.	7.27	3.01	1.45	1.46	1.45	1.46	1.46
1387.	7.10	3.01	1.44	1.42	1.41	1.42	1.42
1419.	7.24	3.01	1.44	1.45	1.44	1.45	1.45
1451.	7.27	3.02	1.45	1.45	1.44	1.45	1.45
1483.	7.28	3.01	1.45	1.46	1.44	1.46	1.46
1507.	7.28	3.00	1.44	1.45	1.44	1.46	1.45

END OF
DISCHARGE

END OF
CHARGE

PACK NO. 238
GULTON HSI 6 A.H.

TEST TEMPERATURE 40 C
ORBIT PERIOD 90 MIN.

CYCLE PACK CURRENT
NO. VOLTAGE 3.0

DEPTH OF DISCHARGE 25
PERCENT OF RECHARGE 160

CELL VOLTAGES
1 2 3 4 5

END OF
DISCHARGE

END OF
CHARGE

1116.	5.67	3.01	1.12	1.12	1.12	1.12	1.12	1.12
1149.	5.60	2.97	1.11	1.11	1.10	1.10	1.10	1.11
1193.	5.56	2.99	1.09	.98	1.09	1.10	1.10	1.10
1229.	5.56	2.99	1.10	1.10	1.10	1.10	1.10	1.11
1263.	5.63	2.96	1.11	1.12	1.11	1.11	1.11	1.12
1293.	5.56	2.96	1.10	.99	1.11	1.10	1.10	1.11
1351.	5.48	2.95	1.08	1.09	1.08	1.09	1.09	1.10
1373.	5.52	2.98	1.10	1.11	1.11	1.11	1.11	1.11
1387.	5.58	2.99	1.10	1.11	1.11	1.09	1.13	1.12
1419.	5.64	2.99	1.12	1.12	1.13	1.12	1.12	1.07
1451.	5.36	2.97	1.07	1.07	1.06	1.06	1.06	1.06
1483.	5.31	2.94	1.06	1.06	1.06	1.06	1.06	1.06
1507.	5.46	2.98	1.08	1.09	1.09	1.09	1.09	1.09

1116.	7.10	2.40	1.42	1.41	1.41	1.41	1.41	1.41
1149.	7.08	2.46	1.42	1.41	1.41	1.41	1.41	1.41
1193.	7.07	2.42	1.41	1.41	1.40	1.41	1.41	1.41
1229.	7.08	2.42	1.42	1.41	1.41	1.41	1.41	1.41
1263.	7.08	2.44	1.42	1.41	1.41	1.41	1.41	1.41
1293.	7.09	2.42	1.41	1.41	1.40	1.41	1.41	1.41
1351.	7.13	2.34	1.43	1.42	1.42	1.42	1.42	1.42
1373.	7.07	2.11	1.42	1.42	1.42	1.42	1.42	1.42
1387.	7.02	2.45	1.40	1.40	1.39	1.40	1.40	1.40
1419.	7.09	2.42	1.42	1.42	1.41	1.41	1.41	1.41
1451.	7.02	2.44	1.40	1.40	1.39	1.40	1.40	1.40
1483.	7.02	2.45	1.41	1.41	1.40	1.41	1.41	1.41
1507.	7.02	2.42	1.41	1.41	1.40	1.40	1.40	1.40

PACK NO. 11
 GU 6 A.H. 3RD ELECTRODE R 24 24 10 8 24
 TEST TEMPERATURE 25 C
 ORBIT PERIOD 90 MIN.

CYCLE NO.	PACK VOLTAGE	CURRENT 4.80	3RD ELECT VOLTAGES				CELL VOLTAGES					
			1	2	3	4	5	1	2	3	4	5
1186.	4.72	4.11	.187	.355	.157	.191	.264	.95	.99	1.04	.95	.97
1251.	5.50	4.82	.290	.281	.253	.267	.251	1.15	1.15	1.14	1.14	1.15
1284.	5.99	4.91	.304	.284	.234	.253	.262	1.25	1.25	1.25	1.24	1.25
1347.	5.52	4.87	.291	.421	.215	.218	.327	1.13	1.14	1.22	1.12	1.12
1410.	4.65	4.26	.219	.238	.155	.170	.221	.92	.99	.99	.99	.99
1490.	5.38	4.83	.291	.279	.193	.198	.246	1.11	1.13	1.13	1.12	1.12
1604.	5.63	4.74	.310	.268	.189	.196	.255	1.17	1.18	1.18	1.17	1.17

AH OUT
 2.393
 2.389
 2.426
 2.422
 2.422
 2.380
 2.362

END OF DISCHARGE

TRIP POINT

1186.	7.08	1.59	.297	.320	.265	.283	.279	1.46	1.46	1.47	1.45	1.46
1251.	7.01	1.07	.312	.314	.266	.276	.274	1.45	1.45	1.46	1.44	1.45
1284.	6.95	.97	.313	.313	.245	.254	.292	1.44	1.44	1.44	1.43	1.44
1347.	7.10	2.25	.322	.315	.218	.237	.275	1.46	1.47	1.48	1.46	1.47
1410.	7.11	1.84	.322	.310	.202	.219	.267	1.47	1.48	1.48	1.47	1.48
1490.	7.12	2.09	.323	.309	.196	.205	.253	1.47	1.47	1.48	1.47	1.47
1604.	7.07	1.58	.324	.294	.187	.191	.250	1.46	1.46	1.47	1.45	1.46

AH IN
 2.963
 2.595
 1.913
 2.289
 2.984
 2.540
 2.556

1186.	6.73	.13	.329	.342	.289	.298	.303	1.41	1.40	1.41	1.40	1.40
1251.	6.78	.13	.345	.351	.291	.299	.313	1.40	1.41	1.41	1.40	1.40
1284.	6.69	.06	.350	.339	.275	.279	.208	1.39	1.39	1.39	1.39	1.39
1347.	6.72	.05	.355	.364	.256	.262	.318	1.40	1.41	1.41	1.40	1.41
1410.	6.85	.09	.340	.341	.220	.230	.294	1.42	1.42	1.43	1.42	1.42
1490.	6.80	.07	.356	.352	.228	.230	.300	1.41	1.41	1.41	1.40	1.41
1604.	6.82	.07	.358	.339	.216	.212	.303	1.41	1.41	1.42	1.41	1.41

PACK NO. 23
 GU 6 A.H. 3RD ELECTRODE R 12 18 20 29 24

CYCLE NO.	PACK VOLTAGE	CURRENT	3RD	DEPTH OF DISCHARGE					25	TEST TEMPERATURE 25 C					AH OUT	END CHARGE
				1	2	3	4	5		1	2	3	4	5		
1240.	5.60	3.38	.208	.225	.226	.292	.275	.275	.275	1.17	1.17	1.17	1.17	1.17	1.518	END CHARGE
1273.	6.11	3.35	.210	.228	.239	.293	.298	.298	.298	1.17	1.27	1.27	1.27	1.27	1.498	DISCHARGE
1330.	5.78	3.09	.193	.352	.214	.287	.368	.368	.368	1.18	1.19	1.27	1.18	1.17	1.475	
1399.	5.55	3.35	.191	.214	.221	.284	.284	.284	.284	1.16	1.16	1.16	1.16	1.16	1.540	
1479.	5.46	3.09	.176	.197	.205	.261	.262	.262	.262	1.14	1.14	1.14	1.14	1.14	1.533	
1536.	5.54	3.05	.174	.192	.201	.253	.260	.260	.260	1.16	1.15	1.15	1.15	1.15	1.562	
1605.	5.60	3.10	.181	.199	.205	.258	.271	.271	.271	1.17	1.17	1.17	1.17	1.17	1.516	
1240.	6.90	.06	.267	.263	.273	.315	.323	.323	.323	1.43	1.43	1.43	1.42	1.43		TRIP POINT
1273.	6.86	.06	.249	.252	.275	.312	.318	.318	.318	1.42	1.42	1.43	1.42	1.42		
1330.	6.86	.03	.255	.265	.274	.309	.335	.335	.335	1.42	1.42	1.43	1.42	1.42		
1399.	6.83	.07	.241	.247	.258	.299	.324	.324	.324	1.43	1.43	1.43	1.42	1.43		
1479.	6.91	.11	.235	.238	.253	.294	.314	.314	.314	1.43	1.43	1.43	1.42	1.43		
1536.	7.02	1.05	.225	.226	.243	.284	.311	.311	.311	1.45	1.45	1.46	1.45	1.45		
1605.	6.90	.01	.232	.236	.250	.292	.318	.318	.318	1.43	1.43	1.43	1.42	1.43		
1240.	6.75	.01	.290	.295	.305	.372	.369	.369	.369	1.40	1.40	1.40	1.39	1.40	1.838	END CHARGE
1273.	6.74	.01	.273	.282	.304	.375	.367	.367	.367	1.39	1.40	1.40	1.40	1.40	2.647	
1330.	6.77	.01	.273	.286	.291	.352	.373	.373	.373	1.40	1.41	1.41	1.40	1.40	1.803	
1399.	6.76	.01	.261	.274	.290	.342	.366	.366	.366	1.40	1.40	1.41	1.40	1.40	1.803	
1479.	6.75	.00	.254	.263	.281	.332	.350	.350	.350	1.40	1.40	1.40	1.39	1.40	1.770	
1536.	6.77	.01	.248	.255	.276	.323	.345	.345	.345	1.40	1.40	1.40	1.40	1.40	1.881	
1605.	6.76	.00	.249	.255	.275	.323	.351	.351	.351	1.40	1.40	1.41	1.40	1.40	1.791	

125