

LMSC-D152635

SERIES 1

25 FEBRUARY 1972

CR 115481

## CASE FILE COPY



FINAL REPORT

PREPARED FOR
THE NATIONAL AERONAUTICS
AND SPACE ADMINISTRATION

MANNED SPACECRAFT CENTER • HOUSTON, TEXAS CONTRACT NAS9-11949



### ANNEX C

## SPACE SHUTTLE CANDIDATE INSULATOR/PROPELLANT COMPATIBILITY TEST PROGRAM

LOCKHEED MISSILES & SPACE COMPANY, INC.
A SUBSIDIARY OF LOCKHEED AIRCRAFT CORPORATION

SUNNYVALE, CALIFORNIA

### SHUTTLE/AGENA STUDY FINAL REPORT

# Annex C SPACE SHUTTLE CANDIDATE INSULATOR/PROPELLANT COMPATIBILITY TEST PROGRAM

Submitted to the

National Aeronautics and Space Administration

Manned Spacecraft Center

Houston, Texas

#### **FOREWORD**

Annex C contains supplemental data pertinent to the Shuttle/Agena Study Final Report. Although not required under Contract NAS9-11949, this preliminary information on the compatibility of candidate shuttle insulator material with earth-storable propellants should prove helpful in any evaluation of Agena capabilities for the proposed space tug missions. It is therefore included as a useful adjunct to the Final Report.

#### Annex C

## SPACE SHUTTLE CANDIDATE INSULATOR/PROPELLANT COMPATIBILITY TEST PROGRAM

It is recognized that some of the Agena space tug propellants could be absorbed by the space shuttle orbiter vehicle's reentry thermal insulation material during an emergency orbital propellant dump. A preliminary test program has been completed with the objective of determining the compatibility of two space shuttle candidate insulation samples with earth-storable propellants. The candidate insulation materials selected were SLA 561 (furnished by NASA) and LI 1500 (furnished by LMSC).

The test program involved nine 2 by 2 by 1 inch samples of each type of material. One sample was not tested and was utilized as a control sample. The propellant combinations used were inhibited red fuming nitric acid (IRFNA); a mixture of IRFNA and nitrogen tetroxide,  $N_2O_4$ ; and unsymmetrical dimethyl hydrazine (UDMH). The test setup is shown in Figs. 1 through 3; pre- and post-test photos of the test samples are shown in Figs. 4 through 8.

Two propellant exposure procedures were followed:

- 1. The specimens were placed in a vacuum chamber that was then evacuated to less than 10 microns. Propellant vapor was slowly injected into the chamber and held for approximately 2 hours.
- 2. The specimens were placed in an open-mouth container. Liquid propellant was admitted to the container at atmospheric conditions (approximately 60°F and 13.7 psia) and held for 2 hours.

Following exposure to propellants, all specimens were placed in an aluminum foil container and heated to 850°F for 5 minutes.

All specimens were weighed and a thermal conductivity index was determined before and after testing. Determination of an accurate, one-direction thermal conductivity value, using the standard equation

$$k = \frac{QL}{A\Delta T}$$

was not possible because the area-to-thickness ratio, A/L, was too small and sample edge heat losses could not be accounted for in the testing setup. Therefore, a thermal "conductivity index" was established in an attempt to evaluate possible degradation of sample chemical conductivity after propellant exposure and thermal conditioning. This conductivity index was calculated from the following equation:

conductivity index = 
$$\frac{\text{power input}}{\text{temperature differential}}$$

No conclusion as to actual thermal conductivity change can be drawn from the conductivity index values (see Table C-1) because of the measurement inaccuracies involved. However, it does appear that the thermal characteristics of the SLA 561 samples sustained a change; the thermal characteristics of the LI 1500 samples were apparently unchanged.

It is recommended that samples at least 12 by 12 inches in size be used for any future test programs of this type.

Table C-1 SPACE SHUTTLE INSULATION COMPATIBILITY TEST DATA

a. LI 1500 (Furnished by LMSC)

Heat Cycle** Visual Inspection	No change observed	No change observed	Limited brownish spotting	Limited brownish spotting	Yellow tint disappeared	No damage; vaporizing acid could be seen during heating; slight brown discoloration	Same as above	No damage; UDMH burned during heating but went out after heat off; some slight discoloration
Propellant Exposure Visual Inspection	No change observed	No change observed	No change observed	No change observed	Sample had yellowish tint	Sample soaked up acid; no damage	Same as above	Sample soaked up UDMH; no damage
Procedure*	H	н	н	н	1	82	2	2
Propellant	IRFNA	IRFNA	HDA	HDA	UDMH	IRFNA	HDA	UDMH
Post-Exposur	0.011	0.011	0.011	0.012	0.011	0.011	0.011	0.011
Pre-Exposur Cond Index	0.011	0.012	0.011	0.011	0.011	0.011	0.010	0.011
Post-Exposus Weight (gram	16.0	15.1	16.1	15.9	17.5	15.7	16.1	17.5
Pre-Exposur Weight (gram	16.9	16.0	16.0	15.9	17.3	16.4	16.0	16.4
Sample No.	1	2	3	4	5	9	7	80
֝֝֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֜֓֓֓֜֜֜֜	Pre-Exposure Weight (gram Post-Exposur Weight (gram Pre-Exposur Cond Index Post-Exposur Post-Exposur Propellant Procedure*	Pre-Exposure Weight (gram Pre-Exposure Weight (gram Pre-Exposure Cond Index Propellant Exposure Visual Inspection Procedure* Toochang Procedure* Toochang Procedure* Toochang Procedure* Toochang Toochang Toochang	Propellant Exposure Propellant P	Pre-Exposure Weight (gram Pre-Exposure Weight (gram Pre-Exposure Weight (gram Prod Index Prod Index Prod Inspection I6.9 16.0 0.011 0.011 IRFNA 1 No change observed I6.0 16.1 0.011 HDA 1 No change observed	Fropellant Exposure Weight (gram Propellant Exposure Weight (gram Propellant Exposure Visual Inspection  16.9 16.0 0.011 0.011 IRFNA 1 No change observed  16.0 15.1 0.012 0.011 IRFNA 1 No change observed  15.9 15.9 0.011 0.012 HDA 1 No change observed	He, 9 16.0 0.011 0.011 IRFNA 1 No change observed  16.9 15.1 0.012 0.011 IRFNA 1 No change observed  15.9 15.9 0.011 0.012 HDA 1 No change observed  17.3 17.5 0.011 0.011 UDMH 1 Sample had yellowish tint	Exposure   Exposure	Exposure   Exposure

\*Procedure 1: Specimen installed in vacuum chamber that was evacuated to less than 10 microns. Propellant vapors slowly injected into chamber and held for approximately 2 hours.

Specimen put in an open-mouth container. Liquid propellant at atmospheric conditions (approximately 60°F and 13.7 psia) admitted to container and held for 2 hours. Procedure 2:

Specimen installed in aluminum foil container and heated to 8500F for 5 minutes. \*\*Heat Cycle:

Table C-1 (cont) b. SLA 561 (Furnished by NASA)

						•				
	Heat Cycle** Visual Inspection	Self-ignited during heating; outer surface burned black	Same as above	Same as above	Same as above	Self-ignited at less than 500 <sup>o</sup> F; temperature exceeded 850 <sup>o</sup> F due to UDMH burning; sample black and cracked	1	1	Self-ignited at less than 500°F; temperature exceeded 850°F due to UDMH burning; sample black and cracked	
b. SLA 301 (Furnished by NASA)	Propellant Exposure Visual Inspection	No change observed	No change observed	No change observed	No change observed	No change observed	Outer surfaces of sample disintegrated. Sample loaded up with acid and was too corrosive to handle. Therefore, post-exposure weight and heat cycle deleted.	Same as above	No visual change but sample soaked up a lot of UDMH	
	Procedure*	H	н	н	П	1	2	2	81	
	Propellant	IRFNA	IRFNA	HDA	HDA	UDMH	IRFNA	НДА	UDMH	
	Post-Exposure Cond Index	0.012	0.012	0.019	0.018	0.012	-	-	0.012	•
	Pre-Exposure Cond Index	0.011	0.011	0,018	0.018	0.011	0.012	0.011	0.011	,
	Post-Exposure Weight (grams)	6.8	8.4	7.8	8.5	10.0			10.0	•
	Pre-Exposure Weight (grams)	13.9	14.8	13.8	14.0	14.3	14.0	14.4	14.8	
	Sample No.	Ţ	2	3	4	2	9	7	œ	+

Specimen installed in vacuum chamber that was evacuated to less than 10 microns. Propellant vapors slowly injected into chamber and held for approximately 2 hours. \*Procedure 1:

Specimen put in an open-mouth container. Liquid propellant at atmospheric conditions (approximately 60°F and 13.7 psia) admitted to container and held for 2 hours. Procedure 2:

Specimen installed in aluminum foil container and heated to  $850^{
m OF}$  for 5 minutes. \*\*Heat Cycle:




Fig. 1 Vacuum Chamber Setup




Fig. 2 Thermal Conductivity Measurement Setup

Fig. 3 Heat Environment Test Setup




Fig. 4 LI 1500 Sample 1 (Pretest)




Fig. 5 LI 1500 Sample 8 (Post-Test)




Fig. 6 SLA 561 Sample 1 (Pretest)




Fig. 7 SLA 561 Sample 1 (Post-Test)




Fig. 8 SLA 561 Sample 3 (Post-Test)

LOCKHEED MISSILES & SPACE COMPANY. INC.

A SUBSIDIARY OF LOCKHEED AIRCRAFT CORPORATION
SUNNYVALE, CALIFORNIA