

7-11-91
E6054

NASA Technical Memorandum 104372

Polymeric Routes to Silicon Carbide and Silicon Oxycarbide CMC

Frances I. Hurwitz
Lewis Research Center
Cleveland, Ohio

and

Paula J. Heimann, John Z. Gyekenyesi,
John Masnovi, and Xin Ya Bu
Cleveland State University
Cleveland, Ohio

Prepared for the
15th Annual Conference on Composites and Advanced Ceramics
sponsored by the American Ceramic Society
Cocoa Beach, Florida, January 13-16, 1991



POLYMERIC ROUTES TO SILICON CARBIDE AND SILICON OXYCARBIDE CMC

Frances I. Hurwitz
National Aeronautics and Space Administration
Lewis Research Center
Cleveland, Ohio 44135

and

Paula J. Heimann,* John Z. Gyekenyesi,*
John Masnovi and Xin Ya Bu
Cleveland State University
Cleveland, Oh

SUMMARY

An overview of two approaches to the formation of ceramic composite matrices from polymeric precursors is presented. Copolymerization of alkyl- and alkenylsilanes (RSiH_3) represents a new precursor system for the production of β -SiC on pyrolysis, with copolymer composition controlling polymer structure, char yield, and ceramic stoichiometry and morphology. Polysilsesquioxanes which are synthesized readily and can be handled in air serve as precursors to Si-C-O ceramics. Copolymers of phenyl and methyl silsesquioxanes display rheological properties favorable for composite fabrication; these can be tailored by control of pH, water/methoxy ratio and copolymer composition. Composites obtained from these utilize a carbon coated, eight harness satin weave Nicalon cloth reinforcement. The material exhibits nonlinear stress-strain behavior in tension.

INTRODUCTION

The use of polymeric precursors to ceramics enables the fabrication of complex-shaped ceramic matrix composites (CMCs) using low processing temperatures and technology currently available for the fabrication of resin matrix composites. Several polymeric systems are under investigation at NASA Lewis Research Center as candidates for CMC matrix precursors. Two of these will be reviewed here: the polymerization of alkyl- and alkenylsilanes as precursors to nonoxide Si-C materials, including crystalline SiC (Part I), and the synthesis of polysilsesquioxanes which yield Si-C-O ceramics on pyrolysis (Part II). The silane polymerization and subsequent composite fabrication requires handling under inert conditions. By contrast, the polysilsesquioxanes are handled readily in air, making them preferable for use in developing fabrication techniques. In both polymer systems, copolymerization is used to control polymer properties as well as ceramic stoichiometry.

The Si-C-O ceramic would be of benefit as a CMC matrix for use in the intermediate (900-1200 °C) temperature range, while the route to SiC would benefit high (>1200 °C) temperature applications.

*NASA Resident Research Associate at Lewis Research Center.

Part I: POLYMERIZATION AND PYROLYSIS OF ALKYL- AND ALKENYLSILANES

The polymerization of alkylsilanes utilizing a dimethyltitanocene catalyst has been demonstrated by Harrod and coworkers (refs. 1 to 5) to yield a polysilane (-Si-Si- backbone) with the evolution of hydrogen. However, when an unsaturated carbon bond is present in the monomer, as is the case in vinylsilane, polymerization using the same titanocene catalyst produces a mixture of polysilane and polycarbosilane (-Si-C- backbone), with the polycarbosilane as the dominant product (refs. 6 and 7). Also, hydrogen addition across the vinyl double bond occurs during polymerization. Three polymerization mechanisms are proposed to explain this result: metathesis, dehydrogenative coupling and hydrosilation (fig. 1), with hydrosilation appearing to be the dominant reaction path.

A number of different alkyl- and alkenylsilanes have been polymerized, including methyl-, ethyl-, allyl- and vinylsilanes. We also have copolymerized methyl- and vinylsilane using several mole ratios of the two monomers, and compared the resulting ceramics with those produced from blends of the homopolymers. The polymer backbone structures, determined by ^{29}Si NMR, char yield on pyrolysis in argon to 1400 °C at 10°/min, with the final temperature maintained for 30 min, and ceramic morphology, obtained by x-ray diffraction, are summarized in table I.

Polymerization of either ethyl- or methylsilane produces polysilane exclusively. Allylsilane polymerization yields a mixture of polysilane and polycarbosilanes in a ratio of 80:20. By contrast, vinylsilane produces more of the polycarbosilane structure. Comparison of char yields for the polymers of ethyl-, allyl-, vinyl- and methylsilane shows char yield to increase with carbosilane backbone structure, with the exception of polymethylsilane which, although exclusively a polysilane, has the highest char yield of the homopolymers. One possible explanation is that the methyl group inserts in the backbone to form a polycarbosilane during pyrolysis, as has been demonstrated by Yajima (ref. 8) to occur on pyrolysis of polydimethylsilane.

Copolymerization of methyl- and vinylsilane produced polymers with mixed polysilane and polycarbosilane backbones, with the percentage of polysilane increasing with methyl/vinyl ratio. Char yields ranged from 61 to 73 percent, and increased with methyl content beyond the 68 percent attained from the polymerization and pyrolysis of methylsilane alone. Blends of methyl + ethyl, ethyl + vinyl and methyl + vinyl derived polymers exhibited backbone structures in ratios that would be predicted based upon the rule of mixtures. Of these, the methyl + vinyl polymer blend showed the highest char yield, 71 to 72 percent. However, unlike the methyl/ vinyl copolymers, the blend was insoluble, and thus not suitable for composite fabrication.

The ethylsilane derived ceramic was x-ray amorphous, while the allyl- and vinylsilane derived materials, though predominantly amorphous, exhibited minor phases of β -SiC. The methyl/vinyl copolymers were characterized by increasing degrees of crystallinity and crystallite size with increasing methyl content. The largest β -SiC crystallites (140 Å) were obtained from the methyl polymer. This polymer also produced crystalline Si as a minor phase. The presence of free Si is considered to be undesirable in a CMC matrix, as it might react with fibers during processing. It also could lead to creep, as well as enhanced oxidation in the final composite. The methyl + ethyl polymer blend also showed a minor Si phase. All blends were characterized by the presence of β -SiC.

Elemental analysis of the ceramic products using combustion techniques was employed for the determination of Si and C. We consider the Si determination to be reliable. However, carbon determination is complicated by the formation of SiO_2 on combustion in air, which leads to underestimation, and dependence of the analysis on relative surface area (i.e., the amount of carbon found increases as particle size is decreased by grinding). Use of higher combustion temperatures (induction furnace method) typically increases C values, but does not eliminate the problem. Some of the polymers also exhibited considerable moisture sensitivity, particularly the polymer of ethylsilane, which would lead to oxygen incorporation and values of Si plus C of considerably less than 100 percent. Moisture sensitivity was observed to decrease as polycarbosilane formation increased.

Results of elemental analyses are summarized in table II. Stoichiometric SiC is 70 percent Si, 30 percent C by weight. On the basis of the Si determination, the methylsilane polymer and methyl + ethyl polysilane blends are closest to stoichiometric SiC; however, both also contain free Si. The methyl/vinyl copolymers and methyl + vinyl polymer blends produce ceramics containing 63-66 percent Si by weight, and thus would be candidates as precursors to SiC. Of these, the 75 methyl/25 vinyl copolymer is the precursor of choice for formation of crystalline SiC, based on a combination of solubility, ceramic stoichiometry, crystallite size and char yield (see tables I and II). The vinylsilane polymer also might be considered as a candidate for producing a carbon-rich, amorphous ceramic.

Part I: CONCLUSIONS

The present work demonstrates that dimethyltitanocene can be as a catalyst used to polymerize alkenylsilanes, in addition to its use in the polymerization of alkylsilanes, as described by Harrod and coworkers (refs 1 to 5). Photoinitiation (ref. 7) permits use of low (mM) concentrations of catalyst. Polymerization of alkylsilanes is found to produce polysilanes, whereas that of alkenylsilanes gives rise to a mixture of polysilane and polycarbosilane backbone structures.

On the basis of the results obtained here, the methyl/vinyl copolymers have been selected as candidates for composite fabrication based upon high char yield, high SiC yield, and the potential for tailoring copolymer composition to obtain either stoichiometric SiC or carbon-rich matrices. The vinylsilane derived polymers also are being investigated for composite fabrication, and would be expected to produce a carbon-rich matrix.

Future work will be focused on establishing methods for composite fabrication and controlling ceramic stoichiometry and morphology through control of copolymer composition and backbone structure. Work also is ongoing to establish an understanding of the polymerization mechanisms using radiolabelling techniques, so as to better tailor polymer structure to optimize the conversion to ceramic.

Many of the polymers produced have exhibited low viscosities. It therefore might be desirable to develop crosslinking groups to control polymer rheology during the composite fabrication process. Disilylethane is one such crosslinking group which has been synthesized successfully; its use in optimizing rheology is under study.

Part II: POLYMERIZATION AND PYROLYSIS OF POLYSILSESQUIOXANES

Homo- and copolymers of phenyl- and methylsilsesquioxanes were synthesized by hydrolysis and condensation of their trimethoxysilane monomers in acid solution (ref. 9). A schematic of the reactions involved is shown in figure 2. Synthesis variables included pH, water to methoxy ratio and phenyl to methyl monomer ratio.

The influence of synthesis conditions on polymer structure was determined by ^{29}Si NMR, as described in detail elsewhere (ref. 9). For a polymer having the structure $\text{RSi}(\text{O-})_x(\text{OH})_{3-x}$, relative quantities of mono- ($x = 1$), di- ($x = 2$) and trifunctional ($x = 3$) Si atoms can be established by peak integration. Occurrence of difunctional silicon (cyclic or linear polymer formation) was observed to increase with water to methoxy ratio, and was accompanied by a decrease in branching, as shown in figure 3. At low water/methoxy values (<1), gelation occurs, while at higher values (8 to 16) a polymer which is more linear, and better suited to composite fabrication, could be obtained.

Branching (or crosslinking) also was found to decrease on increasing pH from 2 to 3 (fig. 4), as evidenced by a decrease in the number of trifunctional groups. The polymer formed at pH 2 was presumed to have a high cyclic content, as evidenced by the absence of many monofunctional Si atoms. The pH 3 material was lowest in viscosity of the polymers obtained over a pH range of 2 to 4, and was most suitable for composite processing.

The influence of copolymer composition on polymer structure is illustrated in figure 5. Polymethylsilsesquioxane exhibits a high degree of crosslinking or cyclic structure. As phenyl groups are incorporated in the polymer, the number of trifunctional Si atoms decreases, and the polymer becomes more linear, and less viscous. The char yield also has been found to decrease with increasing phenyl content; this may be explained, at least in part, by the change in backbone structure. The incorporation of phenyl groups in the polymer also produces an increase in the carbon content of the resulting ceramic char (fig. 6). Therefore, it is expected that polymer rheology, and hence composite fabrication, as well as ceramic matrix properties will be influenced by copolymer composition.

Composites have been fabricated using a carbon coated, eight harness satin Nicalon cloth and 50 phenyl/50 methyl (mole percent) silsesquioxane copolymer. Si-C-O ceramic matrix composites were obtained by pyrolysis, followed by several reimpregnation/pyrolysis cycles. Eight inch long, straight sided specimens tested in tension exhibited non-linear stress-strain behavior typical of composites having woven reinforcement. A representative stress-strain curve, and typical mechanical properties, are shown in figure 7. Tensile fracture surfaces (fig. 8) were characterized by bundle fracture and some fiber pull-out. At the highest magnification, fibers can be observed to bridge matrix cracks perpendicular to the tensile axis. Closer examination of individual fibers which have pulled out from a tow (fig. 9) shows that matrix fragments are adherent to the fiber surface, indicating that further work is needed to optimize the fiber coating and fiber/matrix interface.

Part II: CONCLUSIONS

The polysilsesquioxane copolymers provide a facile and inexpensive route to the formation of Si-C-O matrices, proposed for use in the intermediate (900-1200 °C) temperature range (ref. 10). Copolymer composition, water/methoxy ratio and pH

control polymer structure, and hence rheological behavior and composite processing. Ceramic matrix composites have been fabricated successfully which exhibit nonbrittle fracture when tested in tension at room temperature.

Future work will center on optimizing fiber coatings and coating thickness, determination of the optimum matrix composition needed to maximize composite mechanical behavior and thermo-oxidative stability, and determination of tensile properties at elevated temperatures.

ACKNOWLEDGEMENTS

The authors wish to thank Ralph G. Garlick for x-ray diffraction studies, and Terrence A. Kacik and Ann Modock for thermal analysis characterization.

REFERENCES

1. Samuel, E.; and Harrod, J.F.: Synthesis and Characterization of a Novel Bis(cyclopentadienyl)titanium Hydride Complex, *J. Am. Chem. Soc.*, vol. 106, no. 6, 1984, pp. 1859-1860.
2. Aitken, C.T.; Harrod, J.F.; and Samuel, E.: Polymerization of Primary Silanes to Linear Polysilanes Catalyzed by Titanocene Derivatives, *J. Organomet. Chem.*, vol. 279, no. 11, 1985, pp. C11-C13.
3. Aitken, C.; Harrod, J.F.; and Samuel, E.: Identification of Some Intermediates in the Titanocene-Catalyzed Dehydrogenative Coupling of Primary Organosilanes. *J. Am. Chem. Soc.*, vol. 108, no. 14, 1986, pp. 4059-4066.
4. Harrod, J.F.; and Yun, S.S.; Silyltitanocene Complexes as Catalysts for the Hydrogenation, Isomerization and Hydrosilation of Olefins, *Organometallics*, vol. 6, no. 7, 1987, pp. 1381-1387.
5. Harrod, J.F.: Polymerization of Group 14 Hydrides by Dehydrogenative Coupling, *Inorganic and Organometallic Polymers*, M. Zeldin, J. R. Allcock, and K.J. Wynne, eds. ACS Symposium Monograph 360, American Chemical Society, Washington, D. C., 1988, pp. 89-100.
6. Masnovi, J., et al.: Polymerization of Alkenylsilanes Using Early Transition Metal Catalysts. *Mat. Res. Soc. Symp. Proc.*, vol. 180, 1990, pp. 779-784.
7. Bu, X.Y., et al.: Polycarbosilane from Polymerization of Vinylsilane. Chem. Commun., submitted 1990.
8. Yajima, S., et al.: Synthesis of Continuous Silicon Carbide Fibre with High Tensile Strength and High Young's Modulus, *J. Mater. Sci.*, vol. 13, no. 12, 1978, pp. 2569-2576.
9. Heimann, P.J.; Hurwitz, F.I.; and Rivera, A.L.: Synthesis of Polysilsesquioxanes for Use as Ceramic Precursors. Symposium on Composites: Processing, Microstructure and Properties, Nov. 12-15, 1990, Orlando, FL, to be published.
10. Greil, P.: Thermodynamic Calculations of Si-C-O Fiber Stability in Ceramic Matrix Composites. *J. Eur. Ceram. Soc.*, vol. 6, 1990, pp. 53-64.

TABLE I. - INFLUENCE OF POLYMER COMPOSITION ON POLYMER STRUCTURE,
CHAR YIELD AND CERAMIC MORPHOLOGY

ID	Monomers, mole ratio	Polymer structure		Char yield, wt. %	XRD
		Silane	Carbosilane		
138	Ethyl	100	0	25	Amorphous
139	Allyl	80	20	35	Amorphous, β -SiC
137	Vinyl	20	80	59	Amorphous, β -SiC (minor)
154	35 Methyl/65 vinyl	50	50	61	Amorphous, 80 A β -SiC
156	55 Methyl/45 vinyl	70	30	61	Amorphous, 90 A β -SiC
155	75 Methyl/25 vinyl	85	15	73	95 A β -SiC
161	Methyl	100	0	68	140 A β -SiC, Si (minor)
172	Methyl + ethyl	100	0	51-52	β -SiC, Si (minor)
173	Ethyl + vinyl	60	40	45-50	β -SiC
174	Methyl + vinyl (insol.)	75	25	71-72	β -SiC

TABLE II. - CONVERSION OF POLYMER TO CERAMIC

ID	Polymer	Ceramic composition, weight percent ^a			Comments
		Si	C	^b C	
138	Ethyl	60	27	--	-----
139	Allyl	65	27	--	-----
137	Vinyl	58	39	--	C rich
154	35 Methyl/65 vinyl	63	31	33	-----
156	55 Methyl/45 vinyl	66	28	32	-----
155	75 Methyl/25 vinyl	66	27	28	Choice for SiC
161	Methyl	69	25	26	Free Si
172	Methyl + ethyl	70	27	26	Free Si
173	Ethyl + vinyl	62	32	34	-----
174	Methyl + vinyl	64	31	30	Insoluable

^aStoichiometric SiC is 70 Si, 30 C by weight.

^bInduction furnace method.





Figure 1.—Proposed polymerization mechanisms for the polymerization of vinylsilane using a titanocene catalyst.



Variables: pH, $\text{H}_2\text{O}/\text{-OCH}_3$, phenyl/methyl

Figure 2.—Reactions involved in the synthesis of polysilses-quioxanes.




Figure 3.—Influence of water/methoxy ratio on polysilses-quioxane structure.




Figure 4.—Variation in polysilsesquioxane structure with pH at which the polymer was synthesized.




Figure 5.—Dependence of polysilsesquioxane structure on phenyl/methyl ratio of monomer reactants.




Figure 6.—Variation in ceramic composition with phenyl content of polysilsesquioxane precursor.



Figure 7.—Polished cross-section of Nicalon/Si-C-O composite.




Figure 8.—Typical room temperature tensile stress-strain behavior of Nicalon/Si-C-O composite having eight harness satin weave.





Figure 9.—Tensile fracture surface, eight harness satin weave Nicalon/Si-C-O composite.





Figure 10.—Enlargement of fracture surface to show fiber bundle fracture and adhesion of matrix to fiber.



National Aeronautics and
Space Administration

Report Documentation Page

1. Report No. NASA TM -104372	2. Government Accession No.	3. Recipient's Catalog No.	
4. Title and Subtitle Polymeric Routes to Silicon Carbide and Silicon Oxycarbide CMC		5. Report Date	
		6. Performing Organization Code	
7. Author(s) Frances I. Hurwitz, Paula J. Heimann, John Z. Gyekenyesi, John Masnovi, and Xin Ya Bu		8. Performing Organization Report No. E -6054	
		10. Work Unit No. 505-63-31	
9. Performing Organization Name and Address National Aeronautics and Space Administration Lewis Research Center Cleveland, Ohio 44135 - 3191		11. Contract or Grant No.	
		13. Type of Report and Period Covered Technical Memorandum	
12. Sponsoring Agency Name and Address National Aeronautics and Space Administration Washington, D.C. 20546 - 0001		14. Sponsoring Agency Code	
15. Supplementary Notes Prepared for the 15th Annual Conference on Composites and Advanced Ceramics sponsored by the American Ceramic Society, Cocoa Beach, Florida, January 13-16, 1991. Frances I. Hurwitz, NASA Lewis Research Center. Paula J. Heimann, Cleveland State University, Cleveland, Ohio 44115 and NASA Resident Research Associate at Lewis Research Center, (work funded by NASA Grant NCC3-63). John Z. Gyekenyesi, Cleveland State University and NASA Resident Research Associate at Lewis Research Center, (work funded by NASA Grant NAG3-749). John Masnovi and Xin Ya Bu, Cleveland State University, (work funded by NASA Grant NCC3-63). Responsible person, Frances I. Hurwitz, (216) 433-5503.			
16. Abstract An overview of two approaches to the formation of ceramic composite matrices from polymeric precursors is presented. Copolymerization of alkyl- and alkenylsilanes (RSiH_3) represents a new precursor system for the production of β -SiC on pyrolysis, with copolymer composition controlling polymer structure, char yield, and ceramic stoichiometry and morphology. Polysilsesquioxanes which are synthesized readily and can be handled in air serve as precursors to Si-C-O ceramics. Copolymers of phenyl and methyl silsesquioxanes display rheological properties favorable for composite fabrication; these can be tailored by control of pH, water/ methoxy ratio and copolymer composition. Composites obtained from these utilize a carbon coated, eight harness satin weave Nicalon cloth reinforcement. The material exhibits nonlinear stress-strain behavior in tension.			
17. Key Words (Suggested by Author(s)) Siloxanes; Silicon polymers; Ceramic matrix composites; Ceramics; Tensile properties		18. Distribution Statement Unclassified - Unlimited Subject Categories 27 and 24	
19. Security Classif. (of the report) Unclassified	20. Security Classif. (of this page) Unclassified	21. No. of pages 12	22. Price* A03