

NASA/TM—1999-209059



Pyrometric Gas and Surface Temperature Measurements

Gustave Fralick and Daniel Ng
Glenn Research Center, Cleveland, Ohio

Prepared for the
44th International Gas Turbine and Aerospace Technical Congress
sponsored by the American Society of Mechanical Engineers
Indianapolis, Indiana, June 7-10, 1999

National Aeronautics and
Space Administration

Glenn Research Center

March 1999

Acknowledgments

The authors would like to thank Larry Oberle for operating the atmospheric combustor during the probe test.

This report is a preprint of a paper intended for presentation at a conference. Because of changes that may be made before formal publication, this preprint is made available with the understanding that it will not be cited or reproduced without the permission of the author.

Available from

NASA Center for Aerospace Information
7121 Standard Drive
Hanover, MD 21076
Price Code: A03

National Technical Information Service
5285 Port Royal Road
Springfield, VA 22100
Price Code: A03

PYROMETRIC GAS AND SURFACE TEMPERATURE MEASUREMENTS

Gustave Fralick and Daniel Ng
National Aeronautics and Space Administration
Glenn Research Center
Cleveland, Ohio 44135

ABSTRACT

A multiwavelength pyrometer possessing advantages over the one- and two-wavelength designs is described. Results of its application to surface temperature measurements of ceramics is presented. Also described is a probe suitable for gas temperature measurements to temperatures > 2600 K. The design of the probe includes a multiwavelength pyrometer with fiber optic input.

INTRODUCTION

Temperature measurement of surfaces using the traditional 1-color, 2-color and other pyrometers suffers from the requirement of needing to know additional information concerning the emissivity of the measured surface and the transmissivity of the intervening optical medium. The required knowledge of these quantities ranges from knowing their absolute values at a particular wavelength to knowing their ratio at different wavelengths. This is particularly true for ceramic materials because of their complex optical properties, such as low emissivity, which varies with both temperature and wavelength. We have developed a multiwavelength pyrometer which measures the temperature of surfaces without needing to know such extensive information. This pyrometer has been used to measure the surface temperature of several materials, and has shown good agreement with surface thin film thermocouples (ref. 1). The use of the pyrometer to measure the surface temperature of two ceramics is described in this paper, as well as the use of a probe which was developed to allow this technique to be used to measure gas temperature.

METHOD

The multiwavelength pyrometer consists of a spectrometer and a computer. The computer controls the spectrometer using manufacturer's proprietary software to acquire a spectrum and performs the subsequent data analysis to determine the temperature. The temperature of the measured surface dictates the spectral region in which the spectrometer will operate. The spectral region can be

from 0.5 to 2.5 μm , 1.3 to 4.5 μm or 2 to 14.5 μm depending on the particular requirements. On some occasions, depending on the equipment that is available, the actual spectral region that is selected varies slightly. The emitted/transmitted radiation is described by Planck's law of black body radiation:

$$L_{\lambda} = \epsilon_{\lambda} \tau_{\lambda} \frac{c_1}{\lambda^5} \frac{1}{\exp(c_2/\lambda T) - 1} \quad 1$$

$$= \epsilon_{\lambda} \tau_{\lambda} \frac{c_1}{\lambda^5} \exp(-c_2/\lambda T) \frac{1}{1 - \exp(-c_2/\lambda T)}$$

where c_1 , c_2 are the radiation constants, L_{λ} is the radiation intensity, ϵ_{λ} is the emissivity, and τ_{λ} is the transmissivity of the optical medium between the pyrometer and the radiation source at wavelength λ .

For data analysis, Eqn. 1 is rewritten as

$$\left(\frac{\ln\left(\frac{c_1}{\lambda^5} \frac{1}{L_{\lambda}}\right)}{c_2/\lambda} \right) - \frac{\ln\left(1 - \exp\left(-\frac{c_2}{\lambda T}\right)\right)}{c_2/\lambda} = \frac{1}{T} - \frac{\lambda}{c_2} \ln(\epsilon_{\lambda} \tau_{\lambda}) \quad 2$$

This is the working equation of the traditional 1-color pyrometry method which requires knowing the emissivity and or transmissivity. For the multiwavelength pyrometer, neither quantity is required to determine the temperature. Because the quantity $(1 - \exp(-c_2/\lambda T))$ is practically unity at short wavelengths, its logarithm is approximately zero. We observe from Eqn. 2 that plotting the quantity $y = \ln(c_1/(\lambda^5 L_{\lambda})) / (c_2/\lambda)$ as a function of λ would result in a straight line if $\ln(\epsilon_{\lambda} \tau_{\lambda})$ is wavelength independent, with its slope given by $\ln(\epsilon_{\lambda} \tau_{\lambda}) / c_2$. The quantity $1/y$ at each wavelength λ is often referred to as the radiant temperature. $\tau_{\lambda} = 1$, except when an optical fiber is used, and in that case its value is included in the instrument response function when it is calibrated using a black body furnace. The intercept of the straight line at $\lambda=0$ is $1/T$, the reciprocal of the desired unknown temperature. After the temperature T is determined, when the full expression on the left of Eqn 2 is plotted on the same graph, there is no noticeable difference.

EXPERIMENT

(1) Zirconia (ZrO₂) Thermal Barrier Coating (TBC)

Zirconia is a ceramic material widely used to provide a thermal coating on turbine engine components for high temperature operations to achieve high efficiency and performance. The emissivity of zirconia is generally not well known, and is known to even vary with time and

temperature history. The multiwavelength pyrometer recorded the spectrum of such a coating in an atmospheric jet burner (Fig. 1) with good signal to noise ratio in about 16 seconds. The spectral region from 1.5 to 4.5 μm was used. The spectrum is analyzed according to Eqn. 2 and is shown in Fig. 2. From the graph's intercept, the temperature of the surface is determined. The emissivity of zirconia over most of this spectral region is constant, resulting in a very good straight line by visually fitting.




Fig. 1 Zirconia TBC spectrum




Fig. 2 Transformed zirconia TBC spectrum

(2) Beryllia (BeO)

Beryllia is a high temperature ceramic with very low emissivity. A 6 mm diameter high gas temperature probe, of the type described below, was made using this material. The probe had a type C thermocouple in the center. The multiwavelength pyrometer spectrometer was focused on a spot on the outside of the beryllia tubing surface to record a spectrum for temperature measurement as it was

heated by a portable propane torch. The spectrum obtained is shown in Fig. 3. The transformed (according to Eqn. 2) spectrum is shown in Fig. 4. From the slope, the emissivity was determined to be 0.07, and from the intercept the surface temperature is determined to be 1425K. The corresponding thermocouple reading was 1322K. The difference was due to poor thermal contact between the probe and the thermocouple.




Fig. 3 BeO gas probe spectrum




Fig. 4 BeO gas probe in propane flame

Gas Temperature Measurements

A high gas temperature probe, designed at NASA Glenn Research Center, consists of a BeO sheath inserted into an inconel support section (fig. 5). Such a probe would be used to measure gas temperature in the range above about 1650 K, as might be found in a jet engine combustor. This is beyond the range of conventional thermocouples. Although intrusive, no optical access is required; it is unlikely optical access would be available in a combustor in any case. An in-situ gas temperature measurement is useful in estimating heat loads on combustor walls. Furthermore, high gas temperatures are strongly correlated with the formation of nitrogen oxides. The overall length of the probe is 0.28 m, the diameter of the support section is 12.7 mm, and the sheath diameter is 8 mm. Because of the high temperature materials employed, the probe does not need to be water cooled. As originally designed, there was a W-5%Re/W-26%Re (type C) thermocouple within the BeO sheath. The thermocouple is capable of measuring temperatures as high as 2589 K, but must be in an inert atmosphere, which is the reason for the sheath. The probe has two ports, for pumping and back filling with an inert gas, or for continuously flowing a gas such as argon during a run. BeO was chosen as the sheath material because of its excellent high temperature electrical properties and resistance to thermal shock. Because of the necessity of keeping the thermocouple in an inert environment, and of the difficulty of relating the thermocouple temperature to the gas temperature, the authors decided to use the multi-wavelength pyrometry technique to measure the inside temperature of the BeO sheath. The upper temperature limit of the probe is then the useful upper limit of BeO, which is about 2670 K in oxidizing atmospheres (ref. 2). The sheath acts as a black body, and because of the high thermal conductivity of beryllia, the inside and outside sheath temperatures are nearly the same. The black body signal is then transmitted from the probe to the spectrometer via an optical fiber,

which is focused on the end of the sheath. The fiber itself does not need to extend into the hot region of the probe. If the heat transfer in the probe is treated as conduction in one dimension, the gas temperature is related to the temperature of the probe tip seen by the optical fiber by the expression:


$$T_g = \frac{T(L) \cosh aL - T_b}{\cosh aL - 1} \quad 3$$

where L is the length of the probe, T_g is the gas temperature, $T(L)$ is the temperature at the probe tip, T_b is the temperature at the other end of the probe, and a is a constant related to the thermal conductivity of the sheath material, the sheath thickness, and the convective heat transfer coefficient

A probe of this type was run at two different temperatures in a 3" Becon model 77-1051atmospheric combustor. The combustor consists of a primary and secondary combustion zone. Jet fuel is injected at the entrance of the primary zone, along with sufficient air to initiate burning. Additional air is injected into the secondary zone to complete the combustion, and the flame exits through the nozzle.

The probe and spectrometer were connected by 20 meters of 3 mm silica fiber. The results are shown in figures 6 & 7, where the indicated temperatures are 1360 K and 1745 K respectively. The estimated velocity was about 200 meters per second. The only means of comparison available was a type S thermocouple inserted into the flame at the burner lip. For the two runs, it read 1300 K and 1580K respectively. The temperature difference is explained by the fact that the probe measured the flame temperature in the center of the burner exit, which is hotter than the flame temperature at the outer radius.

Fig. 5 High Gas



Temperature Probe

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (<i>Leave blank</i>)	2. REPORT DATE March 1999	3. REPORT TYPE AND DATES COVERED Technical Memorandum	
4. TITLE AND SUBTITLE Pyrometric Gas and Surface Temperature Measurements		5. FUNDING NUMBERS WU-523-21-13-00	
6. AUTHOR(S) Gustave Fralick and Daniel Ng		8. PERFORMING ORGANIZATION REPORT NUMBER E-11595	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration John H. Glenn Research Center at Lewis Field Cleveland, Ohio 44135-3191		10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA TM-1999-209059	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001		11. SUPPLEMENTARY NOTES Prepared for the 44th International Gas Turbine and Aerospace Technical Congress, sponsored by the American Society of Mechanical Engineers, Indianapolis, Indiana, June 7-10, 1999. Responsible person, Gustave Fralick, organization code 5510, (216) 433-3645.	
12a. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified - Unlimited Subject Categories: 35 and 04 This publication is available from the NASA Center for AeroSpace Information, (301) 621-0390.		12b. DISTRIBUTION CODE Distribution: Nonstandard	
13. ABSTRACT (<i>Maximum 200 words</i>) A multiwavelength pyrometer possessing advantages over the one- and two-wavelength designs is described. Results of its application to surface temperature measurements of ceramics is presented. Also described is a probe suitable for gas temperature measurements to temperatures > 2600 K. The design of the probe includes a multiwavelength pyrometer with fiber optic input.			
14. SUBJECT TERMS Ceramics; Emissivity; Gas temperature; Spectroscopy			15. NUMBER OF PAGES 11
			16. PRICE CODE A03
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT

Fig. 6 Burner data, T=1360 K




Fig. 7 Burner data, T=1745 K

CONCLUSION

The surface temperatures of two ceramic materials, ZrO_2 and BeO were measured using the multiwavelength pyrometer. The multiwavelength pyrometer determines temperature by transforming the radiation spectrum over a broad wavelength region to produce a straight line which intercepts the vertical axis. The inverse of the intercept gives the temperature. One of the surface temperature tests was in comparison with a thermocouple mounted inside the cylindrical surface whose temperature was being measured; the temperature indicated by the pyrometer was about 100 K higher than the thermocouple reading of 1322 K. The pyrometer was also used in conjunction with a black body probe to measure the gas temperature at the center of an atmospheric combustor exit. In this test, the pyrometer/probe indicated a temperature higher than a thermocouple mounted at the edge of the flame. Further tests will have to be conducted to assess the accuracy of the probe.

REFERENCES

1. Ng, D., Fralick, G., Lei, J.F., Temperature Measurement of Ceramic Materials and Thermal Barrier Coatings Using a Multiwavelength Pyrometer, HITEMP Review 1997, paper 49, NASA Conference Publication 10192.
2. Campbell, I. & Sherwood, E., Eds., High Temperature Materials and Technology, John Wiley and Sons, New York (1967)