




# ENGINEERING AND ABUSE TESTING OF PANASONIC LITHIUM-ION BATTERY AND CELLS

## 1999 NASA AEROSPACE BATTERY WORKSHOP

Judith A. Jeevarajan  
*Lockheed Martin/NASA-JSC*

Bobby J. Bragg  
NASA-JSC

# Panasonic Lithium-ion Battery in the IBM Thinkpad



## **Panasonic 17500 Lithium-ion Cells**

### **Physical Characteristics**

**Weight:**  $24.43 \pm 0.6$  g


**Diameter:**  $16.399 \pm 0.4$  mm

**Length:**  $49.648 \pm 1.2$  mm


### **Electrochemical Characteristics**

**Open Circuit Voltage:** 3.9 V

**Capacity (room temperature):** 0.81 Ah



# Charge/Discharge Curves for Panasonic 17500 Li-ion Cell



# Rate Capability of Panasonic 17500 Lithium-ion Cells Under Different Conditions of Charge and Discharge


Cycle Number	1.0 C Charge			0.5 C Charge		
	1 C Discharge	0.5 C Discharge	0.25 C Discharge	1 C Discharge	0.5 C Discharge	0.25 C Discharge
1	0.816	0.837	0.828	0.824	0.837	0.840
5	0.810	0.832	0.827	0.817	0.835	0.838
25	0.801	0.820	0.816	0.802	0.826	0.832
50	0.788	0.809	0.804	0.799	0.822	0.826
100	0.774	0.794	0.792	0.792	0.819	0.822
CDR* Ah/Cycle	0.00038	0.00039	0.00037	0.00027	0.00017	0.00018

\* CDR stands for Capacity Decay Rate. The shaded cell values were used to calculate the CDR.  $CDR = (C_5 - C_{100}) / 95$ ,  $C_5$  and  $C_{100}$  are the capacities at cycle # 5 and 100, respectively.


At 1 C Charge/ Discharge, Capacity Decay is 4%

At 0.5 C Charge/Discharge, Capacity Decay is 1.9 %


# Discharge Capacity for the Panasonic cells at 0.5C Rate of Discharge and Different Rates of Charge



# Discharge Capacities versus Temperature for the Panasonic 17500 Lithium-ion Cells




# Effective Internal Resistance for the Panasonic Lithium-ion cells







# Minimum Voltages Obtained During the Discharge Pulse of the Internal Resistance Test




# Charge Discharge Curve for Charge at 3C Rate to 4.2 V and Discharge with 1C Current to 2.7 V



# Charge-Discharge Curve for Charge to 5.0 V with a 1 C Current and Discharge to 2.7 V with 1C Current



# Overcharge Test Using a 3C Current to 12 V




# Current and Temperature Changes During a High Rate Overcharge (3C current) to 12 V






# Discharge of Panasonic 17500 Lithium-ion Cells Using 3C Current






# Current and Voltage Characteristics During Discharge into Reversal of Panasonic 17500 Lithium-ion Cells with 1C Current




# Heat-to-Vent of Panasonic 17500 Lithium-ion Cells







# Voltage and Temperature Profile During a Soft Internal Short




# Voltage and Temperature Characteristics During a Hard Internal Short



# Current and Temperature Characteristics During An External Short Test Using 40 mohm Load




# Electrolyte Analysis of Panasonic 17500 lithium-ion cell




## Panasonic Lithium-ion IBM Thinkpad Battery

Weight: 366 g  
Dimensions: 4'X 4.5'  
Voltage: 10.8 V  
Capacity: 3.0 Ah  
Configuration: 4P3S (12 cells)




# Circuit Board in the Panasonic Thinkpad Lithium-ion Battery




## Circuit Board in the Panasonic Lithium-ion Battery

- Decisions about turning off charge and discharge switches based on cell bank voltages and current are made by firmware in microcontroller.
- Protective circuit performs capacity gauge function.
- Protective circuit can balance cell bank states-of-charge by putting small (15 mA) discharge currents on individual cell banks.




# Current and Voltage During the Charging of a Panasonic Lithium-ion Battery Using the IBM Thinkpad Charger







# Discharge Characteristics of the Panasonic Lithium-ion Battery with No Programs Running



# Discharge Characteristics of the Panasonic Lithium-ion Battery with the Program Running




# Voltage Profile of Individual Cell Banks During Overdischarge of Top Cell Bank




Load Current for Top Cell Bank : 2 A; For Other Two Cell Banks: 1 A


# Voltage Profile of Individual Cell Banks During Overdischarge of Middle Cell Bank



# Voltage Profile During Reset of Last Cell Bank after an Overdischarge



# Current and Voltage Profile During An Overcharge of the Whole Battery using a 2 A Current



## CONCLUSIONS

- Performance of the cells under different conditions of charge and discharge shows that the 0.5 C rate of charge and discharge might be the ideal condition for long term cycling.
- Overcharge and Overdischarge: The cells and the battery have adequate protection under both conditions to prevent any catastrophic occurrences.
- Temperatures above 150 °C are required to vent the cells or cause a thermal runaway. This situation is non-credible in the cabin of the Space Shuttle or ISS.
- Internal crushes can give different results depending on the nature of the crush. Soft shorts do not exhibit high temperatures or thermal runaway whereas hard internal shorts can exhibit temperatures above 400 °C and expel can contents.
- All batteries will be screened using a vibration test (0.067 g<sup>2</sup>/Hz for one minute) for internal short before flight.

## **ACKNOWLEDGMENT**

**Dr. Wenlin Zhang - Schlumberger, Rosharon, TX**  
**Frank Davies- Hernandez Engineering/NASA-JSC**  
**Gerald Steward- NASA-JSC**  
**Gwen Gilliam- Lockheed Martin/NASA-JSC**  
**Anita Thomas- Lockheed Martin/NASA-JSC**