

In-Space Repair of Reinforced Carbon-Carbon (RCC) Thermal Protection System Structures

M. Singh
QSS Group, Inc.
NASA Glenn Research Center
Cleveland, OH 44135

Advanced repair and refurbishment technologies are critically needed for the RCC-based thermal protection system of current space transportation system as well as for future Crew Exploration Vehicles (CEV). The damage to these components could be caused by impact during ground handling or due to falling of ice or other objects during launch. In addition, in-orbit damage includes micrometeoroid and orbital debris impact as well as different factors (weather, launch acoustics, shearing, etc.) during launch and re-entry. The GRC developed GRABER (Glenn Refractory Adhesive for Bonding and Exterior Repair) material has shown multiuse capability for repair of small cracks and damage in reinforced carbon-carbon (RCC) material. The concept consists of preparing an adhesive paste of desired ceramic with appropriate additives and then applying the paste to the damaged/cracked area of the RCC composites with adhesive delivery system. The adhesive paste cures at 100-120°C and transforms into a high temperature ceramic during simulated entry conditions. A number of plasma torch and ArcJet tests were carried out to evaluate the crack repair capability of GRABER materials for Reinforced Carbon-Carbon (RCC) composites. For the large area repair applications, PLASTER (Patch Laminates and Sealant Technology for Exterior Repair) based systems have been developed. In this presentation, critical in-space repair needs and technical challenges as well as various issues and complexities will be discussed along with the plasma performance and post test characterization of repaired RCC materials.

In-Space Repair of Reinforced Carbon-Carbon Thermal Protection System Structures

**M. Singh
QSS Group, Inc.
NASA Glenn Research Center
Cleveland, OH 44135**

James I. Mueller Memorial Award Lecture



**29th International Conference on Advanced Ceramics and Composites
Cocoa Beach, Florida
January 24, 2005**



Outline

- Introduction and Background
- Need for In-Space Repair and Inspection
- Technical Challenges
 - *Space Environment*
 - *EVA, Tools, Materials Issues*
 - *Inspection, Verification, and Validation*
- RCC Repair Technologies
- GRABER- Key Material Properties
- Testing and Characterization
 - *Plasma Performance (ArcJet Testing, Torch Testing, etc)*
 - *Microstructural Characterization*
- Summary and Conclusions





STS-107 Columbia

Feb. 1, 2003



CAIB Recommendation R6.4-1




- For missions to the ISS, develop a practicable capability to inspect and effect emergency repairs to the widest possible range of damage to the Thermal Protection System, including both tile and RCC, taking advantage of the additional capabilities available when near to or docked at the ISS.
- For non-station missions, develop a comprehensive autonomous (independent of Station) inspection and repair capability to cover the widest possible range of damage scenarios.
- Accomplish an on-orbit Thermal Protection System inspection, using appropriate assets and capabilities, early in all missions.
- The **ultimate objective** should be a fully autonomous capability that an ISS mission fails to achieve the correct orbit, fails to dock successfully, or is damaged during or after undocking.

http://www.nasa.gov/columbia/home/CAIB_Vol1.html



Damage Possibilities to Thermal Protection System (TPS)

- Impact damage during ground handling
- Damage due to falling of ice or other objects during launch
- Micrometeoroid and orbital debris impact
- Damage caused by different factors during launch and reentry (weather, launch acoustics, shearing, etc.)




Launch Pad Debris

Accent EFT Foam Damage

On-Orbit MMOD Damage



Leading Edge Structural Subsystem (LESS) RCC Components




Nose Cap, Chin
Panel, and Seals


Forward External
Tank Attachment
"Arrowhead"
Plate

Wing Leading Edge
Panels and Seals

Leading Edge RCC Panels and T-Seals



Reinforced Carbon-Carbon (RCC) Composite




Dr. Nathan Jacobson, NASA GRC

Glenn Research Center at Lewis Field



Cross Sectional View Showing Carbon/Carbon, SiC, and Type A Sealant





Dr. Nathan Jacobson, NASA GRC

Glenn Research Center at Lewis Field



STS-45 Impact Damage on Atlantis WLE Panel 10R




Detail of Backface Damage




Damage to Leading Edges During Impact Testing on Ground



IML Damage Surface Panel 9L1



OML Damage Surface Panel 9L2




Foam Blasts
16-inch Hole
in Final
Shuttle Test
@SWRI, TX,
July 7, 2003



RCC Repair Evaluation on KC-135 Aircraft and at Neutral Buoyancy Laboratory

KC-135 Test Objectives:

- Evaluation of the repair material wetting characteristics on RCC in micro-G
- Foaming and flow characteristics
- Evaluation of tool design such as crack repair gun/nozzle
- Evaluation of cleaning method, tool/material interaction, etc.




GRABER was successfully tested on a number of KC-135 flights and in DGV experiments

JAXA Astronaut Soichi Neguchi in JSC Neutral Buoyancy Laboratory (NBL) pool





Space Shuttle Re-entry Conditions are Quite Harsh and Extreme



- Temperature to 2000 K
- Reduced pressure--0.005 to 0.010 atm
- Gases--O₂, N₂, CO₂
 - Shock leads to O, N and ions
- Short times ~15 minutes/re-entry
- Best simulated with arc-jet



Repair Concepts for WLE Damage



Glenn Refractory Adhesive for Bonding and Exterior Repair (GRABER)

- High Temperature adhesive based on organic based systems with a number of inorganic constituents.
- Viscosity and curing behavior (time, temperature) can be tailored to suit the needs.
- GRABER has been used to prepreg a wide variety of ceramic fiber weaves (C, SiO₂, SiC).
- It bonds very well with a wide variety of surfaces and cures up to 120°C with heat.
- It can be acid cured at lower temperatures as well.



Multifunctionality of GRABER Based Materials


- **Crack Repair Materials**
 - Repair of cracks and damaged coatings
- **Adhesive and Sealants**
 - Bond and seal the edges in plug concept
- **Inner to Outer Mold Line (ITOM) Materials**
 - Filled Wing Concept
- **Flexible Prepregs**
 - Repair of large size damage
- *Manufacturing of Bulk Composites*
- *Joining and Assembly of C/C Composites*
- *Repair of C/C Based Composites*
- *Functionally Graded Coatings for C/C Composites*



Reproducibility, Storage, and Shelf Life Characterization



Brookfield PVS Rheometer Used for the Viscosity Measurements




*The temperature control bath has capability from
- 20°C (- 4 F) to 180°C (356 F)*



Reproducibility of GRABER 5A

Materials made at different times and in varying amounts show consistent viscosity



Effects of Storage Times & Temperatures


	One Month		Two Months		>Three Months	
	0°C	-15°C	0°C	-15°C	0°C	-15°C
Materials						
Graber-5	X	X	X	X	X	X
Graber-5A	X	X	X	X	X	X
Graber-12A	X	X	X	X	X	X



Storage Temperature Effects on GRABER 5A

Material Stored in a Refrigerator at 0 C

Materials stored for different times (1-3 months) had similar type of viscosity behavior as freshly prepared materials




Material was Tested under Vacuum



Storage Effects on GRABER 5A

Material Stored in a Freezer at -15 C

Materials stored for different times (1-3 months) had similar type of viscosity behavior as freshly prepared materials



Material was Tested under Vacuum



Crack Repair, ArcJet Testing, and Post Test Characterization


- GRABER 5 (0.035" and 0.062" wide cracks-ARC)
- GRABER 5A (0.035" and 0.062"-ARC)
- GRABER 12A (0.035"-JSC and 0.035" and 0.062"-ARC)

**No failure through repaired cracks was observed
during the ArcJet Tests**



WLE Entry Temperature Profiles


Panel 9 (55% Span) Temperature Profile for Nom ISS EOM



Pre-Test Photographs of Repaired Specimens

Run 12 – Model 1993

(0.035" or ~0.89 mm wide crack, GRABER-5A)



Percent Argon = 6% @ 2960F condition

Add air = 11.6% @ 2960F condition


Anomaly: water leak from electrode, which allowed water vapor in the stream



ArcJet Testing of Repaired Specimens

Run 12 – Model 1993

(0.035" or ~0.89 mm wide crack, GRABER-5A)



Front View



Side View

Percent Argon = 6% @ 2960F condition

Add air = 11.6% @ 2960F condition

Anomaly: water leak from electrode, which allowed water vapor in the stream




ArcJet Testing of Repaired Specimens

Run 12 – Model 1993

(0.035" or ~0.89 mm wide crack, GRABER-5A)



Post Test- Front Side







Post Test- Back Side



ArcJet Testing of Repaired Specimens

Run 14 – Model RCC 8

(0.062" or ~1.58 mm wide crack, GRABER-12A)



Percent Argon = 6% @ 2960F condition


Add air = 11.6% @ 2960F condition

Temperatures on model face were higher than previous runs (~3100F)

ArcJet Testing of Repaired Specimen

Run 17 – Model RCC 1

(0.062" or ~1.6 mm wide crack, GRABER-5A)



Front View

Percent Argon = 6% @ 2960F condition



Add air = 11.6% @ 2960F condition

Anamoly: Edge failure, sample removed after ~130 seconds @ 2960F condition

ArcJet Testing of Repaired Specimens

Run 17 – Model RCC 1

(0.062" or ~1.6 mm wide crack, GRABER-5A)



Percent Argon = 6% @ 2960F condition
Add air = 11.6% @ 2960F condition

Anomaly: Edge failure, sample removed after ~130 seconds @ 2960F condition




Microstructural Characterization of ArcJet Tested Specimens




Glenn Research Center at Lewis Field

Arcjet Sample Description and Preparation




ArcJet Sample 1993, Graber 5A, 0.035" Crack Width



Front side



Back side





ArcJet Sample 1993 (150-12), Graber 5A, 0.035" Crack Width



Front Side


There are a few large voids where oxidation has taken place.
The Graber material appears fairly well adhered to the rest
material even after testing.

ArcJet Sample 1993 (150-12), Graber 5A, 0.035" Crack Width



ArcJet Sample 150-14, RCC-8, GRABER 12A, 0.062" Crack Width

Back side





Front side



ArcJet Sample 150-14, RCC-8, GRABER 12A, 0.062" Crack Width



Front Side



There are large voids within the Graber material. The bonding between the Graber material and the C/C substrate looks good as seen on the right.




ArcJet Sample 150-14, RCC-8, GRABER 12A, 0.062" Crack




Backside

ArcJet Sample 150-11, RCC-1, GRABER 5, 0.062" Crack Width



PREISER SCIENTIFIC

Back side




PREISER SCIENTIFIC

Front side



Crack filled with Graber material



ArcJet Sample 150-11, RCC-1, GRABER 5, 0.062" Crack





Front Side



It appears in this sample that oxidation has reached an advanced stage. There is only a skeleton left of the Graber material which appears to be a glassy phase.

ArcJet Sample 150-11, RCC-1, GRABER 5, 0.062" Crack Width




These higher magnification images show more clearly the glassy phase left of the Graber material. You can also see the degradation of the C/C material.




Patch Laminates and Sealant Technology for Exterior Repair (PLASTER)

Sealant Technology Development



- Analogue RCC Plug Sealed with GRABER 5A Crack Sealant
- Survived the Arc-Jet Testing at JSC

Flexible Ceramic Overwrap Technology



Laminates for Patches and Overwraps

Summary and Conclusions

- GRABER-based materials have multiuse capability and multifunctionality for a wide variety of repair applications.
- This system can be easily modified to obtain adhesive materials with desired properties (viscosity, composition, curing behavior, etc.).
- The material has long shelf life. Normal storage and handling techniques can be used.
- These materials are affordable since the cost of raw constituents is very low (few dollars a pound)
- Excellent plasma performance in ArcJet testing conditions at various facilities.



Acknowledgments

- **Glenn Research Center**

- Tarah Shpargel, Jennifer Cerny, Ron Phillips, Jeannie Petko

- **Johnson Space Center, Houston, TX**

- Dr. Brian Mayeaux, A. Rodriguez, Joe Riccio, and ArcJet Staff
- Dr. Koichi Wakata, Dr. Danny Olivas, Jim Reilly

- **Marshall Space Flight Center, Huntsville, AL**

- Mike Effinger, Mike Terry

- **Ames Research Center, CA**

- Frank Hui, George Raiche, and ArcJet Test Facility Staff

- **ATK Thiokol**

- Dean Lester and Plasma Torch Testing Staff



Additional Information about GRABER

- [ON-ORBIT SHUTTLE REPAIR TAKES SHAPE,
www.aiaa.org/aerospace/images/
articleimages/pdf/lannottaugust04.pdf](http://www.aiaa.org/aerospace/images/articleimages/pdf/lannottaugust04.pdf)
- [NASA One Step Closer to Shuttle Repair in Orbit,
New Scientist, May 22, 2004, 24, www.newscientist.com](http://www.newscientist.com)
- [Nepszabadsag Online, www.nol.hu](http://www.nol.hu)
- [NASA Glenn Working to get shuttle flying, The Plain Dealer,
www.cleveland.com, October 21, 2004.](http://www.cleveland.com)
- www.grc.nasa.gov/WWW/MDWeb/hilights/HCY2004.html
- [NASA - Making the Space Shuttles Safer: Return To Flight Efforts,
www.nasa.gov/centers/glenn/projects/RTF_summary.html](http://www.nasa.gov/centers/glenn/projects/RTF_summary.html)

