

Advanced Low Conductivity Thermal Barrier Coatings: Performance and Future Directions (Invited paper)

Dongming Zhu and Robert A. Miller
NASA Glenn Research Center
21000 Brookpark Road, Cleveland, Ohio 44135

Thermal barrier coatings will be more aggressively designed to protect gas turbine engine hot-section components in order to meet future engine higher fuel efficiency and lower emission goals. In this presentation, thermal barrier coating development considerations and performance will be emphasized. Advanced thermal barrier coatings have been developed using a multi-component defect clustering approach, and shown to have improved thermal stability and lower conductivity. The coating systems have been demonstrated for high temperature combustor applications. For thermal barrier coatings designed for turbine airfoil applications, further improved erosion and impact resistance are crucial for engine performance and durability. Erosion resistant thermal barrier coatings are being developed, with a current emphasis on the toughness improvements using a combined rare earth- and transition metal-oxide doping approach. The performance of the toughened thermal barrier coatings has been evaluated in burner rig and laser heat-flux rig simulated engine erosion and thermal gradient environments. The results have shown that the coating composition optimizations can effectively improve the erosion and impact resistance of the coating systems, while maintaining low thermal conductivity and cyclic durability. The erosion, impact and high heat-flux damage mechanisms of the thermal barrier coatings will also be described.



Advanced Low Conductivity Thermal Barrier Coatings: Performance and Future Directions


Dongming Zhu and Robert A. Miller



**Durability and Protective Coatings Branch, Structures and Materials Division
NASA John H. Glenn Research Center
Cleveland, Ohio 44135, USA**

**Contact: Dr. Dongming Zhu
(216) 433-5422
Dongming.Zhu@nasa.gov**

**35th International Conference On Metallurgical Coatings And Thin Films (ICMCTF 2008)
San Diego, California, April 27-May 2, 2008**



Acknowledgments

This work was supported by NASA Fundamental Aeronautics (FA) Program Supersonics and Subsonic Rotary Wing Projects.

Collaborators

GE Aviation

Pratt and Whitney

Rolls Royce-Liberty Works

SUNY/Mesoscibe Tech.

Howmet Coatings



Honeywell Engines

UCSB

Direct Vapor Technol.

Motivation

- Thermal barrier coatings (TBCs) can significantly increase gas temperatures, reduce cooling requirements, and improve engine fuel efficiency and reliability





(a) Current TBCs

(b) Advanced TBCs

NASA Ceramic Coating Development Goals

- Meet engine temperature and performance requirements
 - improved engine efficiency
 - reduced emission
 - increase long-term durability
- Improve technology readiness
- The programs require a step-increase in coating capability
- Reliability critical





Outline




- **Simulated high-heat-flux testing approaches**
 - Laser high heat flux
 - Burner and laser high temperature erosion
 - High pressure burner and high heat-flux capability
- **Low conductivity thermal barrier coating developments**
 - Low conductivity TBC design requirements
 - Performance of low k four-component TBC systems
 - Conductivity, and cyclic durability
 - High toughness Low k four- and six-component turbine airfoil TBC development – erosion resistance
 - CMAS interaction testing
- **Future directions**
- **Summary**

High Heat-Flux Test Approaches


- High-heat-flux tests crucial for turbine TBC developments
 - CO₂ laser simulated turbine engine high-heat-flux rig
 - Atmospheric burner rig simulated heat flux testing
 - High pressure burner rig simulated engine heat flux and pressure environments

Turbine blade TBC testing requirements


- $\Delta T \sim 450^\circ\text{F}$ (250°C) across 5mil coating
- Heat flux up to 400 W/cm^2



High Velocity Burner Erosion Rig and Laser high Heat Flux Erosion Test Rig for Turbine TBC Testing




Mach 0.3-1.0 burner erosion rig



Laser heat flux erosion rig


ZrO_2 -(7-8) wt% Y_2O_3 Thermal Barrier Coating Systems


- Relatively low intrinsic thermal conductivity $\sim 2.5 \text{ W/m-K}$
- High thermal expansion to better match superalloy substrates
- Good high temperature stability and mechanical properties
- Additional conductivity reduction by micro-porosity




Sintering and Conductivity Increase of ZrO_2 -(7-8) wt% Y_2O_3

- Significant conductivity increase at high temperature due to sintering
- Accelerated failure due to phase stability and reduced strain tolerance







Sintering Kinetics of Plasma-Sprayed $\text{ZrO}_2\text{-8wt\%Y}_2\text{O}_3$ Coatings



Zhu & Miller, Surf. Coat. Technol., 1998; MRS Bulletin, 2000

Sintering Cracks and Delaminations



- High heat flux surface sintering cracking and resulting coating delaminations



Zhu et al, Surf. Coat. Tech., 138 (2001), 1-8

Sintering Cracks and Delaminations - continued


- Sintering strain corresponding to the thermal gradient across the coating ($T_{\text{surface}}=1280^{\circ}\text{C}$, $T_{\text{interface}}=1095^{\circ}\text{F}$)





Low Conductivity and Sintering Resistant Thermal Barrier Coating Design Requirements

- **Low conductivity (“1/2” of the baseline) retained at 2400°F**
- **Improved sintering resistance and phase stability (up to 3000°F)**
- **Excellent durability and mechanical properties**
 - **Cyclic life**
 - **Toughness**
 - **Erosion/impact resistance**
 - **CMAS and corrosion resistance**
 - **Compatibility with the substrate/TGO**
- **Processing capability using existing infrastructure and alternative coating systems**
- **Other design considerations**
 - **Favorable optical properties**
 - **Potentially suitable for various metal and ceramic components**
 - **Affordable and safe**




Low Conductivity Thermal Barrier Coating Design Approaches


- Efforts on modifying coating microstructures and porosity, composite TBCs, or alternative oxide compounds
- Emphasize ZrO_2 - or HfO_2 -based *alloy* systems – defect cluster approach for toughness consideration
- Advantages of defect cluster approach
 - **Advanced design approach:** design of the clustering
 - **Better thermal stability:** point defects are thermodynamically stable
 - **Improved sintering resistance:** effective defect concentration reduced and activation energies increased by clustering
 - **Easy to fabricate:** plasma-sprayed or EB-PVD processes

Development of Advanced Defect Cluster Low Conductivity Thermal Barrier Coatings


- Multi-component oxide defect clustering approach (Zhu and Miller, US Patents No. 6,812,176, No.7,001,859, and No. 7,186,466)
e.g.: $\text{ZrO}_2\text{-Y}_2\text{O}_3\text{-Nd}_2\text{O}_3(\text{Gd}_2\text{O}_3, \text{Sm}_2\text{O}_3)\text{-Yb}_2\text{O}_3(\text{Sc}_2\text{O}_3)$ systems
 - ↳ Primary stabilizer
 - ↳ Oxide cluster dopants with distinctive ionic sizes
- Defect clusters associated with dopant segregation
- The nanometer sized clusters for reduced thermal conductivity, improved stability, and mechanical properties



Plasma-sprayed $\text{ZrO}_2\text{-(Y, Nd, Yb)}_2\text{O}_3$




EB-PVD $\text{ZrO}_2\text{-(Y, Nd, Yb)}_2\text{O}_3$




EELS elemental maps of EB-PVD $\text{ZrO}_2\text{-(Y, Gd, Yb)}_2\text{O}_3$

Defect Clusters in a Plasma-Sprayed Y_2O_3 , Nd_2O_3 and Yb_2O_3 Co-Doped ZrO_2 -Thermal Barrier Coating


- Yb, Nd rich regions consisting of small clusters with size of 5 to 20 nm



Yb, Nd rich region clusters




Overall EDS




Yb rich region EDS

Low Conductivity Defect Cluster Coatings Demonstrated Improved Thermal Stability

- Thermal conductivity significantly reduced at high temperatures for the low conductivity TBCs




(a) Plasma-sprayed coatings



(b) EB-PVD coatings


Thermal Conductivity of Defect Cluster Thermal Barrier Coatings




(k_0 , k_5 and k_{20} are the initial thermal conductivity, and the conductivity at 5 and 20 hours, respectively)

Thermal Conductivity of Defect Cluster Thermal Barrier Coatings

- Thermal conductivity benefit of oxide defect cluster thermal barrier coatings demonstrated




(k_0 , and k_{20} are the initial thermal conductivity, and the conductivity at 5 and 20 hours, respectively)



Furnace Cyclic Behavior of $\text{ZrO}_2\text{-(Y,Gd,Yb)}_2\text{O}_3$ Thermal Barrier Coatings


- **t'** low k TBCs had good cyclic durability
- The cubic-phase low conductivity TBC durability needed improvements



Zhu and Miller, Ceram. Sci. Eng. Proc., 2002



Furnace Cyclic Behavior of $\text{ZrO}_2\text{-(Y,Gd,Yb)}_2\text{O}_3$ Thermal Barrier Coatings - Continued

- t' low k TBCs had good cyclic durability
- The cubic-phase low conductivity TBC durability initially improved by an 7YSZ or low k t' -phase interlayer




Advanced Low Conductivity TBC Showed Excellent Cyclic Durability

— Coating validated for down-selected low conductivity coating systems




Laser heat flux tests



Burner rig tests

Advanced Low Conductivity Combustor Thermal Barrier Coating Developments



- Low k TBC coated components demonstrated in simulated engine environments
- Low k TBC being incorporated in advanced engine development programs




Low conductivity TBC flame tube and combustor deflector demos in Advanced Subsonic Combustion Rig (ASCR)



Flame tube



Low conductivity TBC combustor liner demonstration in Combustor rig



Outer liner

Inner liner


Low conductivity TBC: combustor liner demonstration



Low conductivity TBC Propulsion 21 flame tube and deflector demonstrations


Erosion and Impact Resistant Turbine TBC Development

- Multi-component ZrO_2 low k coatings showed promise in improving erosion and impact resistance




Zhu & Miller, NASA R&T, 2004

Erosion and impact resistance, measured as the erodent Al_2O_3 weight required to penetrate unit thickness coating





2200°F burner rig erosion





Advanced Multi-Component Erosion Resistant Turbine Blade Thermal Barrier Coating Development

- Rare earth (RE) and transition metal oxide defect clustering approach (US Patents No. 6,812,176, No.7,001,859, and 7,186,466; US patent application 11/510,574) specifically by additions of RE_2O_3 , TiO_2 and Ta_2O_5
- Significantly improved toughness, cyclic durability and erosion resistance while maintaining low thermal conductivity
- Improved thermal stability due to reduced diffusion at high temperature





Furnace Cyclic Test Lifetime and Thermal Conductivity of TiO₂ Doped Thermal Barrier Coatings





— Unpublished work 2003



Furnace Cyclic Lifetime of Advanced Turbine Thermal Barrier Coatings


- Furnace cyclic life can be optimized with RE_2O_3 and TT additions
- Stability and volatility with too high TT concentrations







Cyclic Life of Four-Component Thermal Barrier Coatings

- Furnace and high heat flux cyclic life being optimized for long-term durability







Thermal Conductivity of Selected Low k Thermal Barrier Coatings



Impact Resistance of Advanced Multi-component Low Conductivity Thermal Barrier Coatings


- Improved impact/erosion resistance observed for advanced low conductivity six-component coatings







Erosion Resistance of Advanced Multi-component Low Conductivity Thermal Barrier Coatings

- The original cubic low k coating showed significant increase in erosion resistance due to the incorporation of TiO_2 and Ta_2O_5




Tetragonality of Multi-Component ZrO_2 being Evaluated and Correlated to Coating Performance

- Multi-component TiO_2/Ta_2O_5 and rare earth dopants increase the tetragonality (c/a ratio)
- Current efforts in optimizing the dopant composition ranges




Area detector x-ray diffractometer used for EB-PVD coatings




Impact Failure of Advanced Multi-Component Low Conductivity Thermal Barrier Coatings

- Surface sintering and impact densification zones observed, with subsequent spallation under the erodent further impacts
- Toughened structures observed

SEM micrographs of advanced thermal barrier coating after impact/erosion damage





Secondary electron image



Backscattered electron image

Impact Failure of Advanced Multi-Component Low Conductivity Thermal Barrier Coatings

– Effect of erosion parameters will be modeled and validated




Time →



High Heat Flux Testing of Turbine EB-PVD Thermal Barrier Coatings to Study CMAS Effect


- Specimens typically tested at $T_{\text{surface}} \sim 2400^{\circ}\text{F}$, $T_{\text{interface}} 2000^{\circ}\text{F}$
- Heat flux up to $250\text{-}300 \text{ W/cm}^2$, cooling heat transfer coefficient up to $h_c 0.32 \text{ W/cm}^2\text{-K}$
- Accelerated failure observed with CMAS interactions
- Advanced multi-component coatings completed 50 hr testing



Specimen under the rig test




(a) Upon initial heating



(b) After testing

Combustor TBC



Baseline coating



Advanced coatings
50 hrs

Turbine TBCs




Future Directions for Low Conductivity TBC Development


- **Emphasize high heat flux durability and erosion resistance**
 - **Optimize high toughness erosion resistant turbine coatings**
 - **Improve turbine airfoil TBCs with up to 3x erosion resistance**
 - **Emphasize creep, fatigue, erosion, and CMAS interactions**
 - **Develop multilayered damping and erosion coatings**
 - **Develop turbine blade TBC life prediction model**

Future Directions for Low Conductivity TBC Development


- Emphasize thin ceramic matrix composite turbine coating processing
 - Advanced processing for integrated TEBCs
 - Ceramic nanocomposite and nanotube-based TEBCs for improved durability and optical properties
 - Embedded sensors
 - Life prediction methodology and design tool development



CMC Turbine Blade coatings



CMC combustor liner and vane



Summary

- **Four-component low k TBC systems developed for low k combustor applications**
- **Advanced turbine airfoil TBCs being developed with combined low conductivity and high toughness**
- **Improved erosion/impact resistance observed for the multi-component coating t' and t' /cubic nano-composite systems**
- **Coatings being optimized for cyclic life, thermal conductivity and erosion/impact and CMAS resistance**
- **High heat flux durability, multifunctional coatings and lifing models being emphasized in the current research programs**