

- [Find Similar Abstracts \(with default settings below\)](#)
- [arXiv e-print](#) (arXiv:1108.4632)
- [References in the Article](#)
- [Also-Read Articles](#) (Reads History)
- [Translate This Page](#)

**Title:** Proximity Effects and Nonequilibrium Superconductivity in Transition-Edge Sensors

**Authors:** [Sadleir, John E.](#); [Smith, Stephen J.](#); [Robinson, Ian K.](#); [Finkbeiner, Fred M.](#); [Chervenak, James A.](#); [Bandler, Simon R.](#); [Eckart, Megan E.](#); [Kilbourne, Caroline A.](#)

**Publication:** eprint arXiv:1108.4632

**Publication Date:** 08/2011

**Origin:** ARXIV

**Keywords:** Condensed Matter - Superconductivity, Astrophysics - Instrumentation and Methods for Astrophysics, Physics - Instrumentation and Detectors

**Comment:** 10 pages, 8 figures

**Bibliographic Code:** [2011arXiv1108.4632S](#)

### Abstract

We have recently shown that normal-metal/superconductor (N/S) bilayer TESs (superconducting Transition-Edge Sensors) exhibit weak-link behavior.<sup>1</sup> Here we extend our understanding to include TESs with added noise-mitigating normal-metal structures (N structures). We find TESs with added Au structures also exhibit weak-link behavior as evidenced by exponential temperature dependence of the critical current and Josephson-like oscillations of the critical current with applied magnetic field. We explain our results in terms of an effect converse to the longitudinal proximity effect (LoPE)<sup>1</sup>, the lateral inverse proximity effect (LaiPE), for which the order parameter in the N/S bilayer is reduced due to the neighboring N structures. Resistance and critical current measurements are presented as a function of temperature and magnetic field taken on square Mo/Au bilayer TESs with lengths ranging from 8 to 130  $\mu\text{m}$  with and without added N structures. We observe the inverse proximity effect on the bilayer over in-plane distances many tens of microns and find the transition shifts to lower temperatures scale approximately as the inverse square of the in-plane N-structure separation distance, without appreciable broadening of the transition width. We also present evidence for nonequilibrium superconductivity and estimate a quasiparticle lifetime of  $1.8 \times 10^{-10}$  s for the bilayer. The LoPE model is also used to explain the increased conductivity at temperatures above the bilayer's steep resistive transition.

---

[Bibtex entry for this abstract](#) [Preferred format for this abstract](#) (see [Preferences](#))

---

Add this article to private library

Remove this article from private library