


National Aeronautics and Space Administration
Marshall Space Flight Center




Standardization in Additive Manufacturing: Challenges in Structural Integrity Assurance

**Doug Wells
NASA MSFC
Huntsville AL**

**Symposium on Fatigue and Fracture of
Additive Manufactured
Materials and Components**

November 15-16, 2017



Structural Integrity in Additive Manufacturing



- NASA is integrating critical AM parts into human-rated flight systems:
Space Launch System : : Orion Spacecraft : : Commercial Crew



Aerojet Rocketdyne RS-25




SpaceX SuperDraco

**Ensuring structural integrity is the highest challenge -
Quality Assurance and standardization are fundamental
to this endeavor.**

1. Additive Manufacturing Standards Landscape
2. Integration of structural integrity rationale in AM
3. Process qualifications – standardization
4. Material property transferability
5. NDE standardization status in AM
6. Impending, near-term reliance on computed tomography
7. Coming reliance on in-situ monitoring

SC30



$$S_1 = 6M / Wt^2$$

$$\frac{|W/2-B|}{W/2} \leq 0.9$$





$$\frac{c}{\text{Min}(B, |W-B|)} < 1$$

$$0 \leq a/t \leq 0.95$$

$$0 \leq a/c \leq 8$$

$$X = x/t, \quad 0 \leq X \leq 1$$

$$S_i(X), \quad i=0,1,2,3$$





Standardization in Additive Manufacturing



America Makes/ANSI Additive Manufacturing Standardization Collaborative **AMSC**

Focused on identifying gaps in AM standardization



<p>ASTM International</p> 	<p>International Organization For Standardization</p> 	<p>American Society of Mechanical Engineers</p> 
<p>SAE International</p> 	<p>American Welding Society</p> 	<p>Institute of Electrical and Electronics Engineers</p> 
<p>MITA MEDICAL IMAGING & TECHNOLOGY ALLIANCE A DIVISION OF KEMA</p> 	<p>Association for the Advancement of Medical Instrumentation</p> 	<p>IPC - Association Connecting Electronics Industries</p> 
<p>Metal Powder Industries Federation</p> 		



Integration of Structural Integrity



- **AM components often require a more integrated approach to substantiate the rationale for structural integrity**
 - Not a new concept, foundation of fracture control, just atypically complex
 - Developing a structural integrity rationale from multiple mitigations to guard against multiple risks is new to many.
 - Fracture control challenges are more frequent

MSFC-STD-3716: *Standard for Additively Manufactured Spaceflight Hardware by Laser Powder Bed Fusion in Metals*

- **AM *Part Production Plan*** required to illuminate risks
- Includes the ***Integrated Structural Integrity Rationale*** – a concise summary of how structural integrity is assured commensurate with the part's risk classification





Integrated Structural Integrity Rationale



Mitigations

Process Controls

Process
Qualifications



Process Witness Testing

NDE: CT, RT, PT, ET, UT

Part Acceptance Tests
(dimensional, proof, leak)

PPA assessment

Risks

Process Escapes:

Physical defects (cracks, voids)


Material capability debits


High structural demand

Complex geometry

Surface quality

Uninspectable volume
and surface





Process Qualification



Standardization Need: Definition of a Qualified AM Process

Most fundamental of mitigations to ensure structural integrity


MSFC-SPEC-3717: *Specification for Control and Qualification of Laser Powder Bed Fusion Metallurgical Processes*

- Defines a Qualified Metallurgical Process (QMP) (represents a first cut)
- Consensus Standards are beginning to establish definitions and requirements

A Qualified AM Process is *critical* to knowing

- Consistency of process over time and across platforms,
 - Individual machine capability
- What material condition is characterized/represented in design data
- What material condition is expected in parts
- Transferability and equivalence in material structural performance

IN718 Microstructural Evolution





Defining Qualified AM Processes



Need consensus definitions of AM process quality for consistency

- Powder controls
- Process parameters
- Material integrity / acceptable defect state
- Microstructure evolution
- Mechanical properties
- Surface quality and detail resolution
- Variability across build volume

The first question to ask when looking at any data, parts, or products from AM:

How was the AM process qualified?

Coming hurdle: Accommodating adaptive AM processes


- Move from qualifying process to qualifying algorithm
- Increased reliance on pre-production article evaluations

Standardization Need: Establishing Material Property Transferability

- Evaluation of standard coupons for mechanical properties in tensile, fatigue fracture mechanics developed by AM processes
 - **Will be used to establish engineering design values**
- How do properties vary within AM parts?
- Essential to association of process qualification to part qualification
- Critical to know properties within part are represented by characterization

Critical aspects in structural integrity

- Witness specimen correlation
- “Influence factors” in AM materials
 - Thermal history in build
 - Surface texture
 - Thin section capability
- Capability and reliability of post-processing to homogenize and control microstructural evolution to lessen transferability risk.



ASTM F42.01 Work Item WK49229: Orientation and Location Dependence Mechanical Properties for Metal Additive Manufacturing


Standardization Need: Non-destructive Evaluation for AM

E07.10 Work Item – WK47031: *Standard Guide for Nondestructive Testing of Metal Additively Manufactured Aerospace Parts After Build*

F42.01 Work Item – WK56649: *Standard Practice/Guide for Intentionally Seeding Replica into Additively Manufactured (AM) Structures*

High Priority: Defect Catalog for AM


- Analogous to references used to identify defects in casting or welding
- Correlation of defect type to AM process, NDE method, and reliability of detection
- Correlation of defect risk to structural integrity



Vertical Lack-of-Fusion




Layer, “Multi-site damage”



Horizontal Lack-of-Fusion



Zero-volume Lack-of-Fusion after HIP





Near-term Reliance on CT



Standardization Need: Computed Tomography (CT) with Quantified Reliability
For aerospace, CT is not an industry standard technique with quantified reliability for detection of defects – Probability of Detection (POD)

Current state of the art: reliance on Representative Quality Indicators (RQIs)

- See ASTM E1817 *Standard Practice for Controlling Quality of Radiological Examination by Using Representative Quality Indicators (RQIs)*


AM Complications for CT:

- Penetration vs resolution
- Complex AM geometry
- **Low-volume defects**
- Physics: beam hardening, edge artifacts, etc.
- Makes generalization difficult

Planned work in E07.01 Radiography

- Build on 2D CT and DR standards
- Application to structural integrity requirements such as POD methods may require broader cooperative efforts

MSFC Modular CT Reference Standard



Numerical CT simulations may help with defining detection capability and uncertainty quantification.



Coming Reliance on In-Situ Monitoring



How to approach in-situ monitoring of AM processes?


- Harnessing the technology is only half the battle
 - Detectors, data stream, data storage, computations
- Second half of the battle is quantifying in-situ process monitoring **reliability**

Community must realize passive in-situ monitoring is an NDE technique

1. Understand physical basis for measured phenomena
2. Proven causal correlation of measured phenomena to a well-defined defect state
3. Proven level of reliability for detection of the defective process state
 - False negatives and false positives -> understanding and balance is needed

Closed loop in-situ monitoring adds significantly to the reliability challenge


- No longer a NDE technique – may not be non-destructive
- Establishing the reliability of the algorithm used to interact and intervene in the AM process adds considerable complexity over passive systems




Example of development: In-Situ Monitoring



Additive Manufacturing Qualification Process




Pore Area and Flaw Type versus SLM Parameters




C3-02DE (DOE 1 (20))


(vertical sections through samples, 50X, as polished)



C3-573 (DOE 2 (12))



C3-568 (DOE 2 (1))



C3-412 (DOE 1b2 (18))


Flaw types clearly defined and correlated with pore area gradient.




Example of development: In-Situ Monitoring




Unique Off-Nominal Signatures



Process Limit Approach Developed



Cluster Analysis Methodology



- Unique part signatures are generated for DOE processing condition and identified as discernably different than the nominal response
- Methodology to establish control limits around the nominal part signature

Unique Signatures Generated and Discernable For Each DOE Processing Condition




Used with Permission: Nick Mulé
Distribution Statement A: Approved for Public Release



Final Summary



1. Additive Manufacturing Standards Landscape
 - Diverse and developing rapidly, still limited in detail for structural integrity challenges
2. Integration of structural integrity rationale in AM
 - Essential to understanding risks on a part-by-part basis
3. Process qualifications – standardization
 - AM process qualification needs standard definition
4. Material property transferability
 - Applicability of design values depends upon methods to understand property transferability from coupon to part
5. NDE standardization status in AM
 - Primary, quantifiable reference for structural integrity. Active work items in E07
6. Near-term reliance on computed tomography
 - Needs methodologies to quantify reliability, particularly for low-volume defects
7. Coming reliance on in-situ monitoring
 - Potential great enabler for structural integrity, but caution required.



Thank You

Additive Manufacturing at MSFC

