



Additive Manufacturing of Liquid Rocket Engine Combustion Devices: A Summary of Process Developments and Hot-Fire Testing Results

Paul Gradl, Sandy Greene, Chris Protz, Brad Bullard, James Buzzell, Chance Garcia, Jessica Wood, Ken Cooper
NASA Marshall Space Flight Center (MSFC)

James Hulka
Jacobs Technology, ESSCA Group



Robin Osborne
ERC, ESSCA Group

9-11 July 2018

Additive Manufacturing (AM) Overview



- Additive Manufacturing (AM) is an emerging technology with a focus on complex metallic component fabrication
 - Enables complex shapes and internal features that were not possibly with traditional manufacturing techniques
 - Significant schedule and overall lifecycle cost reductions
- To date at the NASA Marshall Space Flight Center (MSFC), combustion devices component hardware ranging in size from 100 - 35,000 lbf has been designed and manufactured using AM and many of these pieces have been hot-fire tested.




Metal AM Processes: Powder Bed Based



• Selective Laser Melting (SLM)

- Basic Process: Uses a layer-by-layer powder-bed approach in which the desired component features are sintered and subsequently solidified using a laser. Used widely in combustion devices applications.
- Advantages: Allows for high resolution, fine features, including complex internal designs to be fabricated, such as cooling channels
- Disadvantages: The scale for SLM is limited and does not provide a solution for all components



SLM Fabrication Process Overview.

• Electron Beam Melting

- Basic Process: Similar to SLM, but uses an electron beam instead of a laser. Not frequently used in combustion devices applications.
- Advantages: Build is performed under vacuum, which can be useful for reactive materials such as titanium



Metal AM Processes: Directed Energy Deposition (DED)



Freeform fabrication technique focused on near net shapes as a forging or casting replacement and also near-final geometry fabrication. Can be implemented using powder or wire as additive medium.


Blown Powder Deposition / Hybrid

Melt pool created by laser and off-axis nozzles inject powder into melt pool; installed on gantry or robotic system




Arc-Based Deposition (wire)

Pulsed-wire metal inert gas (MIG) welding process creates near net shapes with the deposition heat integral to a robot



Laser Wire Deposition

A melt pool is created by a laser and uses an off-axis wire-fed deposition to create freeform shapes, attached to robot system



Electron Beam Deposition (wire)

An off-axis wire-fed deposition technique using electron beam as energy source; completed in a vacuum.



Overview of Additive Manufacturing Component Focuses



Augmented Spark Igniters



Injectors




Channel-cooled Nozzles



Combustion Chambers




AM Thrust Chamber Injectors: Overview



100lb LOX/Propane Nanolaunch Injector. Built 2012. Tested 2013.



1.2K LOX/Hydrogen Injector
First Tested in June 2013.
>7200 seconds hotfire




Methane 4K Injector with printed manifolds, parametric features.
Tested Sept 2015.



20K LPS Subscale Injector.
Tested August 2013



35K AMDE Injector with Welded Manifolds, Tested 2015



LOX/Methane Gas Generator Injector, Tested Summer 2017

- MSFC has developed a total of 10 unique AM injectors between 2012-2018
 - Materials: Inco 625, Inco 718, Monel K-500
 - Element Types: swirl coax, shear coax, FOF
 - Number of Elements: ranging from 6 to 62
 - Diameters: ranging from 1.125" to 7.5"
 - Hot fire tests performed on 7 of these 10 AM injectors
- To date, all MSFC injector designs have been manufactured with a powder-bed process.
- Advantages of AM application to injectors:
 - Reduction of reducing part count, braze/weld operations, cost, and schedule
 - Allows non-conventional manifolding schemes and element designs
- Challenges of AM fabrication of injectors:
 - Feature size resolution (particularly radial to the build direction)
 - Excessive surface roughness
 - Removing powder prior to heat treatments (even stress relief) is both necessary and challenging

AM Thrust Chamber Injectors: Test Evaluations



- Pathfinder approach for comparing AM against conventionally machined injectors
 - To evaluate structural and performance capabilities of AM in liquid rocket injector applications, two early test programs were initiated at NASA MSFC to directly compare the operating characteristics of conventionally manufactured 20 KlbF LOX/H₂ swirl coaxial element injectors to those of similarly designed SLM manufactured injectors.
 - Results of hot-fire testing showed characteristic exhaust velocity efficiencies for the two different manufacturing techniques to be within measurement error.
- Follow-on efforts included successful hot fire test firings of a range of element types (swirl coaxial, shear coaxial, impinging), propellant combinations (LOX/H₂, LOX/CH₄, LOX/C₃H₈), and thrust classes (100 lbf to 35K lbf) to validate AM use in these applications.

Stable performance of AM Injectors and Efficiency Approaching Traditional (98-99%)



Water Flow of the AMDE Injector LOX Circuit; Hot Fire Test of the AMDE Injector.

Four Thrusters with 1200 lbf Shear Coaxial Injectors.

AM Combustion Chambers: Overview



- MSFC has developed over 10 unique AM chambers between 2013-2018
 - Materials: Inco 625, Inco 718, GRCo-84, C-18150, Monel K-500
 - Propellants: LOX/GH2, LOX/LCH4, LOX/RP-1
 - Additive Process: SLM and SLM/DED
 - Over 110 starts and 6100+ seconds of hot fire test.
- Chambers have been fabricated using SLM powder bed AM technique, with a few test articles incorporating DED techniques for a bimetallic end product.

Total Accumulated Hot-fire Time on Copper-alloy Chambers = >6100 sec


2013 – 2015

2016

2017

2018

Feasibility Hardware



1.2K Workhorse

2365 sec



MET1

25 sec



LOX/RP1 Faceplate

25 sec




LCUSP 3.0

45 sec



META4

26 sec



1.2K Commercial Liners

2500 sec



LCUSP 2.2

102 sec



META4 #2



134+ sec



AM Combustion Chambers: Methane Engine SLM Chamber Development




Inco 625 Pathfinder




- **Inco 625 Pathfinder:** Included pressure and temperature ports along the length of one coolant channel to gather critical data for thermal models.
- **META4:** Full-length, regeneratively cooled GRCop-84 chamber developed for LOX/LCH4 in-space applications; fabricated in two sections and welded together due to SLM build height limitations
- **META4X4:** Second iteration of META4 concept; same thrust level but smaller package with a bolted center interface in place of a welded joint
- **MET1:** Scaled down approach from META4 for smaller in-space missions or for clustering together to provide multiples of 1 Klfb thrust; could be printed in one build with no mid-section interface


META 4 and META 4X4





MET1



AM Combustion Chambers: Workhorse SLM Chamber Development





- NASA MSFC built a series of SLM workhorse chamber liners to allow liners to be rapidly tested and changed in a simplified test bed to demonstrate various materials.
 - Objective of liner tests was to complete cyclic testing on material and demonstrate SLM lifecycle. Liners were successfully tested and did not show indications of erosion even with wall temperatures over 1,000 °F.
 - A total of three chambers were tested: two manufactured from GRCop-84 using different SLM build parameter settings and one from C-18150.
 - Designed for water-cooling, LOX/GH2 and 1,200 – 1,500 lbf.
 - Chambers were fabricated at MSFC and from commercial vendors.



AM Combustion Chambers: Bimetallic AM Combustion Chambers




- The Low Cost Upper Stage-Class Propulsion (LCUSP) project developed SLM fabrication of GRCop84 and DED Electron Beam Free Form Fabrication (EBF³) with Inco 625 manufacturing technologies to produce a combustion chamber at a lower cost and schedule.
 - Chamber was designed and fabricated by MSFC, GRC, and LaRC, and hot-fire tested at MSFC.
 - LOX/LH₂, nominal thrust of 35,000 lbf.
 - Demonstrated key manufacturing technologies in a relevant environment, taking the AM LCUSP chamber and the one piece AM cooled nozzle to 100% of design conditions.




AM Channel-Cooled Nozzles: Overview






- NASA is investigating AM methods for targeting increased scale required for current NASA and commercial space program channel wall nozzle applications.
- Channel-cooled nozzles present a unique manufacturing challenge due to the scale and complexity required at these scales.



AM Channel-Cooled Nozzles: Evolution to Large-scale



- NASA is evolving scale of nozzle hardware through additive new additive manufacturing technologies
 - Current SLM technology limited to ~16-inches (400mm)
 - Developing new processes using DED processes
 - Blown Powder Deposition, Laser Wire Closeout, Arc-based Deposition



Hot-fire testing of “maximum” scale SLM Inco 625 nozzle on LCUSP chamber



Large Scale DED Techniques for Forming Nozzles and Chambers

AM Channel-Cooled Nozzles: Development at MSFC




- Several AM methods are being investigated for forming the inner liner, producing the coolant channels, and fabricating the manifolds and combinations of channels and manifolds:
 - Laser Wire Direct Closeout (LWDC)
 - Arc-Based Wire Deposition
 - Blown Powder Deposition (BPD)
 - Selective Laser Melting (SLM)


Nozzle Component Description	Propellants	Additive Process	Material	Starts	Hot-fire Time (sec)
1,200 lbf LWDC Regen Nozzle, PH034	LOX/GH2	LWDC	SS347	4	160
1,400 lbf LWDC Regen Nozzle, Additive Liner, PH034	LOX/GH2	LWDC	Inco 625	9	880
Integrated Nozzle Film Coolant Ring (INFCR), PF086	LOX/GH2	SLM	Inco 625	12	147
1,200 lbf DED Regen Nozzle, PH034	LOX/GH2	DED	Inco 625	1	15
800 lbf Radiatively-cooled Nozzle, PD020C	LOX/GH2	SLM	Inco 718	1	30
			TOTAL	23	1232



Liner Formed using Arc-Deposition Additive



Laser Wire Direct Closeout



DED Blown Powder Nozzle and DED Nozzle during feasibility hot-fire test.


Arc-based additive deposition and LWDC integrated into channel wall nozzle for hot-fire.

AM Augmented Spark Igniters




- AM of Augmented Spark Igniters (ASI) has been targeted as a potential upgrade for the RS-25 engine. The use of hybrid DED/CNC process allows for the bimetallic copper and nickel alloy design to be fabricated through an AM process.
 - Approach offers the advantage of smooth, machined finishes in locations that are not possible with SLM

ASI Description	Propellants	Additive Process	Material	Starts
Regen-cooled ASI, AR-1	LOX/LH2	SLM	Inco 625	11
Regen-cooled ASI, AM-3	LOX/LH2	SLM	Inco 625	16
Baseline ASI, AR-B-1	LOX/LH2	SLM	Inco 625	15
Baseline ASI, AR-B-2	LOX/LH2	SLM	Inco 625	21
Regen-cooled ASI, API-1	LOX/LH2	SLM	Inco 625	13
Hybrid, Bi-metallic ASI	LOX/LH2	Hybrid	Inco 625 / C18150	33
			TOTAL	109



Photos taken during the BPD build process of the prototype RS-25 ASI.



Bi-metallic prototype of the RS-25 ASI, built using hybrid manufacturing.


Summary




- Numerous combustion devices components – injectors, combustion chambers, channel-wall nozzles, and augmented spark igniters – have been designed and built using AM and hot-fire tested over the past 8 years at NASA MSFC.
 - Component level and integrated system level testing in a variety of propellants have been conducted and performance derived from these tests.
 - AM technologies – specifically SLM and DED – have been found to be readily applicable for combustion devices components.
- NASA is continuing to evolve these technologies on a path towards flight systems



Nanolaunch Injector Water Flow Test



META4X4 Chamber Hot-Fire Test



LWDC Nozzle #1 Hot-Fire Test



Contact: Paul Gradl
NASA MSFC
256.544.2455
Paul.R.Gradl@nasa.gov



Acknowledgements




Gregg Jones
Jessica Wood
Dale Jackson
Chip Kopicz
Sandy Greene
Ian Johnston
Cory Medina
Will Brandsmeier
Kevin Baker
Dwight Goodman
Shawn Skinner
Adam Willis
Bob Witbrodt
Armando Martinez
Matt Cross
Rory Jones
William Till
Robert Hickman
Dave Ellis
Bob Carter
Brad Lerch

Ivan Locci
Laura Evans
Karen Taminger
Darron Rice
Greg Barnett
Majid Babai
Zach Jones
Omar Mireles
Jim Lydon
Brian West
Phillip Steele
James Walker
David Myers
Ron Beshears
Doug Wells
Cynthia Sprader (TS115 Crew)
Ryan Wall (TS116 Crew)
Paul Dumbacher (Test Cell crew)
David Olive
Steve Wofford
Mike Shadoan

Carol Jacobs (retired)
Andy Hardin
Keegan Jackson
John Vickers
John Fikes
Jim Turner
Greg Chavers
Nick Case
Greg Hyatt (DMG)
Sean Sporie (DMG)
Bryant Walker (Keystone)
Albert Hammeke (LTA)
Bhaskar Dutta (DM3D)
Joe Sims (ASRC)
Judy Schneider (UAH)
Moog
Stratasys
Incodema
Aerojet Rocketdyne
Commercial Space Partners

References



1. Betts, E.M., Eddleman, D.E., Reynolds, D.C., Hardin, N.A., "Using Innovative Technologies for Manufacturing Rocket Engine Hardware," JANNAF 6th Liquid Propulsion Subcommittee Meeting; 5-9 Dec. 2011; Huntsville, AL.
2. Ballard, R.O., "Next-Generation RS-25 Engines for the NASA Space Launch System," NASA M17-6076. 7th European Conference for Aeronautics and Space Sciences (EUCASS 2017). Milan; Italy. 3-6 Jul. (2017).
3. Gradl, P., Brandsmeier, W., Calvert, M., et al., "Additive Manufacturing Overview: Propulsion Applications, Design for and Lessons Learned. Presentation," M17-6434. 1 December (2017).
4. ASTM Committee F42 on Additive Manufacturing Technologies. Standard Terminology for Additive Manufacturing Technologies ASTM Standard: F2792-12a. (2012).
5. Ek, K., "Additive Manufactured Metals," Master of Science thesis, KTH Royal Institute of Technology (2014).
6. Qian, M., W. Xu, M. Brandt, and H. P. Tang, "Additive manufacturing and postprocessing of Ti-6Al-4V for superior mechanical properties," *MRS Bulletin* 41, no. 10 (2016): 775-784.
7. O'Neill, W., Cockburn, A., et al., "Supersonic Laser Deposition of Ti and Ti64 Alloys," 5th International Symposium on High Power Fibre Laser and their Applications/14th International Conference on Laser Optics. July 1, 2010. St. Petersburg, Russia.
8. Bremen, S., Meiners, W. and Diatlov, A., Selective Laser Melting. *Laser Technik Journal*, 9(2), pp.33-38. (2012).
9. Sames, W.J., List, F.A., Pannala, S., Dehoff, R.R. and Babu, S.S., "The metallurgy and processing science of metal additive manufacturing," *International Materials Reviews*, 61(5), pp.315-360. (2016).
10. VDI-Guideline 3404 (2009) Additive Fabrication-Rapid Technologies (Rapid Prototyping) – Fundamentals, Terms and Definitions, Quality Parameter, Supply Agreements. (2014).
11. Gradl, P., "Rapid Fabrication Techniques for Liquid Rocket Channel Wall Nozzles," AIAA-2016-4771, 52nd AIAA/SAE/ASEE Joint Propulsion Conference, July 27, 2016. Salt Lake City, UT.
12. Syed, W.U.H., Pinkerton, A.J. and Li, L., "A comparative study of wire feeding and powder feeding in direct diode laser deposition for rapid prototyping," *Applied Surface Science*, 247(1), pp.268-276 (2005).
13. Honore, M., "Structural strengthening of Rocket Nozzle Extensions by Means of Laser Metal Depositioning," In Support of Volvo Channel Wall Nozzle. Force Technology. MTI Mtg Laserfusing Presentation. 1 February, 2013.
14. Gradl, P.R., Reynolds, D.C. and Walker, B.H., National Aeronautics and Space Administration (NASA), 2017. Freeform deposition method for coolant channel closeout. U.S. Patent 9,835,114. Issued December 5, 2017
15. Gradl, P., Greene, S., Brandsmeier, W., Johnston, I., "Channel Wall Nozzle Manufacturing and Hot-Fire Testing using a Laser Wire Direct Closeout Technique for Liquid Rocket Engines," 54th AIAA/SAE/ASEE Joint Propulsion Conference, AIAA Propulsion and Energy Forum, (AIAA-2018). July 9-12, 2018. Cincinnati, OH.
16. Colegrove, P. and Williams, S., "High deposition rate high quality metal additive manufacture using wire+ arc technology," Cranfield University. (2012)
17. Xiong, Jun, et al., "Fabrication of Inclined Thin-walled Parts in Multi-layer Single-pass GMAW-based Additive Manufacturing with Flat Position Deposition," *Journal of Materials Processing Technology* 240: 397-403. (2016).
18. Ruan, J., Sparks, T. E., Fan, Z., Stroble, J. K., Panackal, A., Liou, F., (2006) "A review of layer based manufacturing processes for metals," *17th Solid Freeform Fabrication Symposium, Austin (USA)* (pp. 233-245).
19. Gradl, P.R., Brandsmeier, W. Alberts, D., Walker, B., Schneider, J.A., "Manufacturing Process Developments for Large Scale Regeneratively-cooled Channel Wall Rocket Nozzles," 63rd JANNAF Propulsion Meeting/9th Liquid Propulsion Subcommittee, December 5-9, 2016. Phoenix, AZ.
20. Scheck, C., Jones, N., Farina, S., George, C. and Melendez, M., "Technical Overview of Additive Manufacturing," Naval Surface Warfare Center, Carderock Division. NSWCDD-61-TR-2014/16. (April 2014).
21. Buzzell, J., and Bullard, B., "100 lbf LOX-Propane Nanolaunch Thruster Hot-Fire Test Program," ER32 Branch, NASA MSFC, MSFC Internal Presentation, 11/14/2013.
22. Barnett, G.L., and Bullard, D.B., "Test Summary Report for Test Program PD114, 28 Element Subscale SLM Injector Testing," NASA Marshall Space Flight Center, December 13, 2013.
23. Barnett, G.L., and Bullard, D.B., "Test Summary Report for Test Program PE040, 40 Element Subscale 3-D Printed Injector Testing," NASA Marshall Space Flight Center, January 2015.
24. Barnett, G. L., and Bullard, D. B., "Summary of Liquid Oxygen/Hydrogen, Direct Metal Laser Sintering Injector Testing and Evaluation Effort at Marshall Space Flight Center," 62nd JANNAF Propulsion Meeting and Joint Meeting of the 10th Modeling & Simulation Subcommittee (MSS) / 8th Liquid Propulsion Subcommittee (LPS) / 7th Spacecraft Propulsion Subcommittee (SPS), Nashville, TN, June 1-5, 2015.
25. Bullard, D.B., Rice, D.C., Nelson, G.M., Case, N.L., Rucker, M., Wall, T.R., and Hulka, J.R., "Design, Fabrication and Hot-Fire Test of an Additively Manufactured Liquid Oxygen/Hydrogen 35-klbf Swirl Coaxial Element Injector," Joint Meeting of the Programmatic and Industrial Base (PIB) / 11th Modeling & Simulation Subcommittee (MSS) / 9th Liquid Propulsion Subcommittee (LPS) / 8th Spacecraft Propulsion Subcommittee (SPS), Phoenix, AZ, December 5-9, 2016.
26. Elam Greene, S., "Test Summary Report for Test Program PF037, 4000 lbf LOX-CH4 Regen Cooled Thruster," NASA Marshall Space Flight Center, September 8, 2016.
27. Elam Greene, S., "Test Summary Report for Test Program PC020B, Acoustic Model 4-Thruster System Testing," NASA Marshall Space Flight Center, Test Report TR RT10-13-01, April 8, 2013.
28. Elam Greene, S., "Test Summary Report for Test Program PC020C, Acoustic Model Spare Thruster Testing," NASA Marshall Space Flight Center, Test Report TR RT10-13-02, June 14, 2013.

References



29. Elam Greene, S., and Wood, J., "Test Summary Report for Test Program PH127, Methane Engine Testing for 1K lbf (MET1)," NASA Marshall Space Flight Center, October 4, 2017.
30. Buzzell, J., "Test Summary Report for Test Program PG056, LOX-Methane GG Injector & Workhorse Chamber Assembly," ER36 Branch, NASA MSFC, Unreleased MSFC Test Report. (2017).
31. Protz, C., Bowman, R., Cooper, K., Fikes, J., Taminger, K., Wright, B., "Additive Manufacturing of Low Cost Upper Stage Propulsion Components," Joint Army-Navy-NASA-Air Force (JANNAF) Liquid Propulsion Subcommittee (LPS) Advanced Materials Panel (AMP) Additive Manufacturing for Propulsion Applications Technical Interchange Meeting (TIM); 3-5 Sept. (2014.)
32. Carter, R. W., Ellis, D.L., Locci, I.E., Evans, L.J., Lerch, B., Jones, Z.C., Cooper, K. G., "Evaluation of GRCop-84 Produced Using Selective Laser Melting," 62nd JANNAF Propulsion Meeting and Joint Meeting of the 10th Modeling & Simulation Subcommittee (MSS) / 8th Liquid Propulsion Subcommittee (LPS) / 7th Spacecraft Propulsion Subcommittee (SPS), Nashville, TN, June 1-5, 2015.
33. Garcia, C.P., Gradl, P.R., Protz, C.S., Wood, J., and Greene, S. E., "Characterizing Performance of Additively Manufacturing Regenerative Cooled Combustion Chambers through Hot Fire Testing," 65th JANNAF Propulsion Meeting/10th Liquid Propulsion Subcommittee, May 21-24, 2018. Long Beach, CA.
34. Greene, S.E., "Methane Engine Thrust Assembly for 4K lbf with a 4 Inch Diameter Chamber (META4X4)," Test Summary Report, Test Program PI051. NASA MSFC, May 8, 2018.
35. Gradl, P., Greene, S.E., Valentine, P., Crisanti, M., "Subscale Carbon-Carbon Nozzle Extension Development and Hot Fire Testing in Support of Upper Stage Liquid Rocket Engines", JANNAF 63rd Propulsion Meeting/9th Liquid Propulsion Subcommittee Meeting, December 5-9, 2016. Phoenix, AZ.
36. Gradl, P.R., and Valentine, P.G., "Carbon-Carbon Nozzle Extension Development in Support of In-space and Upper-Stage Liquid Rocket Engines," AIAA 2017-5064, 53rd AIAA/SAE/ASEE Joint Propulsion Conference, AIAA Propulsion and Energy Forum, Atlanta, GA. (2017).
37. Greene, S.E., and Gradl, P., "C-CAT Nozzle Material Testing," NASA Internal Test Summary Report, Test Program PG034 & PG053. NASA MSFC, January 13, 2017.
38. Gradl, P. and Greene, S.E., "Channel Wall Nozzle Testing," Test Summary Report, Test Program PH034. NASA MSFC, February 12, 2018.
39. Greene, S.E., and Gradl, P., "Subscale Nozzle Testing for Orbital ATK," NASA Test Summary Report , Test Program PH171. NASA MSFC, January 10, 2018.
40. Gradl, P.R., Protz, C., Greene, S.E., Ellis, D., Lerch, B., and Locci, I., "Development and Hot-fire Testing of Additively Manufactured Copper Combustion Chambers for Liquid Rocket Engine Applications," 53rd AIAA/SAE/ASEE Joint Propulsion Conference, AIAA Propulsion and Energy Forum, (AIAA 2017-4670)
41. Gradl, P., Protz, C., Greene, S.E., Garcia, C., Brandsmeier, W., Medina. C., Goodman, D., Baker, K., Barnett, G., "Design, Development and Hotfire Testing of Monolithic Copper and Bimetallic Additively Manufactured (AM) Combustion Chambers for LOX/Methane and LOX/Hydrogen Applications," 63rd JANNAF Propulsion Meeting/9th Liquid Propulsion Subcommittee, December 5-9, 2016. Phoenix, AZ.
42. Gradl, P.R., Brandsmeier, W. Alberts, D., Walker, B., Schneider, J.A., "Manufacturing Process Developments for Large Scale Regeneratively-cooled Channel Wall Rocket Nozzles," 63rd JANNAF Propulsion Meeting/9th Liquid Propulsion Subcommittee, December 5-9, 2016. Phoenix, AZ.
43. C. S. Protz, W. C. Brandsmeier, K. G. Cooper, J. Fikes, P. R. Gradl, Z. C. Jones, and C. R. Medina, D. L. Ellis, K. M. Taminger. "Thrust Chamber Assembly using GRCop-84 Bimetallic Additive Manufacturing and Integrated Nozzle Coolant Ring Supporting Low Cost Upper Stage Propulsion," 65th JANNAF Propulsion Meeting/10th Liquid Propulsion Subcommittee, May 21-24, 2018. Long Beach, CA.
44. Gradl, P.R., Greene, S. E., Brandsmeier, W., Johnston, M.I., "Hot-Fire Testing and Large-Scale Deposition Manufacturing Development Supporting Liquid Rocket Engine Channel Wall Nozzle Fabrication," 65th JANNAF Propulsion Meeting/10th Liquid Propulsion Subcommittee, May 21-24, 2018. Long Beach, CA.
45. Fikes, J., Vickers, J., Gradl, P., Protz, C. (n.d.), "Rapid Analysis and Manufacturing Propulsion Technology (RAMPT)," Retrieved April 24, 2018, from <https://gameon.nasa.gov/projects/rapid-analysis-and-manufacturing-propulsion-technology-ramp/>
46. Sporie, S., Schneider, J.A., Osborne, R., "Using hybrid manufacturing in the freeform fabrication of bi-metallic components". IAC-17-C2.9.7.x41117. 68th International Astronautical Congress (IAC), Adelaide, Australia, 25-29 September 2017
47. Ellis, D.L., 2003. Conductivity of GRCop-42 Alloy Enhanced, NASA Glenn Research Center Research & Technology, p.16.