



US010174780B2

(12) **United States Patent**
Hofmann et al.

(10) **Patent No.:** **US 10,174,780 B2**

(45) **Date of Patent:** **Jan. 8, 2019**

(54) **SYSTEMS AND METHODS FOR STRUCTURALLY INTERRELATING COMPONENTS USING INSERTS MADE FROM METALLIC GLASS-BASED MATERIALS**

(58) **Field of Classification Search**
CPC F16B 35/041; F16B 33/02; F16B 33/006; B29L 2009/003; B29K 2063/00
See application file for complete search history.

(71) Applicant: **California Institute of Technology**,
Pasadena, CA (US)

(56) **References Cited**

U.S. PATENT DOCUMENTS

(72) Inventors: **Douglas C. Hofmann**, Altadena, CA (US); **Samuel C. Bradford**, Pasadena, CA (US)

3,435,512 A * 4/1969 MacRobbie B21F 15/00 29/517

3,529,457 A 9/1970 Bowers
3,682,606 A 8/1972 Anderson et al.

(Continued)

(73) Assignee: **California Institute of Technology**,
Pasadena, CA (US)

FOREIGN PATENT DOCUMENTS

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 333 days.

CN 101709773 A 5/2010
CN 102563006 A 7/2012

(Continued)

(21) Appl. No.: **15/067,561**

OTHER PUBLICATIONS

(22) Filed: **Mar. 11, 2016**

US 9,285,027, 03/2016, Hofmann et al. (withdrawn)

(Continued)

(65) **Prior Publication Data**

US 2016/0265576 A1 Sep. 15, 2016

Related U.S. Application Data

Primary Examiner — John C Hong

(74) *Attorney, Agent, or Firm* — KPPB LLP

(60) Provisional application No. 62/131,467, filed on Mar. 11, 2015.

(57) **ABSTRACT**

Systems and methods in accordance with embodiments of the invention operate to structurally interrelate two components using inserts made from metallic glass-based materials. In one embodiment, a method of structurally interrelating two components includes: forming an insert from a metallic glass-based composition; where the formed insert includes a metallic glass-based material; affixing the insert to a first component; and structurally interrelating the second component to the first component using the insert.

(51) **Int. Cl.**

F16B 35/04 (2006.01)

F16B 33/00 (2006.01)

B29C 65/48 (2006.01)


F16B 33/02 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **F16B 35/041** (2013.01); **F16B 33/006** (2013.01); **F16B 33/02** (2013.01); **B29K 2063/00** (2013.01); **B29L 2009/003** (2013.01)

14 Claims, 8 Drawing Sheets



- (51) **Int. Cl.**
B29K 63/00 (2006.01)
B29L 9/00 (2006.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,986,412	A	10/1976	Farley et al.
RE29,989	E	5/1979	Polk
4,173,393	A	11/1979	Maurer
4,202,404	A	5/1980	Carlson
4,711,795	A	12/1987	Takeuchi et al.
4,749,625	A	6/1988	Obayashi et al.
4,810,314	A	3/1989	Henderson et al.
4,812,150	A	3/1989	Scott
4,823,638	A	4/1989	Ishikawa
4,851,296	A	7/1989	Tenhover et al.
4,883,632	A	11/1989	Goto et al.
5,168,918	A	12/1992	Okuda et al.
5,288,344	A	2/1994	Peker et al.
5,310,432	A	5/1994	Yamanaka et al.
5,485,761	A	1/1996	Rouverol
5,509,978	A	4/1996	Masumoto et al.
5,636,550	A	6/1997	Deane
5,722,295	A	3/1998	Sakai et al.
5,746,844	A	5/1998	Sterett et al.
5,772,803	A	6/1998	Peker et al.
5,866,272	A	2/1999	Westre et al.
5,896,642	A	4/1999	Peker et al.
6,162,130	A	12/2000	Masumoto et al.
6,273,322	B1	8/2001	Yamamoto et al.
6,620,264	B2	9/2003	Kundig et al.
6,652,679	B1	11/2003	Inoue et al.
6,771,490	B2	8/2004	Peker et al.
6,843,496	B2	1/2005	Peker et al.
6,887,586	B2	5/2005	Peker et al.
7,052,561	B2	5/2006	Lu et al.
7,073,560	B2	7/2006	Kang et al.
7,075,209	B2	7/2006	Howell et al.
7,357,731	B2	4/2008	Johnson et al.
7,360,419	B2	4/2008	French et al.
7,497,981	B2	3/2009	Graham et al.
7,500,987	B2	3/2009	Bassler et al.
7,552,664	B2	6/2009	Bulatowicz
7,862,323	B2	1/2011	Micarelli et al.
7,883,592	B2	2/2011	Hofmann et al.
7,896,982	B2	3/2011	Johnson et al.
7,955,713	B2	6/2011	Roebroeks et al.
8,042,770	B2	10/2011	Martin et al.
8,400,721	B2	3/2013	Bertele et al.
8,418,366	B2	4/2013	Wang et al.
8,485,245	B1	7/2013	Prest et al.
8,596,106	B2	12/2013	Tang et al.
8,613,815	B2	12/2013	Johnson
8,789,629	B2	7/2014	Parness et al.
8,986,469	B2	3/2015	Khalifa et al.
9,057,120	B2	6/2015	Pham et al.
9,328,813	B2	5/2016	Hofmann et al.
9,610,650	B2	4/2017	Hofmann et al.
9,783,877	B2	10/2017	Hofmann et al.
9,791,032	B2	10/2017	Hofmann et al.
9,868,150	B2	1/2018	Hofmann et al.
2002/0053375	A1	5/2002	Hays et al.
2002/0100573	A1	8/2002	Inoue et al.
2002/0184766	A1	12/2002	Kobayashi et al.
2003/0062811	A1	4/2003	Peker et al.
2004/0103536	A1	6/2004	Kobayashi et al.
2004/0103537	A1	6/2004	Kobayashi et al.
2004/0154701	A1	8/2004	Lu et al.
2005/0034792	A1	2/2005	Lu et al.
2005/0127139	A1	6/2005	Slattery et al.
2006/0156785	A1	7/2006	Mankame et al.
2007/0034304	A1	2/2007	Inoue et al.
2007/0226979	A1	10/2007	Paton et al.
2008/0085368	A1	4/2008	Gauthier et al.
2008/0121316	A1	5/2008	Duan et al.
2009/0011846	A1*	1/2009	Scott

A63B 69/3608
473/201

2009/0114317	A1	5/2009	Collier et al.
2009/0194205	A1	8/2009	Loffler et al.
2009/0288741	A1	11/2009	Zhang et al.
2010/0313704	A1	12/2010	Wang et al.
2011/0048587	A1	3/2011	Vecchio et al.
2011/0154928	A1	6/2011	Ishikawa
2011/0302783	A1	12/2011	Nagata et al.
2012/0067100	A1	3/2012	Stefansson et al.
2012/0073710	A1	3/2012	Kim et al.
2012/0077052	A1	3/2012	Demetriou et al.
2013/0062134	A1	3/2013	Parness et al.
2013/0112321	A1	5/2013	Poole et al.
2013/0133787	A1	5/2013	Kim
2013/0139964	A1	6/2013	Hofmann et al.
2013/0309121	A1	11/2013	Prest et al.
2013/0333814	A1	12/2013	Fleury et al.
2014/0004352	A1	1/2014	McCrea et al.
2014/0020794	A1	1/2014	Hofmann et al.
2014/0030948	A1	1/2014	Kim et al.
2014/0045680	A1	2/2014	Nakayama et al.
2014/0083640	A1	3/2014	Waniuk et al.
2014/0093674	A1	4/2014	Hofmann et al.
2014/0141164	A1	5/2014	Hofmann et al.
2014/0202595	A1	7/2014	Hofmann et al.
2014/0213384	A1	7/2014	Johnson et al.
2014/0224050	A1	8/2014	Hofmann et al.
2014/0227125	A1	8/2014	Hofmann et al.
2014/0246809	A1	9/2014	Hofmann
2014/0293384	A1	10/2014	O'keeffe et al.
2014/0312098	A1	10/2014	Hofmann et al.
2014/0342179	A1	11/2014	Hofmann et al.
2014/0348571	A1	11/2014	Prest et al.
2015/0047463	A1	2/2015	Hofmann et al.
2015/0068648	A1	3/2015	Schroers et al.
2015/0075744	A1	3/2015	Hofmann et al.
2015/0289605	A1	10/2015	Prest et al.
2015/0314566	A1	11/2015	Mattlin et al.
2016/0178047	A1	6/2016	Kennett et al.
2016/0186850	A1	6/2016	Hofmann et al.
2016/0258522	A1	9/2016	Hofmann et al.
2016/0263937	A1	9/2016	Parness et al.
2016/0299183	A1	11/2016	Lee
2016/0361897	A1	12/2016	Hofmann et al.
2017/0121799	A1	5/2017	Hofmann et al.
2017/0137955	A1	5/2017	Hofmann et al.
2018/0119259	A1	5/2018	Hofmann et al.

FOREIGN PATENT DOCUMENTS

CN	103153502	A	6/2013
DE	102010062089	A1	5/2012
EP	0127366	A1	5/1984
EP	1063312	A1	12/2000
EP	1138798	A1	10/2001
EP	1696153	A1	8/2006
EP	1404884	B1	7/2007
EP	1944138	A2	7/2008
JP	61276762	A	12/1986
JP	2002045960	A	2/2002
JP	2004353053	A	12/2004
JP	2007040517	A	2/2007
JP	2007040518	A	2/2007
JP	2007247037	A	9/2007
JP	2008264865	A	11/2008
JP	2013238278	A	11/2013
WO	2007038882	A1	4/2007
WO	2008156889	A2	12/2008
WO	2011159596	A1	12/2011
WO	2012031022	A2	3/2012
WO	2012147559	A1	11/2012
WO	2013138710	A1	9/2013
WO	2013141878	A1	9/2013
WO	2013141882	A1	9/2013
WO	2014004704	A1	1/2014
WO	2014012113	A2	1/2014
WO	2014058498	A3	4/2014

(56) **References Cited**

FOREIGN PATENT DOCUMENTS

WO 2015042437 A1 3/2015
 WO 2015156797 A1 10/2015

OTHER PUBLICATIONS

- Li et al., "Wear behavior of bulk $Zr_{41}Ti_{14}Cu_{12.5}Ni_{10}Be_{22.5}$ metallic glasses", *J. Mater. Res.*, Aug. 2002, vol. 17, No. 8, pp. 1877-1880.
- Lillo et al., "Microstructure, Processing, Performance Relationships for High Temperature Coatings", U.S. Department of Energy, Office of Fossil Energy, under DOE Idaho Operations Office, Contract DE-AC07-05ID14517; 22nd Annual Conference on Fossil Energy Materials, Pittsburgh, U.S., 8 pgs., Jul. 1, 2008.
- List, A. et al., "Impact Conditions for Cold Spraying of Hard Metallic Glasses", *Journal of Thermal Spray Technology*, Jun. 1, 2012, vol. 21, No. 3-4, pp. 531-540.
- Liu, X. Q., "Microstructure and properties of Fe-based amorphous metallic coating produced by high velocity axial plasma spraying", *Science Direct, Journal of Alloys and Compounds*, Apr. 23, 2009, vol. 484, pp. 300-307.
- Liu et al., "Influence of Heat Treatment on Microstructure and Sliding Wear of Thermally Sprayed Fe-Based Metallic Glass coatings", *Tribol. Lett.*, Mar. 4, 2012, vol. 46, pp. 131-138.
- Liu et al., "Metallic glass coating on metals plate by adjusted explosive welding technique", *Applied Surface Science*, Jul. 16, 2009, vol. 255, pp. 9343-9347.
- Liu et al., "Sliding Tribological Characteristics of a Zr-based Bulk Metallic Glass Near the Glass Transition Temperature", *Tribol. Lett.*, Jan. 29, 2009, vol. 33, pp. 205-210.
- Liu et al., "Wear behavior of a Zr-based bulk metallic glass and its composites", *Journal of Alloys and Compounds*, May 5, 2010, vol. 503, pp. 138-144.
- Lupoi, R. et al., "Deposition of metallic coatings on polymer surfaces using cold spray", *Science Direct, Surface & Coatings Technology*, Sep. 6, 2010, vol. 205, pp. 2167-2173.
- Ma et al., "Wear resistance of Zr-based bulk metallic glass applied in bearing rollers", *Materials Science and Engineering*, May 4, 2004, vol. A386, pp. 326-330.
- Maddala et al., "Effect of notch toughness and hardness on sliding wear of $Cu_{50}Hf_{41.5}Al_{18.5}$ bulk metallic glass", *Scripta Materialia*, Jul. 6, 2011, vol. 65, pp. 630-633.
- Narayan et al., "On the hardness and elastic modulus of bulk metallic glass matrix composites", *Scripta Materialia*, Jun. 9, 2010, vol. 63, Issue 7, pp. 768-771.
- Ni et al., "High performance amorphous steel coating prepared by HVOF thermal spraying", *Journal of Alloys and Compounds*, Jan. 7, 2009, vol. 467, pp. 163-167, Nov. 29, 2007.
- Nishiyama, N. et al., "Recent progress of bulk metallic glasses for strain-sensing devices", *Materials Science and Engineering: A*, vols. 449-451, Mar. 25, 2007, 79-83.
- Oh et al., "Microstructure and tensile properties of high-strength high-ductility Ti-based amorphous matrix composites containing ductile dendrites", *Acta Materialia*, Sep. 23, 2011, vol. 59, Issue 19, pp. 7277-7286.
- Parlar et al., "Sliding tribological characteristics of Zr-based bulk metallic glass", *Intermetallics*, Jan. 2008, vol. 16, pp. 34-41.
- Pauly et al., "Modeling deformation behavior of Cu—Zr—Al bulk metallic glass matrix composites", *Applied Physics Letters*, Sep. 2009, vol. 95, pp. 101906-1-101906-3.
- Pauly et al., "Transformation-mediated ductility in CuZr-based bulk metallic glasses", *Nature Materials*, May 16, 2010, vol. 9, Issue 6, pp. 473-477.
- Ponnambalam, et al., "Fe-based bulk metallic glasses with diameter thickness larger than one centimeter", *J Mater Res*, Feb. 17, 2004, vol. 19; pp. 1320-1323.
- Porter et al., "Incorporation of Amorphous Metals into MEMS for High Performance and Reliability", Rockwell Scientific Company, Final Report, Nov. 1, 2003, 41 pgs.
- Prakash et al., "Sliding wear behavior of some Fe-, Co-and Ni-based metallic glasses during rubbing against bearing steel", *Tribology Letters*, May 1, 2000, vol. 8, pp. 153-160.
- Qiao et al., "Development of plastic Ti-based bulk-metallic-glass-matrix composites by controlling the microstructures", *Materials Science and Engineering: A*, Aug. 20, 2010, vol. 527, Issues 29-30, pp. 7752-7756.
- Ramamurty et al., "Hardness and plastic deformation in a bulk metallic glass", *Acta Materialia*, Feb. 2005, vol. 53, pp. 705-717.
- Revesz et al., "Microstructure and morphology of Cu—Zr—Ti coatings produced by thermal spray and treated by surface mechanical attrition", *ScienceDirect, Journal of Alloys and Compounds*, Jul. 14, 2011, vol. 509S, pp. S482-S485, Nov. 4, 2010.
- Rigney et al., "The Evolution of Tribomaterial During Sliding: A Brief Introduction", *Tribol. Lett.*, Jul. 1, 2010, vol. 39, pp. 3-7.
- Roberts et al., "Cryogenic Charpy impact testing of metallic glass matrix composites", *Scripta Materialia*, Nov. 11, 2011, 4 pgs.
- Schuh et al., "A survey of instrumented indentation studies on metallic glasses", *J. Mater. Res.*, Jan. 2004, vol. 19, No. 1, pp. 46-57.
- Segu et al., "Dry Sliding Tribological Properties of Fe-Based Bulk Metallic Glass", *Tribol. Lett.*, Apr. 28, 2012, vol. 47, pp. 131-138.
- Shen et al., "Exceptionally high glass-forming ability of an FeCoCrMoCBy alloy", *Applied Physics*, Apr. 5, 2005, vol. 86, pp. 151907-1-151907-3.
- Singer et al., "Wear behavior of triode-sputtered MoS₂ coatings in dry sliding contact with steel and ceramics", *Wear*, Jul. 1996, vol. 195, Issues 1-2, pp. 7-20.
- Sinmazcelik et al., "A review: Fibre metal laminates, background, bonding types and applied test methods", *Materials and Design*, vol. 32, Issue 7, 3671, Mar. 4, 2011, pp. 3671-3685.
- Song et al., "Strategy for pinpointing the formation of B2 CuZr in metastable CuZr-based shape memory alloys", *Acta Materialia*, Aug. 6, 2011, vol. 59, pp. 6620-6630.
- Sundaram et al., "Mesoscale Folding, Instability, and Disruption of Laminar Flow in Metal Surfaces", *Physical Review Letters*, Sep. 7, 2012, vol. 109, pp. 106001-1-106001-5.
- Szuecs et al., "Mechanical Properties of $Zr_{56.2}Ti_{13.8}Nb_{5.0}Cu_{6.9}Ni_{5.6}Be_{12.5}$ Ductile Phase Reinforced Bulk Metallic Glass Composite", *Acta Materialia*, Feb. 2, 2001, vol. 49, Issue 9, pp. 1507-1513.
- Tam et al., "Abrasion resistance of Cu based bulk metallic glasses", *Journal of Non-Crystalline Solids*, Oct. 18, 2004, vol. 347, pp. 268-272.
- Tam et al., "Abrasive wear of $Cu_{60}Zr_{30}Ti_{10}$ bulk metallic glass", *Materials Science and Engineering*, Apr. 1, 2004, vol. A384 pp. 138-142.
- Tan et al., "Synthesis of La-based in-situ bulk metallic glass matrix composite", *Intermetallics*, Nov. 2002, vol. 10, Issues 11-12, pp. 1203-1205.
- Tao et al., "Effect of rotational sliding velocity on surface friction and wear behavior in Zr-based bulk metallic glass", *Journal of Alloys and Compounds*, Mar. 4, 2010, vol. 492, pp. L36-L39.
- Tao et al., "Influence of isothermal annealing on the micro-hardness and friction property in CuZrAl bulk metallic glass", *Advanced Materials Research*, Jan. 1, 2011, vols. 146-147, pp. 615-618.
- Tobler et al., "Cryogenic Tensile, Fatigue, and Fracture Parameters for a Solution-Annealed 18 Percent Nickel Maraging Steel", *Journal of Engineering Materials and Technology*, Apr. 1, 1978, vol. 100, pp. 189-194.
- Wagner, "Mechanical Behavior of 18 Ni 200 Grade Maraging Steel at Cryogenic Temperatures", *J Aircraft*, Nov. 1, 1986, vol. 23, No. 10, pp. 744-749.
- Wang et al., "Progress in studying the fatigue behavior of Zr-based bulk-metallic glasses and their composites", *Intermetallics*, Mar. 6, 2009, vol. 17, pp. 579-590.
- Wikipedia, "Harmonic Drive", printed Feb. 20, 2014, 4 pgs.
- Wu et al., "Bulk Metallic Glass Composites with Transformation-Mediated Work-Hardening and Ductility", *Adv. Mater.*, Apr. 26, 2010, vol. 22, pp. 2770-2773.
- Wu et al., "Dry Sliding tribological behavior of Zr-based bulk metallic glass", *Transactions of Nonferrous Metals Society of China*, Jan. 16, 2012, vol. 22, Issue 3, pp. 585-589.

(56)

References Cited

OTHER PUBLICATIONS

- Wu et al., "Effects of environment on the sliding tribological behaviors of Zr-based bulk metallic glass", *Intermetallics*, Jan. 27, 2012, vol. 25, 115-125.
- Wu et al., "Formation of Cu—Zr—Al bulk metallic glass composites with improved tensile properties", *Acta Materialia* 59, Feb. 19, 2011, pp. 2928-2936.
- Wu et al., "Use of rule of mixtures and metal vol. fraction for mechanical property predictions of fibre-reinforced aluminum laminates", *Journal of Materials Science*, vol. 29, issue 17, 4583, Jan. 1994, 9 pages.
- Yin, Enhuai et al., "Microstructure and mechanical properties of a spray-formed Ti-based metallic glass former alloy", *Journal of Alloys and Compounds*, Jan. 25, 2012, vol. 512, pp. 241-245.
- Zachrisson et al., "Effect of Processing on Charpy impact toughness of metallic glass matrix composites", *Journal of Materials Research*, vol. 26, No. 10, May 28, 2011; abstract; p. 1263, paragraphs 2-3; p. 1265, col. 2, paragraph 2.
- Zhang et al., "Abrasive and corrosive behaviors of Cu—Zr—Al—Ag—Nb bulk metallic glasses", *Journal of Physics: Conference Series*, 2009, vol. 144, pp. 1-4.
- Zhang et al., "Robust hydrophobic Fe-based amorphous coating by thermal spraying", *Appl. Phys. Lett.*, Sep. 20, 2012, vol. 101, pp. 121603-1-121603-4.
- Zhang et al., "Wear behavior of a series of Zr-based bulk metallic glasses", *Materials Science and Engineering*, Feb. 25, 2008, vol. A475, pp. 124-127.
- Zhou et al., "Microstructure and Electrochemical Behavior of Fe-Based Amorphous Metallic Coatings Fabricated by Atmospheric Plasma Spraying", *Journal of Thermal Spray Technology*, Jan. 2011, vol. 20, No. 1-2, pp. 344-350, Aug. 17, 2010.
- Zhu et al., "Ta-particulate reinforced Zr-based bulk metallic glass matrix composite with tensile plasticity", *Scripta Materialia*, Mar. 2010, vol. 62, Issue 5, pp. 278-281.
- Zhuo, Longchao, "Spray formed Al-based amorphous matrix nanocomposite plate", *ScienceDirect, Journal of Alloys and Compounds*, Mar. 1, 2011, vol. 509, pp. L169-L173.
- International Preliminary Report on Patentability for International Application PCT/US2013/047950, dated Dec. 31, 2014, dated Jan. 8, 2015, 7 Pgs.
- International Preliminary Report on Patentability for International Application PCT/US2013/050614, dated Jan. 20, 2015, dated Jan. 29, 2015, 9 Pgs.
- International Preliminary Report on Patentability for International Application PCT/US2014/033510, dated Oct. 12, 2016, dated Oct. 20, 2016, 9 Pgs.
- International Preliminary Report on Patentability for International Application PCT/US2014/056615, dated Mar. 22, 2016, dated Mar. 31, 2016, 11 Pgs.
- International Search Report and Written Opinion for International Application No. PCT/US2013/050614, Completed May 7, 2014, dated May 7, 2014, 12 pgs.
- International Search Report and Written Opinion for International Application PCT/US2013/047950, completed Oct. 8, 2013, dated Oct. 10, 2013, 9 pgs.
- International Search Report and Written Opinion for International Application PCT/US2014/033510, completed Jan. 8, 2015, dated Jan. 8, 2015, 11 Pgs.
- International Search Report and Written Opinion for International Application PCT/US2014/056615, completed Dec. 29, 2014, dated Dec. 30, 2014, 13 Pgs.
- "Corrosion of Titanium and Titanium Alloys", *Total Materia.*, printed Feb. 16, 2016 from <http://www.totalmateria.com/Article24.htm>, published Sep. 2001, 4 pgs.
- "Gear", *Dictionary.com*. Accessed Aug. 30, 2016.
- "Group 4 element", *Wikipedia*. https://en.wikipedia.org/wiki/Group_4_element. Published Jun. 11, 2010. Accessed Aug. 24, 2016.
- "Harmonic Drive AG", website, printed from <http://harmoncdrive.aero/?idcat=471>, Feb. 20, 2014, 2 pgs.
- "Harmonic Drive Polymer GmbH", printed Feb. 20, 2014 from <http://www.harmonicdrive.de/English/the-company/subsidiaries/harmonic-drive-polymer-gmbh.html>, 1 pg.
- "Introduction to Thermal Spray Processing", *ASM International, Handbook of Thermal Spray Technology (#06994G)*, 2004, 12 pgs.
- Abdeljawad et al., "Continuum Modeling of Bulk Metallic Glasses and Composites", *Physical Review Letters*, vol. 105, 205503, Sep. 17, 2010, pp. 125503-1-125503-4.
- Abrosimova et al., "Crystalline layer on the surface of Zr-based bulk metallic glasses", *Journal of Non-Crystalline Solids*, Mar. 6, 2001, vol. 288, pp. 121-126.
- An et al., "Synthesis of single-component metallic glasses by thermal spray of nanodroplets on amorphous substrates", *Applied Physics Letters*, Jan. 26, 2012, vol. 100, pp. 041909-1-041909-4.
- Anstis et al., "A Critical Evaluation of Indentation Techniques for Measuring Fracture Toughness: I, Direct Crack Measurements", *Journal of American Ceramic Society*, Sep. 1, 1981, vol. 64, No. 8, pp. 533-538.
- Ashby et al., "Metallic glasses of structural materials", *Scripta Materialia*, Feb. 2006, vol. 54, pp. 321-326.
- Bakkal, "Sliding tribological characteristics of Zr-based bulk metallic glass under lubricated conditions", *Intermetallics*, Mar. 19, 2010, vol. 18, pp. 1251-1253.
- Bardt et al., "Micromolding three-dimensional amorphous metal structures", *J. Mater. Res.*, Feb. 2007, vol. 22, No. 2, pp. 339-343.
- Basu et al., "Laser surface coating of Fe—Cr—Mo—Y—B—C bulk metallic glass composition on AISI 4140 steel", *Surface & Coatings Technology*, Mar. 15, 2008, vol. 202, pp. 2623-2631.
- Boopathy et al., "Near-threshold fatigue crack growth in bulk metallic glass composites", *J. Mater. Res.*, vol. 24, No. 12, pp. 3611-3619, Dec. 2009.
- Branagan et al., "Wear Resistant Amorphous and Nanocomposite Steel Coatings", *Met. Mater. Trans. A*, Apr. 26, 2001, 32A; Idaho National Engineering and Environmental Laboratory, DOI 10.1007/s11661-001-0051-8, 15 pgs., Oct. 1, 2001.
- Cadney et al., "Cold gas dynamic spraying as a method for reforming and joining materials", *Science Direct, Surface & Coatings Technology*, Mar. 15, 2008, vol. 202, pp. 2801-2806.
- Calin et al., "Improved mechanical behavior of Cu—Ti-based bulk metallic glass by in situ formation of nanoscale precipitates", *Scripta Materialia*, Mar. 17, 2003, vol. 48, pp. 653-658.
- Chen et al., "Elastic Constants, Hardness and Their Implications to Flow Properties of Metallic Glasses", *Journal of Non-crystalline Solids*, Sep. 1, 1975, vol. 18, pp. 157-171.
- Chen et al., "Formation of Micro-Scale Precision Flexures via Molding of Metallic Glass", *Proceeding of the Annual Meeting of the ASPE*, Monterey, CA, 2006, pp. 283-286.
- Chen et al., "Influence of laser surface melting on glass formation and tribological behaviors of Zr₅₅Al₁₀Ni₅Cu₃₀ alloy", *J. Mater. Res.* Oct. 28, 2011, vol. 26, No. 20, pp. 2642-2652.
- Cheng, J. B., "Characterization of mechanical properties of FeCrBSiMn-NbY metallic glass coatings", *J Mater Sci.*, Apr. 16, 2009, vol. 44, pp. 3356-3363.
- Cheng et al., "Correlation of the microstructure and mechanical properties of Zr-based in-situ bulk metallic glass matrix composites", *Intermetallics*, Sep. 24, 2010, vol. 18, Issue 12, pp. 2425-2430.
- Choi et al., "Tribological behavior of the kinetic sprayed Ni₅₉Ti₁₆Zr₂₀Si₂Sn₃", *Journal of Alloys and Compounds*, May 31, 2007, vol. 434-435, pp. 64-67.
- Conner et al., "Shear band spacing under bending of Zr-based metallic glass plates", *Acta Materialia*, Jan. 27, 2004, vol. 52, pp. 2429-2434.
- Conner et al., "Shear bands and cracking of metallic glass plates in bending", *Journal of Applied Physics*, Jul. 15, 2003, vol. 94, No. 2, pp. 904-911.
- Dai et al., "A new centimeter-diameter Cu-based bulk metallic glass", *Scripta Materialia*, Jan. 20, 2006, vol. 54, pp. 1403-1408.
- Davis, "Hardness/Strength Ratio of Metallic Glasses", *Scripta Metallurgica*, Feb. 18, 1975, vol. 9, pp. 431-436.
- De Beer et al., "Surface Folds Make Tears and Chips", *Physics*, Sep. 4, 2012, vol. 100, 3 pgs.

(56)

References Cited

OTHER PUBLICATIONS

- Dislich et al., "Amorphous and Crystalline Dip Coatings Obtained from Organometallic Solutions: Procedures, Chemical Processes and Products", *Metallurgical and Protective Coatings*, Mar. 6, 1981, vol. 77, pp. 129-139.
- Duan et al., "Lightweight Ti-based bulk metallic glasses excluding late transition metals", *Scripta Materialia*, Mar. 2008, vol. 58, pp. 465-468.
- Duan et al., "Tribological properties of $Zr_{41.25}Ti_{13.75}Ni_{10}Cu_{12.5}Be_{22.5}$ bulk metallic glasses under different conditions", *Journal of Alloys and Compounds*, Mar. 2, 2012, 528, pp. 74-78.
- Fan et al., "Metallic glass matrix composite with precipitated ductile reinforcement", *Applied Physics Letters*, Aug. 5, 2002, vol. 81, Issue 6, pp. 1020-1022.
- Fleury et al., "Tribological properties of bulk metallic glasses", *Materials Science and Engineering*, Jul. 2004, vol. A375-377, pp. 276-279.
- Fornell et al., "Enhanced mechanical properties and in vitro corrosion behavior of amorphous and devitrified $Ti_{40}Zr_{10}Cu_{38}Pd_{12}$ metallic glass", *Journal of the Mechanical Behavior of Biomedical Materials*, May 27, 2011, vol. 4, pp. 1709-1717.
- Fu et al., "Sliding behavior of metallic glass Part I. Experimental investigations", *Wear*, Oct. 2001, vol. 250, pp. 409-419.
- Ganesan et al., "Bonding behavior studies of cold sprayed copper coating on the PVC polymer substrate", *Surface & Coatings Technology*, Jul. 10, 2012, vol. 207, pp. 262-269.
- Garrett et al., "Effect of microalloying on the toughness of metallic glasses", *Applied Physics Letter*, Dec. 12, 2012, vol. 101, 241913-1-241913-3.
- Geason Corporation, "Gear Product News", Introducing genesis, the Next Generation in Gear Technology, Apr. 2006, 52 pgs.
- Gloriant, "Microhardness and abrasive wear resistance of metallic glasses and nanostructured composite materials", *Journal of Non-Crystalline Solids*, Feb. 2003, vol. 316, pp. 96-103.
- Greer, "Partially or fully devitrified alloys for mechanical properties", *Materials and Science and Engineering*, May 31, 2001, vol. A304, pp. 68-72.
- Greer et al., "Wear resistance of amorphous alloys and related materials", *International Materials Reviews*, Apr. 1, 2002, vol. 47, No. 2, pp. 87-112.
- Ha et al., "Tensile deformation behavior of two Ti-based amorphous matrix composites containing ductile β dendrites", *Materials Science and Engineering: A*, May 28, 2012, vol. 552, pp. 404-409.
- Hale, "Principles and Techniques for Designing Precision Machines", Ph.D. Thesis, Feb. 1999, 493 pgs.
- Harmon et al., "Anelastic to Plastic Transition in Metallic Glass-Forming Liquids", *Physical Review Letters*, Sep. 28, 2007, vol. 99, 135502-1-135502-4.
- Haruyama et al., "vol. And enthalpy relaxation in $Zr_{55}Cu_{30}Ni_{5}Al_{10}$ bulk metallic glass", *Acta Materialia*, Mar. 2010, vol. 59, pp. 1829-1836.
- Hays, C. C., "Microstructure Controlled Shear Band Pattern Formation and Enhanced Plasticity of Bulk Metallic Glasses Containing in situ Formed Ductile Phase Dendrite Dispersions", *Physical Review Letters*, Mar. 27, 2000, vol. 84, pp. 2901-2904.
- Hejwowski et al., "A comparative study of electrochemical properties of metallic glasses and weld overlay coatings", *Vacuum*, Feb. 2013, vol. 88, pp. 118-123, Feb. 20, 2012.
- Hofmann, "Bulk Metallic Glasses and Their Composites: A Brief History of Diverging Fields", *Journal of Materials*, Jan. 2013, vol. 2013, 7 pgs.
- Hofmann, "Shape Memory Bulk Metallic Glass Composites", *Science*, Sep. 10, 2010, vol. 329, pp. 1294-1295.
- Hofmann, D. C., "Development of tough, low-density titanium-based bulk metallic glass matrix composites with tensile ductility", *PNAS*, Dec. 23, 2008, vol. 105, pp. 20136-20140.
- Hofmann et al., "Designing metallic glass matrix composites with high toughness and tensile ductility", *Nature Letters*, Feb. 28, 2008, vol. 451, pp. 1085-1090.
- Hofmann et al., "Improving Ductility in Nanostructured Materials and Metallic Glasses: Three Laws", *Material Science Forum*, vol. 633-634, 2010, pp. 657-663, published online Nov. 19, 2009.
- Hofmann et al., "Semi-solid Induction Forging of Metallic Glass Matrix Composites", *JOM*, Dec. 2009, vol. 61, No. 12, pp. 11-17, plus cover.
- Hong et al., "Microstructural characteristics of high-velocity oxygen-fuel (HVOF) sprayed nickel-based alloy coating", *Journal of Alloys and Compounds*, Jul. 26, 2013, vol. 581, pp. 398-403.
- Hu et al., "Crystallization Kinetics of the $Cu_{47.5}Zr_{74.5}Al_5$ Bulk Metallic Glass under Continuous and Iso-thermal heating", *App. Mech. And Materials*, vols. 99100, Sep. 8, 2011, p. 1052-1058.
- Huang et al., "Dendritic microstructure in the metallic glass matrix composite $Zr_{56}Ti_{14}Nb_5Cu_7Ni_6Be_{12}$ ", *Scripta Materialia*, Mar. 29, 2005, vol. 53, pp. 93-97.
- Huang et al., "Fretting wear behavior of bulk amorphous steel", *Intermetallics*, Jun. 12, 2011, vol. 19, pp. 1385-1389.
- Inoue et al., "Cobalt-based bulk glassy alloy with ultrahigh strength and soft magnetic properties", *Nature Materials*, Sep. 21, 2003, vol. 2, pp. 661-663.
- Inoue et al., "Development and applications of late transition metal bulk metallic glasses", *Bulk Metallic Glasses*, pp. 1-25, 2008.
- Inoue et al., "Developments and applications of bulk metallic glasses", *Rev. Adv. Mater. Sci.*, Feb. 28, 2008, vol. 18, No. 1., pp. 1-9.
- Inoue et al., "Preparation of 16 mm diameter Rod of Amorphous $Zr_{65}Al_{7.5}Ni_{10}Cu_{17.5}$ Alloy", *Material Transactions, JIM*, 1993, vol. 34, No. 12, pp. 1234-1237.
- Inoue et al., "Recent development and application products of bulk glassy alloys", *Acta Materialia*, Jan. 20, 2011, vol. 59, Issue 6, pp. 2243-2267.
- Ishida et al., "Wear resistivity of super-precision microgear made of Ni-based metallic glass", *Materials Science and Engineering*, Mar. 25, 2007, vol. A449-451, pp. 149-154.
- Jiang et al., "Low-Density High-Strength Bulk Metallic Glasses and Their Composites: A Review", *Advanced Engineering Materials*, Nov. 19, 2014, pp. 1-20, DOI: 10.1002/adem.201400252.
- Jiang et al., "Tribological Studies of a Zr-Based Glass-Forming Alloy with Different States", *Advanced Engineering Materials*, Sep. 14, 2009, vol. 1, No. 11, pp. 925-931.
- Kahraman et al., "A Feasibility Study on Development of Dust Abrasion Resistant Gear Concepts for Lunar Vehicle Gearboxes", *NASA Grant NNX07AN42G Final Report*, Mar. 11, 2009, 77 pgs.
- Kim, Junghwan et al., "Oxidation and crystallization mechanisms in plasma-sprayed Cu-based bulk metallic glass coatings", *Acta Materialia*, Feb. 1, 2010, vol. 58, pp. 952-962.
- Kim et al., "Amorphous phase formation of Zr-based alloy coating by HVOF spraying process", *Journal of Materials Science*, Jan. 1, 2001, vol. 36, pp. 49-54.
- Kim et al., "Enhancement of metallic glass properties of Cu-based BMG coating by shroud plasma spraying", *Science Direct, Surface & Coatings Technology*, Jan. 25, 2011, vol. 205, pp. 3020-3026, Nov. 6, 2010.
- Kim et al., "Production of $Ni_{65}Cr_{15}P_{16}B_4$ Metallic Glass-Coated Bipolar Plate for Fuel Cell by High Velocity Oxy-Fuel (HVOF) Spray Coating Method", *The Japan Institute of Metals, Materials Transactions*, Aug. 25, 2010, vol. 51, No. 9, pp. 1609-1613.
- Kim et al., "Realization of high tensile ductility in a bulk metallic glass composite by the utilization of deformation-induced martensitic transformation", *Scripta Materialia*, May 3, 2011, vol. 65, pp. 304-307.
- Kim et al., "Weldability of $Cu_{54}Zr_{22}Ti_{18}Ni_6$ bulk metallic glass by ultrasonic welding processing", *Materials Letters*, May 17, 2014, 130, pp. 160-163.
- Kobayashi et al., "Fe-based metallic glass coatings produced by smart plasma spraying process", *Materials Science and Engineering*, Feb. 25, 2008, vol. B148, pp. 110-113.
- Kobayashi et al., "Mechanical property of Fe-base metallic glass coating formed by gas tunnel type plasma spraying", *ScienceDirect, Surface & Coatings Technology*, Mar. 14, 2008, 6 pgs.

(56)

References Cited

OTHER PUBLICATIONS

Kobayashi et al., "Property of Ni-Based Metallic Glass Coating Produced by Gas Tunnel Type Plasma Spraying", International Plasma Chemistry Society, ISPC 20, 234, Philadelphia, USA, Jul. 24, 2011, Retrieved from: <http://www.ispc-conference.org/ispcproc/ispc20/234.pdf>.

Kong et al., "Effect of Flash Temperature on Tribological Properties of Bulk Metallic Glasses", Tribol. Lett., Apr. 25, 2009, vol. 35, pp. 151-158.

Kozachkov et al., "Effect of cooling rate on the vol. fraction of B2 phases in a CuZrAlCo metallic glass matrix composite", Intermetallics, Apr. 19, 2013, vol. 39, pp. 89-93.

Kuhn et al., "Microstructure and mechanical properties of slowly cooled Zr—Nb—Cu—Ni—Al composites with ductile bcc phase", Materials Science and Engineering: A, Jul. 2004, vol. 375-377, pp. 322-326.

Kuhn et al., "ZrNbCuNiAl bulk metallic glass matrix composites containing dendritic bcc phase precipitates", Applied Physics Letters, Apr. 8, 2002, vol. 80, No. 14, pp. 2478-2480.

Kumar et al., "Bulk Metallic Glass: The Smaller the Better", Advanced Materials, Jan. 25, 2011, vol. 23, pp. 461-476.

Kwon et al., "Wear behavior of Fe-based bulk metallic glass composites", Journal of Alloys and Compounds, Jul. 14, 2011, vol. 509S, pp. S105-S108.

Launey et al., "Fracture toughness and crack-resistance curve behavior in metallic glass-matrix composites", Applied Physics Letters, Jun. 18, 2009, vol. 94, pp. 241910-1-241910-3.

Launey et al., "Solution to the problem of the poor cyclic fatigue resistance of bulk metallic glasses", PNAS Early Edition, pp. 1-6, Jan 22, 2009.

Lee et al., "Effect of a controlled volume fraction of dendritic phases on tensile and compressive ductility in La-based metallic glass matrix composites", Acta Materialia, vol. 52, Issue 14, Jun. 17, 2004, pp. 4121-4131.

Lee et al., "Nanomechanical properties of embedded dendrite phase and its influence on inelastic deformation of $Zr_{55}Al_{10}Ni_5Cu_{30}$ glassy alloy", Materials Science and Engineering A, Mar. 25, 2007, vol. 375, pp. 945-948.

Extended European Search Report for European Application No. 14889035.3, Search completed Dec. 4, 2017, dated Dec. 13, 2017, 10 Pgs.

Sanders et al., "Stability of Al-rich glasses in the Al—La—Ni system", 2006, Intermetallics, 14, pp. 348-351.

Sun et al., "Fiber metallic glass laminates", Dec. 2010, J. Mater. Res., vol. 25, No. 12, pp. 2287-2291.

Demetriou et al., "Glassy steel optimized for glass-forming ability and toughness", Applied Physics Letters, Jul. 31, 2009, vol. 95; pp. 041907-1-041907-3; <http://dx.doi.org/10.1063/1.3184792>.

Kim et al. "Design and synthesis of Cu-based metallic glass alloys with high glass forming ability", Journal of Metastable and Nanocrystalline Materials, Sep. 1, 2005, vols. 24-25, pp. 93-96.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D




FIG. 4E




FIG. 4F



FIG. 4G




FIG. 4H




FIG. 4I



FIG. 5A




FIG. 5B




FIG. 5C




FIG. 6A




FIG. 6B




FIG. 7A



FIG. 7B




FIG. 7C




FIG. 7D




FIG. 8A




FIG. 8B

1

**SYSTEMS AND METHODS FOR
STRUCTURALLY INTERRELATING
COMPONENTS USING INSERTS MADE
FROM METALLIC GLASS-BASED
MATERIALS**

CROSS-REFERENCE TO RELATED
APPLICATIONS

The current application claims priority to U.S. Provisional Application No. 62/131,467, filed Mar. 11, 2015, the disclosure of which is incorporated herein by reference.

STATEMENT OF FEDERAL FUNDING

The invention described herein was made in the performance of work under a NASA contract NNN12AA01C, and is subject to the provisions of Public Law 96-517 (35 USC 202) in which the Contractor has elected to retain title.

FIELD OF THE INVENTION

The present invention generally relates to structurally interrelating components using inserts fabricated from metallic glass-based materials.

BACKGROUND

The manufacture of a variety of engineered structures typically relies on fastening, or otherwise structurally interrelating, a plurality of components (e.g. in the form of sheet metal). In many instances, conventionally engineered structures are assembled from components made from heritage engineering materials, e.g. steel, aluminum, titanium, etc. Such materials are advantageous in a number of respects, e.g. they are characterized by the requisite toughness for a host of engineering applications. Moreover, such heritage engineering materials can be readily amenable to being adjoined to other engineering materials. For example, threaded holes (which can accommodate screws/bolts) can be practicably machined into steel-based components.

Many modern structures rely on the implementation of composite materials that may not be as easily machinable as heritage engineering materials. For example, carbon fiber composites typically cannot be easily threaded. Accordingly, in many instances, to allow carbon fiber composite materials to be adjoined to other components, threaded inserts are embedded within carbon fiber composite materials that can more easily enable them to be adjoined to other components. For instance, holes can be drilled out of a carbon composite material, and threaded inserts that define threaded holes—typically machined from heritage engineering materials (e.g. steel, aluminum, titanium)—can be epoxy bonded within the holes drilled in the carbon composite material. The embedded threaded inserts can thereby enable another component (e.g. sheet metal made from steel) to be fastened to the carbon fiber composite.

SUMMARY OF THE INVENTION

Systems and methods in accordance with embodiments of the invention operate to structurally interrelate two components using inserts made from metallic glass-based materials. In one embodiment, a method of structurally interrelating two components includes: forming an insert from a metallic glass-based composition; where the formed insert includes a metallic glass-based material; affixing the insert

2

to a first component; and structurally interrelating the second component to the first component using the insert.

In another embodiment, forming an insert from a metallic glass-based composition includes using one of: a thermo-plastic forming technique; and a casting technique.

In yet another embodiment, the formed insert includes a textured outer surface.

In still another embodiment, the formed insert is a threaded insert.

In still yet another embodiment, the formed insert includes extensions that are configured to deploy as the insert is engaged by a screw.

In a further embodiment, the formed insert includes an eye-hook structure.

In a yet further embodiment, the formed insert conforms to one of a cup-shaped geometry and a cone-shaped geometry.

In a still further embodiment, the metallic glass-based composition is based on one of: Ti, Zr, Cu, Ni, Fe, Pd, Pt, Ag, Au, Al, Hf, W, Ti—Zr—Be, Cu—Zr, Zr—Be, Ti—Cu, Zr—Cu—Ni—Al, Ti—Zr—Cu—Be, and combinations thereof.

In a still yet further embodiment, the metallic glass-based composition is based on titanium.

In another embodiment, affixing the formed insert to a first component includes epoxy bonding the formed insert to the first component.

In still another embodiment, affixing the formed insert to a first component includes press fitting the formed insert in to the first component.

In yet another embodiment, the formed insert is a threaded insert such that when it is engaged by a screw, it expands laterally and thereby better adheres to the first component.

In still yet another embodiment, the first component is a carbon composite material.

In a further embodiment, the metallic glass-based material is a titanium-based metallic glass-based material.

In a still further embodiment, the formed insert is a threaded insert, and structurally interrelating the second component to the first component includes fastening the second component to the first component using a screw and the threaded insert.

In a yet further embodiment, structurally interrelating the second component to the first component includes structurally aligning the second component to the first component.

In a still yet further embodiment, an insert configured to structurally interrelate two components includes a metallic glass-based material.

In another embodiment, the insert is a threaded insert.

In yet another embodiment, the insert includes an eye-hook structure.

In still another embodiment, the insert includes a titanium-based metallic glass-based material.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a bolt cast from a MG-based material, demonstrating that MG-based materials can be cast into shapes that include intricate features such as threads in accordance with certain embodiments of the invention.

FIG. 2 illustrates a process for structurally interrelating two components using an insert fabricated from a MG-based material in accordance with certain embodiments of the invention.

FIGS. 3A-3C illustrate casting a MG-based material to create a threaded insert in accordance with certain embodiments of the invention.

FIGS. 4A-4I illustrate a variety of insert geometries that can be fabricated in accordance with certain embodiments of the invention.

FIGS. 5A-5C illustrate a threaded insert including extensions fabricated from a MG-based material in accordance with certain embodiments of the invention.

FIGS. 6A-6B illustrate how the elastic properties of a MG-based material can be harnessed to better adhere a respective insert to a component in accordance with certain embodiments of the invention.

FIGS. 7A-7D schematically depict a process for structurally interrelating two components using an insert fabricated from a MG-based material in accordance with certain embodiments of the invention.

FIGS. 8A-8B illustrate an insert that was fabricated from conventional steel relative to an insert fabricated from a MG-based material in accordance with certain embodiments of the invention.

DETAILED DESCRIPTION

Turning now to the drawings, systems and methods for structurally interrelating two components using inserts made from metallic glass-based materials are illustrated. In many embodiments, threaded inserts that include metallic glass-based materials are embedded within at least a first component to be adjoined to a second component; the threaded insert is then utilized in the adjoining of the at least two components. In a number of instances, cup and cone-shaped inserts that include metallic glass-based materials are embedded within first and second components, and the cup and cone-shaped inserts are used to structurally align the first and second components.

Metallic glasses, also known as amorphous alloys, embody a relatively new class of materials that is receiving much interest from the engineering and design communities. Metallic glasses are characterized by their disordered atomic-scale structure in spite of their metallic constituent elements—i.e. whereas conventional metallic materials typically possess a highly ordered atomic structure, metallic glass materials are characterized by their disordered atomic structure. Notably, metallic glasses typically possess a number of useful material properties that can allow them to be implemented as highly effective engineering materials. For example, metallic glasses are generally much harder than conventional metals, and are generally tougher than ceramic materials. They are also relatively corrosion resistant, and, unlike conventional glass, they can have good electrical conductivity. Importantly, metallic glass materials lend themselves to relatively easy processing in certain respects. For example, the forming of metallic glass materials can be compatible with injection molding processes. Thus, for example, metallic glass compositions can be cast into desired shapes.

Nonetheless, the practical implementation of metallic glasses presents certain challenges that limit their viability as engineering materials. In particular, metallic glasses are typically formed by raising a metallic alloy above its melting temperature, and rapidly cooling the melt to solidify it in a way such that its crystallization is avoided, thereby forming the metallic glass. The first metallic glasses required extraordinary cooling rates, e.g. on the order of 10^6 K/s, and were thereby limited in the thickness with which they could be formed. Indeed, because of this limitation in thickness, metallic glasses were initially limited to applications that involved coatings. Since then, however, particular alloy compositions that are more resistant to crystallization have

been developed, which can thereby form metallic glasses at much lower cooling rates, and can therefore be made to be much thicker (e.g. greater than 1 mm). These metallic glass compositions that can be made to be thicker are known as ‘bulk metallic glasses’ (“BMGs”). As can be appreciated, such BMGs can be better suited for investment molding operations.

In addition to the development of BMGs, ‘bulk metallic glass matrix composites’ (BMGMCs) have also been developed. BMGMCs are characterized in that they possess the amorphous structure of BMGs, but they also include crystalline phases of material within the matrix of amorphous structure. For example, the crystalline phases can exist in the form of dendrites. The crystalline phase inclusions can impart a host of favorable materials properties on the bulk material. For example, the crystalline phases can allow the material to have enhanced ductility, compared to where the material is entirely constituted of the amorphous structure. BMGs and BMGMCs can be referred to collectively as BMG-based materials. Similarly, metallic glasses, metallic glasses that include crystalline phase inclusions, BMGs, and BMGMCs can be referred to collectively as metallic glass-based materials or MG-based materials.

The potential of metallic glass-based materials continues to be explored, and developments continue to emerge. For example, in U.S. patent application Ser. No. 13/928,109, D. Hofmann et al. disclose the implementation of metallic glass-based materials in macroscale gears. The disclosure of U.S. patent application Ser. No. 13/928,109 is hereby incorporated by reference in its entirety, especially as it pertains to metallic glass-based materials, and their implementation in macroscale gears. Likewise, in U.S. patent application Ser. No. 13/942,932, D. Hofmann et al. disclose the implementation of metallic glass-based materials in macroscale compliant mechanisms. The disclosure of U.S. patent application Ser. No. 13/942,932 is hereby incorporated by reference in its entirety, especially as it pertains to metallic glass-based materials, and their implementation in macroscale compliant mechanisms. Moreover, in U.S. patent application Ser. No. 14/060,478, D. Hofmann et al. disclose techniques for depositing layers of metallic glass-based materials to form objects. The disclosure of U.S. patent application Ser. No. 14/060,478 is hereby incorporated by reference especially as it pertains to metallic glass-based materials, and techniques for depositing them to form objects. Furthermore, in U.S. patent application Ser. No. 14/163,936, D. Hofmann et al., disclose techniques for additively manufacturing objects so that they include metallic glass-based materials. The disclosure of U.S. patent application Ser. No. 14/163,936 is hereby incorporated by reference in its entirety, especially as it pertains to metallic glass-based materials, and additive manufacturing techniques for manufacturing objects so that they include metallic glass-based materials. Additionally, in U.S. patent application Ser. No. 14/177,608, D. Hofmann et al. disclose techniques for fabricating strain wave gears using metallic glass-based materials. The disclosure of U.S. patent application Ser. No. 14/177,608 is hereby incorporated by reference in its entirety, especially as it pertains to metallic glass-based materials, and their implementation in strain wave gears. Moreover, in U.S. patent application Ser. No. 14/178,098, D. Hofmann et al., disclose selectively developing equilibrium inclusions within an object constituted from a metallic glass-based material. The disclosure of U.S. patent application Ser. No. 14/178,098 is hereby incorporated by reference, especially as it pertains to metallic glass-based materials, and the tailored development of equi-

librium inclusions within them. Furthermore, in U.S. patent application Ser. No. 14/252,585, D. Hofmann et al. disclose techniques for shaping sheet materials that include metallic glass-based materials. The disclosure of U.S. patent application Ser. No. 14/252,585 is hereby incorporated by reference in its entirety, especially as it pertains to metallic glass-based materials and techniques for shaping sheet materials that include metallic glass-based materials. Additionally, in U.S. patent application Ser. No. 14/259,608, D. Hofmann et al. disclose techniques for fabricating structures including metallic glass-based materials using ultrasonic welding. The disclosure of U.S. patent application Ser. No. 14/259,608 is hereby incorporated by reference in its entirety, especially as it pertains to metallic glass-based materials and techniques for fabricating structures including metallic glass-based materials using ultrasonic welding. Moreover, in U.S. patent application Ser. No. 14/491,618, D. Hofmann et al. disclose techniques for fabricating structures including metallic glass-based materials using low pressure casting. The disclosure of U.S. patent application Ser. No. 14/491,618 is hereby incorporated by reference in its entirety, especially as it pertains to metallic glass-based materials and techniques for fabricating structures including metallic glass-based materials using low pressure casting. Furthermore, in U.S. patent application Ser. No. 14/660,730, Hofmann et al. disclose metallic glass-based fiber metal laminates. The disclosure of U.S. patent application Ser. No. 14/660,730 is hereby incorporated by reference in its entirety, especially as it pertains to metallic glass-based fiber metal laminates. Additionally, in U.S. patent application Ser. No. 14/971,848, A. Kennett et al. disclose techniques for manufacturing gearbox housings made from metallic glass-based materials. The disclosure of U.S. patent application Ser. No. 14/971,848, is hereby incorporated by reference in its entirety, especially as it pertains to the manufacture of metallic glass-based gearbox housings.

Notwithstanding all of these developments, the vast potential of metallic glass-based materials has yet to be fully appreciated. For instance, the fabrication of inserts that can be used to facilitate the structural interrelationship between two components from metallic glass-based materials has yet to be fully explored. Such inserts have typically been fabricated from conventional engineering materials such as steel, aluminum, and/or titanium. This is in part due to the conventional desire to not have two dissimilar metals in intimate contact with each other—i.e. a screw and the respective threaded insert each including dissimilar metals—for fear of the effects of galvanic corrosion. However, MG-based materials can be made to be relatively averse to the effects of galvanic corrosion, and can also be made to develop a robust oxide layer that can further inhibit occurrences of galvanic corrosion. In other words, MG-based materials can be made to practicably operate in intimate contact with dissimilar metals. Whereas such inserts have typically been fabricated from conventional engineering materials (e.g. steel, aluminum, or titanium), they can substantially benefit from the materials properties that many MG-based materials can offer. For instance, inserts made from MG-based materials can have a relatively higher elastic strain limit, better resistance to wear, higher hardness, lower density, better corrosion resistance, and/or better resilience to extreme environments relative to conventionally fabricated inserts. Additionally, MG-based materials can be further advantageous insofar as their inherent mechanical properties can be tunable via alloying. Moreover, MG-based materials are amenable to casting and other thermoplastic forming processes, which can greatly enhance

manufacturing efficiency. By contrast, casting processes are not conventionally used in the fabrication of inserts from heritage engineering materials for a number of reasons. For example, the most appropriate conventional materials for casting techniques are softer materials, which typically are not wear resistant and thereby not best-suited for, e.g., threaded insert applications where screws may be wearing on the respective insert. Methods for structurally interrelating two components using inserts that include MG-based materials in accordance with many embodiments of the invention are now discussed below.

Methods for Structurally Interrelating Two Components Using Inserts Fabricated from MG-Based Materials

In many embodiments of the invention, two components are structurally interrelated using inserts fabricated from MG-based materials. While conventional inserts fabricated from heritage engineering materials have been effective in many respects, fabricating these inserts from MG-based materials can offer a host of previously unrealized advantages. As alluded to above, MG-based materials can offer unique materials profiles that can be advantageous such inserts. Moreover, MG-based materials are amenable to casting and other thermoplastic forming processes, which can allow for the efficient—and bulk—manufacture of even intricate geometries. For example, FIG. 1 illustrates a screw—including threads—that was entirely cast from a MG-based material; FIG. 1 demonstrates that MG-based materials can be cast into intricate geometric shapes. This level of castability can be harnessed in the creating inserts from metallic glass-based materials.

FIG. 2 illustrates a process for structurally interrelating two components in accordance with certain embodiments of the invention. In particular, the method 200 includes forming 210 an insert from a MG-based composition using a casting technique or other thermoplastic forming technique. Any suitable thermoplastic or casting technique can be implemented in accordance with embodiments of the invention. For example, FIGS. 3A-3C schematically illustrate casting a MG-based material to create a threaded insert in accordance with many embodiments of the invention. In particular, FIG. 3A illustrates a MG-based composition in relation to a mold in the shape of a screw; FIG. 3B illustrates casting the MG-based melt around the mold so as to form a MG-based material; and FIG. 3C illustrates removing the cast threaded insert from the plug. In many instances, the forming 210 additionally includes other manufacturing procedures, such as machining. For instance, the forming 210 can include roughening the outer surface of the insert via any of a variety of texturizing techniques.

Note that any suitable MG-based material can be incorporated in accordance with embodiments of the invention; embodiments of the invention are not limited to particular compositions. For example, in many instances, the alloy composition is a composition that is based on one of: Ti, Zr, Cu, Ni, Fe, Pd, Pt, Ag, Au, Al, Hf, W, Ti—Zr—Be, Cu—Zr, Zr—Be, Ti—Cu, Zr—Cu—Ni—Al, Ti—Zr—Cu—Be and combinations thereof. In the instant context, the term ‘based on’ can be understood to mean that the specified element(s) are present in the greatest amount relative to any other present elements. Additionally, within the context of the instant application, the term “MG-based composition” can be understood reference an element, or aggregation of elements, that are capable of forming a metallic glass-based material (e.g. via being exposed to a sufficiently rapid, but viable, cooling rate). While several examples of suitable metallic glass-based materials are listed above, it should be reiterated that any suitable metallic glass-based composition

can be incorporated in accordance with embodiments of the invention; for example, any of the metallic glass-based compositions listed in the disclosures cited and incorporated by reference above can be implemented. In many instances, the particular MG-based composition to be cast is based on an assessment of the anticipated operating environment for the insert. Thus, for example, in many instances the implemented MG-based composition is based the desire to match the coefficient of expansion with that of the component material that it is going to be affixed to. Accordingly, in many embodiments, titanium-based MG-based materials are implemented for use in conjunction with carbon composite materials. In particular, both titanium-based MG-based materials and carbon composite materials are generally characterized by relatively low coefficients of thermal

expansion. In this way, when the insert is affixed to the carbon composite, the stresses between the insert and the carbon composite (e.g. in the epoxy bonding) can be reduced. Note also that both titanium-based MG-based materials and carbon composites are relatively light weight materials, and can thereby be well-suited for space applications. In particular, titanium-based MG-based inserts can offer high hardness at a relatively low density.

In many instances, the selection of the MG-based material to be implemented is based on the desire for one of: environmental resilience, toughness, wear resistance, hardness, density, machinability, and combinations thereof. For reference, Tables 1-6 list materials data that can be relied on in selecting a metallic glass-based composition to be implemented.

TABLE 1

Material Properties of MG-Based Materials relative to Heritage Engineering Materials							
Material	Density (g/cc)	Stiffness, E (GPa)	Tensile Yield (MPa)	Tensile UTS (MPa)	Elastic Limit (%)	Specific Strength	Hardness (HRC)
SS 15500 H1024	7.8	200	1140	1170	<1	146	36
Ti—6Al—4V STA	4.4	114	965	1035	<1	219	41
Ti—6Al—6V—4Sn STA	4.5	112	1035	1100	<1	230	42
Nitronic 60 CW	7.6	179	1241	1379	<1	163	40
Vascomax C300	8.0	190	1897	1966	<1	237	50
Zr-BMG	6.1	97	1737	1737	>1.8	285	60
Ti-BMGMC	5.2	94	1362	1429	>1.4	262	51
Zr-BMGMC	5.8	75	1096	1210	>1.4	189	48

TABLE 2

Material Properties of Select MG-Based Materials as a function of Composition										
name	atomic %	weight %	BMG (%)	bcc (%)	ρ (g/cm ³)	σ_y (MPa)	σ_{max} (MPa)	ϵ_y (%)	E (GPa)	T _s (K)
DV2	Ti ₄₄ Zr ₂₀ V ₁₂ Cu ₅ Be ₁₉	Ti _{41.9} Zr _{36.3} V _{12.1} Cu _{6.3} Be _{3.4}	70	30	5.13	1597	1614	2.1	94.5	956
DV1	Ti ₄₈ Zr ₂₀ V ₁₂ Cu ₅ Be ₁₅	Ti _{44.3} Zr _{35.2} V _{11.8} Cu _{6.1} Be _{2.6}	53	47	5.15	1362	1429	2.3	94.2	955
DV3	Ti ₅₆ Zr ₁₈ V ₁₀ Cu ₄ Be ₁₂	Ti _{51.6} Zr _{31.6} V _{9.8} Cu _{4.9} Be _{2.1}	46	54	5.08	1308	1309	2.2	84.0	951
DV4	Ti ₆₂ Zr ₁₅ V ₁₀ Cu ₄ Be ₉	Ti _{57.3} Zr _{26.4} V _{9.8} Cu _{4.9} Be _{1.6}	40	60	5.03	1086	1089	2.1	83.7	940
DVAI1	Ti ₆₀ Zr ₁₆ V ₉ Cu ₃ Al ₃ Be ₉	Ti _{55.8} Zr _{28.4} V _{8.9} Cu _{3.7} Al _{1.6} Be _{1.6}	31	69	4.97	1166	1189	2.0	84.2	901
DVAI2	Ti ₆₇ Zr ₁₁ V ₁₀ Cu ₅ Al ₂ Be ₅	Ti _{62.4} Zr _{19.5} V _{9.9} Cu _{6.2} Al ₁ Be _{0.9}	20	80	4.97	990	1000	2.0	78.7	998
Ti-6-4a	Ti _{86.1} Al _{10.3} V _{3.6}	Ti ₉₀ Al ₆ V ₄ (Grade 5 Annealed)	na	na	4.43	754	882	1.0	113.8	1877
Ti-6-4s	Ti _{86.1} Al _{10.3} V _{3.6} [Ref]	Ti ₉₀ Al ₆ V ₄ (Grade 5 STA)	na	na	4.43	1100	1170	~1	114.0	1877
CP-Ti	Ti ₁₀₀	Ti ₁₀₀ (Grade 2)	na	na	4.51	380	409	0.7	105.0	~1930

TABLE 3

Material Properties of Select MG-Based Materials as a function of Composition											
Alloy	σ_{max} (MPa)	ϵ_{tot} (%)	σ_y (MPa)	ϵ_y (%)	E (GPa)	ρ (g/cm ³)	G (GPa)	CIT (J)	RoA (%)	ν	
Zr _{36.6} Ti _{31.4} Nb ₇ Cu _{5.9} Be _{19.1} (DH1)	1512	9.58	1474	1.98	84.3	5.6	30.7	26	44	0.371	
Zr _{38.3} Ti _{32.9} Nb _{7.3} Cu _{6.2} Be _{15.3} (DH2)	1411	10.8	1367	1.92	79.2	5.7	28.8	40	50	0.373	
Zr _{39.6} Ti _{33.9} Nb _{7.6} Cu _{6.4} Be _{12.5} (DH3)	1210	13.10	1096	1.62	75.3	5.8	27.3	45	46	0.376	
Zr _{41.2} Ti _{13.8} Cu _{12.5} Ni ₁₀ Be _{22.5} (Vitrelloy 1)	1737	1.98	—	—	97.2	6.1	35.9	8	0	0.355	
Zr _{56.2} Ti _{13.8} Nb _{5.0} Cu _{6.9} Ni _{5.6} Be _{12.5} (LM 2)	1302	5.49	1046	1.48	78.8	6.2	28.6	24	22	0.375	

TABLE 4

Material Properties as a Function of Composition and Structure, where A is Amorphous, X, is Crystalline, and C is Composite			
	A/X/C	2.0 Hv	E (GPa)
(CuZr42Al7Be10)Nb3	A	626.5	108.5
(CuZr46Al5Y2)Nb3	A	407.4	76.9
(CuZrAl7Be5)Nb3	A	544.4	97.8
(CuZrAl7Be7)Nb3	A	523.9	102.0
Cu40Zr40Al10Be10	A	604.3	114.2
Cu41Zr40Al7Be7Co5	C	589.9	103.5
Cu42Zr41Al7Be7Co3	A	532.4	101.3
Cu47.5Zr48Al4Co0.5	X	381.9	79.6
Cu47Zr46Al5Y2	A	409.8	75.3
Cu50Zr50	X	325.9	81.3
CuZr41Al7Be7Cr3	A	575.1	106.5
CuZrAl5Be5Y2	A	511.1	88.5
CuZrAl5Ni3Be4	A	504.3	95.5
CuZrAl7	X	510.5	101.4
CuZrAl7Ag7	C	496.1	90.6
CuZrAl7Ni5	X	570.0	99.2
Ni40Zr28.5Ti16.5Be15	C	715.2	128.4

TABLE 4-continued

Material Properties as a Function of Composition and Structure, where A is Amorphous, X, is Crystalline, and C is Composite			
	A/X/C	2.0 Hv	E (GPa)
Ni40Zr28.5Ti16.5Cu5Al10	X	627.2	99.3
Ni40Zr28.5Ti16.5Cu5Be10	C	668.2	112.0
Ni56Zr17Ti13Si2Sn3Be9	X	562.5	141.1
Ni57Zr18Ti14Si2Sn3Be6	X	637.3	139.4
Ti33.18Zr30.51Ni5.33Be22.88Cu8.1	A	486.1	96.9
Ti40Zr25Be30Cr5	A	465.4	97.5
Ti40Zr25Ni8Cu9Be18	A	544.4	101.1
Ti45Zr16Ni9Cu10Be20	A	523.1	104.2
Vit 1	A	530.4	95.2
Vit105 (Zr52.5Ti5Cu17.9Ni14.6Al10)	A	474.4	88.5
Vit 106	A	439.7	83.3
Zr55Cu30Al10Ni5	A	520.8	87.2
Zr65Cu17.5Al7.5Ni10	A	463.3	116.9
DH1	C	391.1	84.7
GHDT (Ti30Zr35Cu8.2Be26.8)	A	461.8	90.5

TABLE 5

Fatigue Characteristics as a Function of Composition							
Material	Fracture strength (MPa)	Geometry (mm)	Loading mode ^a	Frequency (Hz)	R-ratio	Fatigue limit (MPa)	Fatigue ratio ^b
Zr _{56.2} Cu _{6.9} Ni _{5.6} Ti _{13.8} Nb _{5.0} Be _{12.5} Composites [62]	1480	3 × 3 × 30	4PB	25	0.1	~296	0.200
Zr _{41.2} Cu _{12.5} Ni ₁₀ Ti _{13.8} Be _{22.5} [49]	1900	3 × 3 × 50	4PB	25	0.1	~152	0.080
Zr _{41.2} Cu _{12.5} Ni ₁₀ Ti _{13.8} Be _{22.5} [74]	1900	2 × 2 × 60	3PB	10	0.1	768	0.404
Zr _{41.2} Cu _{12.5} Ni ₁₀ Ti _{13.8} Be _{22.5} [74]	1900	2 × 2 × 60	3PB	10	0.1	359	0.189
Zr ₄₄ Ti ₁₁ Ni ₁₀ Cu ₁₀ Be ₂₅ [75]	1900	2.3 × 2.0 × 85	4PB	5-20	0.3	550	0.289
Zr ₄₄ Ti ₁₁ Ni ₁₀ Cu ₁₀ Be ₂₅ [75]	1900	2.3 × 2.0 × 85	4PB	5-20	0.3	390	0.205
Zr _{52.5} Cu _{17.9} Al ₁₀ Ni _{14.6} Ti ₅ [77]	1700	3.5 × 3.5 × 30	4PB	10	0.1	850	0.500
(Zr ₅₈ Ni _{13.5} Cu ₁₈ Al _{10.4}) ₉₉ Nb ₁ [76]	1700	2 × 2 × 25	4PB	10	0.1	559	0.329
Zr ₅₅ Cu ₃₀ Ni ₅ Al ₁₀ [78]	1560	2 × 20 × 50	Plate bend	40	0.1	410	0.263

TABLE 6

Fatigue Characteristics as a Function of Composition							
Material	Fracture strength (MPa)	Geometry (mm)	Loading mode ^a	Frequency (Hz)	R-ratio	Fatigue limit (MPa)	Fatigue ratio ^b
Zr _{56.2} Cu _{6.9} Ni _{5.6} Ti _{13.8} Nb _{5.0} Be _{12.5} Composites [56]	1480	Ø2.98	TT	10	0.1	239	0.161
Zr ₅₅ Cu ₃₀ Al ₁₀ Ni ₅ Nano [85]	1700	2 × 4 × 70	TT	10	0.1	~340	0.200
Zr _{41.2} Cu _{12.5} Ni ₁₀ Ti _{13.8} Be _{22.5} [55]	1850	Ø2.98	TT	10	0.1	703	0.380
Zr _{41.2} Cu _{12.5} Ni ₁₀ Ti _{13.8} Be _{22.5} [55]	1850	Ø2.98	TT	10	0.1	615	0.332
Zr _{41.2} Cu _{12.5} Ni ₁₀ Ti _{13.8} Be _{22.5} [56]	1850	Ø2.98	TT	10	0.1	567	0.306
Zr _{41.2} Cu _{12.5} Ni ₁₀ Ti _{13.8} Be _{22.5} [80]	1900	—	CC	5	0.1	~1050	0.553
Zr _{41.2} Cu _{12.5} Ni ₁₀ Ti _{13.8} Be _{22.5} [80]	1900	—	TC	5	-1	~150	0.079
Zr ₅₀ Cu ₄₀ Al ₁₀ [53]	1821	Ø2.98	TT	10	0.1	752	0.413
Zr ₅₀ Cu ₃₀ Al ₁₀ Ni ₁₀ [53]	1900	Ø2.98	TT	10	0.1	865	0.455
Zr ₅₀ Cu ₃₇ Al ₁₀ Pd ₃ [57]	1899	Ø2.98	TT	10	0.1	983	0.518
Zr ₅₀ Cu ₃₇ Al ₁₀ Pd ₃ [81]	1899	Ø5.33	TT	10	0.1	~900	0.474
Zr _{52.5} Cu _{17.9} Al ₁₀ Ni _{14.6} Ti ₅ [82]	1660	6 × 3 × 1.5	TT	1	0.1	—	—
Zr _{52.5} Cu _{17.9} Al ₁₀ Ni _{14.6} Ti ₅ [51]	1700	Ø2.98	TT	10	0.1	907	0.534
Zr ₅₀ Cu ₂₀ Al ₁₀ Ni ₈ Ti ₃ [82]	1580	6 × 3 × 1.5	TT	1	0.1	—	—
Zr ₅₅ Cu ₁₅ Al ₁₀ Ni ₁₀ [84]	1300	3 × 4 × 16	TT	20	0.1	~280	0.215
Zr ₅₅ Cu ₃₀ Al ₁₀ Ni ₅ [83]	1560	1 × 2 × 5	TT	0.13	0.5	—	—

Again, while several examples of MG-based materials that can be suitable for implementation within the instant context, embodiments of the invention are not limited to the materials listed in the tables. Rather, any suitable MG-based material can be implemented in accordance with embodiments of the invention.

Importantly, the MG-based composition can be cast into any suitable shape that can facilitate the structural interrelationship between two components. For example, FIGS. 4A-4I depict various geometries that can also be implemented in accordance with embodiments of the invention. Note that FIGS. 4A-4E illustrate threaded insert geometries that are characterized by a rough-textured outer surface, which can facilitate the bonding of the insert to a component. Of course, it should be appreciated that while certain rough textured surfaces are depicted, any of a variety of rough-textured surfaces can be incorporated in accordance with embodiments of the invention. FIG. 4F illustrates an eye-hook geometry can be used to facilitate a tethering structural relationship. In many instances, the formed insert is a threaded insert that includes extensions that flare out when engaged by a screw; extensions can serve to better 'grip' an associated component. FIGS. 5A-5C illustrate a threaded insert that includes extensions that deploy when the insert engages a screw in accordance with an embodiment of the invention. In particular, FIG. 5A illustrates a screw and an insert made from a MG-based material in accordance with an embodiment of the invention. FIG. 5B illustrates the screw being inserted into the threaded insert, and the extensions beginning to deploy. FIG. 5C illustrates that the screw is fully engaged with the threaded insert, and the extensions are fully deployed. This type of design can help the insert better adhere to a component that it is affixed to. To be clear, while several designs have been discussed and illustrated, any suitable insert design can be implemented in accordance with embodiments of the invention. For example, in some embodiments, cup and cone-shaped inserts are fabricated. Cup and cone-shaped inserts can be affixed to first and second components respectively, and can be used to align the first and second component materials. To reiterate, any suitable insert shape can be implemented in accordance with embodiments of the invention.

Returning back to FIG. 2, the method 200 further includes affixing 220 the insert to a first component that is to be structurally interrelated to a second component. The insert can be affixed 220 in any suitable way in accordance with embodiments of the invention. For example, in many embodiments, the insert is epoxy bonded to the component. In a number of embodiments, the operation of a mechanical lock (e.g. the extensions depicted in FIGS. 5A-5C) is relied in affixing the insert to the component. Any suitable technique can be used to affix the insert to the component. In some embodiments, the elastic nature of the constituent MG-based material is relied on to allow the insert to better adhere to a respective component. For example, in some embodiments, a threaded insert is affixed to a component via a press fit; subsequently, when a screw engages the threaded insert, it expands laterally, and thereby better adheres to the component. Note that MG-based materials can have elastic limits as high as 2% or more; accordingly they can accommodate a relatively substantial amount of elastic deformation, which in turn can be used to better affix the insert to the component. FIGS. 6A-6B illustrate a threaded insert fabricated from a MG-based material that expands upon engagement with a screw and thereby better adheres to its respective associated component in accordance with an embodiment of the invention. In particular, FIG. 6A depicts

the insert press-bonded to an associated component; the depicted gap is meant to indicate that the insert is not as tightly bonded to the component as it could be. FIG. 6B illustrates that as the screw begins to engage the insert, it expands laterally and thereby more strongly adheres to the associated component. While several examples of affixing an insert to a component are discussed, it should be clear that any suitable way of affixing the insert to a first component can be implemented in accordance with embodiments of the invention.

Note that the component that the insert is affixed to can be any suitable component in accordance with embodiments of the invention. In many embodiments, the component is in the form of a sheet (e.g. sheet metal). In numerous embodiments, the component made from a relatively modern material, such as a carbon composite material. To be clear though, the component can take any of a variety of forms in accordance with embodiments of the invention.

Returning back to FIG. 2, the method 200 further includes structurally interrelating 230 a second component to the first component using the insert. In many embodiments, the insert is a threaded insert, a screw is used to fasten the second component to the first component using the threaded insert, and the first and second components are thereby structurally interrelated. In a number of embodiments, the insert is a cup-shaped insert designed to accommodate a cone-shaped geometry, the second component has an included cone-shaped geometry, the cup-shaped insert is used to align the first and second components, and the first and second components are thereby structurally interrelated. While several examples are given, it should be clear that the first and second components can be structurally interrelated in any suitable way in accordance with embodiments of the invention.

FIGS. 7A-7D schematically illustrates one example of a process in accordance with the method outlined in FIG. 2. In particular, FIG. 7A illustrates a first component to be structurally interrelated to a second component; in the illustrated embodiment, the first component is in the form of a sheet. As alluded to above, the component can be any suitable material in accordance with embodiments of the invention. FIG. 7B illustrates the formation of a threaded insert from a MG-based material. The insert can be formed using any suitable technique in accordance with embodiments of the invention, including any of the above-listed techniques. FIG. 7C illustrates embedding the insert within the first component. In particular, it is depicted that the insert is embedded within the first component using epoxy bonding. Of course, while epoxy bonding is depicted, the insert could have been affixed to the first component using any suitable technique in accordance with embodiments of the invention. FIG. 7D illustrates fastening a second component to the first component using a screw. As can be appreciated from the above discussion, the second component can take any of a variety of forms in accordance with embodiments of the invention. For example, it can conform to any of a variety of suitable geometries, and it can be made from any of a variety of suitable materials. While a certain process has been schematically illustrated in FIGS. 7A-7D, it should be clear that the process described with respect to FIG. 3 can be implemented in any of a variety of ways in accordance with embodiments of the invention.

FIGS. 8A-8B illustrate views of a MG-based insert relative to a conventional, steel-based insert. In particular, the MG-based insert appears on the right side of FIGS. 8A and 8B. Note that the two inserts are virtually identical in

13

geometry, which demonstrates the viability of fabricating inserts from MG-based materials.

In general, as can be inferred from the above discussion, the above-mentioned concepts can be implemented in a variety of arrangements in accordance with embodiments of the invention. For example, while the process listed in FIG. 3 recites forming an insert using either a thermoplastic forming technique or a casting technique, in many embodiments, the insert is formed without using one of those techniques. Any suitable manufacturing technique can be used to form an insert from a metallic glass-based material in accordance with embodiments of the invention. Accordingly, although the present invention has been described in certain specific aspects, many additional modifications and variations would be apparent to those skilled in the art. It is therefore to be understood that the present invention may be practiced otherwise than specifically described. Thus, embodiments of the present invention should be considered in all respects as illustrative and not restrictive.

What claimed is:

1. A method of structurally interrelating two components comprising:
 - forming an insert from a metallic glass-based composition;
 - wherein the formed insert comprises a metallic glass-based material having an elastic limit of at least 1.4%;
 - affixing the insert to a first component by press fitting the insert into the first component and engaging the insert with a second component, such that the engagement elastically deforms and laterally expands the insert to adhere to the first component; and
 - structurally interrelating the second component to the first component using the insert.
2. The method of claim 1, wherein forming an insert from a metallic glass-based composition comprises using one of: a thermoplastic forming technique; and a casting technique.

14

3. The method of claim 1, wherein the formed insert includes a textured outer surface.

4. The method of claim 1, wherein the formed insert is a threaded insert.

5. The method of claim 4, wherein the formed insert includes extensions that are configured to deploy as the insert is engaged by a screw.

6. The method of claim 1, wherein the formed insert includes an eye-hook structure.

7. The method of claim 1, wherein the formed insert conforms to one of a cup-shaped geometry and a cone-shaped geometry.

8. The method of claim 1, wherein the metallic glass-based composition is based on one of: Ti, Zr, Cu, Ni, Fe, Pd, Pt, Ag, Au, Al, Hf, W, Ti—Zr—Be, Cu—Zr, Zr—Be, Ti—Cu, Zr—Cu—Ni—Al, Ti—Zr—Cu—Be, and combinations thereof.

9. The method of claim 8, wherein the metallic glass-based composition is based on titanium.

10. The method of claim 1, wherein affixing the insert to the first component further comprises epoxy bonding the insert to the first component.

11. The method of claim 1, wherein the first component is a carbon composite material.

12. The method of claim 11, wherein the metallic glass-based material is a titanium-based metallic glass-based material.

13. The method of claim 1, wherein: the formed insert is a threaded insert; and structurally interrelating the second component to the first component comprises fastening the second component to the first component using a screw and the threaded insert.

14. The method of claim 1, wherein structurally interrelating the second component to the first component comprises structurally aligning the second component to the first component.

* * * * *