

EXPLORE MOON *to* MARS


Metal Additive Manufacturing for Spaceflight

Paul Gradl

NASA Marshall Space Flight Center

3 March 2022

Society of Manufacturing Engineers (SME) / Detroit and Houston Chapters



A rocket combustion chamber case study for AM



Category	Traditional Manufacturing	Initial AM Development	Evolving AM Development
Design and Manufacturing Approach	Multiple forgings, machining, slotting, and joining operations to complete a final multi-alloy chamber assembly	Four-piece assembly using multiple AM processes; limited by AM machine size. Two-piece L-PBF GRCo-84 liner and EBW-DED Inconel 625 jacket	Three-piece assembly with AM machine size restrictions reduced and industrialized. Multi-alloy processing; one-piece L-PBF GRCo-42 liner and Inconel 625 LP-DED jacket
Schedule (Reduction)	18 months	8 months (56%)	5 months (72%)
Cost (Reduction)	\$310,000	\$200,000 (35%)	\$125,000 (60%)


As AM process technologies evolve using multi-materials and processes, additional design and programmatic advantages are being discovered



The Case for Additive Manufacturing in Propulsion




- Metal Additive Manufacturing (AM) provides significant advantages for lead time and cost over traditional manufacturing for rocket engines
 - Lead times reduced by 2-10x
 - Cost reduced by more than 50%
- Complexity is inherent in liquid rocket engines and AM provides new design and performance opportunities
- Materials that are difficult to process using traditional techniques, long-lead, or not previously possible are now accessible using metal additive manufacturing






Additive Manufacturing in use on NASA Space Launch System (SLS)




**Successful hot-fire testing of full-scale additive manufacturing (AM) Part to be flown on SLS RS-25
RS-25 Pogo Z-Baffle – Used existing design with AM to reduce complexity from 127 welds to 4 welds**


AM Processes for various applications




Laser Powder Bed Fusion



Electron Beam Powder Bed Fusion




Laser Powder DED




Laser Wire DED




Arc Wire DED



Electron Beam Wire DED



Cold Spray



Additive Friction Stir Deposition



Ultrasonic Additive Manufacturing

A) Laser Powder Bed Fusion [<https://doi.org/10.1016/j.actamat.2017.09.051>], B) Electron Beam Powder Bed Fusion [Credit: Courtesy of Freemelt AB, Sweden], C) Laser Powder DED [Credit: Formalloy], D) Laser Wire DED [Credit: Ramlab and Cavitar], E) Arc Wire DED [Credit: Institut Maupertuis and Cavitar], F) Electron Beam DED [NASA], G) Cold spray [Credit: LLNL], H) Additive Friction Stir Deposition [NASA], I) Ultrasonic AM [Credit: Fabrisonic].




Additive Manufacturing (AM) Development at NASA for Liquid Rocket Engines




Laser Powder Bed Fusion (L-PBF)
Copper Alloys combined with other
AM processes to provide bimetallic



Directed Energy Deposition



L-PBF of complex components, new
alloy developments for harsh
environment







Methodical AM Process Selection



- What is the **alloy** required for the application?
- What is the **overall part size**?
- What is the **feature resolution** and internal **complexities**?
- Is it a **single alloy or multiple**?
- What are **programmatic requirements** such as cost, schedule, risk tolerance?
- What are the end-use environments and **properties required**?
- What is the **qualification/certification** path for the application/process?



Criteria and Comparison Various Metal AM Processes



CREDITS: AFS-D image credits to MELD™ Manufacturing, Cold spray image credits to Spee3D, EBW-DED image credits to Sciaky and Lockheed Martin Corporation, AW-DED image credits to Gefertec, LW-DED image credits to Meltio, UAM image credits to Fabrisonic and NASA JPL, LP-DED image credits to DEPOZ project led by IRT Saint-Exupery and Formally, L-PBF image credits to Renishaw plc and CellCore GmbH/Sol Solutions Group AG, EB-PBF image credits to Wayland and GE Additive/Arcom.

Laser Powder Directed Energy Deposition (DED)





Laser Powder Directed Energy Deposition (LP-DED) Large Scale Nozzles



**60" (1.52 m) diameter and 70" (1.78 m) height with integral channels
90 day deposition**




Reference: P.R. Gradl, T.W. Teasley, C.S. Protz, C. Katsarelis, P. Chen, Process Development and Hot-fire Testing of Additively Manufactured NASA HR-1 for Liquid Rocket Engine Applications, in: AIAA Propuls. Energy 2021, 2021: pp. 1–23. <https://doi.org/10.2514/6.2021-3236>.



**95" (2.41 m) dia and 111" (2.82 m) height
Near Net Shape Forging Replacement**




Additive Manufacturing Typical Process Flow



Proper AM process selection requires an integrated evaluation of all process lifecycle steps

Microstructure of Various AM Processes Inconel 625

As-built microstructure of Inconel 625 => Requires proper post-processing heat treatments




A) Laser Powder Bed Fusion

B) Electron Beam Powder Bed Fusion

C) Laser Powder DED (1070 W)

D) Laser Wire DED

E) Arc Wire DED



F) Electron Beam Wire DED

G) Cold Spray

H) Additive Friction Stir Deposition

I) Ultrasonic Additive Manufacturing

Each AM process results in different grain structures, which ultimately influence properties

- Gradl, P., Tinker, D., Park, A., Mireles, P., Garcia, M., Wilkerson, R., Mckinney, C. (2021). "Robust Metal Additive Manufacturing Process Selection and Development for Aerospace Components". (Journal Article In Review)
- Rivera, O. G., Allison, P. G., Jordon, J. B., Rodriguez, O. L., Brewer, L. N., McClelland, Z., ... & Hardwick, N. (2017). Microstructures and mechanical behavior of Inconel 625 fabricated by solid-state additive manufacturing. Materials Science and Engineering: A, 694, 1-9.




Emerging Areas of Development



- Maturing each of the AM processes and understanding of microstructure, properties, build limitations, and methods for design and post-processing.
- Ongoing development for large scale AM using DED and other processes.
- Continuous hot-fire and component testing to advance various combustion chambers, injectors, nozzles, ignition systems, turbomachinery, valves, lines, ducts, in-space thrusters.
- Polishing (surface enhancements internally) and post-processing development.
- Combining various AM processes for multi-alloy solutions or additional design options.
- Advancement of commercial supply chain for unique alloys (GRCop-42, NASA HR-1, JBK-75).
- New alloy development (Refractory, Ox-rich environments, AM-specific alloys).
- Material databases of metal AM properties to allow for conceptual design – tensile, fatigue, and thermophysical.
- Design complexity using lattices, topology optimization, generative design, and thin-wall structures.
- Standards and certification of metal AM are evolving for human spaceflight.



Industrial Maturity and TRL of AM Processes




L-PBF




Cold spray

LP-DED



L-PBF



L-PBF



EBW-DED



AW-DED



LW-DED



- It's *all* welding, so same physics apply.
- Additive manufacturing is not a solve-all; consider trading with other manufacturing technologies and use only when it makes sense.
- Complete understanding of design process, build-process, and post-processing critical to take full advantage of AM.
- Various processes exist each with unique advantages and disadvantages.
- Additive manufacturing takes practice!
- Standards and certification of the AM processes are in-work.
- AM is evolving and there is a lot of work ahead.





Contact:

Paul Gradl



NASA MSFC

256.544.2455

Paul.R.Gradl@nasa.gov



Various criteria for selecting AM techniques



Complexity of Features

Scale of Hardware

Material Physics

Cost

Material Efficiency

Speed of Process

Material Properties

Internal Geometry


Availability

Post Processing

References:

- Kerstens, F., Cervone, A., & Gradl, P. (2021). End to end process evaluation for additively manufactured liquid rocket engine thrust chambers. *Acta Astronautica*, 182, 454–465. <https://doi.org/10.1016/j.actaastro.2021.02.034>
- AIAA Book: Metal Additive Manufacturing for Propulsion Systems, Gradl, Protz, Mireles, Garcia (unreleased)
- Gradl, P.R., Mireles, O., Andrews, N. "Introduction to Additive Manufacturing for Propulsion Systems. [10.13140/RG.2.2.13113.93285](https://doi.org/10.13140/RG.2.2.13113.93285)
- Gradl, P., Tinker, D., Park, A., Mireles, P., Garcia, M., Wilkerson, R., Mckinney, C. (2021). "Robust Metal Additive Manufacturing Process Selection and Development for Aerospace Components". (Journal Article In Review)

Various Metal AM Processes



Many AM processes exist and must be traded (along with traditional techniques) to optimize



References



- P. Bidare, I. Bitharas, R.M. Ward, M.M. Attallah, A.J. Moore, Fluid and particle dynamics in laser powder bed fusion, *Acta Mater.* 142 (2018) 107–120. <https://doi.org/10.1016/j.actamat.2017.09.051>.
- B. Blakey-Milner, P. Gradl, G. Snedden, M. Brooks, J. Pitot, E. Lopez, M. Leary, F. Berto, A. du Plessis, Metal additive manufacturing in aerospace: A review, *Mater. Des.* 209 (2021) 110008. <https://doi.org/10.1016/j.matdes.2021.110008>.
- S.C. Altıparmak, B. Xiao, A market assessment of additive manufacturing potential for the aerospace industry, *J. Manuf. Process.* 68 (2021) 728–738. <https://doi.org/10.1016/j.jmapro.2021.05.072>.
- R. Liu, Z. Wang, T. Sparks, F. Liou, J. Newkirk, Aerospace applications of laser additive manufacturing, *Laser Addit. Manuf. Mater. Des. Technol. Appl.* (2017) 351–371. <https://doi.org/10.1016/B978-0-08-100433-3.00013-0>.
- A. Uriondo, M. Esperon-Miguez, S. Perinpanayagam, The present and future of additive manufacturing in the aerospace sector: A review of important aspects, *Proc. Inst. Mech. Eng. Part G J. Aerosp. Eng.* 229 (2015) 2132–2147. <https://doi.org/10.1177/0954410014568797>.
- P.R. Gradl, S.E. Greene, C. Protz, B. Bullard, J. Buzzell, C. Garcia, J. Wood, K. Cooper, J. Hulka, R. Osborne, Additive manufacturing of liquid rocket engine combustion devices: A summary of process developments and hot-fire testing results, in: 2018 Jt. Propuls. Conf., AIAA, 2018. <https://doi.org/10.2514/6.2018-4625>.
- F. Kerstens, A. Cervone, P. Gradl, End to end process evaluation for additively manufactured liquid rocket engine thrust chambers, *Acta Astronaut.* 182 (2021) 454–465. <https://doi.org/10.1016/j.actaastro.2021.02.034>.
- B. Barroqueiro, A. Andrade-Campos, R.A.F. Valente, V. Neto, Metal additive manufacturing cycle in aerospace industry: A comprehensive review, *J. Manuf. Mater. Process.* 3 (2019) 1–21. <https://doi.org/10.3390/jmmp3030052>.
- T.A. Rodrigues, V. Duarte, R.M. Miranda, T.G. Santos, J.P. Oliveira, Current status and perspectives on wire and arc additive manufacturing (WAAM), *Materials (Basel)*. 12 (2019). <https://doi.org/10.3390/ma12071121>.
- A. Vafadar, F. Guzzomi, A. Rassau, K. Hayward, Advances in Metal Additive Manufacturing: A Review of Common Processes, Industrial Applications, and Current Challenges, *Appl. Sci.* 11 (2021) 1213. <https://doi.org/10.3390/app11031213>.
- S. Negi, A.A. Nambolan, S. Kapil, P.S. Joshi, M. R, K.P. Karunakaran, P. Bhargava, Review on electron beam based additive manufacturing, *Rapid Prototyp. J.* 26 (2020) 485–498. <https://doi.org/10.1108/RPJ-07-2019-0182>.
- S.A.M. Tofail, E.P. Koumoulos, A. Bandyopadhyay, S. Bose, L. O’Donoghue, C. Charitidis, Additive manufacturing: scientific and technological challenges, market uptake and opportunities, *Mater. Today*. 21 (2018) 22–37. <https://doi.org/10.1016/j.matod.2017.07.001>.
- Gradl, P., Tinker, D., Park, A., Mireles, P., Garcia, M., Wilkerson, R., McKinney, C. (2021). “Robust Metal Additive Manufacturing Process Selection and Development for Aerospace Components”. (Journal Article In Review)
- Gradl, P. R., Teasley, T. W., Protz, C. S., Garcia, M. B., Ellis, D., & Kantzos, C. (2021). Advancing GRCop-based Bi-metallic Additive Manufacturing to Optimize Component Design and Applications for Liquid Rocket Engines. *AIAA Propulsion and Energy 2021*, 1–28. <https://doi.org/10.2514/6.2021-3231>
- Gradl, P., Mireles, O., Andrews, N. (2021). Introduction to Additive Manufacturing for Propulsion and Energy Systems. *AIAA Propulsion and Energy Forum 2021*. August. [10.13140/RG.2.2.29815.55209](https://doi.org/10.13140/RG.2.2.29815.55209)
- A. Gamon, E. Arrieta, P.R. Gradl, C. Katsarelis, L.E. Murr, R.B. Wicker, F. Medina, Microstructure and hardness comparison of as-built Inconel 625 alloy following various additive manufacturing processes, *Results Mater.* 12 (2021). <https://doi.org/10.1016/j.rinma.2021.100239>.
- P.R. Gradl, D.C. Tinker, J. Ivester, S.W. Skinner, T. Teasley, J.L. Bili, Geometric Feature Reproducibility for Laser Powder Bed Fusion (L-PBF) Additive Manufacturing with Inconel 718, *Addit. Manuf.* 47 (2021) 102305. <https://doi.org/10.1016/j.addma.2021.102305>.