

NASA TECH BRIEF




NASA Tech Briefs are issued to summarize specific innovations derived from the U.S. space program, to encourage their commercial application. Copies are available to the public at 15 cents each from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

Production of Crystalline Polymers via Liquid Crystal Monomers

A method for producing crystalline polymers through a liquid crystalline phase of monomers has been developed.

The monomers are from a family with the following basic structures:

(1) Aromatics of the type:



where Z is a polymerizable group such as vinyl, X can be any of the central groups such as $-\text{CH}=\text{CH}-$, $-\text{CH}=\text{N}-$, $-\text{N}=\text{N}-$, $-\text{N}=\text{N}(\text{O})-$, and Y can be any end group such as $\text{CH}_3(\text{CH}_2)_n\text{O}$, Cl, Br, I, NO_2 (described in a review article by G. H. Brown and W. G. Show in *Chemical Reviews* 57, 1049 (1957)). Substituents can also be placed at the ortho and meta positions of the aromatic rings.

(2) Any other nematic, smectic, cholesteric, or lyotropic liquid crystal containing a polymerizable group.


The monomer is polymerized while held in the liquid crystalline phase either thermally, photolytically, catalytically, or by X- or gamma-ray irradiation.

In addition to the previously described polymerizations, polymerization can be performed in an electric or a magnetic field that influences the orientation of the molecules in the liquid crystalline phase.

The principle of this polymerization is as follows: the liquid crystalline phase is one in which long-range order exists between molecules in a phase having the flow properties of a viscous liquid and the optical

properties of an anisotropic solid. Thus, a monomer reacting in this phase should have preferred orientations leading to crystalline polymers. A magnetic or an electric field can increase the ordering in this phase and consequently influence the crystallinity.

As an example of the above reaction, the preparation of new monomers of the following structures can be cited:



where R is CH_3 , C_4 , H_9 , or $\text{C}_{18}\text{H}_{37}$

These vinyl monomers are solids at room temperature. Polymerization can be conducted in the liquid crystalline phase without catalyst and leads to good yield of polymer in several hours.

Notes:

No additional documentation is available. Specific questions, however, may be directed to:
 Technology Utilization Officer
 Headquarters
 National Aeronautics
 and Space Administration
 Washington, D.C. 20546
 Reference: B69-10744

Patent status:

No patent action is contemplated by NASA.

Source: C. Palos and M. Labes of
 Drexel Institute of Technology
 under contract to
 NASA Headquarters
 (HQN-10235)

Category 03