

General Disclaimer

One or more of the Following Statements may affect this Document

- This document has been reproduced from the best copy furnished by the organizational source. It is being released in the interest of making available as much information as possible.
- This document may contain data, which exceeds the sheet parameters. It was furnished in this condition by the organizational source and is the best copy available.
- This document may contain tone-on-tone or color graphs, charts and/or pictures, which have been reproduced in black and white.
- This document is paginated as submitted by the original source.
- Portions of this document are not fully legible due to the historical nature of some of the material. However, it is the best reproduction available from the original submission.



INVESTIGATION OF THE INFLUENCE OF THE ZETA-
POTENTIAL ON THE FILTRATION RATE IN THE PRESENCE OF COLLECTORS

E.V. Prosvirnina, M.B. Barbin

Translation of "Issledovaniye vliyaniya dzeta-
potentsiala na skorost' fil'trovaniya v pri-
sutstvii soberateley," Izvestiya Vysshikh Uchenykh
Zavedeniy, Gornyy Zhurnal, Vol. 17, No. 2,
1974, pp. 160-163

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION
WASHINGTON D.C. 20546 MAY 1984

(NASA-TM-77447) INVESTIGATION OF THE INFLUENCE OF THE ZETA-POTENTIAL ON THE FILTRATION RATE IN THE PRESENCE OF COLLECTORS (National Aeronautics and Space Administration) 7 p HC A02/MF A01 CSCL 07D 63 25 20036 N84-28927 Unclas

| | | | |
|---|--|---|--|
| 1. Report No. NASA TM-77447 | 2. Government Accession No. | 3. Recipient's Catalog No. | |
| 4. Title and Subtitle INVESTIGATION OF THE INFLUENCE OF THE ZETA-POTENTIAL ON THE FILTRATION RATE IN THE PRESENCE OF COLLECTORS | | 5. Report Date MAY 1984 | 6. Performing Organization Code |
| 7. Author(s) E.V. Provirnina, M.B. Barbin | | 8. Performing Organization Report No. | 10. Work Unit No. |
| 9. Performing Organization Name and Address SCITRAN Box 5456 Santa Barbara, CA 93108 | | 11. Contract or Grant No. NASw- 3542 | 12. Type of Report and Period Covered Translation |
| 12. Sponsoring Agency Name and Address National Aeronautics and Space Administration Washington, D.C. 20546 | | 14. Sponsoring Agency Code | |
| 15. Supplementary Notes Translation of "Issledovaniye vliyaniya dzeta-potentsiala na skorost' fil'trovaniya v prisutstvii sobirateley," Izvestiya Vysshikh Uchenykh Zavedeniy, Gornyy Zhurnal, Vol. 17, No. 2, 1974, pp. 160-163 | | | |
| 16. Abstract The value of the zeta-potential does not have an explicit effect, which can be expressed by a simple math correlation, on filtration rate when a soln. of the tested collector is filtered through a cake prepd. under standard conditions from the examined particulate material. The zeta-potential measurements and filtration tests were carried out on silica and galena with solns. contg. a cationic container ANP and Et xanthate, resp. at pH= 6.5, varying concentration of the agent (0-2500 g/ton), and under a vacuum of 100-600mm Hg. | | | |
| 17. Key Words (Selected by Author(s)) | | 18. Distribution Statement Unlimited | |
| 19. Security Classif. (of this report) Unclassified | 20. Security Classif. (of this page) Unclassified | 21. No. of Pages 7 | 22. Price |

Investigation of the Influence of the Zeta-Potential on
the Filtration Rate in the Presence of Collectors

E. V. Prosvirnina, M. B. Barbin
The Order of the Labor Red Banner
Ural Polytechnical Institute im. S. M. Kirov

The paper is devoted to a study of the influence of the zeta-potential of capillary systems formed by the solid phase of suspensions in the presence of collectors, and its influence on the filtration capacity of the sediment. /160*

We studied the influence of the cation collector ANP¹ on quartz suspensions and of ethyl xanthogenate on suspensions of galenite in distilled water at pH = 6.5.

In order to measure the zeta-potential, electric resistance and rate of filtration at constant height of the sediment layer in parallel for each object, we used an instrument designed by Zhukov and Kryukov [1] with internal diameter of the tube of 12 mm.

The zeta-potential as defined in terms of the flow potential:

$$\varphi = \frac{4\pi\eta\chi_v}{l} \frac{E}{P} \cdot 6.75 \cdot 10^7,$$

where φ is the zeta-potential, mV; P is the pressure, cm Hg; η is the viscosity of the solution, poise; χ_v is the electric conductivity of the solution, $\Omega^{-1} \text{ cm}^{-1}$; $6.75 \cdot 10^7$ is a scaling factor to obtain the value of the φ -potential, mV.

The tests were done under steady conditions. Through a sediment

* Numbers in the margin indicate pagination of the original

¹ANP - primary hydrochloride amines with slight admixture (?) of secondary amines.

previously formed in the cell, we filtered solutions under a vacuum of 100-600 mm Hg, changing from one concentration to another without disrupting the structure of the sediment and repeatedly forming a sediment.

When solutions of ANP in the concentration interval from $1 \cdot 10^{-4}$ to $5 \cdot 10^{-3}$ % by weight (50-2500 g of 100% collector per ton of dry sediment) are filtered through a formed layer of quartz sediment with grain size of 60 μm , the zeta-potential of quartz varies continuously from -36.4 mv to +59 mv (Fig. 1, curve 1) because of adsorption of ANP on the surface of the solid particles. The size of the zeta-potential of quartz conforms to the data of other researchers [2]. The rate of filtration does not increase with rise in concentration of the solution of ANP, which is apparently due to blockage of the voids of the sediment and of the pores of the filter partition with adsorbed ANP.




Fig. 1. The zeta-potential of quartz and galenite as function of the concentration of collectors at pH = 6.5; 1 - quartz + cation collector ANP; 2 - galenite + ethyl xanthogenate.

For a filtration with formation of sediment in the corresponding

solution with ANP outlay varying from 0 to 250 g/m, the rate of filtration of pure filtrate across a constant layer of sediment increases by a factor of 1.5-2, depending on the vacuum (Fig. 2, curves 3, 4), which corresponds to a decrease in the zeta-potential, while the maximum rate corresponds to a value of zero. The height of the sediment for a vacuum of 600 mm Hg was increased by 5%. Upon further increase in the outlay of ANP up to 1000 g/m, the rate of filtration remains constant for low vacuum and diminishes slightly as the vacuum is increased. The zeta-potential grows in positive value, suggesting the continuing adsorption of ANP by the surface of the particles. There are two possible reasons for the decrease in rate of filtration after its maximum.




Fig. 2. Influence of the zeta-potential (abscissa) on the rate of filtration (ordinate) at constant height of the layer of sediment with repeated formation of it: 1, 2 - galenite + ethyl xanthogenate; 3, 4 - quartz + cation collector ANP. Vacuum, mm Hg: \circ - 100; \square - 200; \bullet \blacktriangle - 600

Deflocculation, corresponding to a rise in the positive zeta-potential produced by further binding of the hydrocarbon ions of the collector to the surface of the particles, or formation of

micelle-like coatings when the ions are oppositely oriented (polar portion of the ion toward the solution), is unlikely for the given system of quartz + ANP, according to the literature [3].

A blockage of the voids of the sediment and pores of the filter partition with collector is more probable.

Studies done on galenite with grain size of 20 μm in presence of ethyl xanthogenate with repeated formation of sediment as one concentration changes to another and a vacuum of 200-600 mm Hg revealed that, as the outlay of xanthogenate increases from 0 to 2500 g/m, the zeta-potential varies from -7.5 to -40 mv (Fig. 1, curve 2). The rate of filtration increases by 2.2 times for a vacuum of 200 mm Hg and 1.9 times for 600 mm Hg. The height of the sediment for a vacuum of 600 mm Hg is increased by 23%. For both quartz and galenite as the vacuum increases the efficiency of the collectors decreases, due to the greater compaction of the sediments produced in presence of the collectors.

The zeta-potential of galenite in distilled water is 19-20 mv. In our tests it is equal to -7.5 mv [2, 4]. The discrepancy in values of the zeta-potential can be explained by partial oxidation of the galenite surface [5].

On the basis of the findings we may infer that the chief reason for the increase in rate of filtration in presence of collectors is the change in structure of the sediment, produced by aggregation of particles.

When ANP is added to a quartz suspension, evidently a process of coagulation of the mineral grains occurs, the extent of which is governed by the size of the zeta-potential [6]. A decrease in the zeta-potential corresponds to a rise in degree of coagulation of the grains, with maximum coagulation occurring at the zero charge point.

In the presence of ethyl xanthogenate, the rate of filtration of

the galenite suspension increases with the zeta-potential. Consequently, a process of flocculation is possible with one of two mechanisms as proposed on the basis of experimental data [7].

Thus, change in the zeta-potential in the presence of collectors is not a unique characteristic of the filtration capacity of a sediment.

Bibliography

1. Elektrokineticheskiye svoystva kapillyarnykh sistem [Electrokinetic Properties of Capillary Systems], ed. I. I. Zhukov, USSR AS, M/L, 1956.
2. Dolzhenkova, A. I., Strel'tsyn, G. S., "Application of the Electrokinetic Method to Study the Mechanisms of the Flotation Process", Tr. in-ta "Mekhanobr", no. 131, Leningrad, 1962.
3. Dolzhenkova, A. I., Strel'tsyn, G. S., "Change in the Zeta-Potential of Quartz in Presence of Modifiers and Cation Collector", Tr. in-ta "Mekhanobr", no. 131, Leningrad, 1962.
4. Mitrofanov, S. I., Selektivnaya flotatsiya [Selective Flotation], Nedra, M, 1967.
5. Mukai Sigeru, Itidame Minoru, "Nikhop kochoyo kaysi, J. Mining and Met. Inet. Jap.", 87, No. 995, 1971, 85-90, No. 1002, 1971.
7. Lerner, V. N., Berger, G. S., "Comparison of the Data of Flocculation and Zeta-Potential of Several Minerals in Solutions of Long-Chain Collectors", Materialy kollokviuma po teorii flotatsii [Proceedings of a Colloquium on the Theory of Flotation], Nauka Press, Alma Ata, 1970.

Submitted 10 December 1972

Recommended by Chair of Processes and Apparatus
of Chemical Engineering of UPI.